Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Tuesday, December 07, 2004

Lab/Cor Report Number: *041172R3*

Howard Edwards
Ecology and Environment, Inc.
350 Sansome
Ste 300
San Francisco CA 94104

Phone: 415-981-2811
Fax: 415-981-0801

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS
Project Number: 0440.01CP-0001
Client Reference:
Sample Receipt Date: 10/7/2004

Enclosed please find results for samples submitted to our laboratory. A list of samples and analyses follows:

Lab/Cor Analysis #	Client Sample # and Description	Analysis Type and Notes
Batch #: ***B4760***		
S1-A1	APG-L2-13CH-100404	ISO 10312, direct: Rejected - overloaded
S2-A1	APG-L2-1CH-100404	ISO 10312, direct: Rejected - overloaded
S3-A1	APG-L2-1ZB-100404	ISO 10312, direct
S4-A1	APG-L2-2CH-100404	ISO 10312, direct
S5-A1	APG-L2-3CH-100404	ISO 10312, direct
S6-A1	APG-L2-4CH-100404	ISO 10312, direct
S7-A1	APG-L2-5CH-100404	ISO 10312, direct
S8-A1	CC1-L6-1CA-100204	ISO 10312, direct
S9-A1	CC1-L6-1CB-100204	ISO 10312, direct
S10-A1	CC1-L6-2CB-100204	ISO 10312, direct
S11-A1	CC1-L6-3CB-100204	ISO 10312, direct: Rejected - overloaded
S12-A1	CC2A-L6-1CA-100304	ISO 10312, direct
S13-A1	CC2-L6-11CC-100304	ISO 10312, direct
S14-A1	CC2-L6-1CC-100304	ISO 10312, direct
S15-A1	CC2-L6-2CC-100304	ISO 10312, direct
S16-A1	CC2-L6-3CC-100304	ISO 10312, direct
S17-A1	CC2-L6-4CC-100304	ISO 10312, direct
S18-A1	SVBA-H2-1FD-100204	ISO 10312, direct
S19-A1	SVBA-H2-2FD-100204	ISO 10312, direct
S20-A1	SVBA-H2-3FD-100204	ISO 10312, direct
S21-A1	SVBB-H2-1FD-100304	ISO 10312, direct
S22-A1	SVBB-H2-2FD-100304	ISO 10312, direct
S23-A1	SVBB-H2-3FD-100304	ISO 10312, direct
S24-A1	TPG-L2-11CH-100404	ISO 10312, direct
S25-A1	TPG-L2-1CH-100404	ISO 10312, direct
S26-A1	TPG-L2-1ZB-100404	ISO 10312, direct
S27-A1	TPG-L2-2CH-100404	ISO 10312, direct
S28-A1	TPG-L2-3CH-100404	ISO 10312, direct
S29-A1	TPG-L2-4CH-100404	ISO 10312, direct

S30-A1	TPG-L2-5CH-100404	ISO 10312, direct
S31-A1	RHB-H2-1FD-100304	ISO 10312, direct
S32-A1	RHB-H2-2FD-100304	ISO 10312, direct
S33-A1	RHB-H2-3FD-100304	ISO 10312, direct
S34-A1	RHB-L2-1CH-100304	ISO 10312, direct
S35-A1	RHB-L2-2CH-100304	ISO 10312, direct
S36-A1	RHB-L2-3CH-100304	ISO 10312, direct
S37-A1	RHB-L2-4CH-100304	ISO 10312, direct
S38-A1	RHB-L2-5CH-100304	ISO 10312, direct
S39-A1	SVBA-L2-11CH-100204	ISO 10312, direct
S40-A1	SVBA-L2-1CH-100204	ISO 10312, direct
S41-A1	SVBA-L2-2CH-100204	ISO 10312, direct
S42-A1	SVBA-L2-3CH-100204	ISO 10312, direct
S43-A1	SVBA-L2-4CH-100204	ISO 10312, direct
S44-A1	SVBA-L2-5CH-100204	ISO 10312, direct
S45-A1	SVBB-L2-12CH-100304	ISO 10312, direct
S46-A1	SVBB-L2-1CH-100304	ISO 10312, direct
S47-A1	SVBB-L2-2CH-100304	ISO 10312, direct
S48-A1	SVBB-L2-3CH-100304	ISO 10312, direct
S49-A1	SVBB-L2-4CH-100304	ISO 10312, direct
S50-A1	SVBB-L2-5CH-100304	ISO 10312, direct
S51-A1	SVM-H2-1FD-100204	ISO 10312, direct
S52-A1	SVM-H2-2FD-100204	ISO 10312, direct
S53-A1	SVM-H2-3FD-100204	ISO 10312, direct

ISO 10312, direct

Preparation and analysis of the above samples was conducted in accordance with the ISO method 10312 (Direct) for the identification of asbestos. Briefly, the samples were collapsed with acetone, then etched in a low temperature plasma etcher to remove the top surface of the filter and other organics. The samples were carbon coated at high vacuum with a thin layer of carbon, placed on 200 mesh copper grids and allowed to dissolve in acetone until cleared of filter debris.

TEM analysis was performed using a transmission electron microscope equipped with an EDS X ray analyzer. The air samples were analyzed at various approximate screen magnifications of 5,000x for PCM equivalent structures, 10,000x for asbestos structures greater than 5.0 micrometer lengths, and 20,000x for asbestos structures greater than 0.5 micrometer lengths. An accelerating voltage of 100 KV was applied. The sizing of grid openings was performed on the microscope at a magnification of approximately 550X.

Disclaimer

This test report relates only to the items tested in this report. Interpretation of these results is the sole responsibility of the client.

If further clarification of these results is needed, please call us. Thank you for allowing the staff at Lab/Cor, Inc. the opportunity to provide you with analytical services.

Sincerely,

John Harris, M.P.H.
Laboratory Director

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S3 A1
Client Sample No. APG-L2-1ZB-100404
Description
Analysis Date 10/7/2004
Analyst DW

Volume (L) 299.76
No. of Grid Openings 83
Filter Area (mm2) 385
Area Analyzed (mm2) 1.20
Analytical Sens. (struc/cc) 0.00107
Dectection Limit. (struc/cc) 0.00319

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	0.0	<0.00319	0.00 - 0.00319	0
Total Asbestos Structures	0.0	<0.00319	0.00 - 0.00319	0
Asbestos Structures > 5um	0.0	<0.00319	0.00 - 0.00319	0
Asbestos Fibers and Bundles > 5um	0.0	<0.00319	0.00 - 0.00319	0
PCM Equivalent Fibers-US	0.0	<0.00319	0.00 - 0.00319	0
PCM Equivalent Structures-US	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL ASB STRUCS >10	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00319	0.00 - 0.00319	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00319	0.00 - 0.00319	0
AHERA-like Total Structures 3:1	0.0	<0.00319	0.00 - 0.00319	0
AHERA-like Asb Strucs >5 and 3:1	0.0	<0.00319	0.00 - 0.00319	0
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00319	0.00 - 0.00319	0
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00319	0.00 - 0.00319	0
Total Other Amphibole Strucs 3:1	0.0	<0.00319	0.00 - 0.00319	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00319	0.00 - 0.00319	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00319	0.00 - 0.00319	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00319	0.00 - 0.00319	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S4 A1
Client Sample No. APG-L2-2CH-100404
Description
Analysis Date 10/7/2004
Analyst KM

Volume (L) 289.2
No. of Grid Openings 92
Filter Area (mm2) 385
Area Analyzed (mm2) 1.33
Analytical Sens. (struc/cc) 0.000999
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	14.3	0.0190	0.0114 - 0.0296	19
Total Asbestos Structures	14.3	0.0190	0.0114 - 0.0296	19
Asbestos Structures > 5um	7.5	0.00999	0.00479 - 0.0184	10
Asbestos Fibers and Bundles > 5um	6.8	0.00899	0.00411 - 0.0171	9
PCM Equivalent Fibers-US	6.8	0.00899	0.00411 - 0.0171	9
PCM Equivalent Structures-US	7.5	0.00999	0.00479 - 0.0184	10
PROTOCOL ASB STRUCS 5-10	1.5	0.00200	0.00 - 0.00629	2
PROTOCOL ASB STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS TOTAL	1.5	0.00200	0.00 - 0.00629	2
PROTOCOL CHRYS STRUCS 5-10	0.8	0.000999	0.00 - 0.00473	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS TOTAL	0.8	0.000999	0.00 - 0.00473	1
PROTOCOL AMPH STRUCS 5-10	0.8	0.000999	0.00 - 0.00473	1
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	0.8	0.000999	0.00 - 0.00473	1
AHERA-like Total Structures 3:1	14.3	0.0190	0.0114 - 0.0296	19
AHERA-like Asb Strucs >5 and 3:1	7.5	0.00999	0.00479 - 0.0184	10
AHERA-like Asb Strucs 5 - 10 and 3:1	5.3	0.00699	0.00281 - 0.0144	7
AHERA-like Asb Strucs >10 and 3:1	2.3	0.00300	0.00 - 0.00774	3
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S5 A1
Client Sample No. APG-L2-3CH-100404
Description
Analysis Date 10/7/2004
Analyst KM

Volume (L) 295.56
No. of Grid Openings 91
Filter Area (mm2) 385
Area Analyzed (mm2) 1.32
Analytical Sens. (struc/cc) 0.000988
Dectection Limit. (struc/cc) 0.00295

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	6.8	0.00889	0.00407 - 0.0169	9
Total Asbestos Structures	6.8	0.00889	0.00407 - 0.0169	9
Asbestos Structures > 5um	1.5	0.00198	0.00 - 0.00622	2
Asbestos Fibers and Bundles > 5um	1.5	0.00198	0.00 - 0.00622	2
PCM Equivalent Fibers-US	1.5	0.00198	0.00 - 0.00622	2
PCM Equivalent Structures-US	0.8	0.000988	0.00 - 0.00468	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL ASB STRUCS >10	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00295	0.00 - 0.00295	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00295	0.00 - 0.00295	0
AHERA-like Total Structures 3:1	6.8	0.00889	0.00407 - 0.0169	9
AHERA-like Asb Strucs >5 and 3:1	1.5	0.00198	0.00 - 0.00622	2
AHERA-like Asb Strucs 5 - 10 and 3:1	0.8	0.000988	0.00 - 0.00468	1
AHERA-like Asb Strucs >10 and 3:1	0.8	0.000988	0.00 - 0.00468	1
Total Other Amphibole Strucs 3:1	0.0	<0.00295	0.00 - 0.00295	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00295	0.00 - 0.00295	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00295	0.00 - 0.00295	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00295	0.00 - 0.00295	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S6 A1
Client Sample No. APG-L2-4CH-100404
Description
Analysis Date 10/8/2004
Analyst JH

Volume (L) 299.4
No. of Grid Openings 89
Filter Area (mm2) 385
Area Analyzed (mm2) 1.29
Analytical Sens. (struc/cc) 0.000997
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	7.8	0.00997	0.00478 - 0.0183	10
Total Asbestos Structures	7.8	0.00997	0.00478 - 0.0183	10
Asbestos Structures > 5um	3.1	0.00399	0.00109 - 0.0102	4
Asbestos Fibers and Bundles > 5um	3.1	0.00399	0.00109 - 0.0102	4
PCM Equivalent Fibers-US	3.1	0.00399	0.00109 - 0.0102	4
PCM Equivalent Structures-US	3.1	0.00399	0.00109 - 0.0102	4
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	7.8	0.00997	0.00478 - 0.0183	10
AHERA-like Asb Strucs >5 and 3:1	3.1	0.00399	0.00109 - 0.0102	4
AHERA-like Asb Strucs 5 - 10 and 3:1	3.1	0.00399	0.00109 - 0.0102	4
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S7 A1
Client Sample No. APG-L2-5CH-100404
Description
Analysis Date 10/7/2004
Analyst DW

Volume (L) 290.64
No. of Grid Openings 91
Filter Area (mm2) 385
Area Analyzed (mm2) 1.32
Analytical Sens. (struc/cc) 0.00100
Dectection Limit. (struc/cc) 0.00300

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	4.6	0.00603	0.00221 - 0.0131	6
Total Asbestos Structures	4.6	0.00603	0.00221 - 0.0131	6
Asbestos Structures > 5um	0.8	0.00100	0.00 - 0.00476	1
Asbestos Fibers and Bundles > 5um	0.8	0.00100	0.00 - 0.00476	1
PCM Equivalent Fibers-US	0.8	0.00100	0.00 - 0.00476	1
PCM Equivalent Structures-US	0.8	0.00100	0.00 - 0.00476	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL ASB STRUCS >10	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00300	0.00 - 0.00300	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00300	0.00 - 0.00300	0
AHERA-like Total Structures 3:1	4.6	0.00603	0.00221 - 0.0131	6
AHERA-like Asb Strucs >5 and 3:1	0.8	0.00100	0.00 - 0.00476	1
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00300	0.00 - 0.00300	0
AHERA-like Asb Strucs >10 and 3:1	0.8	0.00100	0.00 - 0.00476	1
Total Other Amphibole Strucs 3:1	0.0	<0.00300	0.00 - 0.00300	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00300	0.00 - 0.00300	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00300	0.00 - 0.00300	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00300	0.00 - 0.00300	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S8 A1
Client Sample No. CC1-L6-1CA-100204
Description
Analysis Date 10/8/2004
Analyst TM

Volume (L) 569.77
No. of Grid Openings 47
Filter Area (mm2) 385
Area Analyzed (mm2) 0.681
Analytical Sens. (struc/cc) 0.000992
Dectection Limit. (struc/cc) 0.00297

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	8.8	0.00595	0.00218 - 0.0130	6
Total Asbestos Structures	8.8	0.00595	0.00218 - 0.0130	6
Asbestos Structures > 5um	1.5	0.000992	0.00 - 0.00470	1
Asbestos Fibers and Bundles > 5um	1.5	0.000992	0.00 - 0.00470	1
PCM Equivalent Fibers-US	1.5	0.000992	0.00 - 0.00470	1
PCM Equivalent Structures-US	1.5	0.000992	0.00 - 0.00470	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Total Structures 3:1	8.8	0.00595	0.00218 - 0.0130	6
AHERA-like Asb Strucs >5 and 3:1	1.5	0.000992	0.00 - 0.00470	1
AHERA-like Asb Strucs 5 - 10 and 3:1	1.5	0.000992	0.00 - 0.00470	1
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Total Other Amphibole Strucs 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S9 A1
Client Sample No. CC1-L6-1CB-100204
Description
Analysis Date 10/8/2004
Analyst JH

Volume (L) 607.18
No. of Grid Openings 45
Filter Area (mm2) 385
Area Analyzed (mm2) 0.652
Analytical Sens. (struc/cc) 0.000972
Dectection Limit. (struc/cc) 0.00291

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	7.7	0.00486	0.00158 - 0.0113	5
Total Asbestos Structures	6.1	0.00389	0.00106 - 0.00996	4
Asbestos Structures > 5um	1.5	0.000972	0.00 - 0.00461	1
Asbestos Fibers and Bundles > 5um	1.5	0.000972	0.00 - 0.00461	1
PCM Equivalent Fibers-US	1.5	0.000972	0.00 - 0.00461	1
PCM Equivalent Structures-US	1.5	0.000972	0.00 - 0.00461	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL ASB STRUCS >10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00291	0.00 - 0.00291	0
AHERA-like Total Structures 3:1	6.1	0.00389	0.00106 - 0.00996	4
AHERA-like Asb Strucs >5 and 3:1	1.5	0.000972	0.00 - 0.00461	1
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00291	0.00 - 0.00291	0
AHERA-like Asb Strucs >10 and 3:1	1.5	0.000972	0.00 - 0.00461	1
Total Other Amphibole Strucs 3:1	1.5	0.000972	0.00 - 0.00461	1
Other Amphibole Strucs >5 and 3:1	0.0	<0.00291	0.00 - 0.00291	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00291	0.00 - 0.00291	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00291	0.00 - 0.00291	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S10 A1
Client Sample No. CC1-L6-2CB-100204
Description
Analysis Date 10/8/2004
Analyst DW

Volume (L) 597.98
No. of Grid Openings 44
Filter Area (mm2) 385
Area Analyzed (mm2) 0.638
Analytical Sens. (struc/cc) 0.00101
Dectection Limit. (struc/cc) 0.00302

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	12.5	0.00808	0.00349 - 0.0159	8
Total Asbestos Structures	12.5	0.00808	0.00349 - 0.0159	8
Asbestos Structures > 5um	4.7	0.00303	0.00 - 0.00783	3
Asbestos Fibers and Bundles > 5um	4.7	0.00303	0.00 - 0.00783	3
PCM Equivalent Fibers-US	3.1	0.00202	0.00 - 0.00636	2
PCM Equivalent Structures-US	3.1	0.00202	0.00 - 0.00636	2
PROTOCOL ASB STRUCS 5-10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL ASB STRUCS >10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00302	0.00 - 0.00302	0
AHERA-like Total Structures 3:1	12.5	0.00808	0.00349 - 0.0159	8
AHERA-like Asb Strucs >5 and 3:1	4.7	0.00303	0.00 - 0.00783	3
AHERA-like Asb Strucs 5 - 10 and 3:1	3.1	0.00202	0.00 - 0.00636	2
AHERA-like Asb Strucs >10 and 3:1	1.6	0.00101	0.00 - 0.00479	1
Total Other Amphibole Strucs 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S12 A1
Client Sample No. CC2A-L6-1CA-100304
Description
Analysis Date 10/8/2004
Analyst TM

Volume (L) 269.72
No. of Grid Openings 99
Filter Area (mm2) 385
Area Analyzed (mm2) 1.43
Analytical Sens. (struc/cc) 0.000995
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	7.7	0.0109	0.00546 - 0.0196	11
Total Asbestos Structures	14.6	0.0209	0.0129 - 0.0319	21
Asbestos Structures > 5um	2.1	0.00299	0.00 - 0.00771	3
Asbestos Fibers and Bundles > 5um	0.0	<0.00298	0.00 - 0.00298	0
PCM Equivalent Fibers-US	0.7	0.000995	0.00 - 0.00472	1
PCM Equivalent Structures-US	0.7	0.000995	0.00 - 0.00472	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	7.7	0.0109	0.00546 - 0.0196	11
AHERA-like Asb Strucs >5 and 3:1	2.1	0.00299	0.00 - 0.00771	3
AHERA-like Asb Strucs 5 - 10 and 3:1	2.1	0.00299	0.00 - 0.00771	3
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S13 A1
Client Sample No. CC2-L6-11CC-100304
Description
Analysis Date 10/8/2004
Analyst DW

Volume (L) 530.45
No. of Grid Openings 51
Filter Area (mm2) 385
Area Analyzed (mm2) 0.739
Analytical Sens. (struc/cc) 0.000982
Dectection Limit. (struc/cc) 0.00294

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	4.1	0.00295	0.00 - 0.00761	3
Total Asbestos Structures	2.7	0.00196	0.00 - 0.00619	2
Asbestos Structures > 5um	1.4	0.000982	0.00 - 0.00466	1
Asbestos Fibers and Bundles > 5um	1.4	0.000982	0.00 - 0.00466	1
PCM Equivalent Fibers-US	1.4	0.000982	0.00 - 0.00466	1
PCM Equivalent Structures-US	1.4	0.000982	0.00 - 0.00466	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
AHERA-like Total Structures 3:1	4.1	0.00295	0.00 - 0.00761	3
AHERA-like Asb Strucs >5 and 3:1	2.7	0.00196	0.00 - 0.00619	2
AHERA-like Asb Strucs 5 - 10 and 3:1	1.4	0.000982	0.00 - 0.00466	1
AHERA-like Asb Strucs >10 and 3:1	1.4	0.000982	0.00 - 0.00466	1
Total Other Amphibole Strucs 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S14 A1
Client Sample No. CC2-L6-1CC-100304
Description
Analysis Date 10/9/2004
Analyst JH

Volume (L) 533.62
No. of Grid Openings 51
Filter Area (mm2) 385
Area Analyzed (mm2) 0.739
Analytical Sens. (struc/cc) 0.000976
Dectection Limit. (struc/cc) 0.00292

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	2.7	0.00195	0.00 - 0.00615	2
Total Asbestos Structures	2.7	0.00195	0.00 - 0.00615	2
Asbestos Structures > 5um	1.4	0.000976	0.00 - 0.00463	1
Asbestos Fibers and Bundles > 5um	1.4	0.000976	0.00 - 0.00463	1
PCM Equivalent Fibers-US	0.0	<0.00292	0.00 - 0.00292	0
PCM Equivalent Structures-US	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL ASB STRUCS >10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00292	0.00 - 0.00292	0
AHERA-like Total Structures 3:1	2.7	0.00195	0.00 - 0.00615	2
AHERA-like Asb Strucs >5 and 3:1	1.4	0.000976	0.00 - 0.00463	1
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00292	0.00 - 0.00292	0
AHERA-like Asb Strucs >10 and 3:1	1.4	0.000976	0.00 - 0.00463	1
Total Other Amphibole Strucs 3:1	0.0	<0.00292	0.00 - 0.00292	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00292	0.00 - 0.00292	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00292	0.00 - 0.00292	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00292	0.00 - 0.00292	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S15 A1
Client Sample No. CC2-L6-2CC-100304
Description
Analysis Date 10/9/2004
Analyst KM

Volume (L) 523
No. of Grid Openings 51
Filter Area (mm2) 385
Area Analyzed (mm2) 0.739
Analytical Sens. (struc/cc) 0.000996
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	0.0	<0.00298	0.00 - 0.00298	0
Total Asbestos Structures	0.0	<0.00298	0.00 - 0.00298	0
Asbestos Structures > 5um	0.0	<0.00298	0.00 - 0.00298	0
Asbestos Fibers and Bundles > 5um	0.0	<0.00298	0.00 - 0.00298	0
PCM Equivalent Fibers-US	0.0	<0.00298	0.00 - 0.00298	0
PCM Equivalent Structures-US	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Asb Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S16 A1
Client Sample No. CC2-L6-3CC-100304
Description
Analysis Date 10/9/2004
Analyst KM

Volume (L) 520.12
No. of Grid Openings 52
Filter Area (mm2) 385
Area Analyzed (mm2) 0.753
Analytical Sens. (struc/cc) 0.000982
Dectection Limit. (struc/cc) 0.00294

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	14.6	0.0108	0.00539 - 0.0193	11
Total Asbestos Structures	14.6	0.0108	0.00539 - 0.0193	11
Asbestos Structures > 5um	8.0	0.00589	0.00216 - 0.0128	6
Asbestos Fibers and Bundles > 5um	6.6	0.00491	0.00160 - 0.0115	5
PCM Equivalent Fibers-US	6.6	0.00491	0.00160 - 0.0115	5
PCM Equivalent Structures-US	5.3	0.00393	0.00107 - 0.0101	4
PROTOCOL ASB STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
AHERA-like Total Structures 3:1	14.6	0.0108	0.00539 - 0.0193	11
AHERA-like Asb Strucs >5 and 3:1	8.0	0.00589	0.00216 - 0.0128	6
AHERA-like Asb Strucs 5 - 10 and 3:1	4.0	0.00295	0.00 - 0.00761	3
AHERA-like Asb Strucs >10 and 3:1	4.0	0.00295	0.00 - 0.00761	3
Total Other Amphibole Strucs 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S17 A1
Client Sample No. CC2-L6-4CC-100304
Description
Analysis Date 10/9/2004
Analyst KM

Volume (L) 542.69
No. of Grid Openings 49
Filter Area (mm2) 385
Area Analyzed (mm2) 0.710
Analytical Sens. (struc/cc) 0.000999
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	21.1	0.0150	0.00839 - 0.0247	15
Total Asbestos Structures	21.1	0.0150	0.00839 - 0.0247	15
Asbestos Structures > 5um	5.6	0.00400	0.00109 - 0.0102	4
Asbestos Fibers and Bundles > 5um	4.2	0.00300	0.00 - 0.00774	3
PCM Equivalent Fibers-US	5.6	0.00400	0.00109 - 0.0102	4
PCM Equivalent Structures-US	4.2	0.00300	0.00 - 0.00774	3
PROTOCOL ASB STRUCS 5-10	1.4	0.000999	0.00 - 0.00474	1
PROTOCOL ASB STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS TOTAL	1.4	0.000999	0.00 - 0.00474	1
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS 5-10	1.4	0.000999	0.00 - 0.00474	1
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	1.4	0.000999	0.00 - 0.00474	1
AHERA-like Total Structures 3:1	21.1	0.0150	0.00839 - 0.0247	15
AHERA-like Asb Strucs >5 and 3:1	5.6	0.00400	0.00109 - 0.0102	4
AHERA-like Asb Strucs 5 - 10 and 3:1	4.2	0.00300	0.00 - 0.00774	3
AHERA-like Asb Strucs >10 and 3:1	1.4	0.000999	0.00 - 0.00474	1
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S18 A1
Client Sample No. SVBA-H2-1FD-100204
Description
Analysis Date 10/9/2004
Analyst KM

Volume (L) 556.69
No. of Grid Openings 48
Filter Area (mm2) 385
Area Analyzed (mm2) 0.696
Analytical Sens. (struc/cc) 0.000994
Dectection Limit. (struc/cc) 0.00297

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	24.4	0.0169	0.00985 - 0.0271	17
Total Asbestos Structures	24.4	0.0169	0.00985 - 0.0271	17
Asbestos Structures > 5um	5.8	0.00398	0.00108 - 0.0102	4
Asbestos Fibers and Bundles > 5um	4.3	0.00298	0.00 - 0.00771	3
PCM Equivalent Fibers-US	4.3	0.00298	0.00 - 0.00771	3
PCM Equivalent Structures-US	1.4	0.000994	0.00 - 0.00471	1
PROTOCOL ASB STRUCS 5-10	1.4	0.000994	0.00 - 0.00471	1
PROTOCOL ASB STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS TOTAL	1.4	0.000994	0.00 - 0.00471	1
PROTOCOL CHRYS STRUCS 5-10	1.4	0.000994	0.00 - 0.00471	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS TOTAL	1.4	0.000994	0.00 - 0.00471	1
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Total Structures 3:1	24.4	0.0169	0.00985 - 0.0271	17
AHERA-like Asb Strucs >5 and 3:1	5.8	0.00398	0.00108 - 0.0102	4
AHERA-like Asb Strucs 5 - 10 and 3:1	4.3	0.00298	0.00 - 0.00771	3
AHERA-like Asb Strucs >10 and 3:1	1.4	0.000994	0.00 - 0.00471	1
Total Other Amphibole Strucs 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S19 A1
Client Sample No. SVBA-H2-2FD-100204
Description
Analysis Date 10/10/2004
Analyst KM

Volume (L) 531.47
No. of Grid Openings 50
Filter Area (mm2) 385
Area Analyzed (mm2) 0.724
Analytical Sens. (struc/cc) 0.00100
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	12.4	0.00900	0.00411 - 0.0171	9
Total Asbestos Structures	12.4	0.00900	0.00411 - 0.0171	9
Asbestos Structures > 5um	4.1	0.00300	0.00 - 0.00775	3
Asbestos Fibers and Bundles > 5um	4.1	0.00300	0.00 - 0.00775	3
PCM Equivalent Fibers-US	4.1	0.00300	0.00 - 0.00775	3
PCM Equivalent Structures-US	4.1	0.00300	0.00 - 0.00775	3
PROTOCOL ASB STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
AHERA-like Total Structures 3:1	12.4	0.00900	0.00411 - 0.0171	9
AHERA-like Asb Strucs >5 and 3:1	4.1	0.00300	0.00 - 0.00775	3
AHERA-like Asb Strucs 5 - 10 and 3:1	4.1	0.00300	0.00 - 0.00775	3
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S20 A1
Client Sample No. SVBA-H2-3FD-100204
Description
Analysis Date 10/10/2004
Analyst KM

Volume (L) 562.41
No. of Grid Openings 48
Filter Area (mm2) 385
Area Analyzed (mm2) 0.696
Analytical Sens. (struc/cc) 0.000984
Dectection Limit. (struc/cc) 0.00294

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	4.3	0.00295	0.00 - 0.00763	3
Total Asbestos Structures	4.3	0.00295	0.00 - 0.00763	3
Asbestos Structures > 5um	2.9	0.00197	0.00 - 0.00620	2
Asbestos Fibers and Bundles > 5um	1.4	0.000984	0.00 - 0.00467	1
PCM Equivalent Fibers-US	0.0	<0.00294	0.00 - 0.00294	0
PCM Equivalent Structures-US	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
AHERA-like Total Structures 3:1	4.3	0.00295	0.00 - 0.00763	3
AHERA-like Asb Strucs >5 and 3:1	2.9	0.00197	0.00 - 0.00620	2
AHERA-like Asb Strucs 5 - 10 and 3:1	1.4	0.000984	0.00 - 0.00467	1
AHERA-like Asb Strucs >10 and 3:1	1.4	0.000984	0.00 - 0.00467	1
Total Other Amphibole Strucs 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S21 A1
Client Sample No. SVBB-H2-1FD-100304
Description
Analysis Date 10/10/2004
Analyst DW

Volume (L) 611.75
No. of Grid Openings 43
Filter Area (mm2) 385
Area Analyzed (mm2) 0.623
Analytical Sens. (struc/cc) 0.00101
Dectection Limit. (struc/cc) 0.00302

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	3.2	0.00202	0.00 - 0.00636	2
Total Asbestos Structures	3.2	0.00202	0.00 - 0.00636	2
Asbestos Structures > 5um	0.0	<0.00302	0.00 - 0.00302	0
Asbestos Fibers and Bundles > 5um	0.0	<0.00302	0.00 - 0.00302	0
PCM Equivalent Fibers-US	0.0	<0.00302	0.00 - 0.00302	0
PCM Equivalent Structures-US	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL ASB STRUCS >10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00302	0.00 - 0.00302	0
AHERA-like Total Structures 3:1	3.2	0.00202	0.00 - 0.00636	2
AHERA-like Asb Strucs >5 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
Total Other Amphibole Strucs 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S22 A1
Client Sample No. SVBB-H2-2FD-100304
Description
Analysis Date 10/10/2004
Analyst KM

Volume (L) 563.3
No. of Grid Openings 48
Filter Area (mm2) 385
Area Analyzed (mm2) 0.696
Analytical Sens. (struc/cc) 0.000983
Dectection Limit. (struc/cc) 0.00294

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	0.0	<0.00294	0.00 - 0.00294	0
Total Asbestos Structures	0.0	<0.00294	0.00 - 0.00294	0
Asbestos Structures > 5um	0.0	<0.00294	0.00 - 0.00294	0
Asbestos Fibers and Bundles > 5um	0.0	<0.00294	0.00 - 0.00294	0
PCM Equivalent Fibers-US	0.0	<0.00294	0.00 - 0.00294	0
PCM Equivalent Structures-US	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00294	0.00 - 0.00294	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00294	0.00 - 0.00294	0
AHERA-like Total Structures 3:1	0.0	<0.00294	0.00 - 0.00294	0
AHERA-like Asb Strucs >5 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Total Other Amphibole Strucs 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00294	0.00 - 0.00294	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S23 A1
Client Sample No. SVBB-H2-3FD-100304
Description
Analysis Date 10/10/2004
Analyst DW

Volume (L) 580.91
No. of Grid Openings 46
Filter Area (mm2) 385
Area Analyzed (mm2) 0.667
Analytical Sens. (struc/cc) 0.000994
Dectection Limit. (struc/cc) 0.00297

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	0.0	<0.00297	0.00 - 0.00297	0
Total Asbestos Structures	0.0	<0.00297	0.00 - 0.00297	0
Asbestos Structures > 5um	0.0	<0.00297	0.00 - 0.00297	0
Asbestos Fibers and Bundles > 5um	0.0	<0.00297	0.00 - 0.00297	0
PCM Equivalent Fibers-US	0.0	<0.00297	0.00 - 0.00297	0
PCM Equivalent Structures-US	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Total Structures 3:1	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Asb Strucs >5 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Total Other Amphibole Strucs 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S24 A1
Client Sample No. TPG-L2-11CH-100404
Description
Analysis Date 10/10/2004
Analyst DW

Volume (L) 288.72
No. of Grid Openings 92
Filter Area (mm2) 385
Area Analyzed (mm2) 1.33
Analytical Sens. (struc/cc) 0.00100
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	10.5	0.0140	0.00766 - 0.0235	14
Total Asbestos Structures	10.5	0.0140	0.00766 - 0.0235	14
Asbestos Structures > 5um	6.8	0.00900	0.00412 - 0.0171	9
Asbestos Fibers and Bundles > 5um	6.0	0.00800	0.00346 - 0.0158	8
PCM Equivalent Fibers-US	5.3	0.00700	0.00281 - 0.0144	7
PCM Equivalent Structures-US	3.0	0.00400	0.00109 - 0.0102	4
PROTOCOL ASB STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS >10	1.5	0.00200	0.00 - 0.00630	2
PROTOCOL ASB STRUCS TOTAL	1.5	0.00200	0.00 - 0.00630	2
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS >10	0.8	0.00100	0.00 - 0.00474	1
PROTOCOL CHRYS STRUCS TOTAL	0.8	0.00100	0.00 - 0.00474	1
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS >10	0.8	0.00100	0.00 - 0.00474	1
PROTOCOL AMPH STRUCS TOTAL	0.8	0.00100	0.00 - 0.00474	1
AHERA-like Total Structures 3:1	10.5	0.0140	0.00766 - 0.0235	14
AHERA-like Asb Strucs >5 and 3:1	6.8	0.00900	0.00412 - 0.0171	9
AHERA-like Asb Strucs 5 - 10 and 3:1	2.3	0.00300	0.00 - 0.00775	3
AHERA-like Asb Strucs >10 and 3:1	4.5	0.00600	0.00220 - 0.0131	6
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S25 A1
Client Sample No. TPG-L2-1CH-100404
Description
Analysis Date 10/10/2004
Analyst KM

Volume (L) 291.6
No. of Grid Openings 91
Filter Area (mm2) 385
Area Analyzed (mm2) 1.32
Analytical Sens. (struc/cc) 0.00100
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	19.7	0.0260	0.0170 - 0.0381	26
Total Asbestos Structures	19.7	0.0260	0.0170 - 0.0381	26
Asbestos Structures > 5um	9.9	0.0130	0.00693 - 0.0223	13
Asbestos Fibers and Bundles > 5um	6.8	0.00901	0.00412 - 0.0171	9
PCM Equivalent Fibers-US	6.1	0.00801	0.00346 - 0.0158	8
PCM Equivalent Structures-US	5.3	0.00701	0.00282 - 0.0144	7
PROTOCOL ASB STRUCS 5-10	2.3	0.00300	0.00 - 0.00776	3
PROTOCOL ASB STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS TOTAL	2.3	0.00300	0.00 - 0.00776	3
PROTOCOL CHRYS STRUCS 5-10	0.8	0.00100	0.00 - 0.00475	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS TOTAL	0.8	0.00100	0.00 - 0.00475	1
PROTOCOL AMPH STRUCS 5-10	1.5	0.00200	0.00 - 0.00631	2
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	1.5	0.00200	0.00 - 0.00631	2
AHERA-like Total Structures 3:1	19.7	0.0260	0.0170 - 0.0381	26
AHERA-like Asb Strucs >5 and 3:1	9.9	0.0130	0.00693 - 0.0223	13
AHERA-like Asb Strucs 5 - 10 and 3:1	6.8	0.00901	0.00412 - 0.0171	9
AHERA-like Asb Strucs >10 and 3:1	3.0	0.00401	0.00109 - 0.0103	4
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S26 A1
Client Sample No. TPG-L2-1ZB-100404
Description
Analysis Date 10/11/2004
Analyst JH

Volume (L) 303.6
No. of Grid Openings 88
Filter Area (mm2) 385
Area Analyzed (mm2) 1.28
Analytical Sens. (struc/cc) 0.000995
Dectection Limit. (struc/cc) 0.00297

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	0.0	<0.00297	0.00 - 0.00297	0
Total Asbestos Structures	0.0	<0.00297	0.00 - 0.00297	0
Asbestos Structures > 5um	0.0	<0.00297	0.00 - 0.00297	0
Asbestos Fibers and Bundles > 5um	0.0	<0.00297	0.00 - 0.00297	0
PCM Equivalent Fibers-US	0.0	<0.00297	0.00 - 0.00297	0
PCM Equivalent Structures-US	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Total Structures 3:1	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Asb Strucs >5 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Total Other Amphibole Strucs 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S27 A1
Client Sample No. TPG-L2-2CH-100404
Description
Analysis Date 10/11/2004
Analyst JH

Volume (L) 290.4
No. of Grid Openings 44
Filter Area (mm2) 385
Area Analyzed (mm2) 0.638
Analytical Sens. (struc/cc) 0.00208
Dectection Limit. (struc/cc) 0.00622

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	83.1	0.110	0.0826 - 0.144 (Poisson)	53
Total Asbestos Structures	87.8	0.116	0.0880 - 0.151 (Poisson)	56
Asbestos Structures > 5um	17.3	0.0229	0.0114 - 0.0409	11
Asbestos Fibers and Bundles > 5um	7.8	0.0104	0.00338 - 0.0243	5
PCM Equivalent Fibers-US	6.3	0.00832	0.00227 - 0.0213	4
PCM Equivalent Structures-US	4.7	0.00624	0.00 - 0.0161	3
PROTOCOL ASB STRUCS 5-10	1.6	0.00208	0.00 - 0.00986	1
PROTOCOL ASB STRUCS >10	0.0	<0.00622	0.00 - 0.00622	0
PROTOCOL ASB STRUCS TOTAL	1.6	0.00208	0.00 - 0.00986	1
PROTOCOL CHRYS STRUCS 5-10	1.6	0.00208	0.00 - 0.00986	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00622	0.00 - 0.00622	0
PROTOCOL CHRYS STRUCS TOTAL	1.6	0.00208	0.00 - 0.00986	1
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00622	0.00 - 0.00622	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00622	0.00 - 0.00622	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00622	0.00 - 0.00622	0
AHERA-like Total Structures 3:1	81.6	0.108	0.0808 - 0.142 (Poisson)	52
AHERA-like Asb Strucs >5 and 3:1	17.3	0.0229	0.0114 - 0.0409	11
AHERA-like Asb Strucs 5 - 10 and 3:1	9.4	0.0125	0.00458 - 0.0272	6
AHERA-like Asb Strucs >10 and 3:1	7.8	0.0104	0.00338 - 0.0243	5
Total Other Amphibole Strucs 3:1	0.0	<0.00622	0.00 - 0.00622	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00622	0.00 - 0.00622	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00622	0.00 - 0.00622	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00622	0.00 - 0.00622	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S28 A1
Client Sample No. TPG-L2-3CH-100404
Description
Analysis Date 10/11/2004
Analyst KM

Volume (L) 299.16
No. of Grid Openings 89
Filter Area (mm2) 385
Area Analyzed (mm2) 1.29
Analytical Sens. (struc/cc) 0.000998
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	17.1	0.0220	0.0138 - 0.0332	22
Total Asbestos Structures	17.1	0.0220	0.0138 - 0.0332	22
Asbestos Structures > 5um	4.7	0.00599	0.00220 - 0.0130	6
Asbestos Fibers and Bundles > 5um	1.6	0.00200	0.00 - 0.00629	2
PCM Equivalent Fibers-US	0.8	0.000998	0.00 - 0.00473	1
PCM Equivalent Structures-US	0.8	0.000998	0.00 - 0.00473	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	17.1	0.0220	0.0138 - 0.0332	22
AHERA-like Asb Strucs >5 and 3:1	4.7	0.00599	0.00220 - 0.0130	6
AHERA-like Asb Strucs 5 - 10 and 3:1	3.9	0.00499	0.00162 - 0.0116	5
AHERA-like Asb Strucs >10 and 3:1	0.8	0.000998	0.00 - 0.00473	1
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S29 A1
Client Sample No. TPG-L2-4CH-100404
Description
Analysis Date 10/12/2004
Analyst DW

Volume (L) 290
No. of Grid Openings 17
Filter Area (mm2) 385
Area Analyzed (mm2) 0.246
Analytical Sens. (struc/cc) 0.00539
Dectection Limit. (struc/cc) 0.0161

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	198.9	0.264	0.195 - 0.349 (Poisson)	49
Total Asbestos Structures	215.2	0.286	0.214 - 0.374 (Poisson)	53
Asbestos Structures > 5um	60.9	0.0808	0.0452 - 0.133	15
Asbestos Fibers and Bundles > 5um	8.1	0.0108	0.00 - 0.0340	2
PCM Equivalent Fibers-US	8.1	0.0108	0.00 - 0.0340	2
PCM Equivalent Structures-US	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL ASB STRUCS >10	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL AMPH STRUCS >10	0.0	<0.0161	0.00 - 0.0161	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.0161	0.00 - 0.0161	0
AHERA-like Total Structures 3:1	198.9	0.264	0.195 - 0.349 (Poisson)	49
AHERA-like Asb Strucs >5 and 3:1	60.9	0.0808	0.0452 - 0.133	15
AHERA-like Asb Strucs 5 - 10 and 3:1	32.5	0.0431	0.0186 - 0.0850	8
AHERA-like Asb Strucs >10 and 3:1	28.4	0.0377	0.0152 - 0.0777	7
Total Other Amphibole Strucs 3:1	0.0	<0.0161	0.00 - 0.0161	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.0161	0.00 - 0.0161	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.0161	0.00 - 0.0161	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.0161	0.00 - 0.0161	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S30 A1
Client Sample No. TPG-L2-5CH-100404
Description
Analysis Date 10/12/2004
Analyst JH

Volume (L) 288.84
No. of Grid Openings 71
Filter Area (mm2) 385
Area Analyzed (mm2) 1.03
Analytical Sens. (struc/cc) 0.00130
Dectection Limit. (struc/cc) 0.00387

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	41.8	0.0557	0.0403 - 0.0750 (Poisson)	43
Total Asbestos Structures	48.6	0.0648	0.0481 - 0.0854 (Poisson)	50
Asbestos Structures > 5um	9.7	0.0130	0.00621 - 0.0238	10
Asbestos Fibers and Bundles > 5um	4.9	0.00648	0.00210 - 0.0151	5
PCM Equivalent Fibers-US	3.9	0.00518	0.00141 - 0.0133	4
PCM Equivalent Structures-US	2.9	0.00389	0.00 - 0.0100	3
PROTOCOL ASB STRUCS 5-10	1.9	0.00259	0.00 - 0.00816	2
PROTOCOL ASB STRUCS >10	0.0	<0.00387	0.00 - 0.00387	0
PROTOCOL ASB STRUCS TOTAL	1.9	0.00259	0.00 - 0.00816	2
PROTOCOL CHRYS STRUCS 5-10	1.0	0.00130	0.00 - 0.00614	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00387	0.00 - 0.00387	0
PROTOCOL CHRYS STRUCS TOTAL	1.0	0.00130	0.00 - 0.00614	1
PROTOCOL AMPH STRUCS 5-10	1.0	0.00130	0.00 - 0.00614	1
PROTOCOL AMPH STRUCS >10	0.0	<0.00387	0.00 - 0.00387	0
PROTOCOL AMPH STRUCS TOTAL	1.0	0.00130	0.00 - 0.00614	1
AHERA-like Total Structures 3:1	41.8	0.0557	0.0403 - 0.0750 (Poisson)	43
AHERA-like Asb Strucs >5 and 3:1	9.7	0.0130	0.00621 - 0.0238	10
AHERA-like Asb Strucs 5 - 10 and 3:1	8.7	0.0117	0.00533 - 0.0221	9
AHERA-like Asb Strucs >10 and 3:1	1.0	0.00130	0.00 - 0.00614	1
Total Other Amphibole Strucs 3:1	0.0	<0.00387	0.00 - 0.00387	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00387	0.00 - 0.00387	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00387	0.00 - 0.00387	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00387	0.00 - 0.00387	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S31 A1
Client Sample No. RHB-H2-1FD-100304
Description
Analysis Date 11/3/2004
Analyst JH

Volume (L) 1186.08
No. of Grid Openings 23
Filter Area (mm2) 385
Area Analyzed (mm2) 0.333
Analytical Sens. (struc/cc) 0.000974
Dectection Limit. (struc/cc) 0.00291

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	3.0	0.000974	0.00 - 0.00462	1
Total Asbestos Structures	3.0	0.000974	0.00 - 0.00462	1
Asbestos Structures > 5um	3.0	0.000974	0.00 - 0.00462	1
Asbestos Fibers and Bundles > 5um	3.0	0.000974	0.00 - 0.00462	1
PCM Equivalent Fibers-US	3.0	0.000974	0.00 - 0.00462	1
PCM Equivalent Structures-US	3.0	0.000974	0.00 - 0.00462	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL ASB STRUCS >10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00291	0.00 - 0.00291	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00291	0.00 - 0.00291	0
AHERA-like Total Structures 3:1	3.0	0.000974	0.00 - 0.00462	1
AHERA-like Asb Strucs >5 and 3:1	3.0	0.000974	0.00 - 0.00462	1
AHERA-like Asb Strucs 5 - 10 and 3:1	3.0	0.000974	0.00 - 0.00462	1
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00291	0.00 - 0.00291	0
Total Other Amphibole Strucs 3:1	0.0	<0.00291	0.00 - 0.00291	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00291	0.00 - 0.00291	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00291	0.00 - 0.00291	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00291	0.00 - 0.00291	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S32 A1
Client Sample No. RHB-H2-2FD-100304
Description
Analysis Date 11/3/2004
Analyst JH

Volume (L) 1220
No. of Grid Openings 22
Filter Area (mm2) 385
Area Analyzed (mm2) 0.319
Analytical Sens. (struc/cc) 0.000990
Dectection Limit. (struc/cc) 0.00296

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	18.8	0.00594	0.00218 - 0.0129	6
Total Asbestos Structures	18.8	0.00594	0.00218 - 0.0129	6
Asbestos Structures > 5um	9.4	0.00297	0.00 - 0.00767	3
Asbestos Fibers and Bundles > 5um	9.4	0.00297	0.00 - 0.00767	3
PCM Equivalent Fibers-US	9.4	0.00297	0.00 - 0.00767	3
PCM Equivalent Structures-US	9.4	0.00297	0.00 - 0.00767	3
PROTOCOL ASB STRUCS 5-10	3.1	0.000990	0.00 - 0.00469	1
PROTOCOL ASB STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS TOTAL	3.1	0.000990	0.00 - 0.00469	1
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS 5-10	3.1	0.000990	0.00 - 0.00469	1
PROTOCOL AMPH STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS TOTAL	3.1	0.000990	0.00 - 0.00469	1
AHERA-like Total Structures 3:1	18.8	0.00594	0.00218 - 0.0129	6
AHERA-like Asb Strucs >5 and 3:1	9.4	0.00297	0.00 - 0.00767	3
AHERA-like Asb Strucs 5 - 10 and 3:1	6.3	0.00198	0.00 - 0.00624	2
AHERA-like Asb Strucs >10 and 3:1	3.1	0.000990	0.00 - 0.00469	1
Total Other Amphibole Strucs 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S33 A1
Client Sample No. RHB-H2-3FD-100304
Description
Analysis Date 11/3/2004
Analyst KM

Volume (L) 1140.7
No. of Grid Openings 23
Filter Area (mm2) 385
Area Analyzed (mm2) 0.333
Analytical Sens. (struc/cc) 0.00101
Dectection Limit. (struc/cc) 0.00303

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	6.0	0.00203	0.00 - 0.00638	2
Total Asbestos Structures	6.0	0.00203	0.00 - 0.00638	2
Asbestos Structures > 5um	3.0	0.00101	0.00 - 0.00480	1
Asbestos Fibers and Bundles > 5um	3.0	0.00101	0.00 - 0.00480	1
PCM Equivalent Fibers-US	3.0	0.00101	0.00 - 0.00480	1
PCM Equivalent Structures-US	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL ASB STRUCS >10	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00303	0.00 - 0.00303	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00303	0.00 - 0.00303	0
AHERA-like Total Structures 3:1	6.0	0.00203	0.00 - 0.00638	2
AHERA-like Asb Strucs >5 and 3:1	3.0	0.00101	0.00 - 0.00480	1
AHERA-like Asb Strucs 5 - 10 and 3:1	3.0	0.00101	0.00 - 0.00480	1
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00303	0.00 - 0.00303	0
Total Other Amphibole Strucs 3:1	0.0	<0.00303	0.00 - 0.00303	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00303	0.00 - 0.00303	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00303	0.00 - 0.00303	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00303	0.00 - 0.00303	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S34 A1
Client Sample No. RHB-L2-1CH-100304
Description
Analysis Date 11/3/2004
Analyst TM

Volume (L) 309.12
No. of Grid Openings 86
Filter Area (mm2) 385
Area Analyzed (mm2) 1.25
Analytical Sens. (struc/cc) 0.000999
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	7.2	0.00900	0.00411 - 0.0171	9
Total Asbestos Structures	7.2	0.00900	0.00411 - 0.0171	9
Asbestos Structures > 5um	4.8	0.00600	0.00220 - 0.0131	6
Asbestos Fibers and Bundles > 5um	2.4	0.00300	0.00 - 0.00775	3
PCM Equivalent Fibers-US	2.4	0.00300	0.00 - 0.00775	3
PCM Equivalent Structures-US	2.4	0.00300	0.00 - 0.00775	3
PROTOCOL ASB STRUCS 5-10	0.8	0.000999	0.00 - 0.00474	1
PROTOCOL ASB STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS TOTAL	0.8	0.000999	0.00 - 0.00474	1
PROTOCOL CHRYS STRUCS 5-10	0.8	0.000999	0.00 - 0.00474	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS TOTAL	0.8	0.000999	0.00 - 0.00474	1
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
AHERA-like Total Structures 3:1	7.2	0.00900	0.00411 - 0.0171	9
AHERA-like Asb Strucs >5 and 3:1	4.8	0.00600	0.00220 - 0.0131	6
AHERA-like Asb Strucs 5 - 10 and 3:1	4.0	0.00500	0.00162 - 0.0117	5
AHERA-like Asb Strucs >10 and 3:1	0.8	0.000999	0.00 - 0.00474	1
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S35 A1
Client Sample No. RHB-L2-2CH-100304
Description
Analysis Date 11/3/2004
Analyst DW

Volume (L) 293.4
No. of Grid Openings 91
Filter Area (mm2) 385
Area Analyzed (mm2) 1.32
Analytical Sens. (struc/cc) 0.000995
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	2.3	0.00299	0.00 - 0.00771	3
Total Asbestos Structures	2.3	0.00299	0.00 - 0.00771	3
Asbestos Structures > 5um	1.5	0.00199	0.00 - 0.00627	2
Asbestos Fibers and Bundles > 5um	1.5	0.00199	0.00 - 0.00627	2
PCM Equivalent Fibers-US	1.5	0.00199	0.00 - 0.00627	2
PCM Equivalent Structures-US	0.8	0.000995	0.00 - 0.00472	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	2.3	0.00299	0.00 - 0.00771	3
AHERA-like Asb Strucs >5 and 3:1	1.5	0.00199	0.00 - 0.00627	2
AHERA-like Asb Strucs 5 - 10 and 3:1	0.8	0.000995	0.00 - 0.00472	1
AHERA-like Asb Strucs >10 and 3:1	0.8	0.000995	0.00 - 0.00472	1
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S36 A1
Client Sample No. RHB-L2-3CH-100304
Description
Analysis Date 11/4/2004
Analyst JH

Volume (L) 306.48
No. of Grid Openings 87
Filter Area (mm2) 385
Area Analyzed (mm2) 1.26
Analytical Sens. (struc/cc) 0.000996
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	0.8	0.000996	0.00 - 0.00472	1
Total Asbestos Structures	0.8	0.000996	0.00 - 0.00472	1
Asbestos Structures > 5um	0.8	0.000996	0.00 - 0.00472	1
Asbestos Fibers and Bundles > 5um	0.8	0.000996	0.00 - 0.00472	1
PCM Equivalent Fibers-US	0.8	0.000996	0.00 - 0.00472	1
PCM Equivalent Structures-US	0.8	0.000996	0.00 - 0.00472	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	0.8	0.000996	0.00 - 0.00472	1
AHERA-like Asb Strucs >5 and 3:1	0.8	0.000996	0.00 - 0.00472	1
AHERA-like Asb Strucs 5 - 10 and 3:1	0.8	0.000996	0.00 - 0.00472	1
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S37 A1
Client Sample No. RHB-L2-4CH-100304
Description
Analysis Date 11/4/2004
Analyst KM

Volume (L) 312.48
No. of Grid Openings 86
Filter Area (mm2) 385
Area Analyzed (mm2) 1.25
Analytical Sens. (struc/cc) 0.000989
Dectection Limit. (struc/cc) 0.00296

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	3.2	0.00395	0.00108 - 0.0101	4
Total Asbestos Structures	3.2	0.00395	0.00108 - 0.0101	4
Asbestos Structures > 5um	2.4	0.00297	0.00 - 0.00766	3
Asbestos Fibers and Bundles > 5um	0.8	0.000989	0.00 - 0.00469	1
PCM Equivalent Fibers-US	0.8	0.000989	0.00 - 0.00469	1
PCM Equivalent Structures-US	0.8	0.000989	0.00 - 0.00469	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
AHERA-like Total Structures 3:1	3.2	0.00395	0.00108 - 0.0101	4
AHERA-like Asb Strucs >5 and 3:1	2.4	0.00297	0.00 - 0.00766	3
AHERA-like Asb Strucs 5 - 10 and 3:1	2.4	0.00297	0.00 - 0.00766	3
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Total Other Amphibole Strucs 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S38 A1
Client Sample No. RHB-L2-5CH-100304
Description
Analysis Date 11/4/2004
Analyst KM

Volume (L) 295.56
No. of Grid Openings 90
Filter Area (mm2) 385
Area Analyzed (mm2) 1.30
Analytical Sens. (struc/cc) 0.000999
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	3.1	0.00400	0.00109 - 0.0102	4
Total Asbestos Structures	3.1	0.00400	0.00109 - 0.0102	4
Asbestos Structures > 5um	1.5	0.00200	0.00 - 0.00629	2
Asbestos Fibers and Bundles > 5um	0.8	0.000999	0.00 - 0.00473	1
PCM Equivalent Fibers-US	0.8	0.000999	0.00 - 0.00473	1
PCM Equivalent Structures-US	0.8	0.000999	0.00 - 0.00473	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
AHERA-like Total Structures 3:1	3.1	0.00400	0.00109 - 0.0102	4
AHERA-like Asb Strucs >5 and 3:1	1.5	0.00200	0.00 - 0.00629	2
AHERA-like Asb Strucs 5 - 10 and 3:1	1.5	0.00200	0.00 - 0.00629	2
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S39 A1
Client Sample No. SVBA-L2-11CH-100204
Description
Analysis Date 11/4/2004
Analyst TM

Volume (L) 296.24
No. of Grid Openings 90
Filter Area (mm2) 385
Area Analyzed (mm2) 1.30
Analytical Sens. (struc/cc) 0.000997
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	14.6	0.0189	0.0114 - 0.0296	19
Total Asbestos Structures	14.6	0.0189	0.0114 - 0.0296	19
Asbestos Structures > 5um	10.0	0.0130	0.00690 - 0.0222	13
Asbestos Fibers and Bundles > 5um	6.1	0.00797	0.00344 - 0.0157	8
PCM Equivalent Fibers-US	5.4	0.00698	0.00280 - 0.0144	7
PCM Equivalent Structures-US	3.8	0.00498	0.00162 - 0.0116	5
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	14.6	0.0189	0.0114 - 0.0296	19
AHERA-like Asb Strucs >5 and 3:1	10.0	0.0130	0.00690 - 0.0222	13
AHERA-like Asb Strucs 5 - 10 and 3:1	6.1	0.00797	0.00344 - 0.0157	8
AHERA-like Asb Strucs >10 and 3:1	3.8	0.00498	0.00162 - 0.0116	5
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S40 A1
Client Sample No. SVBA-L2-1CH-100204
Description
Analysis Date 11/4/2004
Analyst DW

Volume (L) 292.44
No. of Grid Openings 90
Filter Area (mm2) 385
Area Analyzed (mm2) 1.30
Analytical Sens. (struc/cc) 0.00101
Dectection Limit. (struc/cc) 0.00302

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	15.3	0.0202	0.0123 - 0.0312	20
Total Asbestos Structures	15.3	0.0202	0.0123 - 0.0312	20
Asbestos Structures > 5um	11.5	0.0151	0.00848 - 0.0250	15
Asbestos Fibers and Bundles > 5um	10.7	0.0141	0.00773 - 0.0237	14
PCM Equivalent Fibers-US	9.2	0.0121	0.00626 - 0.0212	12
PCM Equivalent Structures-US	7.7	0.0101	0.00484 - 0.0186	10
PROTOCOL ASB STRUCS 5-10	0.8	0.00101	0.00 - 0.00479	1
PROTOCOL ASB STRUCS >10	0.8	0.00101	0.00 - 0.00479	1
PROTOCOL ASB STRUCS TOTAL	1.5	0.00202	0.00 - 0.00636	2
PROTOCOL CHRYS STRUCS 5-10	0.8	0.00101	0.00 - 0.00479	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL CHRYS STRUCS TOTAL	0.8	0.00101	0.00 - 0.00479	1
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00302	0.00 - 0.00302	0
PROTOCOL AMPH STRUCS >10	0.8	0.00101	0.00 - 0.00479	1
PROTOCOL AMPH STRUCS TOTAL	0.8	0.00101	0.00 - 0.00479	1
AHERA-like Total Structures 3:1	15.3	0.0202	0.0123 - 0.0312	20
AHERA-like Asb Strucs >5 and 3:1	11.5	0.0151	0.00848 - 0.0250	15
AHERA-like Asb Strucs 5 - 10 and 3:1	4.6	0.00606	0.00222 - 0.0132	6
AHERA-like Asb Strucs >10 and 3:1	6.9	0.00909	0.00415 - 0.0172	9
Total Other Amphibole Strucs 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00302	0.00 - 0.00302	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S41 A1
Client Sample No. SVBA-L2-2CH-100204
Description
Analysis Date 11/5/2004
Analyst JH

Volume (L) 297.72
No. of Grid Openings 90
Filter Area (mm2) 385
Area Analyzed (mm2) 1.30
Analytical Sens. (struc/cc) 0.000992
Dectection Limit. (struc/cc) 0.00296

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	10.7	0.0139	0.00759 - 0.0233	14
Total Asbestos Structures	10.7	0.0139	0.00759 - 0.0233	14
Asbestos Structures > 5um	5.4	0.00694	0.00279 - 0.0143	7
Asbestos Fibers and Bundles > 5um	3.8	0.00496	0.00161 - 0.0116	5
PCM Equivalent Fibers-US	1.5	0.00198	0.00 - 0.00625	2
PCM Equivalent Structures-US	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
AHERA-like Total Structures 3:1	10.7	0.0139	0.00759 - 0.0233	14
AHERA-like Asb Strucs >5 and 3:1	5.4	0.00694	0.00279 - 0.0143	7
AHERA-like Asb Strucs 5 - 10 and 3:1	0.8	0.000992	0.00 - 0.00470	1
AHERA-like Asb Strucs >10 and 3:1	4.6	0.00595	0.00218 - 0.0130	6
Total Other Amphibole Strucs 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S42 A1
Client Sample No. SVBA-L2-3CH-100204
Description
Analysis Date 11/6/2004
Analyst KM

Volume (L) 299.52
No. of Grid Openings 89
Filter Area (mm2) 385
Area Analyzed (mm2) 1.29
Analytical Sens. (struc/cc) 0.000997
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	7.8	0.00997	0.00478 - 0.0183	10
Total Asbestos Structures	7.0	0.00897	0.00410 - 0.0170	9
Asbestos Structures > 5um	4.7	0.00598	0.00219 - 0.0130	6
Asbestos Fibers and Bundles > 5um	3.1	0.00399	0.00109 - 0.0102	4
PCM Equivalent Fibers-US	3.1	0.00399	0.00109 - 0.0102	4
PCM Equivalent Structures-US	1.6	0.00199	0.00 - 0.00628	2
PROTOCOL ASB STRUCS 5-10	1.6	0.00199	0.00 - 0.00628	2
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	1.6	0.00199	0.00 - 0.00628	2
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	1.6	0.00199	0.00 - 0.00628	2
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	1.6	0.00199	0.00 - 0.00628	2
AHERA-like Total Structures 3:1	7.0	0.00897	0.00410 - 0.0170	9
AHERA-like Asb Strucs >5 and 3:1	4.7	0.00598	0.00219 - 0.0130	6
AHERA-like Asb Strucs 5 - 10 and 3:1	2.3	0.00299	0.00 - 0.00772	3
AHERA-like Asb Strucs >10 and 3:1	2.3	0.00299	0.00 - 0.00772	3
Total Other Amphibole Strucs 3:1	0.8	0.000997	0.00 - 0.00472	1
Other Amphibole Strucs >5 and 3:1	0.8	0.000997	0.00 - 0.00472	1
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.8	0.000997	0.00 - 0.00472	1

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S43 A1
Client Sample No. SVBA-L2-4CH-100204
Description
Analysis Date 11/6/2004
Analyst JH

Volume (L) 293.28
No. of Grid Openings 91
Filter Area (mm2) 385
Area Analyzed (mm2) 1.32
Analytical Sens. (struc/cc) 0.000996
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	8.3	0.0110	0.00547 - 0.0196	11
Total Asbestos Structures	8.3	0.0110	0.00547 - 0.0196	11
Asbestos Structures > 5um	6.8	0.00896	0.00410 - 0.0170	9
Asbestos Fibers and Bundles > 5um	6.8	0.00896	0.00410 - 0.0170	9
PCM Equivalent Fibers-US	5.3	0.00697	0.00280 - 0.0144	7
PCM Equivalent Structures-US	5.3	0.00697	0.00280 - 0.0144	7
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	8.3	0.0110	0.00547 - 0.0196	11
AHERA-like Asb Strucs >5 and 3:1	6.8	0.00896	0.00410 - 0.0170	9
AHERA-like Asb Strucs 5 - 10 and 3:1	3.8	0.00498	0.00162 - 0.0116	5
AHERA-like Asb Strucs >10 and 3:1	3.0	0.00398	0.00109 - 0.0102	4
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S44 A1
Client Sample No. SVBA-L2-5CH-100204
Description
Analysis Date 11/6/2004
Analyst KM

Volume (L) 291.12
No. of Grid Openings 93
Filter Area (mm2) 385
Area Analyzed (mm2) 1.35
Analytical Sens. (struc/cc) 0.000981
Dectection Limit. (struc/cc) 0.00293

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	10.4	0.0137	0.00751 - 0.0231	14
Total Asbestos Structures	9.6	0.0128	0.00679 - 0.0218	13
Asbestos Structures > 5um	5.2	0.00687	0.00276 - 0.0142	7
Asbestos Fibers and Bundles > 5um	4.5	0.00589	0.00216 - 0.0128	6
PCM Equivalent Fibers-US	3.7	0.00491	0.00159 - 0.0115	5
PCM Equivalent Structures-US	3.0	0.00393	0.00107 - 0.0101	4
PROTOCOL ASB STRUCS 5-10	0.7	0.000981	0.00 - 0.00465	1
PROTOCOL ASB STRUCS >10	0.0	<0.00293	0.00 - 0.00293	0
PROTOCOL ASB STRUCS TOTAL	0.7	0.000981	0.00 - 0.00465	1
PROTOCOL CHRYS STRUCS 5-10	0.7	0.000981	0.00 - 0.00465	1
PROTOCOL CHRYS STRUCS >10	0.0	<0.00293	0.00 - 0.00293	0
PROTOCOL CHRYS STRUCS TOTAL	0.7	0.000981	0.00 - 0.00465	1
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00293	0.00 - 0.00293	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00293	0.00 - 0.00293	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00293	0.00 - 0.00293	0
AHERA-like Total Structures 3:1	10.4	0.0137	0.00751 - 0.0231	14
AHERA-like Asb Strucs >5 and 3:1	5.2	0.00687	0.00276 - 0.0142	7
AHERA-like Asb Strucs 5 - 10 and 3:1	3.0	0.00393	0.00107 - 0.0101	4
AHERA-like Asb Strucs >10 and 3:1	2.2	0.00294	0.00 - 0.00761	3
Total Other Amphibole Strucs 3:1	0.0	<0.00293	0.00 - 0.00293	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00293	0.00 - 0.00293	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00293	0.00 - 0.00293	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00293	0.00 - 0.00293	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S45 A1
Client Sample No. SVBB-L2-12CH-100304
Description
Analysis Date 11/7/2004
Analyst KM

Volume (L) 288.75
No. of Grid Openings 93
Filter Area (mm2) 385
Area Analyzed (mm2) 1.35
Analytical Sens. (struc/cc) 0.000989
Dectection Limit. (struc/cc) 0.00296

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	3.0	0.00396	0.00108 - 0.0101	4
Total Asbestos Structures	3.7	0.00495	0.00161 - 0.0115	5
Asbestos Structures > 5um	0.7	0.000989	0.00 - 0.00469	1
Asbestos Fibers and Bundles > 5um	0.0	<0.00296	0.00 - 0.00296	0
PCM Equivalent Fibers-US	0.0	<0.00296	0.00 - 0.00296	0
PCM Equivalent Structures-US	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00296	0.00 - 0.00296	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00296	0.00 - 0.00296	0
AHERA-like Total Structures 3:1	3.0	0.00396	0.00108 - 0.0101	4
AHERA-like Asb Strucs >5 and 3:1	0.7	0.000989	0.00 - 0.00469	1
AHERA-like Asb Strucs 5 - 10 and 3:1	0.7	0.000989	0.00 - 0.00469	1
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Total Other Amphibole Strucs 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00296	0.00 - 0.00296	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S46 A1
Client Sample No. SVBB-L2-1CH-100304
Description
Analysis Date 11/7/2004
Analyst TM

Volume (L) 302.56
No. of Grid Openings 88
Filter Area (mm2) 385
Area Analyzed (mm2) 1.28
Analytical Sens. (struc/cc) 0.000998
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	5.5	0.00699	0.00281 - 0.0144	7
Total Asbestos Structures	5.5	0.00699	0.00281 - 0.0144	7
Asbestos Structures > 5um	4.7	0.00599	0.00220 - 0.0130	6
Asbestos Fibers and Bundles > 5um	4.7	0.00599	0.00220 - 0.0130	6
PCM Equivalent Fibers-US	3.1	0.00399	0.00109 - 0.0102	4
PCM Equivalent Structures-US	2.4	0.00299	0.00 - 0.00773	3
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	5.5	0.00699	0.00281 - 0.0144	7
AHERA-like Asb Strucs >5 and 3:1	4.7	0.00599	0.00220 - 0.0130	6
AHERA-like Asb Strucs 5 - 10 and 3:1	1.6	0.00200	0.00 - 0.00629	2
AHERA-like Asb Strucs >10 and 3:1	3.1	0.00399	0.00109 - 0.0102	4
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S47 A1
Client Sample No. SVBB-L2-2CH-100304
Description
Analysis Date 11/7/2004
Analyst DW

Volume (L) 309.16
No. of Grid Openings 86
Filter Area (mm2) 385
Area Analyzed (mm2) 1.25
Analytical Sens. (struc/cc) 0.000999
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	8.0	0.00999	0.00479 - 0.0184	10
Total Asbestos Structures	8.0	0.00999	0.00479 - 0.0184	10
Asbestos Structures > 5um	5.6	0.00700	0.00281 - 0.0144	7
Asbestos Fibers and Bundles > 5um	4.8	0.00600	0.00220 - 0.0131	6
PCM Equivalent Fibers-US	4.8	0.00600	0.00220 - 0.0131	6
PCM Equivalent Structures-US	0.8	0.000999	0.00 - 0.00474	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
AHERA-like Total Structures 3:1	8.0	0.00999	0.00479 - 0.0184	10
AHERA-like Asb Strucs >5 and 3:1	5.6	0.00700	0.00281 - 0.0144	7
AHERA-like Asb Strucs 5 - 10 and 3:1	1.6	0.00200	0.00 - 0.00630	2
AHERA-like Asb Strucs >10 and 3:1	4.0	0.00500	0.00162 - 0.0117	5
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S48 A1
Client Sample No. SVBB-L2-3CH-100304
Description
Analysis Date 11/8/2004
Analyst KM

Volume (L) 312.66
No. of Grid Openings 87
Filter Area (mm2) 385
Area Analyzed (mm2) 1.26
Analytical Sens. (struc/cc) 0.000977
Dectection Limit. (struc/cc) 0.00292

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	4.8	0.00586	0.00215 - 0.0128	6
Total Asbestos Structures	4.8	0.00586	0.00215 - 0.0128	6
Asbestos Structures > 5um	3.2	0.00391	0.00106 - 0.0100	4
Asbestos Fibers and Bundles > 5um	3.2	0.00391	0.00106 - 0.0100	4
PCM Equivalent Fibers-US	3.2	0.00391	0.00106 - 0.0100	4
PCM Equivalent Structures-US	2.4	0.00293	0.00 - 0.00757	3
PROTOCOL ASB STRUCS 5-10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL ASB STRUCS >10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00292	0.00 - 0.00292	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00292	0.00 - 0.00292	0
AHERA-like Total Structures 3:1	4.8	0.00586	0.00215 - 0.0128	6
AHERA-like Asb Strucs >5 and 3:1	3.2	0.00391	0.00106 - 0.0100	4
AHERA-like Asb Strucs 5 - 10 and 3:1	2.4	0.00293	0.00 - 0.00757	3
AHERA-like Asb Strucs >10 and 3:1	0.8	0.000977	0.00 - 0.00463	1
Total Other Amphibole Strucs 3:1	0.0	<0.00292	0.00 - 0.00292	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00292	0.00 - 0.00292	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00292	0.00 - 0.00292	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00292	0.00 - 0.00292	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S49 A1
Client Sample No. SVBB-L2-4CH-100304
Description
Analysis Date 11/8/2004
Analyst KM

Volume (L) 299.35
No. of Grid Openings 60
Filter Area (mm2) 385
Area Analyzed (mm2) 0.869
Analytical Sens. (struc/cc) 0.00148
Dectection Limit. (struc/cc) 0.00442

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	6.9	0.00888	0.00326 - 0.0193	6
Total Asbestos Structures	6.9	0.00888	0.00326 - 0.0193	6
Asbestos Structures > 5um	3.5	0.00444	0.00 - 0.0115	3
Asbestos Fibers and Bundles > 5um	2.3	0.00296	0.00 - 0.00932	2
PCM Equivalent Fibers-US	2.3	0.00296	0.00 - 0.00932	2
PCM Equivalent Structures-US	2.3	0.00296	0.00 - 0.00932	2
PROTOCOL ASB STRUCS 5-10	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL ASB STRUCS >10	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00442	0.00 - 0.00442	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00442	0.00 - 0.00442	0
AHERA-like Total Structures 3:1	6.9	0.00888	0.00326 - 0.0193	6
AHERA-like Asb Strucs >5 and 3:1	3.5	0.00444	0.00 - 0.0115	3
AHERA-like Asb Strucs 5 - 10 and 3:1	2.3	0.00296	0.00 - 0.00932	2
AHERA-like Asb Strucs >10 and 3:1	1.2	0.00148	0.00 - 0.00701	1
Total Other Amphibole Strucs 3:1	0.0	<0.00442	0.00 - 0.00442	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00442	0.00 - 0.00442	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00442	0.00 - 0.00442	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00442	0.00 - 0.00442	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S50 A1
Client Sample No. SVBB-L2-5CH-100304
Description
Analysis Date 11/8/2004
Analyst JH

Volume (L) 313.51
No. of Grid Openings 85
Filter Area (mm2) 385
Area Analyzed (mm2) 1.23
Analytical Sens. (struc/cc) 0.000997
Dectection Limit. (struc/cc) 0.00298

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	3.2	0.00399	0.00109 - 0.0102	4
Total Asbestos Structures	3.2	0.00399	0.00109 - 0.0102	4
Asbestos Structures > 5um	1.6	0.00199	0.00 - 0.00628	2
Asbestos Fibers and Bundles > 5um	1.6	0.00199	0.00 - 0.00628	2
PCM Equivalent Fibers-US	0.8	0.000997	0.00 - 0.00473	1
PCM Equivalent Structures-US	0.8	0.000997	0.00 - 0.00473	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00298	0.00 - 0.00298	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Total Structures 3:1	3.2	0.00399	0.00109 - 0.0102	4
AHERA-like Asb Strucs >5 and 3:1	1.6	0.00199	0.00 - 0.00628	2
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
AHERA-like Asb Strucs >10 and 3:1	1.6	0.00199	0.00 - 0.00628	2
Total Other Amphibole Strucs 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00298	0.00 - 0.00298	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S51 A1
Client Sample No. SVM-H2-1FD-100204
Description
Analysis Date 11/8/2004
Analyst DW

Volume (L) 1209.75
No. of Grid Openings 22
Filter Area (mm2) 385
Area Analyzed (mm2) 0.319
Analytical Sens. (struc/cc) 0.000998
Dectection Limit. (struc/cc) 0.00299

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	6.3	0.00200	0.00 - 0.00629	2
Total Asbestos Structures	6.3	0.00200	0.00 - 0.00629	2
Asbestos Structures > 5um	3.1	0.000998	0.00 - 0.00473	1
Asbestos Fibers and Bundles > 5um	3.1	0.000998	0.00 - 0.00473	1
PCM Equivalent Fibers-US	3.1	0.000998	0.00 - 0.00473	1
PCM Equivalent Structures-US	3.1	0.000998	0.00 - 0.00473	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL ASB STRUCS >10	3.1	0.000998	0.00 - 0.00473	1
PROTOCOL ASB STRUCS TOTAL	3.1	0.000998	0.00 - 0.00473	1
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL CHRYS STRUCS >10	3.1	0.000998	0.00 - 0.00473	1
PROTOCOL CHRYS STRUCS TOTAL	3.1	0.000998	0.00 - 0.00473	1
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00299	0.00 - 0.00299	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00299	0.00 - 0.00299	0
AHERA-like Total Structures 3:1	6.3	0.00200	0.00 - 0.00629	2
AHERA-like Asb Strucs >5 and 3:1	3.1	0.000998	0.00 - 0.00473	1
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
AHERA-like Asb Strucs >10 and 3:1	3.1	0.000998	0.00 - 0.00473	1
Total Other Amphibole Strucs 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00299	0.00 - 0.00299	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S52 A1
Client Sample No. SVM-H2-2FD-100204
Description
Analysis Date 11/8/2004
Analyst DW

Volume (L) 1192.92
No. of Grid Openings 23
Filter Area (mm2) 385
Area Analyzed (mm2) 0.333
Analytical Sens. (struc/cc) 0.000968
Dectection Limit. (struc/cc) 0.00290

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	9.0	0.00291	0.00 - 0.00751	3
Total Asbestos Structures	9.0	0.00291	0.00 - 0.00751	3
Asbestos Structures > 5um	6.0	0.00194	0.00 - 0.00610	2
Asbestos Fibers and Bundles > 5um	6.0	0.00194	0.00 - 0.00610	2
PCM Equivalent Fibers-US	6.0	0.00194	0.00 - 0.00610	2
PCM Equivalent Structures-US	6.0	0.00194	0.00 - 0.00610	2
PROTOCOL ASB STRUCS 5-10	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL ASB STRUCS >10	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00290	0.00 - 0.00290	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00290	0.00 - 0.00290	0
AHERA-like Total Structures 3:1	9.0	0.00291	0.00 - 0.00751	3
AHERA-like Asb Strucs >5 and 3:1	6.0	0.00194	0.00 - 0.00610	2
AHERA-like Asb Strucs 5 - 10 and 3:1	6.0	0.00194	0.00 - 0.00610	2
AHERA-like Asb Strucs >10 and 3:1	0.0	<0.00290	0.00 - 0.00290	0
Total Other Amphibole Strucs 3:1	0.0	<0.00290	0.00 - 0.00290	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00290	0.00 - 0.00290	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00290	0.00 - 0.00290	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00290	0.00 - 0.00290	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

ANALYSIS DETAIL

Lab/Cor Sample No. B4760 S53 A1
Client Sample No. SVM-H2-3FD-100204
Description
Analysis Date 11/8/2004
Analyst DW

Volume (L) 1215.12
No. of Grid Openings 22
Filter Area (mm2) 385
Area Analyzed (mm2) 0.319
Analytical Sens. (struc/cc) 0.000994
Dectection Limit. (struc/cc) 0.00297

Structure Type	Filter Density (s/mm2)	Concen-tration (struc/cc)	95% Confidence Interval (struc/cc)	Struc. Count
Primary Asbestos Structures	3.1	0.000994	0.00 - 0.00471	1
Total Asbestos Structures	3.1	0.000994	0.00 - 0.00471	1
Asbestos Structures > 5um	3.1	0.000994	0.00 - 0.00471	1
Asbestos Fibers and Bundles > 5um	3.1	0.000994	0.00 - 0.00471	1
PCM Equivalent Fibers-US	3.1	0.000994	0.00 - 0.00471	1
PCM Equivalent Structures-US	3.1	0.000994	0.00 - 0.00471	1
PROTOCOL ASB STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL ASB STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL CHRYS STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS 5-10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS >10	0.0	<0.00297	0.00 - 0.00297	0
PROTOCOL AMPH STRUCS TOTAL	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Total Structures 3:1	3.1	0.000994	0.00 - 0.00471	1
AHERA-like Asb Strucs >5 and 3:1	3.1	0.000994	0.00 - 0.00471	1
AHERA-like Asb Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
AHERA-like Asb Strucs >10 and 3:1	3.1	0.000994	0.00 - 0.00471	1
Total Other Amphibole Strucs 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >5 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs 5 - 10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0
Other Amphibole Strucs >10 and 3:1	0.0	<0.00297	0.00 - 0.00297	0

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-1ZB-100404 *Lab/Cor Sample No.:* B4760 S3 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	C43		NSD									
A	7	C23		NSD									
A	8	C3		NSD									
A	9	B13		NSD									
A	10	B33		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	C41		NSD									
A	17	C21		NSD									
A	18	C1		NSD									
A	19	B11		NSD									
A	20	B31		NSD									
A	21	B40		NSD									
A	22	B20		NSD									
A	23	B10		NSD									
A	24	D41		NSD									
A	25	D21		NSD									
A	26	D1		NSD									
A	27	A11		NSD									
A	28	A31		NSD									
A	29	A42		NSD									
A	30	A22		NSD									
A	31	A2		NSD									
A	32	D12		NSD									
A	33	D32		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-1ZB-100404 *Lab/Cor Sample No.:* B4760 S3 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	34	D43		NSD									
B	35	B44		NSD									
B	36	B24		NSD									
B	37	B4		NSD									
B	38	C14		NSD									
B	39	C34		NSD									
B	40	C43		NSD									
B	41	C23		NSD									
B	42	C3		NSD									
B	43	B13		NSD									
B	44	B33		NSD									
B	45	B42		NSD									
B	46	B22		NSD									
B	47	B2		NSD									
B	48	C12		NSD									
B	49	C32		NSD									
B	50	C41		NSD									
B	51	C21		NSD									
B	52	C1		NSD									
B	53	B11		NSD									
B	54	B31		NSD									
B	55	B40		NSD									
B	56	B20		NSD									
B	57	B10		NSD									
B	58	A10		NSD									
B	59	A30		NSD									
B	60	A41		NSD									
B	61	A21		NSD									
C	62	B43		NSD									
C	63	B23		NSD									
C	64	B3		NSD									
C	65	C13		NSD									
C	66	C33		NSD									
C	67	C42		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-1ZB-100404 *Lab/Cor Sample No.:* B4760 S3 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	68	C22		NSD									
C	69	C2		NSD									
C	70	B12		NSD									
C	71	B32		NSD									
C	72	B41		NSD									
C	73	B21		NSD									
C	74	B1		NSD									
C	75	C11		NSD									
C	76	C31		NSD									
C	77	C41		NSD									
C	78	C40		NSD									
C	79	C20		NSD									
C	80	C10		NSD									
C	81	D11		NSD									
C	82	D31		NSD									
C	83	D41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-2CH-100404 *Lab/Cor Sample No.:* B4760 S4 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B34	ADQ	1	1	F	7.5	0.8	9.4			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	2	B14		NSD									
A	3	C14		NSD									
A	4	C44	ADQ	2	2	F	4.8	0.8	6.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	5	B23		NSD									
A	6	B3		NSD									
A	7	C13		NSD									
A	8	C43		NSD									
A	9	B42		NSD									
A	10	B22		NSD									
A	11	B2		NSD									
A	12	C12		NSD									
A	13	C32	AZQ	3	3	F	8	0.5	16	845	544	Mg, Si, Ca, Fe Actinolite Zone Axis [3 1 0] -- KM	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	14	B21		NSD									
A	15	B1		NSD									
A	16	C11		NSD									
A	17	C31		NSD									
A	18	B20		NSD									
A	19	B10		NSD									
A	20	A20		NSD									
A	21	A10		NSD									
A	22	D10	ADQ	4	4	F	2	0.38	5.3			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	23	D40		NSD									
A	24	A21		NSD									
A	25	A1		NSD									
A	26	D11		NSD									
A	27	D31		NSD									
A	28	A32	ADQ	5	5	F	5.5	0.8	6.9			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	29	A12		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-2CH-100404 *Lab/Cor Sample No.:* B4760 S4 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	30	D2	CDQ	6	6	B	4.5	0.2	22	802	546	Mg, Si Chrysotile Confirmed - KM	TAS_AHRA
A	31	D22		NSD									
B	32	B24		NSD									
B	33	B14		NSD									
B	34	C14	ADQ	7	7	F	2.5	0.4	6.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	35	C24		NSD									
B	36	C34		NSD									
B	37	B33	CDQ	8	8	B	24	1	24			Mg, Si Chrysotile	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	38	B13	CDQ	9	9	B	5.3	0.4	13			Mg, Si Chrysotile	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	38	B13	CDQ	10	10	F	1.2	0.08	15			Mg, Si Chrysotile	TAS_AHRA
B	39	C3		NSD									
B	40	C23		NSD									
B	41	C43		NSD									
B	42	B12		NSD									
B	43	C2		NSD									
B	44	C22		NSD									
B	45	C42		NSD									
B	46	B11		NSD									
B	47	C1		NSD									
B	48	C21		NSD									
B	49	C41		NSD									
B	50	B40		NSD									
B	51	B20	ADQ	11	11	F	3.5	0.5	7.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	52	C20		NSD									
B	53	C40		NSD									
B	54	D10	ADQ	12	12	F	4	0.4	10			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	55	D40		NSD									
B	56	A30		NSD									
B	57	A10		NSD									
B	58	A31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-2CH-100404 *Lab/Cor Sample No.:* B4760 S4 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	59	A1		NSD									
B	60	D1		NSD									
B	61	D21		NSD									
B	62	D41		NSD									
C	63	B44		NSD									
C	64	C34	CMQ	13	13	F	1.2	0.1	12			Mg, Si Chrysotile	TAS_AHRA
C	65	C44		NSD									
C	66	B33		NSD									
C	67	B13	ADQ	14	14	F	8.5	0.6	14			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	68	C23		NSD									
C	69	C33		NSD									
C	70	B22		NSD									
C	71	B12		NSD									
C	72	C12		NSD									
C	73	C32		NSD									
C	74	C42		NSD									
C	75	B1		NSD									
C	76	C1		NSD									
C	77	C11		NSD									
C	78	C31		NSD									
C	79	A30		NSD									
C	80	A10		NSD									
C	81	D20		NSD									
C	82	D40		NSD									
C	83	A11	ADQ	15	15	F	5.5	0.7	7.9			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	84	A31		NSD									
C	85	D1		NSD									
C	86	D21		NSD									
C	87	D41		NSD									
C	88	A33	ADQ	16		MD1-0	5.3	1.5	3.5			Actinolite	AS>5, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-2CH-100404 *Lab/Cor Sample No.:* B4760 S4 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	88	A33	ADQ		16	MF	2.2	0.38	5.8			Mg, Al, Si, Ca, Fe Actinolite	
C	89	A13	ADQ	17	17	F	11	2.5	4.4			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	90	D3		NSD									
C	91	D33		NSD									
C	92	A24	CMQ	18	18	F	0.8	0.12	6.7			Mg, Al, Si, Ca, Fe Chrysotile	TAS_AHRA
C	92	A24	ADQ	19	19	F	10.5	1.5	7.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-3CH-100404 *Lab/Cor Sample No.:* B4760 S5 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44	AZQ	1	1	F	8	0.8	10	804	15501	Mg, Si, Ca, Fe Actinolite Zone Axis [5 1 2] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	B43		NSD									
A	7	B3		NSD									
A	8	B3		NSD									
A	9	C13		NSD									
A	10	C33		NSD									
A	11	B12	CDQ	2	2	B	0.7	0.2	3.5	805	548	Mg, Si Chrysotile Confirmed - KM	TAS_AHRA
A	12	C2		NSD									
A	13	C22		NSD									
A	14	C42		NSD									
A	15	B41		NSD									
A	16	B21	AZQ	3	3	F	1.5	0.25	6.0	806	549	Mg, Si, Ca, Fe Actinolite Zone Axis [1 0 1] - KM	TAS_AHRA
A	17	B1		NSD									
A	18	C11		NSD									
A	19	C31		NSD									
A	20	B30		NSD									
A	21	B10		NSD									
A	22	C10		NSD									
A	23	C40		NSD									
A	24	A40		NSD									
A	25	A20		NSD									
A	26	D10		NSD									
A	27	D30		NSD									
A	28	A31		NSD									
A	29	A11		NSD									
A	30	D1		NSD									
A	31	D21		NSD									
B	32	B4		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-3CH-100404 *Lab/Cor Sample No.:* B4760 S5 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	33	C4		NSD									
B	34	C24		NSD									
B	35	A33		NSD									
B	36	D13		NSD									
B	37	D23		NSD									
B	38	D33		NSD									
B	39	D43		NSD									
B	40	A32		NSD									
B	41	D22		NSD									
B	42	D32		NSD									
B	43	D42		NSD									
B	44	A41		NSD									
B	45	A21		NSD									
B	46	D11		NSD									
B	47	D21		NSD									
B	48	D31		NSD									
B	49	D41		NSD									
B	50	D30	ADQ	4		MD1-1	13	4	3.2			Amosite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	50	D30	AZQ		4	MB	10	2	5.0	807	550	Mg, Si, Fe Amosite Zone Axis [1 0 0] - KM	AFB>5, PCMEF-US
B	51	D40		NSD									
B	52	A30	ADQ	5		MD1-0	4	2	2.0			Actinolite	TAS_AHRA
B	52	A30	ADQ		5	MF	1.2	0.22	5.5			Mg, Al, Si, Ca, Fe Actinolite	
B	52	A30	ADQ	6	6	F	5	1	5.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	53	A10		NSD									
B	54	C10		NSD									
B	55	C30		NSD									
B	56	B1	CM	7	7	F	1.2	0.11	11			Chrysotile	TAS_AHRA
B	57	C11		NSD									
B	58	C21		NSD									
B	59	C41		NSD									
B	60	B22		NSD									
B	61	B2		NSD									
C	62	B44		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-3CH-100404 *Lab/Cor Sample No.:* B4760 S5 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	63	B34		NSD									
C	64	B43		NSD									
C	65	B33		NSD									
C	66	B23		NSD									
C	67	B42		NSD									
C	68	B32	ADQ	8	8	F	1.8	0.12	15			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	69	B20		NSD									
C	70	B10		NSD									
C	71	A40		NSD									
C	72	A30		NSD									
C	73	D40	ADQ	9	9	F	1.8	0.3	6.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	74	A21		NSD									
C	75	A11		NSD									
C	76	A42		NSD									
C	77	A32		NSD									
C	78	A22		NSD									
C	79	A2		NSD									
D	80	C10		NSD									
D	81	C20		NSD									
D	82	C30		NSD									
D	83	C40		NSD									
D	84	A21		NSD									
D	85	A1		NSD									
D	86	D11		NSD									
D	87	D31		NSD									
D	88	A42		NSD									
D	89	A22		NSD									
D	90	A2		NSD									
D	91	D31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-4CH-100404 *Lab/Cor Sample No.:* B4760 S6 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A10		NSD									
A	2	A30		NSD									
A	3	B40		NSD									
A	4	B42		NSD									
A	5	B22		NSD									
A	6	B24	AZQ	1	1	F	4.8	0.8	6.0	808	551	Mg, Si, Ca, Fe Actinolite Zone Axis [1 0 0] - KM	TAS_AHRA
A	7	B4		NSD									
A	8	B2		NSD									
A	9	A12		NSD									
A	10	A14	ADQ	2	2	F	4.5	0.6	7.5			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	11	A13		NSD									
A	12	D3		NSD									
A	13	D1		NSD									
A	14	C1		NSD									
A	15	C3	ADQ	3	3	F	5.3	1.2	4.4			Na, Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	16	C24		NSD									
A	17	C22		NSD									
A	18	C20		NSD									
A	19	D21		NSD									
A	20	D23	AZQ	4	4	F	2.3	0.4	5.8	810	553	Mg, Si, Ca, Fe Tremolite Zone Axis [4 1 3] - KM	TAS_AHRA
A	21	D43		NSD									
A	22	D41		NSD									
A	23	C40		NSD									
A	24	C42		NSD									
A	25	C33	ADQ	5	5	F	7.5	0.7	11		554	Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	26	C13		NSD									
A	27	B3		NSD									
A	28	B23	ADQ	6	6	F	4	0.5	8.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	29	B31		NSD									
B	30	A1		NSD									
B	31	A3		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-4CH-100404 *Lab/Cor Sample No.:* B4760 S6 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	32	A23		NSD									
B	33	A43		NSD									
B	34	A41	ADQ	7	7	F	4.8	0.4	12			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	35	B40		NSD									
B	36	B42		NSD									
B	37	B24		NSD									
B	38	B22		NSD									
B	39	B20		NSD									
B	40	A21		NSD									
B	41	A23		NSD									
B	42	A3		NSD									
B	43	A1		NSD									
B	44	B1		NSD									
B	45	B3		NSD									
B	46	C14		NSD									
B	47	C12		NSD									
B	48	C10		NSD									
B	49	D11		NSD									
B	50	D12		NSD									
B	51	D34		NSD									
B	52	D32		NSD									
B	53	D30		NSD									
B	54	C31		NSD									
B	55	C33		NSD									
B	56	C13	ADQ	8	8	F	5.5	1.2	4.6			Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	56	C13	AZQ	9	9	F	5.1	1.5	3.4	843	557	Mg, Si, Ca, Fe Actinolite Ferri-actinolite - Zone Axis [4 0 -1] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	57	B3		NSD									
B	58	B23		NSD									
B	59	B21		NSD									
B	60	A10		NSD									
C	61	D1		NSD									
C	62	D3		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-4CH-100404 *Lab/Cor Sample No.:* B4760 S6 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	63	D24		NSD									
C	64	D22		NSD									
C	65	D20		NSD									
C	66	C23		NSD									
C	67	C44		NSD									
C	68	C42		NSD									
C	69	C40		NSD									
C	70	D43		NSD									
C	71	A1		NSD									
C	72	A22		NSD									
C	73	A20		NSD									
C	74	B21		NSD									
C	75	B13		NSD									
C	76	B4		NSD									
C	77	B2		NSD									
C	78	C1		NSD									
C	79	C3		NSD									
C	80	B10		NSD									
C	81	B20		NSD									
C	82	B22		NSD									
C	83	B12		NSD									
C	84	B3		NSD									
C	85	B1		NSD									
C	86	A2		NSD									
C	87	A12		NSD									
C	88	A32	ADQ	10	10	F	4	1	4.0			Actinolite	TAS_AHRA
C	89	A31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-5CH-100404 *Lab/Cor Sample No.:* B4760 S7 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	C43		NSD									
A	7	C23		NSD									
A	8	C3		NSD									
A	9	B13		NSD									
A	10	B33		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	C41		NSD									
A	17	C21		NSD									
A	18	B11		NSD									
A	19	B31		NSD									
A	20	B41		NSD									
A	21	A31	AZQ	1	1	F	4.8	0.7	6.9	5229	15149	MG,AL,SI,CA,FE Actinolite Zone Axis [1 0 1] - KM	TAS_AHRA
A	22	A11		NSD									
A	23	D1		NSD									
A	24	D21		NSD									
A	25	D41		NSD									
A	26	D42		NSD									
A	27	D22		NSD									
A	28	D2		NSD									
A	29	A12		NSD									
A	30	A32		NSD									
A	31	A42	ADQ	2	2	F	2.5	0.5	5.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	32	A43		NSD									
A	33	A23		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-5CH-100404 *Lab/Cor Sample No.:* B4760 S7 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	34	A3		NSD									
A	35	D13		NSD									
A	36	D33		NSD									
A	37	D44		NSD									
B	38	B44		NSD									
B	39	B24		NSD									
B	40	B4		NSD									
B	41	C14		NSD									
B	42	C34	ADQ	3	3	F	16.5	2.5	6.6			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	43	C44	ADQ	4	4	F	3.5	0.65	5.4			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	44	C43		NSD									
B	45	C23		NSD									
B	46	C3		NSD									
B	47	B13		NSD									
B	48	B23		NSD									
B	49	B43		NSD									
B	50	B42		NSD									
B	51	B22		NSD									
B	52	B2		NSD									
B	53	C12		NSD									
B	54	C32		NSD									
B	55	C41		NSD									
B	56	C11		NSD									
B	57	A41		NSD									
B	58	A21		NSD									
B	59	A1		NSD									
B	60	D11		NSD									
B	61	D31		NSD									
B	62	D41		NSD									
B	63	D21		NSD									
B	64	D1		NSD									
B	65	A11		NSD									
B	66	A31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: APG-L2-5CH-100404 *Lab/Cor Sample No.:* B4760 S7 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	67	A41		NSD									
B	68	A43		NSD									
B	69	A33		NSD									
B	70	A23		NSD									
B	71	A13		NSD									
B	72	A3		NSD									
B	73	D3		NSD									
B	74	D13		NSD									
B	75	D23		NSD									
B	76	D33		NSD									
B	77	D43	CMQ	5	5	F	1	0.05	20	5230	15150	Mg, Si Chrysotile	TAS_AHRA
C	78	C42		NSD									
C	79	C32		NSD									
C	80	C12		NSD									
C	81	C2		NSD									
C	82	B12	CMQ	6	6	F	1.2	0.05	24	5283	15198	Mg, Si Chrysotile	TAS_AHRA
C	83	B4		NSD									
C	84	C4		NSD									
C	85	C14		NSD									
C	86	C24		NSD									
C	87	C34		NSD									
C	88	C44		NSD									
C	89	C43		NSD									
C	90	C33		NSD									
C	91	C23		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC1-L6-1CA-100204 *Lab/Cor Sample No.:* B4760 S8 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A1		NSD									
A	2	A11	AZQ	1	1	F	3.5	0.35	10	844	15152	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [3 0 2] - KM	TAS_AHRA
A	3	A10		NSD									
A	4	B10		NSD									
A	5	B11		NSD									
A	6	B1		NSD									
A	7	C1		NSD									
A	8	C11		NSD									
A	9	C10		NSD									
A	10	D10		NSD									
A	11	D11		NSD									
A	12	D1		NSD									
A	13	A21		NSD									
A	14	A20		NSD									
A	15	B20		NSD									
A	16	B21		NSD									
B	17	B10		NSD									
B	18	B11		NSD									
B	19	B1		NSD									
B	20	C1		NSD									
B	21	C11		NSD									
B	22	C10	CDQ	2	2	F	0.6	0.05	12	5233	15153	Mg, Si, Fe Chrysotile Confirmed - KM	TAS_AHRA
B	22	C10	AZQ	3	3	F	3.5	0.5	7.0	5234	15154	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 0 0] - KM	TAS_AHRA
B	23	D10	AZQ	4	4	F	9.5	2	4.8	5235	15155	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [3 1 0] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	24	D11		NSD									
B	25	D1		NSD									
B	26	A1		NSD									
B	27	A11		NSD									
B	28	A32		NSD									
B	29	A31		NSD									
B	30	A30	ADQ	5	5	F	4.25	1.1	3.9			Mg, Si, Ca, Fe Actinolite	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC1-L6-1CA-100204 *Lab/Cor Sample No.:* B4760 S8 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	31	B30		NSD									
B	32	B31		NSD									
B	33	B32		NSD									
B	34	B33		NSD									
B	35	B34		NSD									
B	36	B14		NSD									
B	37	B13		NSD									
B	38	B12		NSD									
B	39	A12		NSD									
B	40	D2		NSD									
B	41	C2		NSD									
B	42	C3		NSD									
B	43	C4		NSD									
B	44	C24		NSD									
B	45	C23		NSD									
B	46	C22		NSD									
B	47	C21	AZQ	6	6	F1-0	2.2	0.4	5.5	5236	15156	Mg, Si, Ca, Fe Tremolite Zone Axis [3 1 0] - KM	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC1-L6-1CB-100204 *Lab/Cor Sample No.:* B4760 S9 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	D1		NSD									
A	2	D3		NSD									
A	3	D24	CDQ	1		MD1-0	4.9	1.5	3.3			Chrysotile	TAS_AHRA
A	3	D24	CDQ		1	MB	4.9	0.4	12	811	558	Mg, Si Chrysotile Confirmed - KM	
A	4	D22		NSD									
A	5	D20		NSD									
A	6	C21	AZQ	2	2	F	11	1.5	7.3	812	559	Mg, Si, Ca, Fe Actinolite Zone Axis [2 0 -3] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	7	C23	OZQ	3	3	F	4.8	0.6	8.0	813	560	Na, Mg, Al, Si, Ca, Fe Edenite Zone Axis [3 2 1] - KM	TOS_AHRA
A	8	C43		NSD									
A	9	C41		NSD									
A	10	D40		NSD									
A	11	D42		NSD									
A	12	A2		NSD									
A	13	A4		NSD									
A	14	A24		NSD									
A	15	A22		NSD									
A	16	A20		NSD									
A	17	B21		NSD									
A	18	B23		NSD									
A	19	B24		NSD									
A	20	B34		NSD									
A	21	B44		NSD									
A	22	B33		NSD									
A	23	B13		NSD									
A	24	C3		NSD									
B	25	B24		NSD									
B	26	B4		NSD									
B	27	C14		NSD									
B	28	C34		NSD									
B	29	C44		NSD									
B	30	C43		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC1-L6-1CB-100204 *Lab/Cor Sample No.:* B4760 S9 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	31	C23		NSD									
B	32	C3		NSD									
B	33	B13		NSD									
B	34	B33		NSD									
B	35	B22		NSD									
B	36	B2		NSD									
B	37	C12		NSD									
B	38	C32		NSD									
B	39	C42		NSD									
B	40	C41		NSD									
B	41	C21		NSD									
B	42	C1		NSD									
B	43	B11	CDQ	4	4	F	1.2	0.05	24			Chrysotile	TAS_AHRA
B	44	B20	ADQ	5	5	F	1.25	0.4	3.1			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	45	A20		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC1-L6-2CB-100204 *Lab/Cor Sample No.:* B4760 S10 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C24		NSD									
A	6	C44		NSD									
A	7	C43		NSD									
A	8	C23	ADQ	1	1	F	2.5	0.4	6.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	8	C3		NSD									
A	9	B13	ADQ	2	2	F	6	1.3	4.6			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	10	B33		NSD									
A	11	B43		NSD									
A	12	B32		NSD									
A	13	B12		NSD									
A	14	C2		NSD									
A	15	C22		NSD									
A	16	C42		NSD									
A	17	C41		NSD									
A	18	C21		NSD									
A	19	C1		NSD									
A	20	B11		NSD									
A	21	B31		NSD									
A	22	B40	ADQ	3		MD1-0	5	5	1.0			Actinolite	TAS_AHRA
A	22	B40	ADQ		3	MF	2.5	0.3	8.3			Mg, Al, Si, Ca, Fe Actinolite	
A	23	B20		NSD									
A	24	A10		NSD									
A	25	A30		NSD									
A	26	A41		NSD									
A	27	A21		NSD									
A	28	A1	ADQ	4	4	F	5	0.5	10			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	29	D11	CDQ	5	5	F	5	0.15	33	814	561	Mg, Si Chrysotile Confirmed - KM	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC1-L6-2CB-100204 *Lab/Cor Sample No.:* B4760 S10 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	29	D11	AZQ	6	6	F	10	0.7	14	815	562	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [3 0 4] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	30	B44		NSD									
B	31	B24		NSD									
B	32	B4		NSD									
B	33	C14		NSD									
B	34	C34		NSD									
B	35	C43		NSD									
B	36	C23		NSD									
B	37	C3		NSD									
B	38	B13		NSD									
B	39	B33	ADQ	7	7	F	15	3.5	4.3			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	40	B42		NSD									
B	41	B22		NSD									
B	42	B12		NSD									
B	43	B2	ADQ	8	8	F	4	1	4.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	44	C12		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2A-L6-1CA-100304 *Lab/Cor Sample No.:* B4760 S12 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A1		NSD									
A	2	A2		NSD									
A	3	B24	CDQ	1	1	B	8.5	2	4.2	5238	15157	Mg, Si, Fe Chrysotile Confirmed - KM	AS>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	4	B22		NSD									
A	5	B21		NSD									
A	6	B20		NSD									
A	7	A11		NSD									
A	8	A10		NSD									
A	9	B10		NSD									
A	10	B12		NSD									
A	11	C20		NSD									
A	12	C21		NSD									
A	13	C23		NSD									
A	14	C33		NSD									
A	15	C44		NSD									
A	16	C43	CDQ	2		MD2-0	2.5	2	1.2	5239	15158	Mg, Si, Fe Chrysotile Confirmed - KM	TAS_AHRA
A	16	C43	CDQ		2	MF	1.25	0.05	25			Chrysotile	
A	16	C43	CDQ		3	MF	1	0.05	20			Chrysotile	
A	17	C42		NSD									
A	18	C32		NSD									
A	19	D41	ADQ	3	4	F	2.5	0.5	5.0		15159	Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	20	D42		NSD									
A	21	D32		NSD									
A	22	D31		NSD									
A	23	D30		NSD									
A	24	D20	CDQ	4		MD99-0	6	4	1.5	5242	15160	Mg, Si, Fe Chrysotile Confirmed - KM	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	24	D20	CDQ		5	MR50-0	2.5	1.5	1.7			Chrysotile	
A	24	D20	CDQ		6	MR30-0	2.5	1	2.5			Chrysotile	
A	24	D20	CDQ		7	MR15-0	2	1.5	1.3			Chrysotile	
A	24	D20	CDQ		8	MR7-0	2	0.8	2.5			Chrysotile	
A	24	D20	CDQ		9	MR30-0	2	0.5	4.0			Chrysotile	
A	24	D20	CDQ		10	MF	1.2	0.06	20			Chrysotile	

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2A-L6-1CA-100304 *Lab/Cor Sample No.:* B4760 S12 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	24	D20	CDQ		11	MF	0.7	0.05	14			Chrysotile	
A	24	D20	CDQ		12	MF	0.6	0.05	12			Chrysotile	
A	25	D21		NSD									
A	26	D22		NSD									
A	27	D12		NSD									
A	28	D11		NSD									
A	29	D10		NSD									
A	30	D2		NSD									
A	31	A12	CDQ	5	13	F	0.65	0.05	13	5243	15161	Mg, Si, Fe Chrysotile Confirmed - KM	TAS_AHRA
A	32	A22		NSD									
A	33	A30		NSD									
B	34	A1		NSD									
B	35	A11		NSD									
B	36	A10		NSD									
B	37	B10		NSD									
B	38	B11		NSD									
B	39	B1		NSD									
B	40	C1		NSD									
B	41	C11	CDQ	6	14	F	1.1	0.1	11			Mg, Si, Fe Chrysotile	TAS_AHRA
B	42	C10		NSD									
B	43	D10		NSD									
B	44	D11		NSD									
B	45	D1		NSD									
B	46	A2		NSD									
B	47	A12		NSD									
B	48	A22	AZQ	7	15	F	1.25	0.3	4.2	5284	15199	Mg, Si, Ca, Fe Actinolite Zone Axis [5 1 2] - KM	TAS_AHRA
B	49	A21		NSD									
B	50	A20	ADQ	8	16	F	4.5	0.55	8.2			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	51	B20		NSD									
B	52	B21		NSD									
B	53	B22		NSD									
B	54	B12		NSD									
B	55	B2		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2A-L6-1CA-100304 *Lab/Cor Sample No.:* B4760 S12 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	56	C2		NSD									
B	57	C12		NSD									
B	58	C22		NSD									
B	59	C21		NSD									
B	60	C20		NSD									
B	61	D20		NSD									
B	62	D21		NSD									
B	63	D22		NSD									
B	64	D12		NSD									
B	65	D2		NSD									
B	66	A30		NSD									
C	67	A1		NSD									
C	68	A10		NSD									
C	69	B10		NSD									
C	70	B11		NSD									
C	71	B1		NSD									
C	72	C1		NSD									
C	73	C11		NSD									
C	74	C10		NSD									
C	75	D10		NSD									
C	76	B44		NSD									
C	77	B24		NSD									
C	78	B4		NSD									
C	79	C14		NSD									
C	80	C34		NSD									
C	81	B33		NSD									
C	82	B12		NSD									
C	83	C2		NSD									
C	84	C22		NSD									
C	85	C42		NSD									
C	86	B41		NSD									
C	87	B21		NSD									
C	88	C21		NSD									
C	89	C41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2A-L6-1CA-100304 *Lab/Cor Sample No.:* B4760 S12 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	90	C20		NSD									
C	91	C40	CD	9		MD1-0	8	8	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	91	C40	CD		17	MB	3.5	0.5	7.0			Chrysotile	
C	92	B30	CM	10	18	F	0.6	0.1	6.0			Chrysotile	TAS_AHRA
C	93	A20		NSD									
C	94	D20		NSD									
C	95	D40		NSD									
C	96	D33	CM	11		MD3-0	4.5	3.5	1.3			Chrysotile	TAS_AHRA
C	96	D33	CM		19	MF	1.8	0.1	18			Chrysotile	
C	96	D33	CM		20	MB	1.6	0.2	8.0			Chrysotile	
C	96	D33	CM		21	MF	1.2	0.1	12			Chrysotile	
C	97	D13		NSD									
C	98	A2		NSD									
C	99	D12		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-11CC-100304 *Lab/Cor Sample No.:* B4760 S13 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	B34		NSD									
A	6	C23		NSD									
A	7	C3		NSD									
A	8	B23		NSD									
A	9	B33		NSD									
A	10	B42		NSD									
A	11	B22		NSD									
A	12	B2		NSD									
A	13	C12		NSD									
A	14	C32		NSD									
A	15	C31		NSD									
A	16	C11		NSD									
A	17	B1		NSD									
A	18	B10		NSD									
A	19	B20		NSD									
A	20	B30	AZQ	1	1	F	4	0.5	8.0	816	563	Mg, Si, Ca, Fe Actinolite Zone Axis [4 1 1] - KM	TAS_AHRA
A	21	B40		NSD									
A	22	A41		NSD									
A	23	A21		NSD									
A	24	A1		NSD									
A	25	A3		NSD									
B	26	D1		NSD									
B	27	D3		NSD									
B	28	D24		NSD									
B	29	D22		NSD									
B	30	D20		NSD									
B	31	C21		NSD									
B	32	C23		NSD									
B	33	C44		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-11CC-100304 *Lab/Cor Sample No.:* B4760 S13 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	34	C42		NSD									
B	35	C40		NSD									
B	36	D41		NSD									
B	37	D43		NSD									
B	38	B1		NSD									
B	39	B3		NSD									
B	40	B14		NSD									
B	41	B12		NSD									
B	42	B10		NSD									
B	43	A11	ADQ	2	2	F	16	4.5	3.6			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	44	A12	AZQ	3	3	F	6	1.3	4.6	817	564	Na, Mg, Si, Ca, Fe Edenite Zone Axis [9 -1 6] - KM	PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	45	A42		NSD									
B	46	A40		NSD									
B	47	B41		NSD									
B	48	B43		NSD									
B	49	B24		NSD									
B	50	B22		NSD									
B	51	B20		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-1CC-100304 *Lab/Cor Sample No.:* B4760 S14 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A2	CDQ	1	1	B	24	4	6.0	818	565	Mg, Si Chrysotile Confirmed - KM	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	2	A4		NSD									
A	3	A24		NSD									
A	4	A22		NSD									
A	5	A20		NSD									
A	6	B21		NSD									
A	7	B23		NSD									
A	8	B43		NSD									
A	9	B41		NSD									
A	10	A40		NSD									
A	11	A42		NSD									
A	12	A44		NSD									
A	13	A24		NSD									
A	14	A22		NSD									
A	15	A20		NSD									
A	16	B21		NSD									
A	17	B23		NSD									
A	18	B4		NSD									
A	19	B2		NSD									
A	20	A1		NSD									
A	21	A3		NSD									
A	22	D14		NSD									
A	23	D12		NSD									
A	24	D10		NSD									
A	25	C11		NSD									
B	26	D1		NSD									
B	27	D3		NSD									
B	28	D24		NSD									
B	29	D22		NSD									
B	30	D20		NSD									
B	31	C20		NSD									
B	32	D40		NSD									
B	33	D42		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-1CC-100304 *Lab/Cor Sample No.:* B4760 S14 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	34	A1		NSD									
B	35	A3		NSD									
B	36	A24		NSD									
B	37	A22		NSD									
B	38	A21		NSD									
B	39	B20		NSD									
B	40	B11		NSD									
B	41	B21		NSD									
B	42	B31		NSD									
B	43	B40		NSD									
B	44	A41		NSD									
B	45	A43		NSD									
B	46	A33		NSD									
B	47	A13		NSD									
B	48	D33	AZQ	2	2	F	4	0.6	6.7	819	566	Mg, Si, Ca, Fe Actinolite Zone Axis [9 1 10] - KM	TAS_AHRA
B	49	D31		NSD									
B	50	B10		NSD									
B	51	C10		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-2CC-100304 *Lab/Cor Sample No.:* B4760 S15 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B4		NSD									
A	3	C14		NSD									
A	4	C34		NSD									
A	5	C3		NSD									
A	6	C23		NSD									
A	7	C43		NSD									
A	8	B22		NSD									
A	9	B2		NSD									
A	10	C12		NSD									
A	11	C32		NSD									
A	12	B31		NSD									
A	13	C1		NSD									
A	14	C21		NSD									
A	15	C41		NSD									
A	16	D40		NSD									
A	17	D20		NSD									
B	18	B34		NSD									
B	19	B14		NSD									
B	19	C4		NSD									
B	20	C14		NSD									
B	21	C24		NSD									
B	22	C44		NSD									
B	23	B43		NSD									
B	24	B23		NSD									
B	25	B3		NSD									
B	26	C13		NSD									
B	27	C33		NSD									
B	28	B42		NSD									
B	29	B22		NSD									
B	30	B2		NSD									
B	31	C12		NSD									
B	32	C32		NSD									
B	33	B31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-2CC-100304 *Lab/Cor Sample No.:* B4760 S15 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	34	B11		NSD									
C	35	B44		NSD									
C	36	B24		NSD									
C	37	B4		NSD									
C	38	C14		NSD									
C	39	C34		NSD									
C	40	B33		NSD									
C	41	B13		NSD									
C	42	C3		NSD									
C	43	C23		NSD									
C	44	C43		NSD									
C	45	B42		NSD									
C	46	B22		NSD									
C	47	B2		NSD									
C	48	C12		NSD									
C	49	C32		NSD									
C	50	B31		NSD									
C	51	B11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-3CC-100304 *Lab/Cor Sample No.:* B4760 S16 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44	ADQ	1	1	F	8.5	1.5	5.7			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	B33		NSD									
A	7	B13		NSD									
A	8	B23		NSD									
A	9	C23		NSD									
A	10	C43		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	B41	ADQ	2	2	F1-0	4.5	1	4.5			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	17	B21		NSD									
A	18	B1		NSD									
B	19	B44		NSD									
B	20	B24		NSD									
B	21	B4		NSD									
B	22	C14		NSD									
B	22	C34		NSD									
B	23	B33	AZQ	3	3	F	3.8	0.4	9.5	5246	15163	Mg, Si, Ca, Fe Actinolite Zone Axis [5 3 0] - RF	TAS_AHRA
B	24	B13	ADQ	4		MD1-0	3.5	1.2	2.9			Actinolite	TAS_AHRA
B	24	B13	ADQ		4	MF	1.8	0.38	4.7			Actinolite	
B	25	C3	ADQ	5	5	F	6	1	6.0			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	26	C23		NSD									
B	27	C43		NSD									
B	28	B32		NSD									
B	29	C10	AQ	6		MD1-0	17	8	2.1			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-3CC-100304 *Lab/Cor Sample No.:* B4760 S16 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	29	C10	AQ		6	MB	3.8	1.2	3.2			Actinolite	
B	30	C30		NSD									
B	31	A1		NSD									
B	32	D11		NSD									
B	33	D31		NSD									
B	34	D20		NSD									
B	35	D10		NSD									
C	36	A42	ADQ	7	7	F	3.6	0.4	9.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
C	36	A42	ADQ	8	8	F	9	3	3.0			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	37	A22	AZQ	9	9	F	4	1	4.0	5278	15164	Mg, Si, Ca, Fe Amosite Zone Axis [1 2 0] - KM	TAS_AHRA
C	37	A22	ADQ	10		MD1-1	13	7	1.9			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	37	A22	ADQ		10	MF	9.5	2	4.8			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	38	A2		NSD									
C	39	D12		NSD									
C	40	D42		NSD									
C	41	A41		NSD									
C	42	A21		NSD									
C	43	A1		NSD									
C	44	D11		NSD									
C	45	D31		NSD									
C	46	B41		NSD									
C	47	B21		NSD									
C	48	B1	ADQ	11	11	F	10.5	1.2	8.8			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	49	C11		NSD									
C	50	C31		NSD									
C	51	C10		NSD									
C	52	C30		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-4CC-100304 *Lab/Cor Sample No.:* B4760 S17 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	29	B22	ADQ	NSD		F	4.2	0.6	7.0			Actinolite	TAS_AHRA
A	1	B34	CM	1	1	F	0.9	0.08	11			Chrysotile	TAS_AHRA
A	2	B14		NSD									
A	3	C4	ADQ	2	2	F	1.8	0.6	3.0		15165	Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	4	C24		NSD									
A	5	C44		NSD									
A	6	B43		NSD									
A	7	B23	ADQ	3	3	F	2.5	0.5	5.0			Actinolite	TAS_AHRA
A	8	B3		NSD									
A	9	C13		NSD									
A	10	C33		NSD									
A	11	B41		NSD									
A	12	B11		NSD									
A	13	C1		NSD									
A	14	C31		NSD									
A	15	A40		NSD									
A	16	A10		NSD									
A	17	D10		NSD									
B	18	B44	AZQ	4	4	F	7	2	3.5	5279	15197	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [2 1 3] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	19	B24	ADQ	5		MD1-0	3.2	1.2	2.7			Actinolite	TAS_AHRA
B	19	B24	ADQ		5	MF	1.5	0.5	3.0			Actinolite	
B	19	B24		NSD									
B	20	B4		NSD									
B	21	C14		NSD									
B	22	C34		NSD									
B	23	B33	CDQ	6	6	B	6.5	1.5	4.3	5250	15166	Mg, Si Chrysotile Confirmed - KM	AS>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	23	B33	ADQ	7		MD1-1	25	8	3.1			Amosite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	23	B33	ADQ		7	MF	9	0.5	18			Mg, Si, Ca, Fe Amosite	AFB>5, PCMEF-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT
B	24	B13	ADQ	8	8	F	5	1.5	3.3			Actinolite	TAS_AHRA
B	24	B13	CMQ	9	9	F	1.5	0.1	15			Chrysotile	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: CC2-L6-4CC-100304 *Lab/Cor Sample No.:* B4760 S17 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	25	C3		NSD									
B	26	C23		NSD									
B	27	C43		NSD									
B	28	B42		NSD									
B	29	B2		NSD									
B	30	C12		NSD									
B	31	C32		NSD									
B	32	B41		NSD									
B	33	B21		NSD									
C	34	B44		NSD									
C	35	B24		NSD									
C	36	B4	ADQ	10	10	F	1.8	0.6	3.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
C	37	C4		NSD									
C	38	B43	ADQ	11	11	F	5.1	0.7	7.3			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	39	B23		NSD									
C	40	B3	CMQ	12	12	F	0.7	0.1	7.0			Chrysotile	TAS_AHRA
C	40	B3	CDQ	13	13	F	1.2	0.1	12			Chrysotile	TAS_AHRA
C	41	C23		NSD									
C	42	B42		NSD									
C	43	B32		NSD									
C	44	B12		NSD									
C	45	C2		NSD									
C	46	B31		NSD									
C	47	B11	ADQ	14	14	F	3.5	0.4	8.8			Actinolite	TAS_AHRA
C	48	C1		NSD									
C	49	C11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-H2-1FD-100204 *Lab/Cor Sample No.:* B4760 S18 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B34		NSD									
A	2	B14		NSD									
A	3	C4	CDQ	1	1	F	0.9	0.1	9.0	5251	15169	Mg, Si Chrysotile Confirmed - KM	TAS_AHRA
A	4	C24		NSD									
A	5	C44		NSD									
A	6	B43		NSD									
A	7	B23		NSD									
A	8	B3		NSD									
A	9	C13		NSD									
A	10	C33	ADQ	2		MD1-1	14	3.5	4.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	10	C33	ADQ		2	MF	6.5	1	6.5			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
A	10	C33	AZQ	3	3	F	4	0.5	8.0	5252	15171	Mg, Si, Ca, Fe Actinolite Zone Axis [7 1 6] - RF	TAS_AHRA
A	11	B32	ADQ	4	4	F	6.8	0.8	8.5			Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	12	B12		NSD									
A	13	C2		NSD									
A	14	C22	CM	5	5	F	0.8	0.11	7.3			Chrysotile	TAS_AHRA
A	15	C42		NSD									
A	16	B10	CD	6	6	F	1.1	0.1	11			Chrysotile	TAS_AHRA
B	17	B4		NSD									
B	18	C14	CDQ	7	7	F	2.75	0.15	18	5253	15172	Mg, Si Chrysotile 5253A Negative - Confirmed - KM	TAS_AHRA
B	18	C14	CDQ	8	8	B	1.8	0.25	7.2			Mg, Si Chrysotile	TAS_AHRA
B	19	C34		NSD									
B	20	B43		NSD									
B	21	B23		NSD									
B	22	B3	AZQ	9	9	F	2.1	0.45	4.7	5254	15173	Mg, Si, Ca, Fe Actinolite Zone Axis [4 -1 4] - KM	TAS_AHRA
B	23	C13	CMQ	10	10	B	1.5	0.2	7.5			Mg, Si Chrysotile	TAS_AHRA
B	23	C13	CM	11	11	F	2.5	0.1	25			Chrysotile	TAS_AHRA
B	24	C23		NSD									
B	25	B42		NSD									
B	26	B22		NSD									
B	27	B2		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-H2-1FD-100204 *Lab/Cor Sample No.:* B4760 S18 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	28	C12		NSD									
B	29	C32		NSD									
B	30	B41		NSD									
B	31	B21		NSD									
B	32	B1		NSD									
C	33	B44	CDQ	12	12	F	0.6	0.1	6.0			Mg, Si, Fe Chrysotile	TAS_AHRA
C	34	B24		NSD									
C	35	B4		NSD									
C	36	C14		NSD									
C	37	C34	CDQ	13		MD1-1	6	5	1.2			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	37	C34	CDQ		13	MF	6	0.4	15			Mg, Si, Fe Chrysotile	AFB>5, PCMEF-US, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT
C	38	B43	CD	14	14	F	1	0.05	20			Chrysotile	TAS_AHRA
C	39	B23	CDQ	15	15	B	0.75	0.2	3.8			Mg, Si, Fe Chrysotile	TAS_AHRA
C	40	B3		NSD									
C	41	C13		NSD									
C	42	B42		NSD									
C	43	B22		NSD									
C	44	B2	CDQ	16		MD1-0	7	3	2.3			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	44	B2	CDQ		16	MB	1.5	0.2	7.5			Mg, Si, Fe Chrysotile	
C	45	C12	CDQ	17		MD1-0	2	1	2.0			Chrysotile	TAS_AHRA
C	45	C12	CDQ		17	MB	1.15	0.2	5.8			Mg, Si, Fe Chrysotile	
C	46	C32		NSD									
C	47	B41		NSD									
C	48	B21		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-H2-2FD-100204 *Lab/Cor Sample No.:* B4760 S19 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4	CDQ	1	1	F	1.5	0.15	10	5255	15174	Mg,Si,Fe Chrysotile Confirmed - KM	TAS_AHRA
A	4	C14		NSD									
A	5	C34		NSD									
A	6	B43	AZQ	2	2	F	7.25	1.25	5.8	5256	15175	Mg, Si, Ca, Fe Actinolite Zone Axis [1 0 0] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	7	B23		NSD									
A	8	B3		NSD									
A	9	C13		NSD									
A	10	B32		NSD									
A	11	B12		NSD									
A	12	C2	AQ	3	3	F	5.8	0.8	7.2		15176	Mg, Si, Ca, Fe Amosite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	13	C22		NSD									
A	14	B41		NSD									
A	15	B21		NSD									
A	16	B1		NSD									
A	17	C11		NSD									
B	18	B44		NSD									
B	19	B24	CD	4	4	F	0.6	0.1	6.0			Chrysotile	TAS_AHRA
B	20	B4		NSD									
B	21	C14	AQ	5		MD1-0	3.8	1	3.8			Actinolite	TAS_AHRA
B	21	C14	AQ		5	MF	1.5	0.5	3.0			Mg, Si, Ca, Fe Actinolite	
B	22	C23	ADQ	6	6	F	8	2	4.0			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	23	B43		NSD									
B	24	B23		NSD									
B	25	B3		NSD									
B	26	C13		NSD									
B	27	C33		NSD									
B	28	B22	ADQ	7	7	F	4.5	0.6	7.5			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	29	B2		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-H2-2FD-100204 *Lab/Cor Sample No.:* B4760 S19 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	30	C12		NSD									
B	31	C22		NSD									
B	32	B41		NSD									
B	33	B11	CM	8	8	F	1.5	0.11	14			Chrysotile	TAS_AHRA
B	34	C1		NSD									
C	35	B44		NSD									
C	36	B24		NSD									
C	37	B4		NSD									
C	38	C14		NSD									
C	39	C34		NSD									
C	40	B43		NSD									
C	41	B13		NSD									
C	42	C3		NSD									
C	43	C23		NSD									
C	44	C43		NSD									
C	45	B42		NSD									
C	46	B22	CMQ	9	9	F	1	0.1	10			Mg, Si Chrysotile	TAS_AHRA
C	47	B2		NSD									
C	48	C12		NSD									
C	49	C42		NSD									
C	50	B41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-H2-3FD-100204 *Lab/Cor Sample No.:* B4760 S20 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B42		NSD									
A	2	B22		NSD									
A	3	B2		NSD									
A	4	C12		NSD									
A	5	C32		NSD									
A	6	B41		NSD									
A	7	B21		NSD									
A	8	B1		NSD									
A	9	C11		NSD									
A	10	C31		NSD									
A	11	A41		NSD									
A	12	A21	ADQ	1	1	F	4	0.5	8.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	13	A1		NSD									
A	14	D11		NSD									
A	15	D31		NSD									
A	16	D32		NSD									
B	17	B44		NSD									
B	18	B24		NSD									
B	19	B4		NSD									
B	20	C14		NSD									
B	21	C34		NSD									
B	22	B23		NSD									
B	23	B3		NSD									
B	24	C3		NSD									
B	25	C23		NSD									
B	26	C43		NSD									
B	27	B42		NSD									
B	28	B22		NSD									
B	29	B2		NSD									
B	30	C12		NSD									
B	31	C32		NSD									
B	32	C21	AZQ	2		MD1-0	9	8	1.1			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	32	C21	AZQ		2	MF	3.2	0.4	8.0	5259	15177	Mg, Si, Ca, Fe Actinolite Zone Axis [4 1 4] - KM	

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-H2-3FD-100204 *Lab/Cor Sample No.:* B4760 S20 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	33	B34		NSD									
C	34	B14		NSD									
C	35	B4		NSD									
C	36	C4		NSD									
C	37	C24		NSD									
C	38	C44		NSD									
C	39	B42	ADQ	3	3	F	14	4.5	3.1			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	40	B22		NSD									
C	41	B2		NSD									
C	42	C12		NSD									
C	43	C32		NSD									
C	44	A31		NSD									
C	45	A11		NSD									
C	46	D1		NSD									
C	47	D21		NSD									
C	48	D41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-H2-1FD-100304 *Lab/Cor Sample No.:* B4760 S21 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	C43	ADQ	1	1	F	3	0.5	6.0			Na, Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	7	C23		NSD									
A	8	C3	AZQ	2	2	F	2.75	0.4	6.9	847	569	Na, Mg, Al, Si, Ca, Fe Actinolite Zone Axis [3 1 1] - KM	TAS_AHRA
A	9	B13		NSD									
A	10	B33		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	C41		NSD									
A	17	C21		NSD									
A	18	C1		NSD									
A	19	B11		NSD									
A	20	B31		NSD									
A	21	B40		NSD									
A	22	B20		NSD									
A	23	A10		NSD									
A	24	A30		NSD									
A	25	A41		NSD									
A	26	A21		NSD									
A	27	A1		NSD									
A	28	D11		NSD									
B	29	A20		NSD									
B	30	A40		NSD									
B	31	A31		NSD									
B	32	A11		NSD									
B	33	D1		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-H2-1FD-100304 *Lab/Cor Sample No.:* B4760 S21 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	34	D21		NSD									
B	35	D41		NSD									
B	36	D32		NSD									
B	37	D12		NSD									
B	38	A2		NSD									
B	39	A22		NSD									
B	40	A42		NSD									
B	41	B41		NSD									
B	42	B21		NSD									
B	43	B1		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-H2-2FD-100304 *Lab/Cor Sample No.:* B4760 S22 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B34		NSD									
A	3	B24		NSD									
A	4	B14		NSD									
A	5	B4		NSD									
A	6	B43		NSD									
A	7	B33		NSD									
A	8	B23		NSD									
A	9	B13		NSD									
A	10	B3		NSD									
A	11	B42		NSD									
A	12	B32		NSD									
A	13	B22		NSD									
A	14	B12		NSD									
A	15	B41		NSD									
A	16	B31		NSD									
B	17	B44		NSD									
B	18	B24		NSD									
B	19	B4		NSD									
B	20	C4		NSD									
B	21	B43		NSD									
B	22	B23		NSD									
B	23	B3		NSD									
B	24	C3		NSD									
B	25	B42		NSD									
B	26	B22		NSD									
B	27	B2		NSD									
B	28	C2		NSD									
B	29	B41		NSD									
B	30	B21		NSD									
B	31	B1		NSD									
B	32	C1		NSD									
C	33	B44		NSD									
C	34	B24		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-H2-2FD-100304 *Lab/Cor Sample No.:* B4760 S22 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	35	B4		NSD									
C	36	C14		NSD									
C	37	B43		NSD									
C	38	B23		NSD									
C	39	B3		NSD									
C	40	C13		NSD									
C	41	C33		NSD									
C	42	B42		NSD									
C	43	B22		NSD									
C	44	C12		NSD									
C	45	C32		NSD									
C	46	C42		NSD									
C	47	C21		NSD									
C	48	C41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-H2-3FD-100304 *Lab/Cor Sample No.:* B4760 S23 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B34		NSD									
A	3	B24		NSD									
A	4	B4		NSD									
A	5	B33		NSD									
A	6	B13		NSD									
A	7	C3		NSD									
A	8	C23		NSD									
A	9	C42		NSD									
A	10	C32		NSD									
A	11	C12		NSD									
A	12	B2		NSD									
A	13	B22		NSD									
A	14	B42		NSD									
A	15	B31		NSD									
A	16	B11		NSD									
A	17	C1		NSD									
A	18	C21		NSD									
A	19	C41		NSD									
A	20	C30		NSD									
A	21	C10		NSD									
A	22	D1		NSD									
A	23	D21		NSD									
A	24	D41		NSD									
A	25	D32		NSD									
A	26	D12		NSD									
A	27	A2		NSD									
A	28	A22		NSD									
A	29	A42		NSD									
A	30	A33		NSD									
B	31	B44		NSD									
B	32	B24		NSD									
B	33	B4		NSD									
B	34	C14		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-H2-3FD-100304 *Lab/Cor Sample No.:* B4760 S23 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	35	C34		NSD									
B	36	C43		NSD									
B	37	C23		NSD									
B	38	C3		NSD									
B	39	B13		NSD									
B	40	B43		NSD									
B	41	B42		NSD									
B	42	B32		NSD									
B	43	A41		NSD									
B	44	A21		NSD									
B	45	A1		NSD									
B	46	D11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-11CH-100404 *Lab/Cor Sample No.:* B4760 S24 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34	ADQ	1	1	F	5	1.5	3.3			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	6	C43		NSD									
A	7	C23		NSD									
A	8	C3	ADQ	2	2	F	10	2.5	4.0			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	8	C3	ADQ	3	3	F	1.5	0.5	3.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	9	B13	ADQ	4	4	F	14	1.5	9.3			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	10	B33		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	C41		NSD									
A	17	B1		NSD									
A	18	B21		NSD									
A	19	B41		NSD									
A	20	B40		NSD									
A	21	B30		NSD									
A	22	B20		NSD									
A	23	B10		NSD									
A	24	A1		NSD									
A	25	A21		NSD									
A	26	A41		NSD									
A	27	A32		NSD									
A	28	A22		NSD									
A	29	A12		NSD									
A	30	A2		NSD									
A	31	D12		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-11CH-100404 *Lab/Cor Sample No.:* B4760 S24 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	32	D32		NSD									
B	33	B44	AZQ	5	5	F	2.75	0.4	6.9	5281	570	Mg, Si, Ca, Fe Actinolite Zone Axis [3 0 1] - KM	TAS_AHRA
B	34	B24		NSD									
B	35	B4	ADQ	6		MD	5.5	5	1.1			Mg, Si, Ca, Fe Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	35	B4	ADQ		6	MF	5.5	1.5	3.7			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
B	36	C14		NSD									
B	37	C34		NSD									
B	38	C43		NSD									
B	39	C31		NSD									
B	40	C11	ADQ	7		MD1-1	12	6	2.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	40	C11	ADQ		7	MF	8	0.7	11			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
B	41	B21		NSD									
B	42	B41		NSD									
B	43	A40		NSD									
B	44	A20		NSD									
B	45	A10		NSD									
B	46	D10		NSD									
B	47	D30		NSD									
B	48	D22		NSD									
B	49	D2		NSD									
B	50	A12		NSD									
B	51	A32	AZQ	8	8	F	4.5	0.7	6.4	825	571	Na, Mg, Al, Si, Ca, Fe Actinolite Ferrian-actinolite - Zone Axis [2 0 1] - KM	TAS_AHRA
B	52	A44		NSD									
B	53	A24		NSD									
B	54	A4		NSD									
B	55	D14		NSD									
B	56	D24		NSD									
B	57	A13		NSD									
B	58	A11	CDQ	9		MD1-1	18	15	1.2			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	58	A11	CDQ		9	MF	15	0.05	300	826	572	Mg, Si Chrysotile Confirmed - KM	AFB>5, PSAS >10, PSAS TOT, PCAS >10, PCAS TOT

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-11CH-100404 *Lab/Cor Sample No.:* B4760 S24 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	59	B10		NSD									
B	60	B12		NSD									
B	61	B14		NSD									
B	62	B34		NSD									
B	63	B32		NSD									
B	64	B30		NSD									
C	65	A1	CDQ	10	10	B	4	0.6	6.7			Mg, Si Chrysotile	TAS_AHRA
C	66	A21		NSD									
C	67	A41		NSD									
C	68	B40		NSD									
C	69	B20		NSD									
C	70	B10		NSD									
C	71	C20		NSD									
C	72	C40		NSD									
C	73	D41		NSD									
C	74	D21		NSD									
C	75	D1		NSD									
C	76	A11		NSD									
C	77	A31		NSD									
C	78	A43	ADQ	11	11	F	8	1	8.0			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	79	A23		NSD									
C	80	A3		NSD									
C	81	D3		NSD									
C	82	D23		NSD									
C	83	D43		NSD									
C	84	D44		NSD									
C	85	D34	ADQ	12	12	F	10.5	2.5	4.2			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	86	D4		NSD									
C	87	A14		NSD									
C	88	A24	ADQ	13		MD1-0	12	5	2.4			Tremolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	88	A24	AZQ		13	MF	4	0.25	16	827	573	Mg, Si, Ca, Fe Tremolite Zone Axis [5 1 6] - KM	

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-11CH-100404 *Lab/Cor Sample No.:* B4760 S24 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	89	A44	ADQ	14		MD1-1	13	7	1.9			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	89	A44	ADQ		14	MF	13	0.5	26			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US, PSAS >10, PSAS TOT, PSAM >10, PSAM TOT
C	90	B11		NSD									
C	91	B12		NSD									
C	92	B13		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-1CH-100404 *Lab/Cor Sample No.:* B4760 S25 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B34		NSD									
A	2	B14		NSD									
A	3	C24	AZQ	1	1	F	5.5	0.4	14	5262	15181	Mg, Si, Fe Amosite Zone Axis [7 1 20] - JH	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	3	C24	ADQ	2	2	F	18	4	4.5			Mg, Si, Ca,Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	4	C4		NSD									
A	5	C44		NSD									
A	6	B43		NSD									
A	7	B33	AZQ	3		MD1-0	2.5	2	1.2			Actinolite	TAS_AHRA
A	7	B33	AZQ		3	MF	1.7	0.2	8.5	5263	15502	Mg, Si, Ca,Fe Actinolite Zone Axis [3 -1 2] - KM	
A	8	B3	AX	4	4	F	15	2.5	6.0			Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	8	B3	CDQ	5		MD1-0	10	8	1.2			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	8	B3	CDQ		5	MB	1.8	0.15	12	5264	15183	Mg, Si Chrysotile Confirmed - KM	
A	9	C13		NSD									
A	10	C33	ADQ	6	6	F	6.8	1.5	4.5			Mg, Si, Ca,Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	11	B32	CM	7		MD1-0	15	10	1.5			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	11	B32	CM		7	MF	1.2	0.1	12			Chrysotile	
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12	CMQ	8	8	F	1.2	0.1	12			Mg, Si Chrysotile	TAS_AHRA
A	15	C32		NSD									
A	16	B31		NSD									
A	17	B21	CM	9	9	F	1	0.08	12			Chrysotile	TAS_AHRA
A	18	B1		NSD									
A	19	C11	CD	10	10	F	0.8	0.08	10			Chrysotile	TAS_AHRA
A	20	C31		NSD									
A	21	A31	CDQ	11		MD1-0	6.5	6	1.1			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-1CH-100404 *Lab/Cor Sample No.:* B4760 S25 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	21	A31	CDQ		11	MF	1.1	0.1	11			Chrysotile	
A	22	A11	ADQ	12		MD1-1	15	10	1.5			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	22	A11	ADQ		12	MF	10	0.4	25			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT
A	23	D1	CD	13		MD1-0	3	2	1.5			Chrysotile	TAS_AHRA
A	23	D1	CD		13	MF	0.7	0.08	8.8			Chrysotile	
A	24	D21	CDQ	14	14	B	8.5	0.4	21			Mg, Si Chrysotile	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	25	D41		NSD									
A	26	A32		NSD									
A	27	A12		NSD									
A	28	D2		NSD									
A	29	D22		NSD									
A	30	D42		NSD									
A	31	D10		NSD									
B	32	B44		NSD									
B	33	B24		NSD									
B	34	B4		NSD									
B	35	C14		NSD									
B	36	C34		NSD									
B	37	B33	CD	15	15	F	0.9	0.11	8.2			Chrysotile	TAS_AHRA
B	38	B13	ADQ	16	16	F	3.8	0.5	7.6			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	39	C3		NSD									
B	40	C23		NSD									
B	41	C43		NSD									
B	42	B42	CD	17	17	F	1	0.1	10			Chrysotile	TAS_AHRA
B	43	B22		NSD									
B	44	B2	CD	18		MD1-0	5.9	4	1.5			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	44	B2	CD		18	MF	1.5	0.11	14			Chrysotile	
B	45	C12		NSD									
B	46	C32		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-1CH-100404 *Lab/Cor Sample No.:* B4760 S25 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	47	B41		NSD									
B	48	B21		NSD									
B	49	B1		NSD									
B	50	C11		NSD									
B	51	C31		NSD									
B	52	A41		NSD									
B	53	A21		NSD									
B	54	A1		NSD									
B	55	D11		NSD									
B	56	D31		NSD									
B	57	A32	ADQ	19	19	F	5.5	1	5.5			Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	58	A12	CD	20	20	F	0.8	0.11	7.3			Chrysotile	TAS_AHRA
B	59	D2		NSD									
B	60	D22		NSD									
B	61	D42		NSD									
B	62	C10		NSD									
C	63	B34		NSD									
C	64	B14		NSD									
C	65	C4		NSD									
C	66	C24		NSD									
C	67	C44	ADQ	21	21	F	1.8	0.5	3.6			Mg, Si, Ca,Fe Actinolite	TAS_AHRA
C	68	B43		NSD									
C	69	B23	ADQ	22	22	F	10	1.5	6.7			Mg, Si, Ca,Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	70	B3		NSD									
C	71	C13		NSD									
C	72	C33		NSD									
C	73	B32		NSD									
C	74	B12		NSD									
C	74	C2	ADQ	23	23	F	9	3	3.0			Mg, Si, Ca,Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	75	C22		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-1CH-100404 *Lab/Cor Sample No.:* B4760 S25 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	76	C42		NSD									
C	77	B41		NSD									
C	78	B21		NSD									
C	79	B2		NSD									
C	80	C12		NSD									
C	81	C32		NSD									
C	82	A31	CD	24		MD1-0	4.5	3.5	1.3			Chrysotile	TAS_AHRA
C	82	A31	CD		24	MF	0.5	0.08	6.2			Chrysotile	
C	82	A31	ADQ	25	25	F	4.5	1.35	3.3			Mg, Si, Ca,Fe Actinolite	TAS_AHRA
C	83	A11		NSD									
C	84	D1		NSD									
C	85	D21	CD	26	26	F	1	0.12	8.3			Chrysotile	TAS_AHRA
C	86	D41		NSD									
C	87	A42		NSD									
C	88	A22		NSD									
C	89	A2		NSD									
C	90	D12		NSD									
C	91	D32		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-1ZB-100404 *Lab/Cor Sample No.:* B4760 S26 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A1		NSD									
A	2	A21		NSD									
A	3	A41		NSD									
A	4	A43		NSD									
A	5	A23		NSD									
A	6	A3		NSD									
A	7	D13		NSD									
A	8	D33		NSD									
A	9	D40		NSD									
A	10	D20		NSD									
A	11	D10		NSD									
A	12	C10		NSD									
A	13	C20		NSD									
A	14	C40		NSD									
A	15	C42		NSD									
A	16	C22		NSD									
A	17	C2		NSD									
A	18	A12		NSD									
A	19	A32		NSD									
A	20	B44		NSD									
A	21	B24		NSD									
A	22	B4		NSD									
A	23	C14		NSD									
A	24	C34		NSD									
A	25	C44		NSD									
A	26	C33		NSD									
A	27	C13		NSD									
A	28	B3		NSD									
A	29	B23		NSD									
A	30	B43		NSD									
B	31	A10		NSD									
B	32	A42		NSD									
B	33	A22		NSD									
B	34	A2		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-1ZB-100404 *Lab/Cor Sample No.:* B4760 S26 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	35	D12		NSD									
B	36	D32		NSD									
B	37	D44		NSD									
B	38	D24		NSD									
B	39	D4		NSD									
B	40	A14		NSD									
B	41	A34		NSD									
B	42	B40		NSD									
B	43	B20		NSD									
B	44	B10		NSD									
B	45	B42		NSD									
B	46	B22		NSD									
B	47	B2		NSD									
B	48	C12		NSD									
B	49	C32		NSD									
B	50	C44		NSD									
B	51	C24		NSD									
B	52	B4		NSD									
B	53	B24		NSD									
B	54	B44		NSD									
B	55	D1		NSD									
B	56	A1		NSD									
B	57	A11		NSD									
B	58	A21		NSD									
B	59	A31		NSD									
B	60	A41		NSD									
C	61	A4		NSD									
C	62	A2		NSD									
C	63	A11		NSD									
C	64	A13		NSD									
C	65	B10		NSD									
C	66	B12		NSD									
C	67	B14		NSD									
C	68	B24		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-1ZB-100404 *Lab/Cor Sample No.:* B4760 S26 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	69	B22		NSD									
C	70	B20		NSD									
C	71	A21		NSD									
C	72	A23		NSD									
C	73	A33		NSD									
C	74	A43		NSD									
C	75	A42		NSD									
C	76	A40		NSD									
C	77	B41		NSD									
C	78	B43		NSD									
C	79	B44		NSD									
C	80	B1		NSD									
C	81	B3		NSD									
C	82	C14		NSD									
C	83	C12		NSD									
C	84	C10		NSD									
C	85	D11		NSD									
C	86	D13		NSD									
C	87	D34		NSD									
C	88	D32		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-2CH-100404 *Lab/Cor Sample No.:* B4760 S27 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A1	CDQ	1		MD1-0	4.9	3	1.6			Chrysotile	TAS_AHRA
A	1	A1	CDQ		1	MB	4.9	0.3	16	828	574	Mg, Si Chrysotile Confirmed - KM	
A	1	A1	CDQ	2	2	B	0.7	0.2	3.5			Chrysotile	TAS_AHRA
A	1	A1	CDQ	3	3	B	1	0.08	12			Chrysotile	TAS_AHRA
A	1	A1	CDQ	4	4	F	0.6	0.04	15			Chrysotile	TAS_AHRA
A	1	A1	CDQ	5	5	F	0.6	0.04	15			Chrysotile	TAS_AHRA
A	2	A21	CDQ	6		MD2-0	6	2.3	2.6			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	2	A21	CDQ		6	MF	1.5	0.05	30			Chrysotile	
A	2	A21	CDQ		7	MF	2.5	0.05	50			Chrysotile	
A	3	A41		NSD									
A	4	A43	AZQ	7	8	F	4	0.7	5.7	829	575	Na, Mg, Al, Si, Ca, Fe Actinolite Zone Axis [7 1 0] - KM	TAS_AHRA
A	5	A23	CD	8	9	F	0.6	0.05	12			Chrysotile	TAS_AHRA
A	6	A3	CD	9	10	F	0.7	0.05	14			Chrysotile	TAS_AHRA
A	7	D13		NSD									
A	8	D30	CD	10	11	F	1	0.07	14			Chrysotile	TAS_AHRA
A	8	D30	CD	11	12	B	2.3	0.5	4.6			Chrysotile	TAS_AHRA
A	9	D41	CD	12	13	F	0.7	0.05	14			Chrysotile	TAS_AHRA
A	9	D41	CD	13	14	B	17	7	2.4			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	10	C40	ADQ	14	15	F	4.5	0.9	5.0			Mg, Si, Ca,Fe Actinolite	TAS_AHRA
A	11	C20		NSD									
A	12	C10		NSD									
A	13	C42	CD	15		MD2-0	2.6	2.3	1.1			Chrysotile	TAS_AHRA
A	13	C42	CD		16	MF	2.5	0.04	62			Chrysotile	
A	13	C42	CD		17	MF	0.7	0.08	8.8			Chrysotile	
A	14	C22	CD	16		MD1-0	8	5	1.6			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	14	C22	CD		18	MB	2.4	0.2	12			Chrysotile	
A	14	C22	CD	17	19	F	1.1	0.04	28			Chrysotile	TAS_AHRA
A	14	C22	CD	18	20	F	1	0.04	25			Chrysotile	TAS_AHRA
A	15	C2		NSD									
A	16	B12	CD	19	21	F	0.55	0.05	11			Chrysotile	TAS_AHRA
A	17	B22	CD	20	22	B	2.3	0.2	12			Chrysotile	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-2CH-100404 *Lab/Cor Sample No.:* B4760 S27 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	18	B42		NSD									
A	19	B44		NSD									
A	20	B24	CD	21		MD1-0	4	2.3	1.7			Chrysotile	TAS_AHRA
A	20	B24	CD		23	MF	4	0.06	67			Chrysotile	
A	20	B24	ADQ	22	24	F	15	5	3.0			Mg, Si, Ca,Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	21	C4	CD	23	25	CC6-0	2.3	0.4	5.8			Chrysotile	
A	22	C24	CDQ	24	26	F	1.7	0.05	34			Mg, Si Chrysotile	TAS_AHRA
A	22	C24	CD	25	27	F	2.5	0.06	42			Chrysotile	TAS_AHRA
B	23	A10		NSD									
B	24	B40		NSD									
B	25	B41		NSD									
B	26	A41	CD	26	28	F	1	0.1	10			Chrysotile	TAS_AHRA
B	27	A21	CD	27	29	F	0.75	0.05	15			Chrysotile	TAS_AHRA
B	27	A21	ADQ	28		MD1-1	11	10	1.1			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	27	A21	ADQ		30	MF	5.1	1.3	3.9			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
B	28	A1	CDQ	29		MD1-0	5	3.5	1.4			Chrysotile	TAS_AHRA
B	28	A1	CDQ		31	MB	2	0.3	6.7			Mg, Si Chrysotile	
B	28	A1	CD	30		MD1-0	4	2	2.0			Chrysotile	TAS_AHRA
B	28	A1	CD		32	MF	0.6	0.05	12			Chrysotile	
B	29	D11		NSD									
B	30	D31		NSD									
B	31	D41	CMQ	31	33	F	0.6	0.05	12			Mg, Si Chrysotile	TAS_AHRA
B	31	D41	CMQ	32	34	F	1.2	0.05	24			Mg, Si Chrysotile	TAS_AHRA
B	31	D41	CMQ	33	35	F	0.6	0.05	12			Mg, Si Chrysotile	TAS_AHRA
B	31	D41	ADQ	34	36	F	8.5	0.85	10			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	31	D41	CMQ	35	37	B	9	2.5	3.6			Mg, Si Chrysotile	AS>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	32	D21		NSD									
B	32	A1	CMQ	36	38	F	1	0.05	20			Mg, Si Chrysotile	TAS_AHRA
B	33	A1	CMQ	37	39	F	0.75	0.05	15			Mg, Si Chrysotile	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-2CH-100404 *Lab/Cor Sample No.:* B4760 S27 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	33	A1	ADQ	38	40	F	9	2	4.5			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	34	A21	CD	39		MD1-0	20	20	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	34	A21	CD		41	MF	1	0.05	20			Chrysotile	
B	34	A21	CMQ	40	42	F	0.6	0.05	12			Mg, Si Chrysotile	TAS_AHRA
B	34	A21	CMQ	41	43	F	1	0.05	20			Mg, Si Chrysotile	TAS_AHRA
B	34	A21	CMQ	42	44	F	0.6	0.05	12			Mg, Si Chrysotile	TAS_AHRA
B	34	A21	CMQ	43	45	F	0.5	0.05	10			Mg, Si Chrysotile	TAS_AHRA
B	35	A41	CMQ	44		MD1-1	40	15	2.7			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	35	A41	CMQ		46	MF	5.1	0.05	100			Mg, Si Chrysotile	AFB>5, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT
B	36	A32	CMQ	45		MD1-0	5	5	1.0			Chrysotile	TAS_AHRA
B	36	A32	CMQ		47	MF	0.6	0.05	12			Mg, Si Chrysotile	
B	37	A12	CDQ	46	48	F	1.75	0.05	35			Mg, Si Chrysotile	TAS_AHRA
B	38	D2		NSD									
B	39	D22		NSD									
B	40	D42		NSD									
B	41	C44	CMQ	47	49	F	1	0.05	20			Mg, Si Chrysotile	TAS_AHRA
B	42	C24	AQ	48	50	F	4	0.5	8.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	42	C24	CMQ	49	51	F	2.75	0.05	55			Mg, Si Chrysotile	TAS_AHRA
B	43	C4	CMQ	50	52	F	0.6	0.05	12			Mg, Si Chrysotile	TAS_AHRA
B	43	C4	CMQ	51	53	F	1	0.025	40			Mg, Si Chrysotile	TAS_AHRA
B	44	B14	CMQ	52		MD1-0	10	8	1.2			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	44	B14	CMQ		54	MF	0.85	0.1	8.5			Mg, Si Chrysotile	
B	44	B14	CMQ	53		MD2-0	3	2	1.5			Chrysotile	TAS_AHRA
B	44	B14	CMQ		55	MF	1.25	0.15	8.3			Mg, Si Chrysotile	
B	44	B14	CMQ		56	MF	1	0.15	6.7			Mg, Si Chrysotile	

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-3CH-100404 *Lab/Cor Sample No.:* B4760 S28 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	B33		NSD									
A	7	B13		NSD									
A	8	C3		NSD									
A	9	C23		NSD									
A	10	C43		NSD									
A	11	B42		NSD									
A	12	B22	CDQ	1		MD1-0	8	6	1.3			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	12	B22	CDQ		1	MB	1.5	0.38	3.9	5265	15184	Mg, Si Chrysotile Confirmed - KM	
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	B41		NSD									
A	17	B21		NSD									
A	18	B1	CMQ	2	2	B	3.7	0.5	7.4			Mg, Si Chrysotile	TAS_AHRA
A	19	C11		NSD									
A	20	C31	CMQ	3		MD1-0	5.5	3.8	1.4			Mg, Si Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	20	C31	CMQ		3	MF	0.5	0.1	5.0			Mg, Si Chrysotile	
A	21	A41	ADQ	4	4	F	3.7	1.1	3.4			Mg, Si, Ca,Fe Actinolite	TAS_AHRA
A	22	A21		NSD									
A	23	A1		NSD									
A	24	D11		NSD									
A	25	D31		NSD									
A	26	A32		NSD									
A	27	A12		NSD									
A	28	D2		NSD									
A	29	D22		NSD									
A	30	D42		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-3CH-100404 *Lab/Cor Sample No.:* B4760 S28 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	31	B44		NSD									
B	32	B24		NSD									
B	33	B4		NSD									
B	34	C14		NSD									
B	35	C34	AZQ	5		MD1-0	10	6	1.7			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	35	C34	AZQ		5	MF	1.7	0.45	3.8	5285	15185	Mg, Si, Ca,Fe Actinolite Zone Axis [1 0 0] - KM	
B	36	B33		NSD									
B	37	B13		NSD									
B	38	C13		NSD									
B	39	C23		NSD									
B	40	C43		NSD									
B	41	B42		NSD									
B	42	B22		NSD									
B	43	B2		NSD									
B	44	C12		NSD									
B	45	C32	CQ	6		MD1-0	8	6	1.3			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	45	C32	CQ		6	MF	0.7	0.1	7.0			Mg, Si Chrysotile	
B	46	B41		NSD									
B	47	B11		NSD									
B	48	C1		NSD									
B	49	C21		NSD									
B	50	C41		NSD									
B	51	A31		NSD									
B	52	A11	CM	7	7	B	2.2	0.35	6.3			Chrysotile	TAS_AHRA
B	53	D1		NSD									
B	54	D21		NSD									
B	55	D41		NSD									
B	56	A42		NSD									
B	57	A22		NSD									
B	58	A2		NSD									
B	59	D12		NSD									
B	60	D32		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-3CH-100404 *Lab/Cor Sample No.:* B4760 S28 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	61	A12		NSD									
C	61	A32	CMQ	8	8	F	1.7	0.05	34			Mg, Si Chrysotile	TAS_AHRA
C	61	A32	CMQ	9	9	F	1.05	0.05	21			Mg, Si Chrysotile	TAS_AHRA
C	61	A32	CMQ	10	10	F	0.5	0.07	7.1			Mg, Si Chrysotile	TAS_AHRA
C	62	A42	CMQ	11	11	F	0.65	0.05	13			Mg, Si Chrysotile	TAS_AHRA
C	63	A41		NSD									
C	64	A31	CDQ	12	12	B5-0	1.75	0.25	7.0			Mg, Si Chrysotile	TAS_AHRA
C	65	A40		NSD									
C	66	B31	AQ	13	13	F	5	1	5.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
C	67	B32		NSD									
C	68	B33	CMQ	14	14	F	0.5	0.05	10			Mg, Si Chrysotile	TAS_AHRA
C	68	B33	CMQ	15	15	F	1	0.07	14			Mg, Si Chrysotile	TAS_AHRA
C	69	B43		NSD									
C	70	B44	CMQ	16	16	F	1.4	0.05	28			Mg, Si Chrysotile	TAS_AHRA
C	70	B44	CMQ	17	17	F	1.1	0.05	22			Mg, Si Chrysotile	TAS_AHRA
C	71	B34		NSD									
C	72	C31		NSD									
C	73	C42		NSD									
C	74	D20		NSD									
C	75	D30	CDQ	18	18	B6-0	0.75	0.3	2.5			Mg, Si Chrysotile	TAS_AHRA
C	76	D40		NSD									
C	77	D22		NSD									
C	78	D32		NSD									
C	79	D42		NSD									
D	80	D22		NSD									
D	81	D32	CDQ	19	19	F	1	0.05	20			Mg, Si Chrysotile	TAS_AHRA
D	82	D41	CMQ	20	20	F	0.75	0.05	15			Mg, Si Chrysotile	TAS_AHRA
D	82	D41	AQ	21	21	F	15	5	3.0			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
D	83	D40		NSD									
D	84	D31		NSD									
D	85	D30	AQ	22	22	F	5.5	1.3	4.2			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
D	86	C20		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-3CH-100404 *Lab/Cor Sample No.:* B4760 S28 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
D	87	C30		NSD									
D	88	C40		NSD									
D	89	C31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-4CH-100404 *Lab/Cor Sample No.:* B4760 S29 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44	CDQ	1		MD1-0	11	9	1.2			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	1	B44	CDQ		1	MF	1.25	0.15	8.3			Mg, Si Chrysotile	
A	1	B44	CQ	2		MD2-0	10	7	1.4			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	1	B44	CQ		2	MF	0.6	0.05	12			Mg, Si Chrysotile	
A	1	B44	CQ		3	MF	0.7	0.05	14			Mg, Si Chrysotile	
A	1	B44	CQ	3		MD1-0	1	1	1.0			Chrysotile	TAS_AHRA
A	1	B44	CQ		4	MF	0.75	0.15	5.0			Mg, Si Chrysotile	
A	2	B14	CQ	4		MD1-0	4	2	2.0			Chrysotile	TAS_AHRA
A	2	B14	CQ		5	MF	1.25	0.15	8.3			Mg, Si Chrysotile	
A	3	C4	CDQ	5	6	F	1.5	0.05	30			Mg, Si Chrysotile	TAS_AHRA
A	3	C4	CDQ	6	7	F	1.3	0.05	26			Mg, Si Chrysotile	TAS_AHRA
A	3	C4	CQ	7	8	F	0.6	0.01	60			Mg, Si Chrysotile	TAS_AHRA
A	3	C4	CDQ	8		MD2-0	5	5	1.0			Chrysotile	TAS_AHRA
A	3	C4	CDQ		9	MF	2.5	0.05	50			Mg, Si Chrysotile	
A	3	C4	CDQ		10	MF	2	0.05	40	831	577	Mg, Si Chrysotile Confirmed - KM	
A	3	C4	CQ	9	11	F	0.65	0.15	4.3			Mg, Si Chrysotile	TAS_AHRA
A	3	C4	CQ	10	12	F	0.75	0.01	75			Mg, Si Chrysotile	TAS_AHRA
A	4	C24	CM	11		MD2-0	10	7	1.4			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	4	C24	CM		13	MF	1.5	0.05	30			Chrysotile	
A	4	C24	CM		14	MF	0.75	0.05	15			Chrysotile	
A	4	C24	CM	12	15	F	0.5	0.05	10			Chrysotile	TAS_AHRA
A	4	C24	CD	13	16	F	0.5	0.01	50			Chrysotile	TAS_AHRA
A	5	C44	CM	14		MD1-0	1.2	1.2	1.0			Chrysotile	TAS_AHRA
A	5	C44	CM		17	MF	1	0.05	20			Chrysotile	
A	5	C44	CM	15	18	F	0.5	0.05	10			Chrysotile	TAS_AHRA
A	5	C44	CM	16	19	F	1.2	0.05	24			Chrysotile	TAS_AHRA
A	5	C44	CM	17		MD1-0	1.5	0.75	2.0			Chrysotile	TAS_AHRA
A	5	C44	CM		20	MF	1.2	0.05	24			Chrysotile	
A	5	C44	CM	18	21	F	1.5	0.05	30			Chrysotile	TAS_AHRA
A	5	C44	AZQ	19		MD1-0	20	15	1.3			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	5	C44	AZQ		22	MF	4	0.65	6.2	5286	15503	Mg,Al,Si,Ca,Fe Actinolite Zone Axis [1 -1 1] - KM	

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-4CH-100404 *Lab/Cor Sample No.:* B4760 S29 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	6	C43		NSD									
A	7	C33	CM	20		MD1-0	5.5	5	1.1			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	7	C33	CM		23	MF	1	0.05	20			Chrysotile	
A	7	C33	CM	21		MD1-0	20	15	1.3			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	7	C33	CM		24	MF	0.6	0.05	12			Chrysotile	
A	7	C33	CM	22	25	F	0.6	0.01	60			Chrysotile	TAS_AHRA
A	7	C33	CM	23	26	F	0.5	0.05	10			Chrysotile	TAS_AHRA
A	7	C33	CM	24	27	F	1	0.05	20			Chrysotile	TAS_AHRA
A	7	C33	CM	25	28	F	0.75	0.05	15			Chrysotile	TAS_AHRA
A	7	C33	CM	26		MD1-0	15	15	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	7	C33	CM		29	MF	1.2	0.1	12			Chrysotile	
A	7	C33	CM	27		MD1-1	30	15	2.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	7	C33	CM		30	MB	8	1.2	6.7			Chrysotile	AFB>5, PCMEF-US
A	8	C13	CM	28		MD1-0	10	10	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	8	C13	CM		31	MF	0.6	0.05	12			Chrysotile	
A	9	B3	CM	29		MD1-0	20	15	1.3			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	9	B3	CM		32	MF	1	0.05	20			Chrysotile	
A	9	B3	CM	30	33	F	0.65	0.05	13			Chrysotile	TAS_AHRA
A	9	B3	CM	31	34	F	0.65	0.05	13			Chrysotile	TAS_AHRA
A	9	B3	CM	32		MD1-0	7.5	7.5	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	9	B3	CM		35	MF	0.75	0.05	15			Chrysotile	
A	10	B23		NSD									
A	11	B43	CD	33	36	B	2	2	1.0			Chrysotile	TAS_AHRA
A	11	B43	ADQ	34		MD1-1	20	15	1.3			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	11	B43	AQ		37	MF	9	0.75	12			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
A	11	B43	CM	35	38	F	0.75	0.05	15			Chrysotile	TAS_AHRA
A	11	B43	CM	36	39	F	0.75	0.05	15			Chrysotile	TAS_AHRA
A	11	B43	CM	37	40	F	1	0.15	6.7			Chrysotile	TAS_AHRA
A	12	B32	CM	38	41	F	0.6	0.05	12			Chrysotile	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-4CH-100404 *Lab/Cor Sample No.:* B4760 S29 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	12	B32	CM	39		MD2-0	3.5	3	1.2			Chrysotile	TAS_AHRA
A	12	B32	CM		42	MF	0.75	0.05	15			Chrysotile	
A	12	B32	CM		43	MF	0.75	0.05	15			Chrysotile	
A	12	B32	CM	40	44	F	0.5	0.05	10			Chrysotile	TAS_AHRA
A	12	B32	CM	41		MD1-0	6	5	1.2			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	12	B32	CM		45	MF	3.5	0.15	23			Chrysotile	
A	12	B32	CM	42		MD1-0	10	10	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	12	B32	CM		46	MF	1	0.05	20			Chrysotile	
B	13	B31		NSD									
B	14	B11	CM	43	47	F	0.5	0.01	50			Chrysotile	TAS_AHRA
B	15	C1	CM	44	48	F	0.5	0.05	10			Chrysotile	TAS_AHRA
B	16	C21	CM	45		MD1-0	4	2.5	1.6			Chrysotile	TAS_AHRA
B	16	C21	CM		49	MF	1	0.01	100			Chrysotile	
B	16	C21	CM	46	50	F	1.2	0.01	120			Chrysotile	TAS_AHRA
B	16	C21	CM	47	51	F	1	0.01	100			Chrysotile	TAS_AHRA
B	17	C41	CD	48		MD1-0	4	3	1.3			Chrysotile	TAS_AHRA
B	17	C41	CD		52	MF	2.5	0.01	250			Chrysotile	
B	17	C41	CM	49		MD1-0	7.5	7.5	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	17	C41	CM		53	MF	1	0.05	20			Chrysotile	

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-5CH-100404 *Lab/Cor Sample No.:* B4760 S30 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A10		NSD									
A	2	A30		NSD									
A	3	A40	CD	1		MD1-0	3	1.8	1.7			Chrysotile	TAS_AHRA
A	3	A40	CD		1	MB	3	0.1	30	833		Chrysotile Fiber tilts into grid bar. Confirmed - KM	
A	3	A40	CDQ	2	2	B	1.1	0.2	5.5	834	579	Mg, Si Chrysotile Confirmed - KM	TAS_AHRA
A	4	B41	AZQ	3	3	F	4.5	0.3	15	835	580	Mg, Si, Ca, Fe Tremolite Zone Axis [3 0 1] - KM	TAS_AHRA
A	5	B21	CDQ	4	4	F	1.2	0.1	12			Chrysotile	TAS_AHRA
A	6	B1		NSD									
A	7	C11		NSD									
A	8	C31	CDQ	5	5	F	5.2	0.05	100			Chrysotile	AS>5, AFB>5, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	9	C43		NSD									
A	10	C23	CDQ	6	6	F	0.7	0.1	7.0			Chrysotile	TAS_AHRA
A	11	C3		NSD									
A	12	B13		NSD									
A	13	B33		NSD									
A	14	A41		NSD									
A	15	A21		NSD									
A	16	D1		NSD									
A	17	D3		NSD									
A	17	D13	CD	7	7	F	1.2	0.08	15			Chrysotile	TAS_AHRA
A	18	D43		NSD									
B	19	A1		NSD									
B	20	A3	CD	8	8	F	1.2	0.06	20			Chrysotile	TAS_AHRA
B	20	A3	ADQ	9	9	F	2.7	0.3	9.0			Tremolite	TAS_AHRA
B	21	A4		NSD									
B	22	A24		NSD									
B	23	A44	CD	10		CD3-0	3	2	1.5			Chrysotile	TAS_AHRA
B	23	A44	CD		10	CB	3	0.5	6.0			Chrysotile	
B	23	A44	CD		11	CF	2.5	0.05	50			Chrysotile	
B	23	A44	CD		12	CB	2.2	0.6	3.7			Chrysotile	
B	24	A24		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-5CH-100404 *Lab/Cor Sample No.:* B4760 S30 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	25	A22		NSD									
B	26	A2	CD	11	13	F	1.1	0.07	16			Chrysotile	TAS_AHRA
B	27	D12		NSD									
B	28	D32	CD	12	14	B	3.5	0.25	14			Chrysotile	TAS_AHRA
B	29	D40	CD	13	15	F	1.2	0.05	24			Chrysotile	TAS_AHRA
B	30	D20		NSD									
B	31	D10		NSD									
B	32	C20		NSD									
B	33	C40		NSD									
B	34	C42	CD	14	16	F	0.7	0.05	14			Chrysotile	TAS_AHRA
B	35	C22		NSD									
B	36	C2		NSD									
B	37	B12	CD	15	17	F	0.5	0.05	10			Chrysotile	TAS_AHRA
B	38	B32		NSD									
B	39	B44		NSD									
B	40	B24		NSD									
B	41	B4		NSD									
B	42	C14		NSD									
B	43	B1	AZQ	16	18	F	5.1	1	5.1	838	582	Mg, Si, Ca, Fe Actinolite Zone Axis [4 0 3] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	44	B3		NSD									
B	45	B14		NSD									
B	46	B12	CD	17		MD3-0	3	3	1.0			Chrysotile	TAS_AHRA
B	46	B12	CD		19	MB	3	0.2	15			Chrysotile	
B	46	B12	CD		20	MF	2.8	0.05	56			Chrysotile	
B	46	B12	CD		21	MB	2.4	0.15	16			Chrysotile	
B	47	B10		NSD									
B	48	A11		NSD									
B	49	A13		NSD									
B	50	A34	ADQ	18	22	F	7	1	7.0			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	51	A32		NSD									
B	52	A30		NSD									
B	53	B31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-5CH-100404 *Lab/Cor Sample No.:* B4760 S30 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	54	B33	ADQ	19	23	F	1.5	0.3	5.0			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	54	B33	CD	20	24	B	1	0.2	5.0			Chrysotile	TAS_AHRA
B	55	C13	CD	21	25	F	1.2	0.06	20			Chrysotile	TAS_AHRA
B	56	C11	CD	22		MD1-0	5.3	4.8	1.1			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	56	C11	CD		26	MB	2	0.2	10			Chrysotile	
B	56	C11	CD	23	27	F	2.3	0.06	38			Chrysotile	TAS_AHRA
B	56	C11	CD	24		CD3-0	2.8	1	2.8			Chrysotile	TAS_AHRA
B	56	C11	CD		28	CR15-0	2.8	0.6	4.7			Chrysotile	
B	56	C11	CD		29	CF	1.2	0.05	24			Chrysotile	
B	56	C11	CD		30	CF	1	0.04	25			Chrysotile	
B	56	C11	CD	25	31	B	1.5	0.5	3.0			Chrysotile	TAS_AHRA
B	57	D11		NSD									
B	58	D13		NSD									
B	59	D34	ADQ	26	32	F	2.3	0.3	7.7			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	59	D34	ADQ	27		MD1-1	5.2	3	1.7			Tremolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	59	D34	ADQ		33	MF	5.2	0.4	13			Mg, Si, Ca, Fe Tremolite	AFB>5, PCMEF-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT
C	60	B44	CM	28		MD1-0	3.5	3.5	1.0			Chrysotile	TAS_AHRA
C	60	B44	CM		34	MF	2	0.05	40			Chrysotile	
C	61	B24	CM	29	35	F	0.6	0.05	12			Chrysotile	TAS_AHRA
C	61	B24	CM	30	36	F	0.5	0.01	50			Chrysotile	TAS_AHRA
C	61	B24	CM	31		MD1-0	5.5	5.5	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	61	B24	CM		37	MB	2.5	0.3	8.3			Chrysotile	
C	62	B4		NSD									
C	63	C14	CD	32		MD1-0	6.5	6.5	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	63	C14	CM		38	MF	1.5	0.1	15			Chrysotile	
C	63	C14	CM	33	39	F	0.6	0.05	12			Chrysotile	TAS_AHRA
C	63	C14	CM	34	40	F	0.6	0.05	12			Chrysotile	TAS_AHRA
C	64	B33		NSD									
C	65	B13	CM	35	41	F	0.75	0.15	5.0			Chrysotile	TAS_AHRA
C	65	B13	CM	36		MD1-0	4	2.5	1.6			Chrysotile	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: TPG-L2-5CH-100404 *Lab/Cor Sample No.:* B4760 S30 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	65	B13	CM		42	MB	4.5	0.85	5.3			Chrysotile	
C	65	B13	CM	37	43	F	1	0.05	20			Chrysotile	TAS_AHRA
C	66	C3		NSD									
C	67	C23	CM	38		MD1-0	1	1	1.0			Chrysotile	TAS_AHRA
C	67	C23	CM		44	MF	1	0.05	20			Chrysotile	
C	68	C43	CM	39		MD1-1	15	15	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	68	C43	CM		45	MB	9	1.2	7.5			Chrysotile	AFB>5, PCMEF-US
C	69	C32	CM	40	46	F	0.5	0.05	10			Chrysotile	TAS_AHRA
C	70	C12		NSD									
C	71	B2	CM	41	47	F	0.6	0.01	60			Chrysotile	TAS_AHRA
C	71	B2	CM	42		MD2-0	10	10	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	71	B2	CM		48	MB	1.2	0.25	4.8			Chrysotile	
C	71	B2	CM		49	MF	1	0.05	20			Chrysotile	
C	71	B2	CM	43		MD1-0	8	2	4.0			Chrysotile	AS>5, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	71	B2	CM		50	MF	0.6	0.05	12			Chrysotile	

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-H2-1FD-100304 *Lab/Cor Sample No.:* B4760 S31 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A43		NSD									
A	2	A23		NSD									
A	3	A3		NSD									
A	4	D23		NSD									
A	5	D43		NSD									
A	6	D41		NSD									
A	7	D21		NSD									
A	8	D1		NSD									
A	9	A11		NSD									
A	10	A31		NSD									
A	11	B40		NSD									
A	12	B20		NSD									
B	13	B42		NSD									
B	14	B22		NSD									
B	15	C2		NSD									
B	16	C22		NSD									
B	17	C42	AZQ	1	1	F	7	1.7	4.1	978	711	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 0 0] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	18	C40		NSD									
B	19	C20		NSD									
B	20	B10		NSD									
B	21	A41		NSD									
B	22	A11		NSD									
B	23	D1		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-H2-2FD-100304 *Lab/Cor Sample No.:* B4760 S32 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A43		NSD									
A	2	A23		NSD									
A	3	A3		NSD									
A	4	D13		NSD									
A	5	D33	AZQ	1	1	F	4.9	0.7	7.0	979	15504	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 0 0] - KM	TAS_AHRA
A	6	D41		NSD									
A	7	D21	AQ	2		MD1-0	4.3	2.7	1.6			Actinolite	TAS_AHRA
A	7	D21	AQ		2	MF	4	0.45	8.9			Mg, Al, Si, Ca, Fe Actinolite	
A	8	D1		NSD									
A	9	A11		NSD									
A	10	B40		NSD									
A	11	B20		NSD									
A	12	C1		NSD									
B	13	B43	AQ	3	3	F	4.8	1.2	4.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	14	B23		NSD									
B	15	B3		NSD									
B	16	C13		NSD									
B	17	C43		NSD									
B	18	C41	AQ	4	4	F	11	1	11			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	19	C21		NSD									
B	20	C1		NSD									
B	21	B11		NSD									
B	22	B31	AQ	5	5	F	7.7	0.5	15			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	22	B31	AQ	6	6	F	6	1.5	4.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-H2-3FD-100304 *Lab/Cor Sample No.:* B4760 S33 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B42		NSD									
A	2	B12		NSD									
A	3	C12		NSD									
A	4	B14		NSD									
A	5	C14		NSD									
A	6	C44		NSD									
A	7	A20		NSD									
A	8	D10		NSD									
B	9	A32		NSD									
B	10	A2		NSD									
B	11	D22		NSD									
B	12	B31		NSD									
B	13	B1		NSD									
B	14	C21		NSD									
B	15	B13		NSD									
B	16	C3		NSD									
C	17	B23	CDQ	1	1	F	1	0.05	20	980	713	Mg, Si Chrysotile Verified - KM	TAS_AHRA
C	18	B43		NSD									
C	19	B3		NSD									
C	20	C13	AZQ	2		MD1-1	6	6	1.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	20	C13	AZQ		2	MF	8	0.75	11	5438	15505	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 1 4] - KM	AFB>5, PCMEF-US
C	21	C33		NSD									
C	22	C42		NSD									
C	23	C22		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-1CH-100304 *Lab/Cor Sample No.:* B4760 S34 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	C43		NSD									
A	7	C23		NSD									
A	8	C3		NSD									
A	9	B13		NSD									
A	10	B33		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	C41		NSD									
A	17	C21		NSD									
A	18	C1		NSD									
A	19	B11	CDQ	1		MD1-0	6	3.5	1.7			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	19	B11	CDQ		1	MF	0.95	0.1	9.5	5402	15298	Mg, Si, Fe Chrysotile Verified - KM	
A	20	B41		NSD									
A	21	B40		NSD									
A	22	B20		NSD									
A	23	C10	AZQ	2		MD1-0	4	2.5	1.6			Actinolite	TAS_AHRA
A	23	C10	AZQ		2	MF	2	0.25	8.0	5403	15299	Mg, Si, Ca, Fe Actinolite Zone Axis [3 1 -2] - KM	
A	24	C30		NSD									
A	25	D40		NSD									
A	26	D20	AQ	3		MD1-0	25.5	4.25	6.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	26	D20	AQ		3	MF	4.25	0.45	9.4			Mg, Al, Si, Ca, Fe Actinolite Alumino-actinolite	
A	27	A10		NSD									
A	28	A30		NSD									
A	29	A41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-1CH-100304 *Lab/Cor Sample No.:* B4760 S34 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	30	B44		NSD									
B	31	B44		NSD									
B	32	B34		NSD									
B	33	B24		NSD									
B	34	B14	AQ	4	4	F	3.3	0.6	5.5			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	35	C4		NSD									
B	36	C14		NSD									
B	37	C24		NSD									
B	38	C34		NSD									
B	39	C44		NSD									
B	40	C3		NSD									
B	41	C13		NSD									
B	42	C23		NSD									
B	43	C33		NSD									
B	44	C43		NSD									
B	45	C2		NSD									
B	46	C12		NSD									
B	47	C22		NSD									
B	48	C32		NSD									
B	49	C42		NSD									
B	50	C1		NSD									
B	51	C31	AZQ	5	5	F	5.8	1.5	3.9	5404	15300	Mg, Si, Ca Tremolite Zone Axis [3 1 0] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	52	C11		NSD									
B	53	C21		NSD									
B	54	C41		NSD									
B	55	C20		NSD									
B	56	C30	AQ	6		MD1-0	6	2.5	2.4			Tremolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	56	C30	AQ		6	MF	3.8	0.5	7.6			Mg, Si, Ca Tremolite	
C	57	B44		NSD									
C	58	B24		NSD									
C	59	B4		NSD									
C	60	C14		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-1CH-100304 *Lab/Cor Sample No.:* B4760 S34 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	61	C34		NSD									
C	62	B33		NSD									
C	63	B13	CDQ	7	7	B	8	0.35	23	5405	15301	Mg, Si Chrysotile Verified - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	64	C3		NSD									
C	65	C23	AQ	8	8	F	3.7	0.6	6.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	66	C43		NSD									
C	67	B42		NSD									
C	68	B22		NSD									
C	69	B2		NSD									
C	70	C12		NSD									
C	71	C32		NSD									
C	72	B31		NSD									
C	73	B11		NSD									
C	74	C1		NSD									
C	75	C21		NSD									
C	76	C41		NSD									
C	77	B40		NSD									
C	78	B20	AQ	9	9	F	7.8	1.2	6.5			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	79	B10		NSD									
C	80	C10		NSD									
C	81	C30		NSD									
C	82	A41		NSD									
C	83	A21		NSD									
C	84	A11		NSD									
C	85	A1		NSD									
C	86	D11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-2CH-100304 *Lab/Cor Sample No.:* B4760 S35 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B34		NSD									
A	3	B24		NSD									
A	4	B14		NSD									
A	5	B4		NSD									
A	6	C4		NSD									
A	7	C14		NSD									
A	8	C24		NSD									
A	9	C34		NSD									
A	10	C43		NSD									
A	11	C33		NSD									
A	12	C23		NSD									
A	13	C13		NSD									
A	14	C3		NSD									
A	15	B3		NSD									
A	16	B13		NSD									
A	17	B23		NSD									
A	18	B33		NSD									
A	19	B43		NSD									
A	20	B42		NSD									
A	21	B32		NSD									
A	22	B22		NSD									
A	23	B12		NSD									
A	24	B2		NSD									
A	25	C2		NSD									
A	26	C12		NSD									
A	27	C22		NSD									
A	28	C32		NSD									
A	29	C42		NSD									
A	30	C41		NSD									
A	31	C31		NSD									
B	32	B44		NSD									
B	33	B34		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-2CH-100304 *Lab/Cor Sample No.:* B4760 S35 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	34	B24	AZQ	1		MD1-1	16	12	1.3			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	34	B24	AZQ		1	MF	6	1	6.0	981	715	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 1 4] - KM	AFB>5, PCMEF-US
B	35	B14		NSD									
B	36	B4		NSD									
B	37	C4		NSD									
B	38	C14		NSD									
B	39	C24		NSD									
B	40	C34		NSD									
B	41	C44	AZQ	2	2	F	6	1.5	4.0	982	716	Mg, Al, Si, Ca, Fe Tremolite Zone Axis [1 0 0] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	42	C43		NSD									
B	43	C33		NSD									
B	44	C23		NSD									
B	45	C13		NSD									
B	46	C3		NSD									
B	47	B3		NSD									
B	48	B13		NSD									
B	49	B23		NSD									
B	50	B33		NSD									
B	51	B43		NSD									
B	52	B41		NSD									
B	53	B21		NSD									
B	54	B1		NSD									
B	55	C11		NSD									
B	56	C31		NSD									
B	57	D40		NSD									
B	58	D20		NSD									
B	59	A10		NSD									
B	60	A30		NSD									
B	61	A42		NSD									
C	62	A43		NSD									
C	63	A23		NSD									
C	64	A3		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-2CH-100304 *Lab/Cor Sample No.:* B4760 S35 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	65	D13		NSD									
C	66	D33		NSD									
C	67	D41		NSD									
C	68	D21		NSD									
C	69	D1		NSD									
C	70	A11		NSD									
C	71	A31	AQ	3	3	F	1.7	0.5	3.4			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
C	72	B40		NSD									
C	73	B10		NSD									
C	74	C10		NSD									
C	75	C30		NSD									
C	76	C42		NSD									
C	77	C22		NSD									
C	78	C2		NSD									
C	79	B12		NSD									
C	80	B42		NSD									
C	81	B43		NSD									
C	82	B3		NSD									
C	83	C3		NSD									
C	84	C23		NSD									
C	85	C43		NSD									
C	86	C44		NSD									
C	87	C24		NSD									
C	88	C4		NSD									
C	89	D14		NSD									
C	90	A34		NSD									
C	91	A14		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-3CH-100304 *Lab/Cor Sample No.:* B4760 S36 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A44		NSD									
A	2	D24		NSD									
A	3	D34		NSD									
A	4	D32		NSD									
A	5	D12		NSD									
A	6	A2		NSD									
A	7	A12		NSD									
A	8	A32		NSD									
A	9	A42		NSD									
A	10	A40		NSD									
A	11	A20		NSD									
A	12	A10		NSD									
A	13	D10		NSD									
A	14	D30		NSD									
A	15	C41		NSD									
A	16	C21		NSD									
A	17	C1		NSD									
A	18	B11		NSD									
A	19	B31		NSD									
A	20	B41		NSD									
A	21	B43		NSD									
A	22	B23		NSD									
A	23	B3		NSD									
A	24	C13		NSD									
A	25	C33		NSD									
A	26	C43		NSD									
A	27	C44		NSD									
A	28	C24		NSD									
A	29	C4		NSD									
A	30	B14		NSD									
B	31	B43		NSD									
B	32	B33		NSD									
B	33	C23		NSD									
B	34	C43		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-3CH-100304 *Lab/Cor Sample No.:* B4760 S36 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	35	C41		NSD									
B	36	C21		NSD									
B	37	C1		NSD									
B	38	B11		NSD									
B	39	B31		NSD									
B	40	B41		NSD									
B	41	A40		NSD									
B	42	A20		NSD									
B	43	A10		NSD									
B	44	D10		NSD									
B	45	D30		NSD									
B	46	D40		NSD									
B	47	D42		NSD									
B	48	D22		NSD									
B	49	D2		NSD									
B	50	A12		NSD									
B	51	A32		NSD									
B	52	A42		NSD									
B	53	A24		NSD									
B	54	A4		NSD									
B	55	D14		NSD									
B	56	D34		NSD									
B	57	D44		NSD									
B	58	D41		NSD									
C	59	A44		NSD									
C	60	A24		NSD									
C	61	A4		NSD									
C	62	D14		NSD									
C	63	D34		NSD									
C	64	D44		NSD									
C	65	D42		NSD									
C	66	D22		NSD									
C	67	D2		NSD									
C	68	A12		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-3CH-100304 *Lab/Cor Sample No.:* B4760 S36 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	69	A32		NSD									
C	70	A42		NSD									
C	71	A40		NSD									
C	72	A20		NSD									
C	73	A10		NSD									
C	74	D10		NSD									
C	75	C41		NSD									
C	76	C21		NSD									
C	77	C1		NSD									
C	78	B11		NSD									
C	79	B31		NSD									
C	80	B41		NSD									
C	81	B43		NSD									
C	82	B23	AZQ	1	1	F	8	1.5	5.3	983	717	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 0 5] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	83	B3		NSD									
C	84	B23		NSD									
C	85	B43		NSD									
C	86	B44		NSD									
C	87	B24		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-4CH-100304 *Lab/Cor Sample No.:* B4760 S37 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	B33		NSD									
A	7	B13		NSD									
A	8	C3		NSD									
A	9	C23		NSD									
A	10	C43		NSD									
A	11	B32		NSD									
A	12	B12		NSD									
A	13	C2		NSD									
A	14	C22		NSD									
A	15	C42		NSD									
A	16	B31		NSD									
A	17	B21	ADQ	1		MD1-0	6.5	4	1.6			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	17	B21	ADQ		1	MF	2	0.4	5.0		15302	Mg, Al, Si, Ca, Fe Actinolite	
A	18	B1		NSD									
A	19	C11		NSD									
A	20	C31		NSD									
A	21	A31		NSD									
A	22	A21		NSD									
A	23	A1		NSD									
A	24	D11		NSD									
A	25	D31		NSD									
A	26	A32		NSD									
A	27	A12		NSD									
A	28	D2		NSD									
A	29	D22		NSD									
B	30	B44		NSD									
B	31	B24		NSD									
B	32	B4		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-4CH-100304 *Lab/Cor Sample No.:* B4760 S37 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	33	C4		NSD									
B	34	C24		NSD									
B	35	C44		NSD									
B	36	C43	AZQ	2		MD1-0	6	6	1.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	36	C43	AZQ		2	MF	2.5	0.75	3.3	5408	15303	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [2 0 1] - KM	
B	37	C23		NSD									
B	38	C3		NSD									
B	39	B3		NSD									
B	40	B23		NSD									
B	41	B43		NSD									
B	42	B42		NSD									
B	43	B22		NSD									
B	44	B2		NSD									
B	45	C2		NSD									
B	46	C22		NSD									
B	47	C42		NSD									
B	48	C41		NSD									
B	49	C21		NSD									
B	50	C1		NSD									
B	51	B1		NSD									
B	52	B21		NSD									
B	53	B41		NSD									
B	54	B40		NSD									
B	55	B20		NSD									
B	56	C20	AQ	3	3	F	8	0.9	8.9			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	57	C40		NSD									
B	58	D40		NSD									
C	59	B44		NSD									
C	60	B24		NSD									
C	61	B4	AQ	4	4	F	1.2	0.2	6.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	62	C14		NSD									
C	63	C24		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-4CH-100304 *Lab/Cor Sample No.:* B4760 S37 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	64	C42		NSD									
C	65	C22		NSD									
C	66	C2		NSD									
C	67	B12		NSD									
C	68	B32		NSD									
C	69	B42		NSD									
C	70	B40		NSD									
C	71	B20		NSD									
C	72	B10		NSD									
C	73	C10		NSD									
C	74	C30		NSD									
C	75	D41		NSD									
C	76	D21		NSD									
C	77	D1		NSD									
C	78	A11		NSD									
C	79	A31		NSD									
C	80	A41		NSD									
C	81	A13		NSD									
C	82	D3		NSD									
C	83	D23		NSD									
C	84	D33		NSD									
C	85	D43		NSD									
C	86	D42		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-5CH-100304 *Lab/Cor Sample No.:* B4760 S38 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B34		NSD									
A	2	B14		NSD									
A	3	C4		NSD									
A	4	C24		NSD									
A	5	C44		NSD									
A	6	B43		NSD									
A	7	B23		NSD									
A	8	B3		NSD									
A	9	C13		NSD									
A	10	C33		NSD									
A	11	B32		NSD									
A	12	B12		NSD									
A	13	C2		NSD									
A	14	C22		NSD									
A	15	C42		NSD									
A	16	B41		NSD									
A	17	B21		NSD									
A	18	B1		NSD									
A	19	C11		NSD									
A	20	C31		NSD									
A	21	B30		NSD									
A	22	B10		NSD									
A	23	C10		NSD									
A	24	C30		NSD									
A	25	C40		NSD									
A	26	A41		NSD									
A	27	A21		NSD									
A	28	A1		NSD									
A	29	D11		NSD									
A	30	D31	ADQ	1		MD1-0	10	5	2.0			Tremolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	30	D31	ADQ		1	MF	1.6	0.2	8.0			Mg, Al, Si, Ca, Fe Tremolite	
B	31	B34		NSD									
B	32	B14	AZQ	2	2	F	2	0.22	9.1	5439	718	Mg, Al, Si, Ca, Fe Tremolite Zone Axis [1 0 1] - KM	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-5CH-100304 *Lab/Cor Sample No.:* B4760 S38 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	33	C4		NSD									
B	34	C24		NSD									
B	35	C44		NSD									
B	36	B43		NSD									
B	37	B23		NSD									
B	38	B3		NSD									
B	39	C13		NSD									
B	40	C33		NSD									
B	41	B32		NSD									
B	42	B12	ADQ	3	3	F	6	1.5	4.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	43	C2		NSD									
B	44	C22		NSD									
B	45	C42		NSD									
B	46	B31		NSD									
B	47	B21		NSD									
B	48	B11		NSD									
B	49	B1		NSD									
B	50	C1		NSD									
B	51	C11		NSD									
B	52	C21		NSD									
B	53	C31		NSD									
B	54	C41		NSD									
B	55	A41		NSD									
B	56	A31		NSD									
B	57	A21		NSD									
B	58	A11		NSD									
B	59	A1		NSD									
B	60	D1		NSD									
B	61	D11		NSD									
B	62	D21		NSD									
B	63	D31		NSD									
B	64	D41		NSD									
C	65	B43		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: RHB-L2-5CH-100304 *Lab/Cor Sample No.:* B4760 S38 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	66	B33		NSD									
C	67	B23		NSD									
C	68	B13		NSD									
C	69	B3		NSD									
C	70	C3		NSD									
C	71	C13		NSD									
C	72	C23		NSD									
C	73	C33		NSD									
C	74	C43		NSD									
C	75	C42		NSD									
C	76	C32		NSD									
C	77	C22		NSD									
C	78	C12		NSD									
C	79	C2		NSD									
C	80	B2		NSD									
C	81	B12	AZQ	4	4	F	4	0.75	5.3	5440	719	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 0 0] - KM	TAS_AHRA
C	82	B22		NSD									
C	83	B32		NSD									
C	84	B42		NSD									
C	85	B31		NSD									
C	86	B21		NSD									
C	87	B11		NSD									
C	88	B1		NSD									
C	89	C1		NSD									
C	90	C11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-11CH-100204 *Lab/Cor Sample No.:* B4760 S39 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A42		NSD									
A	2	A32		NSD									
A	3	A22		NSD									
A	4	A12		NSD									
A	5	A2	AQ	1		MD1-0	15	15	1.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	5	A2	AQ		1	MF	2.5	0.5	5.0			Mg, Al, Si, Ca, Fe Actinolite	
A	6	D2		NSD									
A	7	D22		NSD									
A	8	D32		NSD									
A	9	D42		NSD									
A	10	A41		NSD									
A	11	A31		NSD									
A	12	A21	AQ	2		MD1-0	10	7.5	1.3			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	12	A21	AQ		2	MF	6	0.85	7.1			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
A	13	A11		NSD									
A	14	A1		NSD									
A	15	D1	AQ	3		MD1-0	15	12	1.2			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	15	D1	AQ		3	MF	4	0.6	6.7		720	Mg, Al, Si, Ca, Fe Actinolite	
A	16	D11	AQ	4	4	F	5.5	1.5	3.7			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	17	D21		NSD									
A	18	D31		NSD									
A	19	D41		NSD									
A	20	B42		NSD									
A	21	B32	AQ	5	5	F	10	2	5.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	22	B22		NSD									
A	23	B12		NSD									
A	24	B2		NSD									
A	25	C2		NSD									
A	26	C12		NSD									
A	27	C22		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-11CH-100204 *Lab/Cor Sample No.:* B4760 S39 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	28	C32		NSD									
A	29	C42		NSD									
A	30	C43		NSD									
A	31	C33		NSD									
B	32	B44		NSD									
B	33	B34		NSD									
B	34	B24		NSD									
B	35	B14		NSD									
B	36	B4		NSD									
B	37	C4		NSD									
B	38	C14		NSD									
B	39	C24		NSD									
B	40	C34		NSD									
B	41	C44		NSD									
B	42	B43		NSD									
B	43	B33		NSD									
B	44	B23		NSD									
B	45	B13	AQ	6	6	F	7.5	1.5	5.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	46	B3		NSD									
B	47	C3		NSD									
B	48	C13		NSD									
B	49	C23		NSD									
B	50	C33		NSD									
B	51	C43		NSD									
B	52	C42		NSD									
B	53	C32		NSD									
B	54	C22	AQ	7		MD1-0	12	7.5	1.6			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	54	C22	AQ		7	MF	2.75	0.85	3.2			Actinolite	
B	55	C12		NSD									
B	56	C2	AQ	8	8	F	4.5	0.75	6.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	57	B2		NSD									
B	58	B12		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-11CH-100204 *Lab/Cor Sample No.:* B4760 S39 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	59	B22		NSD									
B	60	B32		NSD									
B	61	B42		NSD									
B	62	B41		NSD									
C	63	A1	AQ	9		MD1-0	10	6	1.7			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	63	A1	AQ		9	MF	4.5	0.5	9.0			Actinolite	
C	64	A2	AQ	10	10	F	1.2	0.25	4.8			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	64	A2	AQ	11		MD1-1	9	5	1.8			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	64	A2	AQ		11	MF	6.5	0.85	7.6			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	64	A2	AQ	12		MD1-1	10	6	1.7			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	64	A2	AQ		12	MF	5	1	5.0			Mg, Al, Si, Ca, Fe Actinolite	
C	65	A3		NSD									
C	66	A4	AQ	13	13	F	4	1.2	3.3			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	67	D4		NSD									
C	68	A14		NSD									
C	69	A13		NSD									
C	70	A12		NSD									
C	71	A11		NSD									
C	72	A10		NSD									
C	73	A2		NSD									
C	74	A21		NSD									
C	75	A22	AQ	14	14	F	15	4	3.8			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	76	A23		NSD									
C	77	A24		NSD									
C	78	A34		NSD									
C	79	A33		NSD									
C	80	A32		NSD									
C	81	A31		NSD									
C	82	A30	CDQ	15	15	F	3	0.01	300	984	721	Mg, Si Chrysotile Verified - KM	TAS_AHRA
C	83	A40	AQ	16		MD	15	3	5.0			Actinolite	AS>5, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-11CH-100204 *Lab/Cor Sample No.:* B4760 S39 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	83	A40	AQ		16	MF	12	1.3	9.2			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	84	A41	AQ	17	17	F	2.75	0.75	3.7			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	85	A42		NSD									
C	86	A43	AQ	18	18	F	7	0.75	9.3			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	86	A43	AZQ	19	19	F	1.2	0.2	6.0	5441	15334	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 1 2] - KM	TAS_AHRA
C	87	B20		NSD									
C	88	B3		NSD									
C	89	B31		NSD									
C	90	B21		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-1CH-100204 *Lab/Cor Sample No.:* B4760 S40 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B34		NSD									
A	3	B24		NSD									
A	4	B14		NSD									
A	5	B4		NSD									
A	6	C4		NSD									
A	7	C14		NSD									
A	8	C24		NSD									
A	9	C34		NSD									
A	10	C44		NSD									
A	11	C43		NSD									
A	12	C33		NSD									
A	13	C23		NSD									
A	14	B3	AQ	1		MD1-1	14	14	1.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	14	B3	AQ		1	MF	9	2	4.5			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
A	15	C3		NSD									
A	16	B13		NSD									
A	17	B23	AQ	2	2	F	14	2.75	5.1			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	18	B43	AQ	3	3	F	6	1.5	4.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	19	B33		NSD									
A	20	B42	AQ	4	4	F	2.75	0.2	14			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	21	B22	AZQ	5		MD	2.5	1.2	2.1			Actinolite	TAS_AHRA
A	21	B22	AZQ		5	MF	2.5	0.2	12	5444	15335	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 3 2] - KM	
A	22	B12		NSD									
A	23	B2		NSD									
A	24	C2		NSD									
A	25	C12		NSD									
A	26	C22		NSD									
A	27	C32	AQ	6	6	F	1.5	0.3	5.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	27	C32	AQ	7		MD1-0	20	15	1.3			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-1CH-100204 *Lab/Cor Sample No.:* B4760 S40 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	27	C32	AQ		7	MF	3.5	0.35	10			Mg, Al, Si, Ca, Fe Actinolite	
A	28	C42		NSD									
A	29	C41		NSD									
A	30	C31		NSD									
A	31	C21		NSD									
A	32	C11		NSD									
A	33	C1		NSD									
B	34	B24		NSD									
B	35	B14		NSD									
B	36	B4		NSD									
B	37	C4		NSD									
B	38	C14		NSD									
B	39	C24		NSD									
B	40	C34	AQ	8	8	F	4.5	0.4	11			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	40	C43	AQ	9		MD1-1	50	25	2.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	40	C43	AQ		9	MF	20	4	5.0			Mg, Al, Si, Ca, Fe Actinolite	AFB>5
B	41	C44	AQ	10	10	F	23	2.5	9.2			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	42	C42		NSD									
B	43	C22		NSD									
B	44	C2		NSD									
B	45	B12		NSD									
B	46	B32		NSD									
B	47	B42		NSD									
B	48	B40		NSD									
B	49	B20		NSD									
B	50	B10		NSD									
B	51	C10		NSD									
B	52	C30		NSD									
B	53	D41		NSD									
B	54	D21		NSD									
B	55	D1		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-1CH-100204 *Lab/Cor Sample No.:* B4760 S40 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	56	A11	AQ	11	11	F	5.5	1.3	4.2			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	57	A31		NSD									
B	58	A41	AQ	12	12	F	10	3	3.3			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	59	A43		NSD									
B	60	A23	AQ	13	13	F	13.5	2	6.8			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	60	A23	CDQ	14		MD1-0	4.5	3	1.5			Chrysotile	TAS_AHRA
B	60	A23	CDQ		14	MF	3.8	0.05	76	985	722	Mg, Si Chrysotile Verified - KM	
B	61	A3	CD	15		MD1-1	15	10	1.5			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	61	A3	CD		15	MF	6	0.1	60			Chrysotile	AFB>5, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT
C	62	A43		NSD									
C	63	A33		NSD									
C	64	A23	AQ	16	16	F	11	0.5	22			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS >10, PSAS TOT, PSAM >10, PSAM TOT, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	65	A13		NSD									
C	66	A3	AQ	17		MD1-1	9	8	1.1			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	66	A3	AQ		17	MF	9	0.6	15			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	67	D3	AQ	18	18	F	7.5	2.4	3.1			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	68	D13		NSD									
C	69	D23		NSD									
C	70	D33		NSD									
C	71	D43		NSD									
C	72	D41		NSD									
C	73	D21		NSD									
C	74	D1		NSD									
C	75	A11		NSD									
C	76	A31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-1CH-100204 *Lab/Cor Sample No.:* B4760 S40 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	77	A41		NSD									
C	78	B40		NSD									
C	79	B30	AQ	19	19	F	10	2	5.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	80	B20		NSD									
C	81	B10		NSD									
C	82	C10		NSD									
C	83	C20	AQ	20	20	F	84	2.3	37			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	84	C30		NSD									
C	85	C40		NSD									
C	86	C41		NSD									
C	87	C31		NSD									
C	88	C21		NSD									
C	89	C11		NSD									
C	90	C1		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-2CH-100204 *Lab/Cor Sample No.:* B4760 S41 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A42		NSD									
A	2	A22		NSD									
A	3	A12		NSD									
A	4	B44	AQ	1		MD1-0	7.5	5	1.5			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	4	B44	AQ		1	MF	4	0.45	8.9			Mg, Al, Si, Ca, Fe Actinolite	
A	5	B34		NSD									
A	6	B24	CM	2	2	F	2.5	0.05	50			Mg, Si Chrysotile	TAS_AHRA
A	6	B24	AQ	3	3	F	5	1.2	4.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	7	B14		NSD									
A	8	B4		NSD									
A	9	C4		NSD									
A	10	C14		NSD									
A	11	C24		NSD									
A	12	C34		NSD									
A	13	C44		NSD									
A	14	C43		NSD									
A	15	C23		NSD									
A	16	C33	AQ	4	4	F	5	1.2	4.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	17	C13		NSD									
A	18	C3		NSD									
A	19	B3		NSD									
A	20	B13		NSD									
A	21	B23	AQ	5	5	F	20	5	4.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	22	B33	CDQ	6		MD1-0	15	15	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	22	B33	CDQ		6	MB	2	0.35	5.7	986	723	Mg, Si Chrysotile Verified - KM	
A	23	B43		NSD									
A	24	B42	AQ	7	7	F	15	4	3.8			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	25	B32		NSD									
A	26	B22		NSD									
A	27	B12		NSD									
A	28	B2		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-2CH-100204 *Lab/Cor Sample No.:* B4760 S41 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	29	C2		NSD									
A	30	C12		NSD									
A	31	C22		NSD									
A	32	C32		NSD									
A	33	C42	CDQ	8	8	F	4.5	0.15	30	987	724	Mg, Si Chrysotile Verified - KM	TAS_AHRA
A	33	C42	AQ	9	9	F	4	0.85	4.7	5415	15506	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 0 0] - KM	TAS_AHRA
B	34	B43	CQ	10	10	F	1.2	0.1	12			Mg, Si Chrysotile	TAS_AHRA
B	35	B33		NSD									
B	36	B23		NSD									
B	37	B13		NSD									
B	38	B3		NSD									
B	39	C3		NSD									
B	40	C13		NSD									
B	41	C23		NSD									
B	42	C33		NSD									
B	43	C43		NSD									
B	44	C42		NSD									
B	45	C32		NSD									
B	46	C22		NSD									
B	47	C12		NSD									
B	48	C2		NSD									
B	49	B2		NSD									
B	50	B12		NSD									
B	51	B22		NSD									
B	52	B32		NSD									
B	53	B42		NSD									
B	54	B41		NSD									
B	55	B31		NSD									
B	56	B21		NSD									
B	57	B11		NSD									
B	58	B1		NSD									
B	59	C1		NSD									
B	60	C11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-2CH-100204 *Lab/Cor Sample No.:* B4760 S41 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	61	C21		NSD									
B	62	C31		NSD									
B	63	C41		NSD									
C	64	B42		NSD									
C	65	B32	AQ	11		MD1-1	15	15	1.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	65	B32	AQ		11	MF	5.1	1	5.1			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	66	B22	AQ	12	12	F	14	4	3.5			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	67	B12		NSD									
C	68	B2		NSD									
C	69	C2		NSD									
C	70	C12		NSD									
C	71	C22	AQ	13		MD1-1	20	10	2.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	71	C22	AQ		13	MF	6	1.5	4.0			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	72	C32		NSD									
C	73	C42		NSD									
C	74	B41		NSD									
C	75	B31		NSD									
C	76	B21		NSD									
C	77	B11		NSD									
C	78	B1		NSD									
C	79	C1		NSD									
C	80	C11		NSD									
C	81	C21	CM	14	14	F	1.5	0.1	15			Chrysotile	TAS_AHRA
C	82	C31		NSD									
C	83	C41		NSD									
C	84	A11		NSD									
C	85	A1		NSD									
C	86	D1		NSD									
C	87	D11		NSD									
C	88	D21		NSD									
C	89	D31		NSD									
C	90	D41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-3CH-100204 *Lab/Cor Sample No.:* B4760 S42 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C4		NSD									
A	5	C24		NSD									
A	6	C44		NSD									
A	7	C43		NSD									
A	8	C23		NSD									
A	9	C3		NSD									
A	10	B3	AZQ	1		MD1-1	24	5.25	4.6			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	10	B3	AZQ		1	MF	22	3	7.3	5411	15306	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 1 2] - KM	AFB>5, PCMEF-US
A	11	B23		NSD									
A	12	B43		NSD									
A	13	B42	CMQ	2		MD1-0	12.5	9.5	1.3			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	13	B42	CMQ		2	MB	3.4	0.25	14	5443	15307	Mg, Al, Si, Fe Chrysotile No Diffraction	
A	13	B42	OZQ	3		MD1-0	15	11	1.4			Edenite	TOS_AHRA, OS>5_AHRA, OS>10_AHRA
A	13	B42	OZQ		3	MF	4.5	0.6	7.5	5412	15308	Mg, Si, K, Ca, Fe Edenite Zone Axis [4 2 -3] - KM	
A	14	B22		NSD									
A	15	B2		NSD									
A	16	C2		NSD									
A	17	C22		NSD									
A	18	C42		NSD									
A	19	C41	AQ	4	4	F	1.1	0.3	3.7			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	19	C41	AQ	5		MD1-0	5.25	3.5	1.5			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	19	C41	AQ		5	MF	3.5	0.45	7.8			Mg, Al, Si, Ca, Fe Actinolite	
A	20	C21		NSD									
A	21	C1		NSD									
A	22	B1		NSD									
A	23	B21		NSD									
A	24	B41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-3CH-100204 *Lab/Cor Sample No.:* B4760 S42 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	25	A41		NSD									
A	26	A21		NSD									
A	27	A1		NSD									
A	28	D1		NSD									
A	29	D21	ADQ	6		MD1-1	15	7	2.1			Mg, Si, Ca, Fe Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	29	D21	ADQ		6	MF	8	0.8	10			Mg, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
A	30	D31		NSD									
B	31	B34		NSD									
B	32	B14		NSD									
B	33	C4	ADQ	7	7	F	5.5	0.38	14			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	34	C24		NSD									
B	35	C44		NSD									
B	36	B33		NSD									
B	37	B23		NSD									
B	38	B3		NSD									
B	39	C13		NSD									
B	40	C33		NSD									
B	41	B32		NSD									
B	42	B12		NSD									
B	43	C2		NSD									
B	44	C22		NSD									
B	45	C42		NSD									
B	46	B1		NSD									
B	47	C11	CMQ	8		MD1-0	4.5	2.2	2.0			Chrysotile	TAS_AHRA
B	47	C11	CMQ		8	MF	1.5	0.1	15	5442	15309	Mg, Si Chrysotile No Diffraction	
B	48	C21		NSD									
B	49	C31		NSD									
B	50	C41		NSD									
B	51	A31		NSD									
B	52	A11		NSD									
B	53	D1		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-3CH-100204 *Lab/Cor Sample No.:* B4760 S42 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	54	D21		NSD									
B	55	D41		NSD									
B	56	A42		NSD									
B	57	A22		NSD									
B	58	A2		NSD									
B	59	D12		NSD									
B	60	D32		NSD									
C	61	B44		NSD									
C	62	B34		NSD									
C	63	B24		NSD									
C	64	B4	ADQ	9	9	F	5.8	0.4	14			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS 5-10, PSAS TOT, PSAM 5-10, PSAM TOT, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	65	C14		NSD									
C	66	B33		NSD									
C	67	B13		NSD									
C	68	B3		NSD									
C	69	C3		NSD									
C	70	C43		NSD									
C	71	B42		NSD									
C	72	B22		NSD									
C	73	B12	ADQ	10	10	F	4.8	0.8	6.0	1009	15507	Mg, Si, Fe Anthophyllite [8 1 2] Zone - KM	TAS_AHRA
C	74	B2		NSD									
C	75	C2		NSD									
C	76	B41		NSD									
C	77	B31		NSD									
C	78	B21		NSD									
C	79	B11		NSD									
C	80	B1		NSD									
C	81	A41		NSD									
C	82	A21		NSD									
C	83	A1		NSD									
C	84	D11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-3CH-100204 *Lab/Cor Sample No.:* B4760 S42 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	85	D31		NSD									
C	86	A42		NSD									
C	87	A32		NSD									
C	88	A22		NSD									
C	89	A12		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-4CH-100204 *Lab/Cor Sample No.:* B4760 S43 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A44		NSD									
A	2	A42	AZQ	1	1	F	10	1.8	5.6	988	725	Na, Mg, Al, Si, Ca, Fe Actinolite Zone Axis [3 2 1] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	3	A4	AQ	2	2	F	3	0.7	4.3			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	4	D14		NSD									
A	5	D34		NSD									
A	6	D44		NSD									
A	7	D42		NSD									
A	8	D22		NSD									
A	9	D2		NSD									
A	10	A12		NSD									
A	11	A32		NSD									
A	12	A42		NSD									
A	13	A40		NSD									
A	14	A10		NSD									
A	15	D20		NSD									
A	16	D40		NSD									
A	17	C41		NSD									
A	18	C21		NSD									
A	19	B1		NSD									
A	20	B11		NSD									
A	21	B31		NSD									
A	22	B41		NSD									
A	23	B43		NSD									
A	24	B23	AQ	3	3	F	21	7	3.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	25	C3	AQ	4	4	F	2.6	0.8	3.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
A	26	C12	AQ	5	5	F	12	3	4.0			Mg, Al, Si, Ca, Fe Actinolite Alumino-actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	27	C22		NSD									
A	28	C32		NSD									
A	29	C42		NSD									
A	30	C34		NSD									
B	31	B44		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-4CH-100204 *Lab/Cor Sample No.:* B4760 S43 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	32	B24		NSD									
B	33	B14		NSD									
B	34	C4		NSD									
B	35	C42		NSD									
B	36	C22		NSD									
B	37	B22		NSD									
B	38	B32		NSD									
B	39	B42		NSD									
B	40	B40		NSD									
B	41	B30		NSD									
B	42	B10		NSD									
B	43	B30		NSD									
B	44	B40		NSD									
B	45	D41	AQ	6	6	F	18	2.5	7.2			Mg, Al, Si, Ca, Fe Actinolite Alumino-actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	46	D21	AQ	7	7	F	6	1.6	3.8			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	47	D1		NSD									
B	48	A11		NSD									
B	49	D2		NSD									
B	50	D12		NSD									
B	51	D22		NSD									
B	52	D32		NSD									
B	53	D42	AQ	8	8	F	8	0.7	11			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	54	D44		NSD									
B	55	D24		NSD									
B	56	D4		NSD									
B	57	A4		NSD									
B	58	C11		NSD									
B	59	C10		NSD									
B	60	D10		NSD									
C	61	A33		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-4CH-100204 *Lab/Cor Sample No.:* B4760 S43 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	62	A23	AQ	9	9	F	9	2.4	3.7			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	63	A13		NSD									
C	64	A3		NSD									
C	65	D3		NSD									
C	66	D13		NSD									
C	67	D33		NSD									
C	68	D2		NSD									
C	69	D1		NSD									
C	70	A2		NSD									
C	71	A22		NSD									
C	72	A32		NSD									
C	73	A42		NSD									
C	74	A30		NSD									
C	75	A20		NSD									
C	76	D30		NSD									
C	77	C40		NSD									
C	78	C30		NSD									
C	79	B40		NSD									
C	80	B41		NSD									
C	81	B31		NSD									
C	82	B21		NSD									
C	83	B1		NSD									
C	84	C1		NSD									
C	85	C22		NSD									
C	86	C2	AQ	10	10	F	24	3.5	6.9			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	87	C22		NSD									
C	88	C3		NSD									
C	89	C13		NSD									
C	90	C23		NSD									
C	91	C33	AQ	11	11	F	7.5	1.5	5.0			Mg, Al, Si, Ca, Fe Actinolite Alumino-actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-5CH-100204 *Lab/Cor Sample No.:* B4760 S44 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B34		NSD									
A	3	B24		NSD									
A	4	B14	AZQ	1	1	F	9.5	1.5	6.3	5417	15312	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 1 4] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	5	B4		NSD									
A	6	B43	CDQ	2	2	F	1.8	0.1	18	5418	15313	Mg, Si, Ca, Fe Chrysotile Verified - KM	TAS_AHRA
A	7	B33	ADQ	3	3	F	3.8	0.7	5.4			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
A	8	B23		NSD									
A	9	B13		NSD									
A	10	B3		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C2		NSD									
A	15	C12		NSD									
A	16	B41		NSD									
A	17	B21		NSD									
A	18	B1		NSD									
A	19	C11		NSD									
A	20	C31		NSD									
A	21	A11		NSD									
A	22	A1		NSD									
A	23	D1		NSD									
A	24	D11		NSD									
A	25	D21		NSD									
A	26	B40		NSD									
A	27	B30		NSD									
A	28	B20		NSD									
A	29	B10		NSD									
A	30	C10		NSD									
A	31	C20		NSD									
B	32	B44		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-5CH-100204 *Lab/Cor Sample No.:* B4760 S44 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	33	B24		NSD									
B	34	B4		NSD									
B	35	C4		NSD									
B	36	C24	CDQ	4		MD1-1	12	7.75	1.5			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	36	C24	CDQ		4	MB	7	0.4	18	5419	15314	Mg, Si, Fe Chrysotile Verified - KM	AFB>5, PCMEF-US, PSAS 5-10, PSAS TOT, PCAS 5-10, PCAS TOT
B	37	C44		NSD									
B	38	C43		NSD									
B	39	C23		NSD									
B	40	C3		NSD									
B	42	B23	AZQ	5		MD1-0	5.25	2.75	1.9			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	42	B23	AZQ		5	MF	4	0.25	16	5420	15315	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [2 1 0] - KM	
B	41	B3		NSD									
B	43	B43	AQ	6	6	F	1.05	0.25	4.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	44	B42	AQ	7	7	F	5.5	1.25	4.4			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	45	B22		NSD									
B	46	B2		NSD									
B	47	C2		NSD									
B	48	C22		NSD									
B	49	C42	AQ	8	8	F	17.75	1.75	10			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	50	C41	AQ	9	9	F	3.75	0.45	8.3			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	51	C21		NSD									
B	52	C1		NSD									
B	53	B1		NSD									
B	54	B21	CD	10	10	F	0.55	0.05	11			Chrysotile	TAS_AHRA
B	55	B41	AQ	11	11	F	15.5	3.5	4.4			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	56	B40		NSD									
B	57	B20		NSD									
B	58	C10		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-5CH-100204 *Lab/Cor Sample No.:* B4760 S44 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	59	C30	ADQ	12	12	F	3.25	0.75	4.3		15316	Mg, Al, Si, Fe Anthophyllite	TAS_AHRA
B	60	D10		NSD									
B	61	A20		NSD									
B	62	A40	AZQ	13	13	F	2.75	0.6	4.6	5422	15317	Na, Mg, Si, Ca, Fe Winchite Potassianwinchite - Zone Axis [7 -1 2] - KM	TAS_AHRA
C	63	B44		NSD									
C	64	B24		NSD									
C	65	B4		NSD									
C	66	C14		NSD									
C	67	C34		NSD									
C	68	B33		NSD									
C	69	B13		NSD									
C	70	C3		NSD									
C	71	C23		NSD									
C	72	C43		NSD									
C	73	B42		NSD									
C	74	B22		NSD									
C	75	B2	AZQ	14	14	F	6.8	2	3.4	5425	15320	Na, Mg, Al, Si, Fe Anthophyllite Zone Axis [2 1 - 1] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	76	C12		NSD									
C	77	C32		NSD									
C	78	B31		NSD									
C	79	B11		NSD									
C	80	C1		NSD									
C	81	C21		NSD									
C	82	C41		NSD									
C	83	A31		NSD									
C	84	A21		NSD									
C	85	A1		NSD									
C	86	D11		NSD									
C	87	D31		NSD									
C	88	A32		NSD									
C	89	A12		NSD									
C	90	D2		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBA-L2-5CH-100204 *Lab/Cor Sample No.:* B4760 S44 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	91	D22		NSD									
C	92	D42		NSD									
C	93	B21		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-12CH-100304 *Lab/Cor Sample No.:* B4760 S45 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	52	B41		NSD									
A	1	B24		NSD									
A	2	B4		NSD									
A	3	C14		NSD									
A	4	C24		NSD									
A	5	C34		NSD									
A	6	B33		NSD									
A	7	B13		NSD									
A	8	C3	CMQ	1	1	F	1.8	0.1	18	991	726	Mg, Si Chrysotile	TAS_AHRA
A	9	C23		NSD									
A	10	C43		NSD									
A	11	B32		NSD									
A	12	B22		NSD									
A	13	B2	AZQ	2	2	F	4.5	1	4.5	992	727	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 1 0] - KM	TAS_AHRA
A	14	C12		NSD									
A	15	C32		NSD									
A	16	C42		NSD									
A	17	B31		NSD									
A	18	B11		NSD									
A	19	C1		NSD									
A	20	C21		NSD									
A	21	C41		NSD									
A	22	A31		NSD									
A	23	A11		NSD									
A	24	D1		NSD									
A	25	D21		NSD									
A	26	D41		NSD									
A	27	A42		NSD									
A	28	A22		NSD									
A	29	A2		NSD									
A	30	D12		NSD									
A	31	D32		NSD									
B	32	B44		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-12CH-100304 *Lab/Cor Sample No.:* B4760 S45 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	33	B24		NSD									
B	34	B4		NSD									
B	35	C14		NSD									
B	36	C34		NSD									
B	37	B43		NSD									
B	38	B33		NSD									
B	39	B23		NSD									
B	40	B13		NSD									
B	41	B3		NSD									
B	42	C3		NSD									
B	43	C13		NSD									
B	44	C23		NSD									
B	45	C33		NSD									
B	46	B42		NSD									
B	47	B22		NSD									
B	48	B2		NSD									
B	49	C12		NSD									
B	50	C22		NSD									
B	51	C32	CDQ	3	3	F	0.8	0.11	7.3	1002	736	Mg, Si Chrysotile Verified - KM	TAS_AHRA
B	53	B31		NSD									
B	54	B21		NSD									
B	55	B1		NSD									
B	56	C11		NSD									
B	57	C31		NSD									
B	58	A41		NSD									
B	59	A31		NSD									
B	60	A21		NSD									
B	61	A11		NSD									
B	62	A10		NSD									
C	63	B4		NSD									
C	64	C4		NSD									
C	65	C14		NSD									
C	66	C24		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-12CH-100304 *Lab/Cor Sample No.:* B4760 S45 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	67	C34		NSD									
C	68	B33		NSD									
C	69	B23		NSD									
C	70	B3		NSD									
C	71	C13		NSD									
C	72	C33		NSD									
C	73	A22		NSD									
C	74	A12		NSD									
C	75	A2		NSD									
C	76	D12		NSD									
C	77	D22	CD	4		MD2-0	8	8	1.0			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	77	D22	CD		4	MF	2	0.08	25			Chrysotile	
C	77	D22	CD		5	MF	1.2	0.1	12			Chrysotile	
C	78	A21		NSD									
C	79	A1		NSD									
C	80	A30		NSD									
C	81	A20		NSD									
C	82	A10		NSD									
C	83	D10		NSD									
C	84	B30		NSD									
C	85	B20		NSD									
C	86	B10		NSD									
C	87	C10		NSD									
C	88	C20		NSD									
C	89	B11		NSD									
C	90	B1		NSD									
C	91	C1		NSD									
C	92	C11		NSD									
C	93	C21		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-1CH-100304 *Lab/Cor Sample No.:* B4760 S46 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24	AZQ	1	1	F	7.5	1	7.5	1003	728	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 1 0] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	3	B4		NSD									
A	4	C14	AQ	2	2	F	22	4	5.5			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	5	C34		NSD									
A	6	B33		NSD									
A	7	B13		NSD									
A	8	C3		NSD									
A	9	C23		NSD									
A	10	C43	AQ	3	3	F	11.5	2	5.8			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12		NSD									
A	15	C32		NSD									
A	16	B31		NSD									
A	17	B11		NSD									
A	18	C1		NSD									
A	19	C21		NSD									
A	20	C41		NSD									
A	21	A41		NSD									
A	22	A21		NSD									
A	23	A1		NSD									
A	24	D11	ADQ	4	4	F	23	4.2	5.5			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	25	D31		NSD									
A	26	A32		NSD									
A	27	A12		NSD									
A	28	D2		NSD									
A	29	D22		NSD									
A	30	D42		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-1CH-100304 *Lab/Cor Sample No.:* B4760 S46 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	31	B44		NSD									
B	32	B24		NSD									
B	33	B4		NSD									
B	34	C14		NSD									
B	35	C34		NSD									
B	36	B33		NSD									
B	37	B13		NSD									
B	38	C3		NSD									
B	39	C23		NSD									
B	40	C43		NSD									
B	41	B42		NSD									
B	42	B32		NSD									
B	43	B22		NSD									
B	44	B12		NSD									
B	45	B2		NSD									
B	46	C2		NSD									
B	47	C12		NSD									
B	48	C22		NSD									
B	49	C32		NSD									
B	50	C42		NSD									
B	51	A41		NSD									
B	52	A31		NSD									
B	53	A21		NSD									
B	54	A11		NSD									
B	55	A1		NSD									
B	56	D1		NSD									
B	57	D11		NSD									
B	58	D21		NSD									
B	59	D31		NSD									
B	60	D41		NSD									
B	61	D32		NSD									
B	62	D12		NSD									
B	63	A2		NSD									
C	64	B44		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-1CH-100304 *Lab/Cor Sample No.:* B4760 S46 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	65	B24		NSD									
C	66	B4		NSD									
C	67	C14		NSD									
C	68	C34		NSD									
C	69	C44		NSD									
C	70	C43		NSD									
C	71	C33		NSD									
C	72	C23		NSD									
C	73	C13		NSD									
C	74	C3		NSD									
C	75	B3		NSD									
C	76	B13		NSD									
C	77	B23	AQ	5	5	F	5	0.85	5.9			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	78	B33		NSD									
C	79	B22		NSD									
C	80	B12		NSD									
C	81	B2	AQ	6	6	F	10	2.5	4.0			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
C	81	B2	AQ	7		MD1-1	20	20	1.0			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	81	B2	AQ		7	MF	20	2	10			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	82	C2		NSD									
C	83	C12		NSD									
C	84	C22		NSD									
C	85	C32		NSD									
C	86	C42		NSD									
C	87	C41		NSD									
C	88	C31		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-2CH-100304 *Lab/Cor Sample No.:* B4760 S47 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B34		NSD									
A	3	B24		NSD									
A	4	B14		NSD									
A	5	C14	AQ	1		MD1-1	11	6	1.8			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	5	C14	AQ		1	MF	11	2.5	4.4		729	Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
A	6	C24		NSD									
A	7	C34		NSD									
A	8	C44		NSD									
A	9	C23		NSD									
A	10	C13		NSD									
A	11	C3		NSD									
A	12	B13	AZQ	2		MD1-1	10	6	1.7			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	12	B13	AZQ		2	MF	7.5	0.75	10	5445	15336	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 1 0] - KM	AFB>5, PCMEF-US
A	13	B23		NSD									
A	14	B33		NSD									
A	15	B43		NSD									
A	16	B42		NSD									
A	17	B32		NSD									
A	18	B22		NSD									
A	19	B12		NSD									
A	20	B2		NSD									
A	21	C2		NSD									
A	22	C12		NSD									
A	23	C22		NSD									
A	24	C32		NSD									
A	25	C42		NSD									
A	26	C41		NSD									
A	27	C31		NSD									
A	28	C21	AQ	3	3	F	12	1	12			Mg, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	29	C11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-2CH-100304 *Lab/Cor Sample No.:* B4760 S47 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	30	C1		NSD									
A	31	B1		NSD									
A	32	B11		NSD									
B	33	B44		NSD									
B	34	B34		NSD									
B	35	B24		NSD									
B	36	B14		NSD									
B	37	B4		NSD									
B	38	C4		NSD									
B	39	C14		NSD									
B	40	C24		NSD									
B	41	C34		NSD									
B	42	C33		NSD									
B	43	C23		NSD									
B	44	C13	AQ	4		MD1-0	7	4	1.8			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	44	C13	AQ		4	MF	2.75	0.85	3.2			Mg, Al, Si, Ca, Fe Actinolite	
B	45	C3		NSD									
B	46	B3		NSD									
B	47	B13		NSD									
B	48	B23		NSD									
B	49	B33		NSD									
B	50	B43		NSD									
B	51	B42		NSD									
B	52	B32		NSD									
B	53	B22		NSD									
B	54	B12		NSD									
B	55	B2		NSD									
B	56	C2		NSD									
B	57	C12		NSD									
B	58	C22		NSD									
B	59	C32		NSD									
B	60	C42		NSD									
C	61	B44		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-2CH-100304 *Lab/Cor Sample No.:* B4760 S47 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	62	B34	CDQ	5	5	F	1	0.1	10	995	731	Mg, Si Chrysotile Verified - KM	TAS_AHRA
C	63	B24		NSD									
C	64	B14		NSD									
C	65	B4		NSD									
C	66	C4		NSD									
C	67	C14		NSD									
C	68	C24		NSD									
C	69	C34		NSD									
C	70	C43		NSD									
C	71	C33		NSD									
C	72	C23	AQ	6	6	F	5	1.2	4.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	73	C13	AQ	7		MD1-1	20	7.5	2.7			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	73	C13	AQ		7	MF	16	2.5	6.4			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	74	C3		NSD									
C	75	B3		NSD									
C	76	B13		NSD									
C	77	B23	AQ	8		MD1-1	15	10	1.5			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	77	B23	AQ		8	MF	13	1.3	10			Mg, Al, Si, Ca, Fe Actinolite	AFB>5, PCMEF-US
C	78	B33		NSD									
C	79	B43		NSD									
C	80	B42		NSD									
C	81	B32		NSD									
C	82	B22		NSD									
C	83	B12	AZQ	9		MD1-1	11	7.5	1.5			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	83	B12	AZQ		9	MF	11	0.75	15	5424	15319	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 -1 2] - KM	AFB>5, PCMEF-US
C	84	B2	CMQ	10	10	F	1.5	0.1	15			Mg, Si Chrysotile	TAS_AHRA
C	85	B1		NSD									
C	86	B11		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-3CH-100304 *Lab/Cor Sample No.:* B4760 S48 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44	AZQ	1		MD1-1	9.5	4	2.4			Actinolite	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	1	B44	AZQ		1	MF	9	1.3	6.9	5426	15321	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [3 -1 2] - KM	AFB>5, PCMEF-US
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C44		NSD									
A	6	B33		NSD									
A	7	B13		NSD									
A	8	C3		NSD									
A	9	C23		NSD									
A	10	C43		NSD									
A	11	B42		NSD									
A	12	B22		NSD									
A	13	B2		NSD									
A	14	C12	ADQ	2	2	F	7.8	2.5	3.1			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
A	15	C32		NSD									
A	16	B31		NSD									
A	17	B11		NSD									
A	18	C1		NSD									
A	19	C21		NSD									
A	20	C41		NSD									
A	21	A41		NSD									
A	22	A31		NSD									
A	23	A21		NSD									
A	24	A11		NSD									
A	25	A1		NSD									
A	26	D1		NSD									
A	27	A40		NSD									
A	28	A30		NSD									
A	29	A10		NSD									
B	30	B42		NSD									
B	31	B22		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-3CH-100304 *Lab/Cor Sample No.:* B4760 S48 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	32	B12		NSD									
B	33	B2		NSD									
B	34	C2		NSD									
B	35	C12		NSD									
B	36	B21		NSD									
B	37	B11		NSD									
B	38	B1		NSD									
B	39	C1		NSD									
B	40	C11		NSD									
B	41	C21		NSD									
B	42	C10		NSD									
B	43	B20		NSD									
B	44	B10		NSD									
B	45	A30		NSD									
B	46	D30	AZQ	3	3	F	7.5	0.6	12	5428	15323	Mg, Al, Si, Ca, Fe Tremolite Zone Axis [5 1 6] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	47	D40		NSD									
B	48	A31		NSD									
B	49	A21		NSD									
B	50	A11		NSD									
B	51	A1		NSD									
B	52	D11		NSD									
B	53	D21		NSD									
B	54	A12		NSD									
B	55	D2		NSD									
B	56	D12	ADQ	4	4	F	2.8	0.45	6.2			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	57	D22		NSD									
C	58	A33	AZQ	5	5	F	15	1.6	9.4	1007	738	Mg, Al, Si, Ca, Fe Tremolite Zone Axis [5 1 4] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
C	59	A13		NSD									
C	60	D3		NSD									
C	61	D23		NSD									
C	62	D43		NSD									
C	63	D41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-3CH-100304 *Lab/Cor Sample No.:* B4760 S48 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	64	D21		NSD									
C	65	D1		NSD									
C	66	A11		NSD									
C	67	A31		NSD									
C	68	A41		NSD									
C	69	B20		NSD									
C	70	B10		NSD									
C	71	C10		NSD									
C	72	C30		NSD									
C	73	C40		NSD									
C	74	C42		NSD									
C	75	C22		NSD									
C	76	C2		NSD									
C	77	B12		NSD									
C	78	B22		NSD									
C	79	B42		NSD									
C	80	B43		NSD									
C	81	B23		NSD									
C	82	B3	AQ	6	6	F	3.5	0.7	5.0			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
C	83	C13		NSD									
C	84	C33		NSD									
C	85	C34		NSD									
C	86	C44		NSD									
C	87	C24		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-4CH-100304 *Lab/Cor Sample No.:* B4760 S49 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B44		NSD									
A	2	B24		NSD									
A	3	B4		NSD									
A	4	C14		NSD									
A	5	C34		NSD									
A	6	B33		NSD									
A	7	B13		NSD									
A	8	C3		NSD									
A	9	C23		NSD									
A	10	C43		NSD									
A	11	B42	AZQ	1	1	F	15	2.5	6.0	1004	15323	Mg, Al, Si, Ca, Fe Tremolite Zone Axis [1 0 1] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	12	B22		NSD									
A	13	B2	CDQ	2		MD1-0	4.5	3	1.5			Chrysotile	TAS_AHRA
A	13	B2	CDQ		2	MF	1	0.08	12	5429	15324	Mg, Si Chrysotile Verified - KM	
A	14	C12		NSD									
A	15	C32		NSD									
A	16	B31		NSD									
A	17	B11		NSD									
A	18	C1		NSD									
A	19	C21		NSD									
A	20	C41		NSD									
A	21	A41		NSD									
A	22	A21		NSD									
A	23	A1		NSD									
A	24	D11		NSD									
A	25	D31		NSD									
A	26	A32		NSD									
A	27	D22	AZQ	3		MD1-0	4.7	1	4.7			Actinolite	TAS_AHRA
A	27	D22	AZQ		3	MF	4.7	0.6	7.8	1008	15325	Mg, Al, Si, Ca, Fe Actinolite [1 0 1] Zone - KM	
A	28	A12		NSD									
A	29	D2		NSD									
A	30	A10		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-4CH-100304 *Lab/Cor Sample No.:* B4760 S49 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	31	B34		NSD									
B	32	B14		NSD									
B	33	C4		NSD									
B	34	C24		NSD									
B	35	C44		NSD									
B	36	B43		NSD									
B	37	B13		NSD									
B	38	C3		NSD									
B	39	C43	CMQ	4		MD1-0	9	5	1.8			Chrysotile	AS>5, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	39	C43	CMQ		4	MF	1	0.12	8.3			Mg, Si Chrysotile	
B	40	C23		NSD									
B	41	B42		NSD									
B	42	B22		NSD									
B	43	B2		NSD									
B	44	C12		NSD									
B	45	C32		NSD									
B	46	B41		NSD									
B	47	B21		NSD									
B	48	B1		NSD									
B	49	C11		NSD									
B	50	C21		NSD									
B	51	A41		NSD									
B	52	A21		NSD									
B	53	A1		NSD									
B	54	D11		NSD									
B	55	D21		NSD									
B	56	B40		NSD									
B	57	B20		NSD									
B	58	A30	ADQ	5	5	F	3.8	0.4	9.5			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA
B	59	A20		NSD									
B	60	A10	ADQ	6	6	F	5.5	0.6	9.2			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-5CH-100304 *Lab/Cor Sample No.:* B4760 S50 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	A43		NSD									
A	2	A23		NSD									
A	3	A3		NSD									
A	4	D13		NSD									
A	5	D33		NSD									
A	6	D43		NSD									
A	7	D41		NSD									
A	8	D21		NSD									
A	9	D1		NSD									
A	10	A11		NSD									
A	11	A31		NSD									
A	12	A41		NSD									
A	13	B40		NSD									
A	14	B20		NSD									
A	15	B10		NSD									
A	16	C10	AZQ	1	1	F	15	2	7.5	997	732	Na, Mg, Al, Si, Ca, Fe Actinolite Zone Axis [1 2 2] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	17	C30		NSD									
A	18	C40		NSD									
A	19	C42		NSD									
A	20	C22		NSD									
A	21	C2		NSD									
A	22	B12		NSD									
A	23	B32		NSD									
A	24	B42		NSD									
A	25	B43		NSD									
A	26	B23		NSD									
A	27	B3		NSD									
A	28	C13		NSD									
A	29	C33		NSD									
B	30	B14		NSD									
B	31	C4		NSD									
B	32	C34	CDQ	2	2	F	1.3	0.05	26	998	733	Mg, Si Chrysotile Verified - KM	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.
Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-5CH-100304 *Lab/Cor Sample No.:* B4760 S50 A1
Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
B	33	C44		NSD									
B	34	C42		NSD									
B	35	C22		NSD									
B	36	C2		NSD									
B	37	B12		NSD									
B	38	B33		NSD									
B	39	B40		NSD									
B	40	B20		NSD									
B	41	B10		NSD									
B	42	C10	ADQ	3	3	F	3.9	0.2	20			Mg, Si, Ca, Fe Actinolite	TAS_AHRA
B	43	C30		NSD									
B	44	C40		NSD									
B	45	D41		NSD									
B	46	D21		NSD									
B	47	D1		NSD									
B	48	A11		NSD									
B	49	A31		NSD									
B	50	A41		NSD									
B	51	A43	AQ	4	4	F	25	4	6.2			Mg, Al, Si, Ca, Fe Actinolite	AS>5, AFB>5, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	52	A23		NSD									
B	53	A3		NSD									
B	54	D13		NSD									
B	55	D33		NSD									
B	56	D34		NSD									
B	57	D14		NSD									
B	58	A4		NSD									
C	59	A43		NSD									
C	60	A23		NSD									
C	61	A3		NSD									
C	62	D13		NSD									
C	63	D33		NSD									
C	64	D43		NSD									
C	65	D41		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVBB-L2-5CH-100304 *Lab/Cor Sample No.:* B4760 S50 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
C	66	D21		NSD									
C	67	D1		NSD									
C	68	A11		NSD									
C	69	A31		NSD									
C	70	A41		NSD									
C	71	B20		NSD									
C	72	B10		NSD									
C	73	C10		NSD									
C	74	C30		NSD									
C	75	C40		NSD									
C	76	C42		NSD									
C	77	C12		NSD									
C	78	C2		NSD									
C	79	B2		NSD									
C	80	B22		NSD									
C	81	B32		NSD									
C	82	B42		NSD									
C	83	B33		NSD									
C	84	B13		NSD									
C	85	C3		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVM-H2-1FD-100204 *Lab/Cor Sample No.:* B4760 S51 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B41		NSD									
A	2	B31		NSD									
A	3	B21		NSD									
A	4	B11		NSD									
A	5	B1		NSD									
A	6	C11		NSD									
A	7	C31	CMQ	1	1	B	16	0.5	32	999	734	Mg, Si Chrysotile No Diffraction	AS>5, AFB>5, PCMEF-US, PCMES-US, PSAS >10, PSAS TOT, PCAS >10, PCAS TOT, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
A	8	C42		NSD									
A	9	C22		NSD									
A	10	C2	CMQ	2	2	B	2.5	0.4	6.2			Mg, Si Chrysotile	TAS_AHRA
A	11	B12		NSD									
B	12	A41		NSD									
B	13	A21		NSD									
B	14	A11		NSD									
B	15	D1		NSD									
B	16	D11		NSD									
B	17	D31		NSD									
B	18	D42		NSD									
B	19	D22		NSD									
B	20	D2		NSD									
B	21	A12		NSD									
B	22	A32		NSD									

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVM-H2-2FD-100204 *Lab/Cor Sample No.:* B4760 S52 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B34		NSD									
A	2	B24		NSD									
A	3	B14		NSD									
A	4	C4		NSD									
A	5	C14		NSD									
A	6	C34		NSD									
A	7	C43		NSD									
A	8	C33		NSD									
A	9	C13		NSD									
A	10	C3		NSD									
A	11	B13		NSD									
A	12	B23		NSD									
A	13	A41		NSD									
A	14	A21		NSD									
B	15	B44		NSD									
B	16	B34		NSD									
B	17	B24		NSD									
B	18	C4		NSD									
B	19	C14		NSD									
B	20	C24		NSD									
B	21	C34	CDQ	1	1	B	10	2	5.0	1010	15331	Mg, Si Chrysotile Verified - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	22	C44		NSD									
B	23	C23	AZQ	2	2	F	10	2	5.0	5435	15330	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 3 2] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS5-10_AHRA
B	23	C23	AQ	3	3	F	5	0.85	5.9			Mg, Al, Si, Ca, Fe Actinolite	TAS_AHRA

Lab/Cor, Inc.

A Professional Service Corporation in the Northwest

Report # 041172R3

Client: Ecology and Environment, Inc.

Project Name: Site# 0440.01CP, 0440.01CP-0001- FINAL RESULTS

TEM ASBESTOS STRUCTURE COUNT - RAW DATA

Sample No.: SVM-H2-3FD-100204 *Lab/Cor Sample No.:* B4760 S53 A1

Descripiton:

Gr	No.	Loc.	ID	Prim	Tot	Class	Len	Wid	Asp	Neg#	EDS#	Comment	Count Categories
A	1	B34		NSD									
A	2	B24		NSD									
A	3	B14		NSD									
A	4	B4		NSD									
A	5	C4		NSD									
A	6	C14		NSD									
A	7	C34		NSD									
A	8	B12		NSD									
A	9	C32		NSD									
A	10	B41		NSD									
A	11	B31		NSD									
A	12	B1		NSD									
B	13	B41		NSD									
B	14	B31		NSD									
B	15	B21		NSD									
B	16	B11		NSD									
B	17	B1		NSD									
B	18	C11		NSD									
B	19	C31		NSD									
B	20	C42		NSD									
B	21	C33	AZQ	1	1	F	11	1.5	7.3	5437	15333	Mg, Al, Si, Ca, Fe Actinolite Zone Axis [5 -1 2] - KM	AS>5, AFB>5, PCMEF-US, PCMES-US, TAS_AHRA, AS>5_AHRA, AS>10_AHRA
B	22	C23		NSD									

NSD = No Structures Detected
PAS = Primary Asbestos Structures
TAS = Total Asbestos Structures
AS>5 = Asbestos Structures > 5um
AFB>5 = Asbestos Fibers and Bundles > 5um
PCMEF-US = PCM Equivalent Fibers-US
PCMES-US = PCM Equivalent Structures-US
PCMEF-ISO = PCM Equivalent Fibers-ISO
PCMES-ISO = PCM Equivalent Structures-ISO

CF = Cleavage Fragments
TS = Transitional Structures

PSAS 5-10 = PROTOCOL ASB STRUCS 5-10
PSAS >10 = PROTOCOL ASB STRUCS >10
PSAS TOT = PROTOCOL ASB STRUCS TOTAL
PSCH 5-10 = PROTOCOL CHRYS STRUCS 5-10
PSCH >10 = PROTOCOL CHRYS STRUCS >10
PSCH TOT = PROTOCOL CHRYS STRUCS TOTAL
PSAM 5-10 = PROTOCOL AMPH STRUCS 5-10
PSAM >10 = PROTOCOL AMPH STRUCS >10
PSAM TOT = PROTOCOL AMPH STRUCS TOTAL

PChS = Primary Chrysotile Structures
PAmS = Primary Amphibole Structures

TAS_AHRA = AHERA-like Total Strucs 3:1
AS>5_AHRA = AHERA-like Asb Strucs >5 and 3:1
AS5-10_AHRA = AHERA-like Asb Strucs 5 - 10 and 3:1
AS>10_AHRA = AHERA-like Asb Strucs >10 and 3:1
TOS_AHRA = Total Other Amphibole Strucs 3:1
OS>5_AHRA = Other Amphibole Struc >5 and 3:1
OS5-10_AHRA = Other Amphibole Struc 5 - 10 and 3:1
OS>10_AHRA = Other Amphibole Strucs >10 and 3:1