ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-165

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1012	0-10'	10	0.010	0.010	none	0.3
1013	10-20'	10	0.010	0.010	none	0.1
1014	20-30'	10	0.010	0.010	none	0.1
1015	30-40'	10	trace	0.010	none	0.2
1016	40-50'	10	0.010	0.010	none	0.1
1017	50-60'	10	trace	-	none	-
1018	60-70'	10	trace	-	none	-
1019	70-80'	10	trace	-	none	-
1020	80-90'	10	0.034	0.010	0.03	none
1021	90-100'	10	trace	-	none	-
1022	100-110'	10	0.014	0.010	none	0.1
1023	110-120'	10	trace	-	none	-
1024	120-130'	10	trace	-	0.02	-
1025	130-140'	10	0.012	0.010	none	none
1026	140-150'	10	trace	-	none	-
1027	150-160'	10	trace	-	none	-
1028	160-170'	10	trace	-	none	-
1029	170-180'	10	0.018	0.010	none	none
1030	180-190'	10	trace	-	none	-
1031	190-200'	10	trace	-	none	-
1032	200-210'	10	trace	-	none	-
1033	210-220'	10	trace	-	none	-
1034	220-230'	10	0.154	0.010	none	none
1035	230-240'	10	0.012	0.010	none	none
1036	240-250'	10	0.012	0.005	none	none
1037	250-260'	10	0.012	0.010	none	none
1038	260-270'	10	0.012	trace	none	0.1
1039	270-280'	10	trace	none	none	0.1
1040	280-290'	10	0.024	trace	none	none
1041	290-300'	10	0.060	0.010	0.02	0.1
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-166

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1345	0-10'	10	0.020	-	0.16	-
1346	10-20'	10	0.028	0.020	0.09	-
1347	20-30'	10	0.812	0.510	0.47	-
1348	30-40'	10	0.050	0.200	0.03	-
1349	40-50'	10	0.062	0.040	none	-
1350	50-60'	10	0.054	0.045	none	-
1351	60-70'	10	0.020	0.020	none	-
1352	70-80'	10	0.014	0.020	none	-
1353	80-90'	10	trace	trace	none	-
1354	90-100'	10	0.012	0.010	none	-
1355	100-110'	10	0.016	0.010	none	-
1356	110-120'	10	0.026	0.010	none	-
1357	120-130'	10	trace	trace	none	-
1358	130-140'	10	0.012	0.010	0.01	-
1359	140-150'	10	0.014	0.010	0.03	-
1360	150-160'	10	0.014	0.010	none	-
1361	160-170'	10	0.162	0.050	none	-
1362	170-180'	10	0.032	0.060	0.11	-
1363	180-190'	10	0.054	0.030	none	-
1364	190-200'	10	0.042	0.025	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-167

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1042	0-10'	10	0.026	0.020	none	none
1043	10-20'	10	trace	-	0.04	-
1044	20-30'	10	trace	-	0.10	-
1045	30-40'	10	trace	-	none	-
1046	40-50'	10	0.012	0.005	none	none
1047	50-60'	10	0.010	trace	none	none
1048	60-70'	10	trace	trace	none	none
1049	70-80'	10	0.010	trace	0.03	none
1050	80-90'	10	trace	-	none	-
1051	90-100'	10	trace	-	none	-
1052	100-110'	10	trace	-	none	-
1053	110-120'	10	trace	-	none	-
1054	120-130'	10	none	-	none	-
1055	130-140'	10	-	trace	-	-
1056	140-150'	10	trace	-	none	-
1057	150-160'	10	trace	-	none	-
1058	160-170'	10	trace	-	none	-
1059	170-180'	10	0.022	0.005	0.04	0.1
1060	180-190'	10	trace	trace	0.24	none
1061	190-200'	10	0.014	0.005	none	none
1062	200-210'	10	0.024	0.010	0.04	none
1063	210-220'	10	0.010	0.010	none	none
1064	220-230'	10	trace	-	none	-
1065	230-240'	10	0.010	0.010	0.01	none
1066	240-250'	10	0.010	-	none	-
1067	250-260'	10	trace	trace	0.06	-
1068	260-270'	10	trace	-	0.04	-
1069	270-280'	10	0.038	0.040	none	none
1070	280-290'	10	0.014	0.010	none	0.1
1071	290-300'	10	trace	0.010	none	0.2
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-168

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1327	0-10'	10	0.022	0.020	0.22	-
1328	10-20'	10	0.018	0.010	none	-
1329	20-30'	10	trace	-	none	-
1330	30-40'	10	0.012	0.010	none	-
1331	40-50'	10	0.016	-	none	-
1332	50-60'	10	0.014	0.010	none	-
1333	60-70'	10	0.024	0.010	none	-
1334	70-80'	10	0.034	0.015	none	-
1335	80-90'	10	0.052	0.030	none	-
1336	90-100'	10	0.046	-	0.01	-
1337	100-110'	10	0.024	-	none	-
1338	110-120'	10	0.064	0.040	none	-
1339	120-130'	10	0.068	-	none	-
1340	130-140'	10	0.036	0.040	none	-
1341	140-150'	10	0.032	0.035	none	-
1342	150-160'	10	0.048	-	none	-
1343	160-170'	10	0.010	0.010	none	-
1344	170-180'	10	0.036	0.020	0.16	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-169

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1072	0-10'	10	0.052	-	0.13	-
1073	10-20'	10	0.052	-	0.13	-
1074	20-30'	10	0.038	0.040	none	-
1075	30-40'	10	0.022	0.010	none	-
1076	40-50'	10	0.022	0.015	none	-
1077	50-60'	10	0.028	-	0.03	-
1078	60-70'	10	0.032	0.010	none	-
1079	70-80'	10	0.014	-	none	-
1080	80-90'	10	0.016	-	none	-
1081	90-100'	10	0.016	0.010	0.06	-
1082	100-110'	10	trace	0.010	none	-
1083	110-120'	10	0.026	-	0.010	-
1084	120-130'	10	0.016	0.010	none	-
1085	130-140'	10	trace	-	none	-
1086	140-150'	10	trace	-	none	-
1087	150-160'	10	trace	-	none	-
1088	160-170'	10	0.024	0.010	0.010	-
1089	170-180'	10	trace	-	0.02	-
1090	180-190'	10	trace	-	0.12	-
1091	190-200'	10	trace	-	none	-
1092	200-210'	10	trace	-	none	-
1093	210-220'	10	trace	-	0.16	-
1094	220-230'	10	trace	-	none	-
1095	230-240'	10	-	0.010	-	-
1096	240-250'	10	-	-	0.26	-
1097	250-260'	10	trace	-	0.16	-
1098	260-270'	10	0.018	0.010	none	-
1099	270-280'	10	trace	-	none	-
1100	280-290'	10	trace	-	0.010	-
1101	290-300'	10	0.010	0.010	none	-

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-170

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1302	0-10'	10	0.018	0.010	none	-
1303	10-20'	10	0.018	0.010	none	-
1304	20-30'	10	0.022	0.030	none	-
1305	30-40'	10	0.508	0.700	0.71	-
1306	40-50'	10	0.026	0.020	none	-
1307	50-60'	10	0.036	0.030	none	-
1308	60-70'	10	0.036	0.030	none	-
1309	70-80'	10	0.048	0.020	none	-
1310	80-90'	10	0.086	0.100	none	-
1311	90-100'	10	0.026	0.040	none	-
1312	100-110'	10	0.046	0.080	none	-
1313	110-120'	10	0.068	0.080	0.03	-
1314	120-130'	10	0.062	-	none	-
1315	130-140'	10	0.032	0.020	none	-
1316	140-150'	10	0.026	0.040	none	-
1317	150-160'	10	0.038	0.020	none	-
1318	160-170'	10	0.044	0.030	none	-
1319	170-180'	10	0.040	-	none	-
1320	180-190'	10	0.022	0.030	none	-
1321	190-200'	10	0.078	0.070	none	-
1322	200-210'	10	0.056	-	-	-
1323	210-220'	10	0.048	0.040	none	-
1324	220-230'	10	0.012	0.010	none	-
1325	230-240'	10	0.030	0.020	none	-
1326	240-250'	10	0.018	0.020	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-171

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1102	0-10'	10	0.046	-	0.43	-
1103	10-20'	10	0.062	-	0.16	-
1104	20-30'	10	0.028	-	0.15	-
1105	30-40'	10	0.012	-	0.11	-
1106	40-50'	10	0.014	0.010	none	-
1107	50-60'	10	trace	0.010	none	-
1108	60-70'	10	0.050	0.010	none	-
1109	70-80'	10	trace	-	none	-
1110	80-90'	10	0.012	0.010	none	-
1111	90-100'	10	trace	-	none	-
1112	100-110'	10	0.026	-	0.03	-
1113	110-120'	10	0.010	-	0.17	-
1114	120-310'	10	trace	-	none	-
1115	130-140'	10	trace	-	none	-
1116	140-150'	10	0.014	0.010	none	-
1117	150-160'	10	trace	0.010	none	-
1118	160-170'	10	0.010	0.010	0.37	-
1119	170-180'	10	trace	-	none	-
1120	180-190'	10	trace	-	none	-
1121	190-200'	10	trace	-	0.06	-
1122	200-210'	10	trace	-	0.14	-
1123	210-220'	10	trace	-	0.08	-
1124	220-230'	10	trace	-	none	-
1125	230-240'	10	trace	-	none	-
1126	240-250'	10	0.012	0.010	none	-
1127	250-260'	10	0.018	0.010	none	-
1128	260-270'	10	trace	-	none	-
1129	270-280'	10	trace	-	0.08	-
1130	280-290'	10	trace	-	none	-
1131	290-300'	10	0.010	0.010	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-172

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1279	0-10'	10	0.026	0.030	none	-
1280	10-20'	10	0.016	-	0.18	-
1281	20-30'	10	0.010	0.020	none	-
1282	30-40'	10	trace	-	none	-
1283	40-50'	10	trace	0.005	none	-
1284	50-60'	10	0.010	0.005	none	-
1285	60-70'	10	0.010	0.005	none	-
1286	70-80'	10	0.012	0.010	0.02	-
1287	80-90'	10	0.020	0.015	none	-
1288	90-100'	10	0.010	0.015	none	-
1289	100-110'	10	trace	-	none	-
1290	110-120'	10	0.010	-	none	-
1291	120-130'	10	0.010	0.020	none	-
1292	130-140'	10	trace	-	none	-
1293	140-150'	10	0.010	0.030	0.13	-
1294	150-160'	10	0.010	0.010	none	-
1295	160-170'	10	0.012	0.010	none	-
1296	170-180'	10	0.010	-	none	-
1297	180-190'	10	trace	0.010	none	-
1298	190-200'	10	-	0.005	-	-
1299	200-210'	10	trace	-	none	-
1300	210-220'	10	trace	-	0.66	-
1301	220-230'	10	0.010	-	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-173

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1132	0-10'	10	0.058	-	0.23	-
1133	10-20'	10	0.018	-	0.40	-
1134	20-30'	10	0.084	-	0.46	-
1135	30-40'	10	0.024	0.015	none	-
1136	40-50'	10	0.012	0.010	none	-
1137	50-60'	10	trace	-	0.02	-
1138	60-70'	10	trace	-	none	-
1139	70-80'	10	trace	-	0.08	-
1140	80-90'	10	0.012	-	none	-
1141	90-100'	10	trace	-	none	-
1142	100-110'	10	trace	-	none	-
1143	110-120'	10	trace	-	0.16	-
1144	120-130'	10	0.010	0.010	none	-
1145	130-140'	10	trace	-	none	-
1146	140-150'	10	trace	-	none	-
1147	150-160'	10	trace	-	2.02	-
1148	160-710'	10	trace	-	0.28	-
1149	170-180'	10	trace	-	-	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-174

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1252	0-10'	10	trace	-	0.06	-
1253	10-20'	10	trace	-	none	-
1254	20-30'	10	trace	-	none	-
1255	30-40'	10	trace	-	none	-
1256	40-50'	10	trace	-	none	-
1257	50-60'	10	0.014	0.010	none	-
1258	60-70'	10	trace	-	none	-
1259	70-80'	10	none	-	none	-
1260	80-90'	10	none	-	none	-
1261	90-100'	10	trace	-	none	-
1262	100-110'	10	trace	-	none	-
1263	110-120'	10	trace	-	0.18	-
1264	120-130'	10	trace	-	0.38	-
1265	130-140'	10	none	-	none	-
1266	140-150'	10	trace	-	none	-
1267	150-160'	10	trace	-	none	-
1268	160-170'	10	trace	-	none	-
1269	170-180'	10	trace	-	none	-
1270	180-190'	10	trace	-	none	-
1271	190-200'	10	none	-	none	-
1272	200-210'	10	trace	-	none	-
1273	210-220'	10	none	-	none	-
1274	220-230'	10	trace	-	none	-
1275	230-240'	10	none	-	none	-
1276	240-250'	10	trace	-	none	-
1277	250-260'	10	trace	-	none	-
1278	260-270'	10	trace	-	0.02	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-175

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1150	0-10'	10	0.010	-	none	-
1151	10-20'	10	0.012	0.010	none	-
1152	20-30'	10	0.010	0.010	none	-
1153	30-40'	10	0.054	0.040	0.37	-
1154	40-50'	10	0.026	0.040	0.3	-
1155	50-60'	10	0.018	0.030	0.16	-
1156	60-70'	10	0.036	0.030	none	-
1157	70-80'	10	0.036	0.030	none	-
1158	80-90'	10	0.012	0.010	none	-
1159	90-100'	10	trace	-	none	-
1160	100-110'	10	0.010	-	none	-
1161	110-120'	10	0.012	0.010	none	-
1162	120-130'	10	0.010	-	0.03	-
1163	130-140'	10	trace	-	none	-
1164	140-150'	10	none	-	none	-
1165	150-160'	10	0.016	0.015	none	-
1166	160-170'	10	trace	-	none	-
1167	170-180'	10	trace	-	none	-
1168	180-190'	10	trace	-	none	-
1169	190-200'	10	trace	-	none	-
1170	200-210'	10	0.010	0.010	none	-
1171	210-220'	10	trace	-	-	-
1172	220-230'	10	trace	-	none	-
1173	230-240'	10	trace	-	none	-
1174	240-250'	10	trace	-	none	-
1175	250-260'	10	none	-	none	-
1176	260-270'	10	trace	-	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-176

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1202	0-10'	10	0.010	0.010	0.1	-
1203	10-20'	10	0.010	0.010	0.1	-
1204	20-30'	10	0.010	0.010	0.1	-
1205	30-40'	10	0.010	0.010	0.1	-
1206	40-50'	10	0.022	0.010	none	-
1207	50-60'	10	0.016	0.010	none	-
1208	60-70'	10	0.018	0.010	0.14	-
1209	70-80'	10	0.014	0.010	none	-
1210	80-90'	10	0.018	0.010	none	-
1211	90-100'	10	0.016	0.010	none	-
1212	100-110'	10	0.014	0.010	none	-
1213	110-120'	10	0.018	0.010	0.02	-
1214	120-130'	10	0.016	0.010	none	-
1215	130-140'	10	0.014	0.010	none	-
1216	140-150'	10	trace	0.010	none	-
1217	150-160'	10	0.010	0.010	0.13	-
1218	160-170'	10	trace	-	none	-
1219	170-180'	10	trace	-	none	-
1220	180-190'	10	trace	-	none	-
1221	190-200'	10	trace	-	none	-
1222	200-210'	10	trace	-	none	-
1223	210-220'	10	0.010	0.010	none	-
1224	220-230'	10	0.018	0.010	none	-
1225	230-240'	10	0.010	0.010	none	-
1226	240-250'	10	0.012	0.010	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-177

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1177	0-10'	10	none	-	none	-
1178	10-20'	10	none	-	none	-
1179	20-30'	10	trace	-	none	-
1180	30-40'	10	trace	-	none	-
1181	40-50'	10	trace	-	none	-
1182	50-60'	10	trace	-	0.04	-
1183	60-70'	10	trace	-	0.02	-
1184	70-80'	10	0.010	0.010	none	-
1185	80-90'	10	-	-	-	-
1186	90-100'	10	0.012	0.010	0.07	-
1187	100-110'	10	0.010	0.010	none	-
1188	110-120'	10	0.024	0.010	none	-
1189	120-130'	10	0.062	0.050	none	-
1190	130-140'	10	0.070	0.050	0.65	-
1191	140-150'	10	0.068	0.050	0.53	-
1192	150-160'	10	0.034	0.010	0.41	-
1193	160-170'	10	trace	0.010	none	-
1194	170-180'	10	0.022	0.010	none	-
1195	180-190'	10	0.030	0.010	none	-
1196	190-200'	10	trace	-	none	-
1197	200-210'	10	trace	-	0.08	-
1198	210-220'	10	trace	-	none	-
1199	220-230'	10	trace	-	none	-
1200	230-240'	10	trace	0.010	none	-
1201	240-250'	10	trace	-	0.08	-

T.D.

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-178

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1445	0-10'	10	0.022	0.020	none	-
1446	10-20'	10	trace	0.010	none	-
1447	20-30'	10	0.030	0.010	0.11	-
1448	30-40'	10	0.024	0.010	0.16	-
1449	40-50'	10	0.038	0.020	none	-
1450	50-60'	10	0.034	0.020	none	-
1451	60-70'	10	0.020	0.010	none	-
1452	70-80'	10	0.016	0.010	none	-
1453	80-90'	10	0.012	0.020	none	-
1454	90-100'	10	trace	0.010	0.24	-
1455	100-110'	10	0.010	0.010	0.03	-
1456	110-120'	10	0.012	0.010	none	-
1457	120-130'	10	0.012	0.010	none	-
1458	130-140'	10	trace	0.010	none	-
1459	140-150'	10	0.010	0.010	none	-
1460	150-160'	10	0.010	0.010	none	-
1461	160-170'	10	0.020	0.010	none	-
1462	170-180'	10	-	0.010	-	-
1463	180-190'	10	0.010	0.060	none	-
1464	190-200'	10	0.010	0.010	none	-
1465	200-210'	10	0.016	0.010	none	-
1466	210-220'	10	0.012	0.015	none	-
1467	220-230'	10	trace	-	none	-
1468	230-240'	10	trace	-	0.18	-
1469	240-250'	10	0.016	0.010	0.02	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-179

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1470	0-10'	10	trace	0.010	0.12	-
1471	10-20'	10	0.014	0.010	0.11	-
1472	20-30'	10	0.018	0.010	0.74	-
1473	30-40'	10	0.016	0.010	0.10	-
1474	40-50'	10	0.020	0.010	0.34	-
1475	50-60'	10	0.046	0.030	0.65	-
1476	60-70'	10	0.032	0.040	0.17	-
1477	70-80'	10	0.062	0.040	none	-
1478	80-90'	10	0.068	0.050	none	-
1479	90-100'	10	0.068(A)	0.050	none	-
			0.060(B)	0.050	none	-
1480	100-110'	10	0.048	0.050	none	-
1481	110-120'	10	0.028	0.050	none	-
1482	120-130'	10	0.058	0.060	none	-
1483	130-140'	10	0.050	0.040	none	-
1484	140-150'	10	0.058	0.040	0.46	-
1485	150-160'	10	0.072	0.060	none	-
1486	160-170'	10	0.060	0.050	none	-
1487	170-180'	10	0.042	0.050	0.88	-
1488	180-190'	10	0.040	0.030	0.26	-
1489	190-200'	10	0.016	0.010	none	-
1490	200-210'	10	trace	0.010	0.10	-
1491	210-220'	10	0.014	0.015	0.09	-
1492	220-230'	10	trace	-	0.06	-
1493	230-240'	10	trace	-	0.16	-
1494	240-250'	10	trace	-	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-180

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-756	0-10'	10	-	-	-	-
757	10-20'	10	0.012	0.010	none	none
758	20-30'	10	-	-	-	-
759	30-40'	10	trace	-	0.16	-
760	40-50'	10	trace	0.015	0.16	none
761	50-60'	10	0.010	0.010	0.1	0.1
762	60-70'	10	trace	-	none	-
763	70-80'	10	trace	-	none	-
764	80-90'	10	trace	-	none	-
765	90-100'	10	trace	-	none	-
766	100-110'	10	-	0.010	-	none
767	110-120'	10	trace	-	none	-
768	120-130'	10	-	0.010	-	none
769	130-140'	10	trace	-	0.22	-
770	140-150'	10	trace	-	0.04	-
771	150-160'	10	trace	-	0.24	-
772	160-170'	10	trace	-	0.10	-
773	170-180'	10	trace	-	none	-
774	180-190'	10	trace	-	none	-
775	190-200'	10	trace	-	0.22	-
776	200-210'	10	0.010	0.010	0.05	none
777	210-220'	10	-	-	-	-
778	220-230'	10	0.012	-	0.17	-
779	230-240'	10	trace	0.010	none	none
780	240-250'	10	0.010	0.010	0.07	none
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-181

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1495	0-10'	10	0.010	0.050	0.06	-
1496	10-20'	10	0.018	0.030	0.16	-
1497	20-30'	10	0.010	0.030	none	-
1498	30-40'	10	-	0.010	-	-
1499	40-50'	10	trace	0.010	0.04	-
1500	50-60'	10	trace	-	0.24	-
1501	60-70'	10	0.036	0.020 .028	0.04	-
1502	70-80'	10	0.018	0.020	none	-
1503	80-90'	10	0.012	0.010	0.03	-
1504	90-100'	10	0.010	0.010	none	-
1505	100-110'	10	trace	0.010	0.02	-
1506	110-120'	10	0.010	0.020	0.03	-
1507	120-130'	10	0.014	0.020	0.05	-
1508	130-140'	10	0.016	0.060	none	-
1509	140-150'	10	trace	-	0.06	-
1510	150-160'	10	-	0.015(A)	-	-
			-	0.005(B)	-	-
1511	160-170'	10	trace	-	none	-
1512	170-180'	10	0.010	0.005	0.17	-
1513	180-190'	10	0.014	0.010	0.25	-
1514	190-200'	10	0.020	0.020	none	-
1515	200-210'	10	0.040	0.040 .026	none	-
1516	210-220'	10	0.020	0.020	none	-
1517	220-230'	10	0.014	0.010	none	-
1518	230-240'	10	0.026	none	none	-
1519	240-250'	10	0.096	0.110 ?	none	-
	T.D.		.103			

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-182

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-781	0-10'	10	trace	0.010	none	0.1
782	10-20'	10	0.016	0.010	0.06	none
783	20-30'	10	0.024	0.010	none	0.1
784	30-40'	10	0.016	0.010	0.14	none
785	40-50'	10	0.010	0.010	0.07	0.1
786	50-60'	10	0.022	0.010	none	none
787	60-70'	10	trace	-	none	-
788	70-80'	10	trace	-	none	-
789	80-90'	10	0.026	0.010	none	none
790	90-100'	10	0.010	0.010	0.07	none
791	100-110'	10	0.016	0.010	0.24	0.2
792	110-120'	10	trace	-	none	-
793	120-130'	10	trace	-	none	-
794	130-140'	10	-	0.010	-	none
795	140-150'	10	trace	-	0.10	-
796	150-160'	10	-	0.005	-	none
797	160-170'	10	trace	-	0.28	-
798	170-180'	10	0.010	trace	0.25	none
799	180-190'	10	trace	-	0.14	-
800	190-200'	10	trace	trace	none	none
901	200-210'	10	none	-	none	-
902	210-220'	10	trace	-	none	-
903	220-230'	10	trace	-	none	-
904	230-240'	10	none	-	none	-
905	240-250'	10	trace	-	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-183

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1520	0-10'	10	-	-	-	-
1521	10-20'	10	-	-	-	-
1522	20-30'	10	-	-	-	-
1523	30-40'	10	-	-	-	-
1524	40-50'	10	0.010	0.010	none	-
1525	50-60'	10	none	-	none	-
1526	60-70'	10	trace	-	none	-
1527	70-80'	10	0.010	0.010	none	-
1528	80-90'	10	trace	-	none	-
1529	90-100'	10	0.016	0.090	none	-
1530	100-110'	10	0.020	0.040	none	-
1531	110-120'	10	0.010	0.010	none	-
1532	120-130'	10	trace	-	0.04	-
1533	130-140'	10	trace	-	none	-
1534	140-150'	10	0.010	0.010	none	-
1535	150-160'	10	trace	-	none	-
1536	160-170'	10	trace	-	none	-
1537	170-180'	10	trace	-	none	-
1538	180-190'	10	trace	-	none	-
1539	190-200'	10	trace	-	none	-
1540	200-210'	10	trace	-	none	-
1541	210-220'	10	trace	-	none	-
1542	220-230'	10	trace	-	none	-
1543	230-240'	10	none	-	none	-
1544	240-250'	10	0.010	0.010	none	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-184

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-906	0-10'	10	0.018	0.010	0.04	none
907	10-20'	10	0.014	0.010	0.10	none
908	20-30'	10	0.016	0.020	0.10	none
909	30-40'	10	-	-	-	-
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-185

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1545	0-10'	10	trace	0.010	none	-
1546	10-20'	10	trace	0.010	none	-
1547	20-30'	10	trace	0.010	none	-
1548	30-40'	10	0.010	0.010	none	-
1549	40-50'	10	0.010	0.010	none	-
1550	50-60'	10	0.020	0.010	0.82	-
1551	60-70'	10	0.054	0.030	none	-
1552	70-80'	10	0.014	0.005	none	-
1553	80-90'	10	0.010	0.010	0.07	-
1554	90-100'	10	trace	0.010	0.14	-
1555	100-110'	10	0.010	0.010	0.23	-
1556	110-120'	10	trace	-	0.14	-
1557	120-130'	10	trace	-	none	-
1558	130-140'	10	trace	-	none	-
1559	140-150'	10	trace	-	none	-
1560	150-160'	10	trace(A)	-	none	-
			trace(B)	-	0.04	-
1561	160-170'	10	trace	-	none	-
1562	170-180'	10	0.012	0.010	none	-
1563	180-190'	10	trace	none	none	-
1564	190-200'	10	0.010	trace	0.15	-
1565	200-210'	10	trace	-	0.12	-
1566	210-220'	10	trace	-	none	-
1567	220-230'	10	-	0.010	-	-
1568	230-240'	10	-	trace	-	-
1569	240-250'	10	trace	-	none	-

T.D.

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-186

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-910	0-10'	10	0.034	0.030	0.63	none
911	10-20'	10	trace	-	none	-
912	20-30'	10	trace	-	0.32	-
913	30-40'	10	trace	-	0.10	-
914	40-50'	10	0.012	0.010	none	none
915	50-60'	10	0.018	0.010	0.02	none
916	60-70'	10	0.014	0.010	none	none
917	70-80'	10	0.010	0.010	none	0.1
918	80-90'	10	0.010	0.010	none	0.1
919	90-100'	10	0.010	0.010	none	none
920	100-110'	10	trace	0.010	0.08	none
921	110-120'	10	0.014	0.010	0.11	none
922	120-130'	10	trace	0.010	none	none
923	130-140'	10	0.012	0.010	none	0.1
924	140-150'	10	0.010	0.005	0.03	none
925	150-160'	10	0.010	0.010	none	none
926	160-170'	10	0.010	0.010	0.21	none
927	170-180'	10	trace	0.010	none	none
928	180-190'	10	0.014	0.010	0.25	none
929	190-200'	10	none	0.005	none	none
930	200-210'	10	0.010	0.005	0.01	none
931	210-220'	10	0.014	0.005	none	none
932	220-230'	10	0.010	0.005	none	none
933	230-240'	10	0.010	0.005	0.05	none
934	240-250'	10	0.014	0.010	0.05	none
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-187

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-1570	0-10'	10	0.014		0.31	
1571	10-20'	10	0.012		0.17	
1572	20-30'	10	0.014		0.07	
1573	30-40'	10	trace		0.02	
1574	40-50'	10	0.010		0.05	
1575	50-60'	10	0.022		none	
1576	60-70'	10	0.010		none	
1577	70-80'	10	trace		none	
1578	80-90'	10	trace		none	
1579	90-100'	10	0.010		none	
1580	100-110'	10	0.012		none	
1581	110-120'	10	0.010		0.09	
1582	120-130'	10	trace		0.30	
1583	130-140'	10	0.010		0.45	
1584	140-150'	10	trace		0.36	
1585	150-160'	10	trace		none	
1586	160-170'	10	trace		none	
1587	170-180'	10	0.012		0.15	
1588	180-190'	10	trace		0.48	
1589	190-200'	10	none		0.66	
1590	200-210'	10	0.010		0.37	
1591	210-220'	10	trace		0.14	
1592	220-230'	10	trace		none	
1593	230-240'	10	trace		none	
1594	240-250'	10	0.006		none	
	T.D.					

ASSAY LOG

Gilt Edge Project
Lawrence County, South Dakota

RDH 79-GLE-188

Sample No.	Interval	Ft.	Au Oz/ton Hunter	Au Oz/ton Union	Ag Oz/ton Hunter	Ag Oz/ton Union
79GE-935	0-10'	10	0.022	0.020	0.18	0.1
936	10-20'	10	0.022	0.020	0.18	0.1
937	20-30'	10	trace	-	0.08	-
938	30-40'	10	0.030	0.020	none	0.1
939	40-50'	10	0.010	0.010	0.09	none
940	50-60'	10	trace	0.010	none	none
941	60-70'	10	0.010	0.010	0.23	none
942	70-80'	10	trace	-	none	-
943	80-90'	10	trace	-	0.24	-
944	90-100'	10	trace	-	none	-
945	100-110'	10	0.010	0.010	none	none
946	110-120'	10	trace	-	none	-
947	120-130'	10	0.010	0.010	none	none
948	130-140'	10	none	-	0.04	-
949	140-150'	10	0.010	0.010	0.07	none
950	150-160'	10	0.014	0.010	0.91	0.1
951	160-170'	10	0.010	0.010	none	0.1
952	170-180'	10	-	-	-	-
953	180-190'	10	-	-	-	-
954	190-200'	10	-	-	-	-
955	200-210'	10	-	-	-	-
956	210-220'	10	-	-	-	-
957	220-230'	10	-	-	-	-
958	230-240'	10	-	-	-	-
959	240-250'	10	-	-	-	-

T.D.

79 GLE 125

0-60' brown FeO_x stained medium grained quartz latite. Rock contains 2-4% disseminated pyrite. Minor jarosite on some fractures.

60-80' light brown moderatly clay alt'd latite or dacite. Rock contain 1-2% dessemnated, oxidized pyrite.

80-170' same as 0-60' only moderally clay alt'd. in some intervals.

170-250 same as 80-170 with ~~only partial portally~~ pyrite ~~is only~~ slightly oxidized to unoxidized ~~in most cases~~.

79 GLE 126

0 – 70 light brown partially clay alt'd coarse grained quartz latite (?) porphyry. Rock appears to have contained 1-3% pyrite both disseminated and in clots. Sulfide is almost totally oxidized.

70 – 180 white partially clay alt'd medium grained latite, w/ decreasing qtz content and fresh pyrite, 1 – 3%, in clots and as disseminated cubes.

180 – 250 gray coarse grained latite porphyry w/ 2-5% pyrite partially oxidized and FeOx staining on some fractures. Rock appears to be slightly silica flooded.

79 GLE 127

0 – 80 light brown to brown FeOx stained medium grained latite. Some fragments are coated w/ ~~clay~~ brown clay. Rock contained 2–5% pyrite both disseminated and ~~in~~ coating fractures. Rock is totally oxidized.

80 – 160 white to light brown partially oxidized medium grained latite. Rock contains 1–3% pyrite generally disseminated. A few pyrite grains are coated w/ ~~CuOx~~ black CuOx.

160 – 250 dark gray medium to fine grained latite(?) w/ 1–3% disseminated pyrite and trace amounts of dark sulfide (probably ~~sphalerite~~ sphalerite). A few fragments of (pE) biotite schist at 240 – 250'.

pE

79 GLE 128

0-80 light red brown, partially clay alt'd coarse grained latite (?) porphyry. Rock contained 1-2% disseminated pyrite which is partially ~~oxidized~~ to totally oxidized. 60-80 increasing silicification

80-160 white to tan partially clay alt'd coarse grained latite (?) porphyry. Rock contains 1-3% dessemnated pyrite. A few cubes of pyrite are coated w/ black CuOx.

160-170 same as 0-80 partially oxidized.

170-250 same as 80-160 w/ decreasing pyrite content.