EMSL Analytical, Inc.

200 Route 130 North, Cinnaminson, NJ 08077
(800) 220-3675

INVOICE NO.	PAGE
04250725	1 of 1
INVOICE DATE	
1/5/2011	

BILL TO
Air Management Services
Attn: Rich Annunziato
Dept. of Public Health
321 University Avenue - 3rd Floor
Philadelphia,P A 19104

REPORT TO
Air Management Services
Attn: Rich Annunziato
Dept. of Public Health
321 University Avenue - 3rd Floor
Philadelphia, PA 19104

SLSM.	SHIP VIA	TERMS	PIC	BILLING FREQUENCY	CUST. NO.
sross	Walk In	Net30 Days	SI	With Report	AIRM55

DATE	ORDER NO.	QTY	TEST CODE	TEST DESCRIPTION	UNIT	UNIT PRICE	AMOUNT
1/4/2011	041100145	9	PLM	Asbestos Analysis ofB ulk Materials via EPA 600/R-93/116 Method using Polarized LightM icroscopy 6 Hour Project: PROJECT NAME/NUMBER: ARSENAL BUSINESS CENTER BLDG 301	EA	15.75	141.75
						SUB TOTAL	141.75
						INVOICE TOTAL	$141.75

Please review your invoice promptly.W e will gladly correct any errors within 60 days of the invoice date.A fter that, we deem the invoice to be correct and reserve the rightno t to issue credits, in whole or part. A 1.5% finance charge will be added to invoices over 30 days.

Billing Inquiries - please call 1-800-220-3675

Please detach and return with payment

1/5/2011 CUST # AIRM55 INV # 04250725 $141.75

DEPT: 04

Please Remit to: EMSL ANALYTICAL, INC.
200 Route 130 North
Cinnaminson,N J 08077

Billing Inquiries - please call 1-800-220-3675

Paymenti n US Funds Only.

EMSL Analytical, Inc.
Chain of Custody

Asbestos

EMSL Representative: **Scott Ross**

Air Management Services
City of Philadelphia
321 University Ave.
2nd Floor

EMSL Bill to:
Dept. of Public Health
Air Management Services
321 University Ave.
Philadelphia, PA 19104

Phone Results to: Richard Annunziato
Telephone No: (215) 685-9458

Fax Results to: Richard Annunziato
Fax No: (215) 685-9496

Project Name/Number: Arsenal Business Center Bldg 301

Purchase Order # ES-01-04-11-A thru G

Matrix		
☐ Air	☐ Soil	☐ Micro Vac.
☑ Bulk	☐ Drinking Water	

Turnaround			
☐ 3 hour	☐ 6 hour	☑ 12 hours	☐ 24 hour
☐ 48 hour	☐ 72 hour	☐ 96 hour	☐ 120 hour

PCM – Air	TEM – Air	TEM – Water
☐ NIOSH 7400(A) Issue 2: August 1994	☐ AHERA 40 CFR, Part 763 Subpart E	☐ EPA 100.1
☐ OSHA w/TWA	☐ NIOSH 7402	☐ EPA 100.2
☐ Other:	☐ EPA Level III	☐ NYS 198.2
PLM – Bulk	**TEM – Bulk**	**TEM – Microvac/Wipe**
☑ EPA 600/R-93/116	☐ Drop Mount/ Qualitative	☐ ASTM D 5755-95 (Quantitative Method)

Sample Numbers: ES-01-04-11 - A,B,C,D,E,F, G Number of Samples: 9

Relinquished by: [signature] Date: 1/4/2011 Time: 12:50p

Relinquished by: Date: Time:

EMSL Analytical, Inc.
200 Route 130 North, Cinnaminson, NJ 08077
Phone: (800) 220-3675 Fax: (856) 786-5974 Email: westmontaslab@EMSL.com

Attn: **Rich Annunziato**
Air Management Services
Dept. of Public Health
321 University Avenue - 3rd Floor
Philadelphia, PA 19104

Fax: (215) 685-9496 Phone: (215) 685-9458

Project: **PROJECT NAME/NUMBER: ARSENAL BUSINESS CENTER BLDG 301**

Customer ID: AIRM55
Customer PO:
Received: 01/04/11 9:00 PM
EMSL Order: 041100145

EMSL Proj:
Analysis Date: 1/4/2011

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos %	Fibrous	Non-Asbestos %	Non-Fibrous	Asbestos %	Type
ES-01-04-11-A *041100145-0001*	BLDG 301-NEAR ENTRANCE	Tan Non-Fibrous Heterogeneous	2%	Cellulose	94%	Non-fibrous (other)	4%	Chrysotile
ES-01-04-11-A1 *041100145-0002*	BLDG 301-NEAR ENTRANCE	Black Non-Fibrous Heterogeneous	4%	Cellulose	94%	Non-fibrous (other)	2%	Chrysotile
ES-01-04-11-B *041100145-0003*	BLDG 301-NEAR ENTRANCE	Various Non-Fibrous Heterogeneous	4%	Cellulose	96%	Non-fibrous (other)	None Detected	
ES-01-04-11-C *041100145-0004*	BLDG 301-1ST FLOOR	Various Fibrous Homogeneous	1%	Cellulose	89%	Non-fibrous (other)	7% 3%	Amosite Chrysotile
ES-01-04-11-D *041100145-0005*	BLDG 301-1ST FLOOR	Tan Non-Fibrous Heterogeneous	2%	Cellulose	95%	Non-fibrous (other)	3%	Chrysotile
ES-01-04-11-D1 *041100145-0006*	BLDG 301-1ST FLOOR	Black Non-Fibrous Heterogeneous	4%	Cellulose	94%	Non-fibrous (other)	2%	Chrysotile
ES-01-04-11-E *041100145-0007*	BLDG 301-BASEMENT	White Fibrous Homogeneous			80%	Non-fibrous (other)	10% 10%	Amosite Chrysotile

Initial reportf rom 01/05/2011 07:01:54

Analyst(s)

Anne Paul(9)

Stephen Siegel,C IH, Laboratory Manager
or other approved signatory

EMSL maintains liability limited to the costo fan alysis. This reportr elates only to the samples reported above and may notbe reproduced,e xcepti n full,w ithout written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations.I nterpretation and use of testr esults are the responsibility of the client.T his report mustno tbe used by the client to claim productc ertification, approval or endorsement by NVLAP, NIST or any agency of the federal government.T he test results contained within this reportm eett he requirements of NELAC unless otherwise specified.S amples received in good condition unless otherwise noted.
Samples analyzed by EMSL Analytical,I nc.20 0 Route 130 North, Cinnaminson NJ NVLAP Lab Code 101048-0,A IHA-LAP,LL C-IHLAP Lab 100194, NYS ELAP 10872, NJ DEP 03036

EMSL Analytical, Inc.
200 Route 130 North, Cinnaminson, NJ 08077
Phone: (800) 220-3675 Fax: (856) 786-5974 Email: westmontasblab@EMSL.com

Attn: **Rich Annunziato**
Air Management Services
Dept. of Public Health
321 University Avenue - 3rd Floor
Philadelphia, PA 19104

Fax: (215) 685-9496 Phone: (215) 685-9458

Project: **PROJECT NAME/NUMBER: ARSENAL BUSINESS CENTER BLDG 301**

Customer ID: AIRM55
Customer PO:
Received: 01/04/11 9:00 PM
EMSL Order: 041100145

EMSL Proj:
Analysis Date: 1/4/2011

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos % Fibrous	Non-Asbestos % Non-Fibrous	Asbestos % Type
ES-01-04-11-F *041100145-0008*	BLDG 301 - BASEMENT MECHANICAL AREA	White Fibrous Homogeneous		73% Non-fibrous (other)	**3% Crocidolite** **20% Amosite** **4% Chrysotile**
ES-01-04-11-G *041100145-0009*	BLDG 301- OUTSIDE REAR OF BUILDING	Brown/Silver Fibrous Homogeneous	10% Cellulose	70% Non-fibrous (other)	**20% Chrysotile**

Initial reportf rom 01/05/2011 07:01:54

Analyst(s)

Anne Paul(9)

Stephen Siegel,C IH, Laboratory Manager
or other approved signatory

EMSL maintains liability limited to the costo fan alysis. This reportr elates only to the samples reported above and may notbe reproduced,e xcepti n full,w ithout written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations.I nterpretation and use of testr esults are the responsibility of the client.T his report mustno tbe used by the client to claim productc ertification, approval or endorsement by NVLAP, NIST or any agency of the federal government.T he test results contained within this reportm eett he requirements of NELAC unless otherwise specified.S amples received in good condition unless otherwise noted.
Samples analyzed by EMSL Analytical,I nc.20 0 Route 130 North, Cinnaminson NJ NVLAP Lab Code 101048-0,A IHA-LAP,LL C-IHLAP Lab 100194, NYS ELAP 10872, NJ DEP 03036

THIS IS THE LAST PAGE OF THE REPORT.