LEEDER Chemical Division

Reliance Universal Inc.

Reliance

Compounds for Cleaning and Processing

16220 ILLINOIS AVENUE • PARAMOUNT, CALIFORNIA 90723 • (213) 636-9277

LEEDER 518-T-66

POLYMER PEEL COAT

DESCRIPTION:

Leeder 518-T-66 is a peelable plastic coating used for protecting aluminum and steel alloys against weathering, oxidation, scratching, etc. during handling and storage, indoors or outdoors.

PROPERTIES:

Heavy bodied blue liquid.
Meets Rule 66.
Freely strippable.
Excellent chemical resistance.
Corrosion resistant.

GENERAL APPLICATION:

Remove all traces of dirt, oil or grease. Be sure surface to be coated is completely dry and clean before applying Leeder 518-T-66. Standard pressure spray equipment is ideal for applying this material. A wide fan, with the gun held 6 to 8 inches from the work, provides the most uniform coating in the least time. The fluid line pressure should be between 10-20 lbs. with an air pressure of 50-70 lbs. When applying Leeder 518-T-66 observe normal handling and ventilation precautions associated with pressure spraying operations.

DOCUMENTATION:

Leeder 518-T-66 meets Douglas Aircraft Co. Specification DPM 3558-1.

PRECAUTIONS:

Leeder 518-T-66 contains flammable solvents. Keep away from heat, sparks or open flames. Refer to product label for additional precautionary and handling information.

LC11278

OUR GUARANTEE: "Since methods and conditions of application and use are beyond our control, all merchandise is sold and received subject to the condition that our liability for any defect in quality, or for any lack of fitness for the use made thereof, is limited to the return of the purchase price if written claim is made within 90 days from the date of shipment."

TECHNICAL ADVICE: The technical advice contained herein is based on tests believed to be reliable and is offered as a helpful suggestion. It is expressly understood, however, that all such technical advice is given gratis and Reliance assumes no obligation or liability for the advice given or the results obtained, all such advice being given and accepted at buyer's risk. Further, where equipment or other companies' products are mentioned, we do not imply an unqualified recommendation as there are undoubtedly others of similar types on the market which may be equally or better suited for the purpose.

FORM NO. 147-500-7-70 E.P.