PRODUCT DESIGNATION

METLBOND 2030-85

MATERIAL SAFETY DATA SHEET

FEB 09 1982

DPM 2299

SECTION I SOURCE AND NOMENCLATURE

MANUFACTURER'S NAME NARMCO MATERIALS, INC.	EMERGENCY TELEPHONE NO. (714) 548-1144
ADDRESS (Number, Street, City, State, ZIP Code) A SUBSIDIARY OF [illegible]ELANESE CORPORATION 600 VICTORIA STREET • COSTA MESA, CALIFORNIA 92627	
TRADE NAME AND SYNONYMS METLBOND 2030-85	CHEMICAL FAMILY EPOXY/PHENOLIC
CHEMICAL NAME AND SYNONYMS	FORMULA

SECTION II INGREDIENTS

BASIC MATERIAL	APPROXIMATE OR MAXIMUM % WT. OR VOL.	ESTABLISHED OSHA STANDARD	LD 50 ORAL	LD 50 PERCUT.	LC 50 SPECIES	LC 50 CONC.
Epoxy Resin	11					
Phenolic Resin	30					
Amine Hardener	4					
Aluminum Powder	40					
Acetone	15					

SECTION III PHYSICAL DATA

BOILING POINT ACETONE 132°F °F.	VAPOR PRESSURE mm Hg.
MELTING POINT °F.	VAPOR DENSITY (Air=1)
SPECIFIC GRAVITY (H_2O=1)	EVAPORATION RATE (=1)
SOLUBILITY IN WATER Pts/100 pts H_2O	VOLATILE % Vol. % Wt.
APPEARANCE AND ODOR ACETONE ODOR	

SECTION IV FIRE AND EXPLOSION HAZARD DATA

FLASH POINT ACTONE 4°F METHOD USED	ASTM METHOD D1310	FLAMMABLE (EXPLOSIVE) LIMITS	UPPER / LOWER
EXTINGUISHING MEDIA	WATER, CO_2, OR DRY CHEMICALS		
SPECIAL FIRE FIGHTING PROCEDURES	USE OXYGEN RESPIRATOR WHEN FIRE FIGHTING.		
UNUSUAL FIRE AND EXPLOSION HAZARDS	KEEP AWAY FROM HEAT, FLAMES, SPARKS.		

IS FURNISHED WITHOUT WARRANTY, REPRESENTATION, INDUCEMENT OR LICENSE OF ANY KIND, EXCEPT THAT IT IS ACCURATE TO THE BE[illegible] INC.'S KNOWLEDGE, OR OBTAINED FROM SOURCES BELIEVED BY NARMCO MATERIALS, INC. TO BE ACCURATE, AND NARMCO [illegible] DOES NOT ASSUME ANY LEGAL RESPONSIBILITY FOR USE OR RELIANCE UPON SAME. CUSTOMERS ARE ENCOURAGED TO CONDUCT THEIR [illegible] ANY PRODUCT, READ ITS LABEL.