DESOTO, INC.
MATERIAL SAFETY DATA SHEET NPCA 1-72
FOR COATINGS, RESINS, AND RELATED MATERIALS
(APPROVED BY US DEPARTMENT OF LABOR "ESSENTIALLY SIMILAR" TO FORM OSHA-20)

SECTION I

DESOTO, INC.
ADMINISTRATIVE AND RESEARCH CENTER

1700 S. MT. PROSPECT ROAD
DES PLAINES, ILLINOIS 60018

EMERGENCY TELEPHONE (312) 391-9000

PRODUCT CLASS
MODIFIED POLYESTER

MANUFACTURERS CODE IDENTIFICATION
820X311

TRADE NAME SUPER DESOTHANE
SUPERSEDES 01/14/82 MSDS

DATE OF PREPARATION 09/15/82

********** SECTION II-HAZARDOUS INGREDIENTS **********

INGREDIENT	% BY WEIGHT	PPM	TLV MG/CU.M	LEL	VAPOR PRESSURE @ 20 DEG C
BUTYL ACETATE	15.0	150	710	1.7	8.0
2-ETHOXYETHYL ACETATE-SKIN **	25.0	50	270	1.8	2.0
METHYL ETHYL KETONE	10.0	200	590	1.8	70
METHYL ISOBUTYL KETONE-SKIN	15.0	50	205	1.4	15
ORGANO TIN COMPOUND-SKIN	< 0.1		0.1 AS SN	NA	NA

NE = NOT ESTABLISHED
NA = NOT APPLICABLE

********** SECTION III-PHYSICAL DATA **********

PROPERTY	MEASUREMENT
BOILING RANGE	176.0 TO 313.0 DEG F. @760 MM HG; 80.0 TO 156.0 DEG C.
VAPOR DENSITY	X HEAVIER; LIGHTER THAN AIR
WEIGHT PER GALLON	8.2 LBS.
PERCENT VOLATILE BY VOLUME	66.7
EVAPORATION RATE	FASTER; X SLOWER THAN ETHER

289