Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R89-31499.4 (COMPLETE)

REFERENCE INFO: BROHM

CLIENT: BROHM MINING CORPORATION
PROJECT: NONE GIVEN

SUBMITTED BY: DEADWOOD
DATE PRINTED: 27-SEP-89

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	60	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	2	0.002 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	60	2 -150	60	ASSAY PREP	60
				SAMPLE PICKUP/MILE	1

REMARKS: FINAL REPORT
1AT GOLD (29.17G)

REPORT COPIES TO: MR. JIM BARRON
MR. ROD MCCLEOD

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R89-31499.4

~~DATE PRINTED: 27-SEP-89~~
PROJECT: NONE GIVEN

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT
Z2 R89-572 0-5		0.003	
Z2 R89-572 5-10		0.004	
Z2 R89-572 10-15		0.005	
Z2 R89-572 15-20		0.007	
Z2 R89-572 20-25		0.011	
Z2 R89-572 25-30		0.004	
Z2 R89-572 30-35		0.006	
Z2 R89-572 35-40		0.009	
Z2 R89-572 40-45		0.004	
Z2 R89-572 45-50		0.006	
~~DUPLICATE~~		~~0.007~~	
Z2 R89-572 50-55		0.008	
Z2 R89-572 55-60		0.007	
Z2 R89-572 60-65		0.012	
Z2 R89-572 65-70		0.003	
Z2 R89-572 70-75		0.002	
Z2 R89-572 75-80		0.009	
Z2 R89-572 80-85		0.005	
Z2 R89-572 85-90		0.009	
Z2 R89-572 90-95		0.006	
Z2 R89-572 95-100		0.006	
~~DUPLICATE~~		~~0.007~~	
Z2 R89-572 100-105		0.004	
Z2 R89-572 105-110		0.003	
Z2 R89-572 110-115		0.005	
Z2 R89-572 115-120		0.011	
Z2 R89-572 120-125		0.013	
Z2 R89-572 125-130		0.009	
Z2 R89-572 130-135		0.015	
Z2 R89-572 135-140		0.006	
Z2 R89-572 140-145		0.004	
Z2 R89-572 145-150		0.005	
Z2 R89-572 150-155		0.002	
Z2 R89-572 155-160		<0.002	0.010 = .004
~~DUPLICATE~~		~~0.002~~	
Z2 R89-572 160-165		0.017	
Z2 R89-572 165-170		0.007	
Z2 R89-572 170-175		0.004	
Z2 R89-572 175-180		0.008	
Z2 R89-572 180-185		0.002	

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT
Z2 R89-572 185-190		<0.002	
Z2 R89-572 190-195		<0.002	
Z2 R89-572 195-200		<0.002	
Z2 R89-572 200-205		0.002	
Z2 R89-572 205-210		0.002	0.009 = .004
~~DUPLICATE~~		~~0.002~~	
Z2 R89-572 210-215		<0.002	
~~DUPLICATE~~		~~0.002~~	
Z2 R89-572 215-220		0.006	
Z2 R89-572 220-225		0.003	
Z2 R89-572 225-230		<0.002	
Z2 R89-572 230-235		0.004	
Z2 R89-572 235-240		<0.002	
Z2 R89-572 240-245		<0.002	
Z2 R89-572 245-250		<0.002	
Z2 R89-572 250-255		0.003	
Z2 R89-572 255-260		<0.002	
Z2 R89-572 260-265		<0.002	
Z2 R89-572 265-270		<0.002	
~~DUPLICATE~~		~~<0.002~~	
Z2 R89-572 270-275		<0.002	
Z2 R89-572 275-280		0.003	
Z2 R89-572 280-285		0.005	
Z2 R89-572 285-290		0.005	
Z2 R89-572 290-295		0.003	
Z2 R89-572 295-300		<0.002	

RECEIVED
OCT 2 1989
BROHM MINING CO.

RECEIVED
OCT 2 1989
BROHM MINING CO.

BONDAR-CLEGG

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

Invoice : R076490, Page 1

BROHM MINING CORPORATION
MR. JIM BARRON
PO BOX 485
DEADWOOD, SOUTH DAKOTA
57732

Date : 26-SEP-89

Report No: R89-31499.4
Project : NONE GIVEN
Reference: BROHM

60 Analyses of Gold	at $ 7.00	$ 420.00	
Subtotal		$ 420.00	$ 420.00
Sample Preparation			
60 Samples of ASSAY PREP	at $ 3.00	$ 180.00	
1 Sample of SAMPLE PICKUP/MILE	at $12.00	$ 12.00	
Subtotal		$ 192.00	$ 192.00
Miscellaneous Charges			
4% S.D. State Sales Tax		$ 7.68	
2% Deadwood City Sales Tax		$ 3.84	
Subtotal		$ 11.52	$ 11.52
Invoice Total:			$ 623.52 U.S.

THIS IS A PROFESSIONAL SERVICE
ACCOUNTS DUE WHEN RENDERED

RECEIVED
[illegible] 19[illegible]
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BC
BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R89-31900.4 (COMPLETE)

REFERENCE INFO: NONE GIVEN

CLIENT: BROHM MINING CORPORATION
PROJECT: NONE GIVEN

SUBMITTED BY: BARRON
DATE PRINTED: 29-SEP-89

ORDER	ELEMENT		NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au	Gold	57	0.002 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	57	2 -150	57	ASSAY PREP	57
				SAMPLE PICKUP/MILE	1

REMARKS: = DUPLICATE NOT AVAILABLE
1AT GOLD (29.17G)

REPORT COPIES TO: MR. JIM BARRON
MR. ROD MCCLEOD

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 29-SEP-89

REPORT: R89-31900.4

PROJECT: NONE GIVEN

SAMPLE NUMBER	ELEMENT UNITS	Au OPT
Z2 R89-572 300-305		0.006
~~DUPLICATE~~		~~-~~
Z2 R89-572 305-310		<0.002
Z2 R89-572 310-315		0.010
Z2 R89-572 315-320		0.019
Z2 R89-572 320-325		0.003
Z2 R89-572 325-330		0.003
Z2 R89-572 330-335		0.053
Z2 R89-572 335-340		0.103
Z2 R89-572 340-345		0.032
Z2 R89-572 345-350		0.014
Z2 R89-572 350-355		0.006
~~DUPLICATE~~		~~-~~
Z2 R89-572 355-360		0.005
Z2 R89-572 360-365		0.013
Z2 R89-572 365-370		0.032
Z2 R89-572 370-375		0.004
Z2 R89-572 375-380		<0.002
Z2 R89-572 380-385		0.005
Z2 R89-572 385-390		0.023
Z2 R89-572 390-395		0.039
Z2 R89-572 395-400		0.025
Z2 R89-572 400-405		0.037
Z2 R89-572 405-410		0.029
Z2 R89-572 410-415		0.029
~~DUPLICATE~~		~~0.028~~
Z2 R89-572 415-420		0.020
Z2 R89-572 420-425		0.006
Z2 R89-572 425-430		0.003
Z2 R89-572 430-435		0.002
Z2 R89-572 435-440		<0.002
Z2 R89-572 440-445		0.012
Z2 R89-572 445-450		0.009
Z2 R89-572 450-455		0.012
Z2 R89-572 455-460		0.004
Z2 R89-572 460-465		0.016 .014
~~DUPLICATE~~		~~0.013~~
Z2 R89-572 465-470		0.060
Z2 R89-572 470-475		0.017
Z2 R89-572 475-480		0.009
Z2 R89-572 480-485		0.019
Z2 R89-572 485-490		0.006
Z2 R89-572 490-495		0.004
Z2 R89-592 495-500		0.006
Z2 R89-572 500-505		0.022
Z2 R89-572 505-510		0.012
Z2 R89-572 510-515		0.003
Z2 R89-572 515-520		0.003
Z2 R89-572 520-525		0.002
~~DUPLICATE~~		~~0.003~~
Z2 R89-572 525-530		0.002
Z2 R89-572 530-535		0.002
Z2 R89-572 535-540		<0.002
Z2 R89-572 540-545		0.003
Z2 R89-572 545-550		0.003
Z2 R89-572 550-555		0.018
Z2 R89-572 555-560		0.004
Z2 R89-572 560-565		<0.002
Z2 R89-572 565-570		<0.002
Z2 R89-572 570-575		0.005
~~DUPLICATE~~		~~0.005~~
Z2 R89-572 575-580		0.068
Z2 R89-572 580-585		0.004

RECEIVED
OCT 5 1989
BROHM MINING CO.

RECEIVED
OCT 5 1989
BROHM MINING CO.

BONDAR-CLEGG

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

Invoice : R076604, Page 1

BROHM MINING CORPORATION
MR. JIM BARRON
PO BOX 485
DEADWOOD, SOUTH DAKOTA
57732

Date : 29-SEP-89

Report No: R89-31900.4
Project : NONE GIVEN
Reference: NONE GIVEN

BARRON

57 Analyses of Gold	at $ 7.00	$ 399.00	
Subtotal		$ 399.00	$ 399.00
Sample Preparation			
57 Samples of ASSAY PREP	at $ 3.00	$ 171.00	
1 Sample of SAMPLE PICKUP/MILE	at $12.00	$ 12.00	
Subtotal		$ 183.00	$ 183.00
Miscellaneous Charges			
4% S.D. SALES TAX		$ 7.32	
2% DEADWOOD CITY SALES TAX		$ 3.66	
Subtotal		$ 10.98	$ 10.98
Invoice Total:			$ 592.98 U.S.

THIS IS A PROFESSIONAL SERVICE
ACCOUNTS DUE WHEN RENDERED