Contractor: Douglas Exploration | Coordinates: N47324.91 E25240.55 | Project: Anchor Hill Oxide Expl. | Hole No.: R91-828 (A-8)

Drill Type: I.V.I Buggy | Casing Depth: | State: SD | Sheet 1 of 3

Hole Size: 4½" | Bearing: S45E | Inclination: -50° | Date Started: 11-19-91 1:00pm | Property: Gilt Edge

Collar Elev.: 5668.82 | Final Depth: 400' | Date Completed: 11-22-91 5:00pm | Hole Surveyed: NO

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION (1 Weak, 2 Moderate, 3 Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	% Sulfides	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE)	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement)	TYPE	ASSAY Au	ASSAY Ag
			85	3	0-5	Oxide	Tqtp	0-400 Quartz Trachyte Porphyry, m.g., orange-brown tan, & maroon FeOx stained as noted.	0-400 Oxide (No visible sulfides)			
					20-25							
					45-50							
					70-75			(70-125) mod. orange-brown & maroon FeOx.				
					95-100							
					120-125			(115-125) mod. maroon FeOx				
								(125-185) mod. maroon & orange-brown FeOx.				
					145-150							
					170-175							

DRILL CUTTING LOG

Logged by: S. Bingheffer

Contractor _____ Coordinates _____ Project _____ Hole No. R91-828

Drill Type _____ Casing Depth _____ State _____ Sheet 2 of 3

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

GRAPHIC LOGS															GEOLOGIC NOTES				
DISTANCE (feet)	ALTERATION								TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	% Sulphides	ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION Massive, Disseminated, Veinlets, Replacement	TYPE	ASSAY Au	ASSAY Ag
										25	3	175-180	Oxide	Tqtp	(Qtz. Trachyte porph. con't)	Oxide con't			
															(190-270) Alternating weak-mod. maroon FeOx				
												195-200							
												220-225							
												245-250							
												270-275			(270-340) strong maroon FeOx ⇒ Fract/ Breccia zone				
												295-300							
												320-325			(310-330) 2-5% AE Qtz mica schist frags. tr. Quartzite frags. Probably xenoliths in Qtz. Trachyte porph.				
												345-350			(345-350) 5-10% H.blnd. Trachyte? frags.				

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. R91-828

Drill Type _____ Casing Depth _____ State _____ Sheet 3 of 3

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION (1 Weak, 2 Moderate, 3 Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE)	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement)	TYPE	ASSAY: Au	Ag
			85	3	350-355	Oxide	Tgtp					
					370-375			(370-380) mod-st. MAROON FeOx				
								(380-400) weak MAROON FeOx & orange-brown. FeOx				
								(395-400) tr. H2O				
					395-400			Hole TD @ 400'				

DRILL CUTTING LOG

Logged by:

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

BROHM MINING CORPORATION
MR. ROD MACLEOD
PO BOX 485
DEADWOOD, SOUTH DAKOTA
57732

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R91-12487.4 (COMPLETE)

REFERENCE INFO: NONE GIVEN

CLIENT: BROHM MINING CORPORATION
PROJECT: NONE GIVEN

SUBMITTED BY: SYMONDS
DATE PRINTED: 13-DEC-91

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	118	0.002 OPT		Fire Assay
2	Au DUP Gold Duplicate	12	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	5	0.002 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
P PREPARED PULP	118	4 AS REC'D	118	AS RECEIVED, NO SP	118

REMARKS: PRELIM RESULTS ONLY. CHECKS TO FOLLOW
PAUL BAKER

REPORT COPIES TO: MR. ROD MACLEOD

INVOICE TO: MR. ROD MACLEOD

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R91-12487.4 (COMPLETE)

DATE PRINTED: 13-DEC-91
PROJECT: NONE GIVEN

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	Au DUP OPT	AU Dup OPT
P4 R91-828 0-5		<0.002		
P4 R91-828 5-10		<0.002		
P4 R91-828 10-15		<0.002		
P4 R91-828 15-20		0.007		
P4 R91-828 20-25		0.012		
P4 R91-828 25-30		<0.002		
P4 R91-828 30-35		<0.002		
P4 R91-828 35-40		0.003	0.010	
P4 R91-828 40-45		0.005		
P4 R91-828 45-50		0.004		
P4 R91-828 50-55		<0.002		
P4 R91-828 55-60		<0.002		
P4 R91-828 60-65		<0.002		
P4 R91-828 65-70		0.009		
P4 R91-828 70-75		<0.002		
P4 R91-828 75-80		0.010		
P4 R91-828 80-85		0.004		
P4 R91-828 85-90		0.006	0.006	
P4 R91-828 90-95		0.004		
P4 R91-828 95-100		0.004		
P4 R91-828 100-105		<0.002		
P4 R91-828 105-110		0.005		
P4 R91-828 110-115		<0.002		
P4 R91-828 115-120		0.002		
P4 R91-828 120-125		0.006		
P4 R91-828 125-130		<0.002		
P4 R91-828 130-135		<0.002		
P4 R91-828 135-140		<0.002		
P4 R91-828 140-145		<0.002		
P4 R91-828 145-150		0.014	0.009	
P4 R91-828 150-155		0.012		
P4 R91-828 155-160		0.006		
P4 R91-828 160-165		<0.002		
P4 R91-828 165-170		0.003		
P4 R91-828 170-175		<0.002		
P4 R91-828 175-180		0.027		
P4 R91-828 180-185		0.045		
P4 R91-828 185-190		0.030		0.025
P4 R91-828 190-195		0.425		0.390
P4 R91-828 195-200		0.030	0.038	
P4 R91-828 200-205		0.064		
P4 R91-828 205-210		0.133		0.112
P4 R91-828 210-215		0.010		
P4 R91-828 215-220		0.015		
P4 R91-828 220-225		<0.002		
P4 R91-828 225-230		0.015		
P4 R91-828 230-235		<0.002		
P4 R91-828 235-240		0.114		
P4 R91-828 240-245		0.053		
P4 R91-828 245-250		<0.002		
P4 R91-828 250-255		<0.002		
P4 R91-828 255-260		<0.002	<0.002	
P4 R91-828 260-265		0.006		
P4 R91-828 265-270		<0.002		
P4 R91-828 270-275		<0.002		
P4 R91-828 275-280		0.006		
P4 R91-828 280-285		0.010		
P4 R91-828 285-290		0.005		
P4 R91-828 290-295		0.017		
P4 R91-828 295-300		0.032		0.028
P4 R91-828 300-305		0.045		0.038
P4 R91-828 305-310		0.222	0.234	
P4 R91-828 310-315		0.052		
P4 R91-828 315-320		0.037		
P4 R91-828 320-325		0.018		
P4 R91-828 325-330		0.031		
P4 R91-828 330-335		0.012		
P4 R91-828 335-340		0.015		
P4 R91-828 340-345		0.035		
P4 R91-828 345-350		0.005		
P4 R91-828 350-355		<0.002		
P4 R91-828 355-360		0.017		
P4 R91-828 360-365		0.008		
P4 R91-828 365-370		0.016	0.015	
P4 R91-828 370-375		0.032		
P4 R91-828 375-380		0.017		
P4 R91-828 380-385		0.012		
P4 R91-828 385-390		0.018		
P4 R91-828 390-395		0.018		
P4 R91-828 395-400		0.008		

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

Geochemical Lab Report

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

REPORT: R91-12487.4 (COMPLETE)

DATE PRINTED: 13 DEC 91
PROJECT: NONE GIVEN

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	Au DUP OPT	AU Dup OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT	Au DUP OPT	AU Dup OPT
P4 R91-829 0-5		<0.002							
P4 R91-829 5-10		0.012							
P4 R91-829 10-15		<0.002							
P4 R91-829 15-20		<0.002	<0.002						
P4 R91-829 20-25		<0.002	<0.002						
P4 R91-829 25-30		<0.002							
P4 R91-829 30-35		<0.002							
P4 R91-829 35-40		<0.002							
P4 R91-829 40-45		<0.002							
P4 R91-829 45-50		<0.002							
P4 R91-829 50-55		<0.002							
P4 R91-829 55-60		<0.002							
P4 R91-829 60-65		<0.002							
P4 R91-829 65-70		<0.002							
P4 R91-829 70-75		<0.002							
P4 R91-829 75-80		<0.002	<0.002						
P4 R91-829 80-85		<0.002							
P4 R91-829 85-90		<0.002							
P4 R91-829 90-95		<0.002							
P4 R91-829 95-100		<0.002							
P4 R91-829 100-105		<0.002							
P4 R91-829 105-110		<0.002							
P4 R91-829 110-115		<0.002							
P4 R91-829 115-120		<0.002							
P4 R91-829 120-125		<0.002							
P4 R91-829 125-130		<0.002							
P4 R91-829 130-135		<0.002	<0.002						
P4 R91-829 135-140		<0.002							
P4 R91-829 140-145		<0.002							
P4 R91-829 145-150		<0.002							
P4 R91-829 150-155		<0.002							
P4 R91-829 155-160		<0.002							
P4 R91-829 160-165		<0.002							
P4 R91-829 165-170		<0.002							
P4 R91-829 170-175		<0.002							
P4 R91-829 175-180		<0.002							
P4 R91-829 180-185		<0.002							
P4 R91-829 185-190		<0.002	<0.002						

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R91-12487.4 (COMPLETE)

DATE PRINTED: 13-DEC-91
PROJECT: NONE GIVEN

STANDARD NAME	ELEMENT UNITS	Au OPT	Au DUP OPT	AU Dup OPT	STANDARD NAME	ELEMENT UNITS	Au OPT	Au DUP OPT	AU Dup OPT
ANALYTICAL BLANK		<0.002	-	-					
ANALYTICAL BLANK		<0.002	-	-					
ANALYTICAL BLANK		<0.002	-	-					
Number of Analyses		3	-	-					
Mean Value		0.00100	-	-					
Standard Deviation		0.000000	-	-					
Accepted Value		0.002	-	-					
AU ASSAY STD		0.145	-	-					
Number of Analyses		1	-	-					
Mean Value		0.1450	-	-					
Standard Deviation		-	-	-					
Accepted Value		0.150	-	-					
AU ASSAY STD		0.014	-	-					
Number of Analyses		1	-	-					
Mean Value		0.0140	-	-					
Standard Deviation		-	-	-					
Accepted Value		0.015	-	-					
AU PULP STD		0.172	-	-					
Number of Analyses		1	-	-					
Mean Value		0.1720	-	-					
Standard Deviation		-	-	-					
Accepted Value		0.184	-	-					

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R91-12487.4 (COMPLETE)

DATE PRINTED: 13-DEC-91
PROJECT: NONE GIVEN

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	Au DUP OPT	AU Dup OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT	Au DUP OPT	AU Dup OPT
R91-828 35-40		0.003	0.010						
Duplicate		0.010							
R91-828 85-90		0.006	0.006						
Duplicate		0.006							
R91-828 145-150		0.014	0.009						
Duplicate		0.009							
R91-828 195-200		0.030	0.038						
Duplicate		0.038							
R91-828 255-260		<0.002	<0.002						
Duplicate		<0.002							
R91-828 305-310		0.222	0.234						
Duplicate		0.234							
R91-828 365-370		0.016	0.015						
Duplicate		0.015							
R91-829 15-20		<0.002	<0.002						
Duplicate		<0.002							
R91-829 20-25		<0.002	<0.002						
Duplicate		<0.002							
R91-829 75-80		<0.002	<0.002						
Duplicate		<0.002							
R91-829 130-135		<0.002	<0.002						
Duplicate		<0.002							
R91-829 185-190		<0.002	<0.002						
Duplicate		<0.002							

```
"TITLE 11-12-91 16:23:30 R91-12487.4   SYMONDS                05/12/91"
"CLIENT BROHM MINING CORPORATION                                       "
"PROJECT NONE GIVEN      #SAMPLES:  118 REFERENCE: NONE GIVEN                    "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT  118 0.002 999999 Results Reported     "
"  02 Au DUP FA        OPT   12 0.002 999999 Results Reported     "
"  03 AU Dup FA        OPT  118 0.002 9999.0 Test not yet complete"
"SAMPLE PREPS"
"  40 SAMPLE TYPE=P      PREPARED PULP       "
"  41 P68= 118           AS RECEIVED, NO SP  "
"REMARKS"
"  50 PRELIM RESULTS ONLY, CHECKS TO FOLLOW          "
"  51                            PAUL BAKER          "
"****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au" "Au DUP" "AU Dup"
"24870001" "P" "4" "R91-828 0-5          "   -0.002       -9       -9
"24870002" "P" "4" "R91-828 5-10         "   -0.002       -9       -9
"24870003" "P" "4" "R91-828 10-15        "   -0.002       -9       -9
"24870004" "P" "4" "R91-828 15-20        "    0.007       -9       -9
"24870005" "P" "4" "R91-828 20-25        "    0.012       -9       -9
"24870006" "P" "4" "R91-828 25-30        "   -0.002       -9       -9
"24870007" "P" "4" "R91-828 30-35        "   -0.002       -9       -9
"24870008" "P" "4" "R91-828 35-40        "    0.003    0.010       -9
"24870010" "P" "4" "R91-828 40-45        "    0.005       -9       -9
"24870011" "P" "4" "R91-828 45-50        "    0.004       -9       -9
"24870012" "P" "4" "R91-828 50-55        "   -0.002       -9       -9
"24870013" "P" "4" "R91-828 55-60        "   -0.002       -9       -9
"24870014" "P" "4" "R91-828 60-65        "   -0.002       -9       -9
"24870015" "P" "4" "R91-828 65-70        "    0.009       -9       -9
"24870016" "P" "4" "R91-828 70-75        "   -0.002       -9       -9
"24870017" "P" "4" "R91-828 75-80        "    0.010       -9       -9
"24870018" "P" "4" "R91-828 80-85        "    0.004       -9       -9
"24870019" "P" "4" "R91-828 85-90        "    0.006    0.006       -9
"24870020" "P" "4" "R91-828 90-95        "    0.004       -9       -9
"24870021" "P" "4" "R91-828 95-100       "    0.004       -9       -9
"24870022" "P" "4" "R91-828 100-105      "   -0.002       -9       -9
"24870025" "P" "4" "R91-828 105-110      "    0.005       -9       -9
"24870026" "P" "4" "R91-828 110-115      "   -0.002       -9       -9
"24870027" "P" "4" "R91-828 115-120      "    0.002       -9       -9
"24870028" "P" "4" "R91-828 120-125      "    0.006       -9       -9
"24870029" "P" "4" "R91-828 125-130      "   -0.002       -9       -9
"24870030" "P" "4" "R91-828 130-135      "   -0.002       -9       -9
"24870031" "P" "4" "R91-828 135-140      "   -0.002       -9       -9
"24870032" "P" "4" "R91-828 140-145      "   -0.002       -9       -9
"24870033" "P" "4" "R91-828 145-150      "    0.014    0.009       -9
"24870035" "P" "4" "R91-828 150-155      "    0.012       -9       -9
"24870036" "P" "4" "R91-828 155-160      "    0.006       -9       -9
"24870037" "P" "4" "R91-828 160-165      "   -0.002       -9       -9
"24870038" "P" "4" "R91-828 165-170      "    0.003       -9       -9
"24870039" "P" "4" "R91-828 170-175      "   -0.002       -9       -9
"24870040" "P" "4" "R91-828 175-180      "    0.027       -9       -9
"24870041" "P" "4" "R91-828 180-185      "    0.045       -9       -9
"24870042" "P" "4" "R91-828 185-190      "    0.030       -9       -9
"24870043" "P" "4" "R91-828 190-195      "    0.425       -9       -9
"24870044" "P" "4" "R91-828 195-200      "    0.030    0.038       -9
"24870045" "P" "4" "R91-828 200-205      "    0.064       -9       -9
"24870046" "P" "4" "R91-828 205-210      "    0.133       -9       -9
```

170-210 @ .095

$\bar{x} = .034$

"24870049"	"P"	"4"	"R91-828 210-215 "	0.010	-9	-9	
"24870050"	"P"	"4"	"R91-828 215-220 "	0.015	-9	-9	
"24870051"	"P"	"4"	"R91-828 220-225 "	-0.002	-9	-9	
"24870052"	"P"	"4"	"R91-828 225-230 "	0.015	-9	-9	
"24870053"	"P"	"4"	"R91-828 230-235 "	-0.002	235-245 -9	-9	
"24870054"	"P"	"4"	"R91-828 235-240 "	0.114	-9	-9	
"24870055"	"P"	"4"	"R91-828 240-245 "	0.053	10' @ .084 -9	-9	
"24870056"	"P"	"4"	"R91-828 245-250 "	-0.002	-9	-9	
"24870057"	"P"	"4"	"R91-828 250-255 "	-0.002	-9	-9	
"24870058"	"P"	"4"	"R91-828 255-260 "	-0.002	-0.002	-9	
"24870060"	"P"	"4"	"R91-828 260-265 "	0.006	-9	-9	
"24870061"	"P"	"4"	"R91-828 265-270 "	-0.002	-9	-9	
"24870062"	"P"	"4"	"R91-828 270-275 "	-0.002	-9	-9	
"24870063"	"P"	"4"	"R91-828 275-280 "	0.006	-9	-9	
"24870064"	"P"	"4"	"R91-828 280-285 "	0.010	-9	-9	
"24870065"	"P"	"4"	"R91-828 285-290 "	0.005	-9	-9	
"24870066"	"P"	"4"	"R91-828 290-295 "	0.017	295-345 -9	-9	
"24870067"	"P"	"4"	"R91-828 295-300 "	0.032	-9	-9	
"24870068"	"P"	"4"	"R91-828 300-305 "	0.045	-9	-9	
"24870069"	"P"	"4"	"R91-828 305-310 "	0.222	0.234 $\bar{x}$ = .238	-9	
"24870070"	"P"	"4"	"R91-828 310-315 "	0.052	-9	-9	
"24870073"	"P"	"4"	"R91-828 315-320 "	0.037	-9 50' @ .050	-9	
"24870074"	"P"	"4"	"R91-828 320-325 "	0.018	-9	-9	
"24870075"	"P"	"4"	"R91-828 325-330 "	0.031	-9	-9	
"24870076"	"P"	"4"	"R91-828 330-335 "	0.012	-9	-9	
"24870077"	"P"	"4"	"R91-828 335-340 "	0.015	-9	-9	
"24870078"	"P"	"4"	"R91-828 340-345 "	0.035	-9	-9	
"24870079"	"P"	"4"	"R91-828 345-350 "	0.005	-9	-9	
"24870080"	"P"	"4"	"R91-828 350-355 "	-0.002	-9	-9	
"24870081"	"P"	"4"	"R91-828 355-360 "	0.017	-9	-9	
"24870082"	"P"	"4"	"R91-828 360-365 "	0.008	-9	-9	
"24870083"	"P"	"4"	"R91-828 365-370 "	0.016	0.015	-9	
"24870085"	"P"	"4"	"R91-828 370-375 "	0.032	-9 370-375	-9	
"24870086"	"P"	"4"	"R91-828 375-380 "	0.017	-9	-9	
"24870087"	"P"	"4"	"R91-828 380-385 "	0.012	-9	-9	
"24870088"	"P"	"4"	"R91-828 385-390 "	0.018	-9	-9	
"24870089"	"P"	"4"	"R91-828 390-395 "	0.018	-9	-9	
"24870090"	"P"	"4"	"R91-828 395-400 "	0.008	-9	-9	
"24870091"	"P"	"4"	"R91-829 0-5 "	-0.002	-9	-9	
"24870092"	"P"	"4"	"R91-829 5-10 "	0.012	-9	-9	
"24870093"	"P"	"4"	"R91-829 10-15 "	-0.002	-9	-9	
"24870094"	"P"	"4"	"R91-829 15-20 "	-0.002	-0.002	-9	
"24870097"	"P"	"4"	"R91-829 20-25 "	-0.002	-0.002	-9	
"24870098"	"P"	"4"	"R91-829 25-30 "	-0.002	-9	-9	N.S.A.
"24870099"	"P"	"4"	"R91-829 30-35 "	-0.002	-9	-9	
"24870100"	"P"	"4"	"R91-829 35-40 "	-0.002	-9	-9	
"24870101"	"P"	"4"	"R91-829 40-45 "	-0.002	-9	-9	
"24870102"	"P"	"4"	"R91-829 45-50 "	-0.002	-9	-9	
"24870103"	"P"	"4"	"R91-829 50-55 "	-0.002	-9	-9	
"24870104"	"P"	"4"	"R91-829 55-60 "	-0.002	-9	-9	
"24870105"	"P"	"4"	"R91-829 60-65 "	-0.002	-9	-9	
"24870106"	"P"	"4"	"R91-829 65-70 "	-0.002	-9	-9	
"24870107"	"P"	"4"	"R91-829 70-75 "	-0.002	-9	-9	
"24870108"	"P"	"4"	"R91-829 75-80 "	-0.002	-0.002	-9	
"24870110"	"P"	"4"	"R91-829 80-85 "	-0.002	-9	-9	
"24870111"	"P"	"4"	"R91-829 85-90 "	-0.002	-9	-9	
"24870112"	"P"	"4"	"R91-829 90-95 "	-0.002	-9	-9	
"24870113"	"P"	"4"	"R91-829 95-100 "	-0.002	-9	-9	
"24870114"	"P"	"4"	"R91-829 100-105 "	-0.002	-9	-9	
"24870115"	"P"	"4"	"R91-829 105-110 "	-0.002	-9	-9	
"24870116"	"P"	"4"	"R91-829 110-115 "	-0.002	-9	-9	
"24870117"	"P"	"4"	"R91-829 115-120 "	-0.002	-9	-9	
"24870118"	"P"	"4"	"R91-829 120-125 "	-0.002	-9	-9	
"24870121"	"P"	"4"	"R91-829 125-130 "	-0.002	-9	-9	
"24870122"	"P"	"4"	"R91-829 130-135 "	-0.002	-0.002	-9	
"24870123"	"P"	"4"	"R91-829 135-140 "	-0.002	-9	-9	

"24870124"	"P"	"4"	"R91-829	140-145	"	-0.002	-9	-9
"24870125"	"P"	"4"	"R91-829	145-150	"	-0.002	-9	-9
"24870126"	"P"	"4"	"R91-829	150-155	"	-0.002	-9	-9
"24870127"	"P"	"4"	"R91-829	155-160	"	-0.002	-9	-9
"24870128"	"P"	"4"	"R91-829	160-165	"	-0.002	-9	-9
"24870129"	"P"	"4"	"R91-829	165-170	"	-0.002	-9	-9
"24870130"	"P"	"4"	"R91-829	170-175	"	-0.002	-9	-9
"24870131"	"P"	"4"	"R91-829	175-180	"	-0.002	-9	-9
"24870132"	"P"	"4"	"R91-829	180-185	"	-0.002	-9	-9
"24870133"	"P"	"4"	"R91-829	185-190	"	-0.002	-0.002	-9

"END"

BC
BONDAR-CLEGG

SUBMITTAL FORM

Please Print

Report No. R91-12487

130 Pemberton Ave.
N. Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, Washington
98230

Tel (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071

5420 Canotek Rd.
Ottawa, Ontario
K1J 9G2
Tel (613) 749-2220
Fax (613) 749-7170

Westend Industrial Pk.
Pasedena, Nfld.
A0L 1K0
Tel (709) 686-5393
Fax (709) 686-2393

700 Neree Tremblay
Ste-Foy, Quebec
G1N 4H7
Tel (418) 683-1777
Fax (418) 683-7791

1320 Rue Harricana
Val d'Or, Quebec
G9X 3X6
Tel (819) 825-0178
Fax (819) 825-0256

625 Spice Island Dr.
Sparks, Nevada
89431
Tel (702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado
80228
Tel (303) 989-1404
Fax (303) 986-9441

6631 Wes Way
Anchorage, Alaska
99518
Tel (907) 561-0909

2440 McDonald St.
Missoula, Montana
59801
Tel (406) 721-4452
Fax (406) 721-4294

457 Steelhead Way
Boise, Idaho
83704
Tel (208) 375-3206

P.O. Box 8
Hibbing, Mn 55746
Tel (218) 262-5003

Hermosillo, Sonora
Mexico

Oruro, Bolivia
Fono 591 52 54156

La Paz, Bolivia
Fono 591 23 70849

Santa Cruz, Bolivia
Fono 591 33 22613

Quito, Equador
Fono 593 24 47025

Please analyze by: **Assay (% ore grade)** [X] **Geochemical (ppm, trace level)** [ ]

Comments 1-A.T. Fire Gravimetric Finish

Sample Type	# of Samples	Sample Numbers (Series)	Au	Ag	Cu	Pb	Zn	Mo	Bi	As	Sb	Hg	Gen Ex	Au +8	Au +16	Au +29	Au +33	Pt +6	ICP 28	ICP 34	Whole Rock	Other
Pulp		R91-828 0-5 thru 395-400	X																			
Pulp		R91-829 0-5 thru 185-190	X																			

Total No. of Samples 118 Date Shipped 11-27-91 Waybill No. _____ Prepaid X

No. Parcels Shipped 3 Date Rec'd at B-C _____ Shipment No. _____ Collect _____

Sample Submitter Robin Symonds Project No. _____ Purchase Order No. _____

Sample Disposition

Reject Pulp

- [ ] [ ] Discard after completed analysis
- [ ] [✓] Return collect after completed analysis
- [ ] Return collect after 60 days
- [ ] Return collect after 1 year
- [ ] Storage after 60 days @ $1.50 / box / mo.
- [ ] Storage after 1 year @ $1.50 / box / mo.

Note: Rejects are stored for sixty days and pulps for one year free of charge then discarded unless otherwise indicated above.

[ ] [ ] Name _____
Address _____
City / St / Prov _____
Tel _____ Fax _____

Report Distribution

Results Invoice

[✓] [✓] Name Red McLeod c/o Bridwin Mining
Address P.O. Box 485
City / St / Prov Deadwood, S.D. 57732
Tel (605) 578-2107 Fax (605) 578-1109

[ ] [ ] Name _____
Address _____
City / St / Prov _____
Tel _____ Fax _____

[ ] [ ] Name _____
Address _____
City / St / Prov _____
Tel _____ Fax _____

White - send with samples Yellow - Client copy

Printed in Canada 03 04 91

BONDAR-CLEGG

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

Invoice : R088766, Page 1

BROHM MINING CORPORATION
MR. ROD MACLEOD
PO BOX 485
DEADWOOD, SOUTH DAKOTA
57732

Date : 16-DEC-91

Report No: R91-12487.4
Project : NONE GIVEN
Reference: NONE GIVEN

SYMONDS

118 Analyses of Gold	at $ 6.95	$ 820.10	
12 Analyses of Gold Duplicate	at $ 0.00	$ 0.00	
5 Analyses of Gold Duplicate	at $ 0.00	$ 0.00	
Subtotal		$ 820.10	$ 820.10

Invoice Total: $ 820.10 U.S.

R.J. MacLeod
7006 027
1/2/92

THIS IS A PROFESSIONAL SERVICE
ACCOUNTS DUE WHEN RENDERED

BROHM MINING CORPORATION
Gilt Edge Project

Pit-Bench-Pattern #
R91-820/821/828

Submittal Date
3-10-92

(2)

BLAST HOLE

Hot NaCN Shake
and
FIRE DETERMINATIONS

DATE: 3-10-92

NAME: RS.

		FIRE	NaCN			FIRE	NaCN
	SAMPLE	Au.	Au.		SAMPLE	Au.	Au.
1.	250/255		.036	25.	Standard ✓		.014
2.	315/320		.025	26.	215/220		.006
3.	325/330		.044	27.	225/230		.013
4.	375/380		.016	28.	235/240		.025
5.	380/385		.024	29.	240/245		.031
6.	385/390		.023	30.	290/295		.018
7.	390/395		.027	31.	295/300		.025
8.	Standard ✓		.015	32.	300/305		.036
9.	395/400		.020	33.	[redacted]		
10.	✓ 7		.027	34.	[redacted]		
11.	405/410-1		.017	35.	305/310		.136
12.	405/410-2		.017	36.	310/315		.041
13.	410/415		.019	37.	315/320		.035
R91-821 14.	0/5		.014	38.	320/325		.018
15.	5/10		.011	39.	325/330		.030
16.	[redacted]			40.	335/340		.019
17.	[redacted]			41.	340/345		.015
R91-828 18.	175/180		.011	42.	Standard ✓		.014
19.	180/185		.018	43.	355/360		.010
20.	185/190		.016	44.	365/370		.019
21.	190/195		.195	45.	370/375		.038
22.	195/200		.022	46.	375/380		.017
23.	200/205		.026	47.	[illegible]/390		.016
24.	205/210		.005	48.			

BROHM MINING CORPORATION
Gilt Edge Project

Pit-Bench-Pattern #
R91-820/821/828

Submittal Date
3-10-92

(2)

BLAST HOLE

Hot NaCN Shake
and
FIRE DETERMINATIONS

DATE: 3-10-92

NAME: RS.

		SAMPLE	FIRE Au.	NaCN Au.		SAMPLE	FIRE Au.	NaCN Au.
	1.	250/255		.036	25.	Standard ✓		.014
	2.	315/320		.025	26.	215/220		.006
	3.	325/330		.044	27.	225/230		.013
	4.	375/380		.016	28.	235/240		.025
	5.	380/385		.024	29.	240/245		.031
	6.	385/390		.023	30.	290/295		.018
	7.	390/395		.027	31.	295/300		.025
	8.	Standard ✓		.015	32.	300/305		.036
	9.	395/400		.020	33.	[redacted]		
	10.	✓-1		.021	34.			
	11.	405/410-1		.017	35.	305/310		.136
	12.	405/410-2		.017	36.	310/315		.041
	13.	410/415		.019	37.	315/320		.035
R91-821	14.	0/5		.014	38.	320/325		.018
	15.	5/10		.011	39.	325/330		.030
	16.	[redacted]			40.	335/340		.019
	17.				41.	340/345		.015
R91-828	18.	175/180		.011	42.	Standard ✓		.014
	19.	180/185		.018	43.	355/360		.010
	20.	185/190		.016	44.	365/370		.019
	21.	190/195		.195	45.	370/375		.038
	22.	195/200		.022	46.	375/380		.017
	23.	200/205		.026	47.	[illegible]/340		.016
	24.	205/210		.005	48.			

BROHM MINING CORPORATION
Gilt Edge Project

Pit-Bench-Pattern #
R91-828/833/836

Submittal Date
3-10-92

(3)

BLAST HOLE

Hot NaCN Shake
and
FIRE DETERMINATIONS

DATE: 3-16-92

NAME:

		SAMPLE	AG ~~FIRE~~ ~~Au.~~	NaCN Au.		SAMPLE	AG ~~FIRE~~ ~~Au.~~	NaCN Au.
R91-828	1.	390/395	.056	.022	25.	Standard ✓	.059	.015
R91-833	2.	85/90	.255	.022	26.	35/40	.109	.163
	3.	105/110	.084	.081	27.	40/45	.070	.075
	4.	110/115	.094	.085	28.	50/55	.123	.029
	5.	115/120	.090	.036	29.	55/60	.078	.067
	6.	120/125	.155	.027	30.	80/85	.040	.021
	7.	125/130	.232	.057	31.	85/90	.107	.018
	8.	Standard ✓	.058	.015	32.	105/110	.086	.034
	9.	130/135	.132	.053	33.			
	10.	~7	.037	.026	34.			
	11.	135/140-1	.139	.021	35.	110/115	.089	.045
	12.	135/140-2	.139	.021	36.	115/120	.272	.037
	13.	140/145	.109	.099	37.	130/135	.101	.014
	14.	145/150	.221	.034	38.	135/140	.087	.047
	15.	210/215	.028	.024	39.	150/155	.073	.031
	16.				40.	155/160	.051	.028
	17.				41.	170/175	.071	.018
	18.	224/225	.233	.351	42.	Standard ✓	.058	.015
	19.	255/260	.012	.043	43.	175/180	.053	.040
	20.	275/280	.069	.383	44.	270/275	.074	.012
R91-836	21.	5/10	.103	.018	45.	280/285	.178	.039
	22.	10/15	.107	.078	46.	290/295	.118	.013
	23.	15/20	.066	.058	47.	295/300	.109	.015
	24.	30/35	.241	.200	48.			