PRODUCT BULLETIN DRYWALL ACCESSORY PRODUCTS	COVER-TEX WALL TEXTURE	BULLETIN NO: J-5303 DATE: 6/3/74 PAGE: 1 of 2
APPROVALS:	PRODUCING PLANT: SEATTLE	CANCELS: J-5303 DATE: 3/23/73

BULLETIN	DESCRIPTION	%	POUNDS	GALLONS
221	Limestone	54.00	2200	
442	Westal 302 Talc	25.76	1050	
045	Asbestos 7RF10	4.91	200	
251	Mica, AMC	4.91	200	
446	Titanium Pigment	1.84	75	
056	Wyojel Clay	4.30	175	
330	Polyvinyl Alcohol	1.47	60	
200	Keltose	.25	10	
245	Methocel 228	.25	10	
453	Preservative	.12	5	
164	Glyoxal 80%	.30	12	
350	Monsanto KGR	.30	12	
436	Staramic 747	1.47	60	
454	Defoamer, Nopco PD-1	.12	5	
	TOTAL	100.00	4074	

MANUFACTURING INSTRUCTIONS:

1. Mixing time shall be 8 minutes minimum and 12 minutes maximum.

QUALITY CONTROL:

TM-1	Viscosity, 100 gm cone @ 5 sec 200 gram to 150 cc water	30 - 40
TM-3A	Bond	Equal to Standard

KG2001655

PRODUCT BULLETIN DRYWALL ACCESSORY PRODUCTS	COVER-TEX WALL TEXTURE	BULLETIN NO: J-5303 DATE: 6/3/74 PAGE: 2 of 2
APPROVALS:	PRODUCING PLANT: SEATTLE	CANCELS: J-5303 DATE: 3/23/73

PRODUCT SPECIFICATIONS:

Test Method		
TM-1	Viscosity, 100 gm cone @ 5 secs 200 gm to 150 cc water	30-40 mm
TM-1A	Viscosity, (mixing water of 110 cc/ 100 gm) cps	25,000 - 35,000
TM-2	pH (Corning meter)	8.2 - 8.8
TM-2A	Indicator Paper	7.0 - 8.5
TM-3A	Bond @ 70°F	Satisfactory
TM-17	Application	Equal to Standard
TM-18	Water Resistance (minutes)	2 minimum
TM-19	Settling (inches)	3/16" maximum
TM-20	Cracking	No cracks
TM-25	Normal Application Consistency, cc	85-95
TM-35	Resistance to Souring	Equal to Standard
TM-39	Paintability Test	Equal to Standard
TM-41	Wet Pub Test	Equal to Standard