Contractor: Lang | Coordinates: 47402.68 25764.18 | Project: Expansion | Hole No. R90-663

Drill Type: D40K | Casing Depth: | State: | Sheet 1 of 3

Hole Size: | Bearing: | Inclination: -90° | Date Started: 1/25/90 | Property: Gilt Edge / Anchor Hill

Collar Elev.: 5646.9' | Final Depth: 475' | Date Completed: 1/25/90 | Hole Surveyed:

DRILL CUTTING LOG

Logged by: J. Groff

Distance (feet)	Alteration (Weak / Strong)	Total Sulfides (vol %)	Rock Code	Core Code	Down Hole Location: Distance Down Hole (feet)	Down Hole Location: Elevation	Rock Type	Description: Mineralogy, Alteration, Textures, Grain Size, Fragment Size	Mineralization: Distribution (Massive, Disseminated, Veinlets, Replacement) / Type	Assay: Au	Assay: Ag
			50	3	0-5		Thtp	0-225 Hornblende trachyte	0-50 Oxide		
								0-85 Highly altered - sericitic ? -			
								(15-95 Quartz veins)			
					20-25						
									(40-475 magnetite veinlets and loose)		
					45-50						
				2					50-55 Mix 1% pyrite		
				3					55-65 Oxide		
				2					65-140 Mix, 1% pyrite		
					70-75						
					95-100						
								(105-110 Quartz veins)			
					120-125			125-225 varying intensity of alteration			
								(125-130 Quartz veins)			
				3				140-200 Highly altered, sericitic ?	140-145 Oxide		
				2	145-150				145-155 Mix 1% pyr.		
								(150-225 Quart veins)			
				3					155-170 Oxide		
				2	170-175				170-175 Mix 1% pyrite		

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 2 of 3

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

GRAPHIC LOGS			DOWN HOLE LOCATION		GEOLOGIC NOTES				
DISTANCE (feet)	ALTERATION: Weak, Moderate, Strong	TOTAL SULFIDES % (vol %)	ROCK CODE	ORE CODE	DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement) / TYPE	ASSAY: Au / Ag
			50	3	175-180		Thtp	175-180 white clay	175-200 oxide	
					195-200					
				2					200-475 Mix 1% pyrite	
					220-225					
			30				Cdh	225-415 Deadwood hornfels		
					245-250					
								(255-265 Quartz veins)		
				2						
					270-275					
								(285-400 Quartz veins)		
					295-300					
					320-325			(Qtz rims around K Felds phenos & qtz veins through K felds phenos in Ttp)		
								(330-335 Frags of Quartz trachyte)		
					345-350			(345-360 Dark brown hornfels)	less magnetite in dark brown Cdh	

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 3 of 3

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	MINERALIZATION: Distribution (Massive, Disseminated, Veinlet, Replacement) / Type	ASSAY: Au	ASSAY: Ag
			30	2	350-355		cdh	Cdh Cont			
					370-375				(370 - 400 2% diss. pyrite)		
								(385-390. Few highly silicified Frags one with garnets)			
					395-400						
								(400-405 some Frags of quartz trachyte)			
			40				Cdq	415-435 Deadwood Quartzite			
					420-425						
			10				pt	435-475, Precambrian Amphibolite			
					445-450				(445-470 Oxide mostly on Fractures, sulfide within Frags)		
					470-475						
								E.O.H. 475'			
					495-500						
					520-525						

DRILL CUTTING LOG

Logged by:

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30073.4 (COMPLETE)

REFERENCE INFO: 0-400

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-663

SUBMITTED BY: BARRON
DATE PRINTED: 7-FEB-90

ORDER	ELEMENT		NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au	Gold	15	0.002 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	15	2 -150	15	ASSAY PREP	15
				EXCESSIVE WETNESS/LB	307

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building T, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 7-FEB-90

REPORT: R90-300073.4

PROJECT: R90-663

SAMPLE NUMBER	ELEMENT UNITS	Au OPT
Z2 R90-663 400-405		0.002
Z2 R90-663 405-410		0.002
Z2 R90-663 410-415		<0.002
Z2 R90-663 415-420		0.011
Z2 R90-663 420-425		0.007
Z2 R90-663 425-430		0.002
Z2 R90-663 430-435		<0.002
Z2 R90-663 435-440		<0.002
Z2 R90-663 440-445		<0.002
Z2 R90-663 445-450		<0.002
Z2 R90-663 450-455		<0.002
Z2 R90-663 455-460		<0.002
Z2 R90-663 460-465		<0.002
Z2 R90-663 465-470		<0.002
Z2 R90-663 470-475		<0.002

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building T, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

Geochemical Lab Report

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

DATE PRINTED: 7-FEB-90

REPORT: R90-30073.4

PROJECT: R90-663 PAGE 2

SAMPLE NUMBER	ELEMENT UNITS	Au OPT
R90-663 415-420		0.011
Duplicate		0.007
R90-663 465-470		<0.002
Duplicate		<0.002

BROHM MINING CO.
FEB 15 1990
RECEIVED

RECEIVED
FEB 12 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-3007 2.4 (COMPLETE)

REFERENCE INFO: 0-400

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-663

SUBMITTED BY: BARRON
DATE PRINTED: 5-FEB-90

ORDER	ELEMENT		NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au	Gold	80	0.002 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	80	2 -150	80	ASSAY PREP	80
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 14, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 5-FEB-90

REPORT: R90-300072.4

PROJECT: R90-663

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT
Z2 R90-663 0-5		<0.002	Z2 R90-663 200-205		<0.002
Z2 R90-663 5-10		<0.002	Z2 R90-663 205-210		0.010
Z2 R90-663 10-15		<0.002	Z2 R90-663 210-215		0.011
Z2 R90-663 15-20		<0.002	Z2 R90-663 215-220		0.004
Z2 R90-663 20-25		<0.002	Z2 R90-663 220-225		0.004
Z2 R90-663 25-30		<0.002	Z2 R90-663 225-230		0.005
Z2 R90-663 30-35		<0.002	Z2 R90-663 230-235		<0.002
Z2 R90-663 35-40		<0.002	Z2 R90-663 235-240		0.003
Z2 R90-663 40-45		<0.002	Z2 R90-663 240-245		0.037
Z2 R90-663 45-50		<0.002	Z2 R90-663 245-250		<0.002
Z2 R90-663 50-55		<0.002	Z2 R90-663 250-255		<0.002
Z2 R90-663 55-60		<0.002	Z2 R90-663 255-260		0.004
Z2 R90-663 60-65		<0.002	Z2 R90-663 260-265		<0.002
Z2 R90-663 65-70		<0.002	Z2 R90-663 265-270		0.011
Z2 R90-663 70-75		<0.002	Z2 R90-663 270-275		0.014
Z2 R90-663 75-80		<0.002	Z2 R90-663 275-280		0.002
Z2 R90-663 80-85		<0.002	Z2 R90-663 280-285		0.003
Z2 R90-663 85-90		<0.002	Z2 R90-663 285-290		<0.002
Z2 R90-663 90-95		<0.002	Z2 R90-663 290-295		<0.002
Z2 R90-663 95-100		<0.002	Z2 R90-663 295-300		<0.002
Z2 R90-663 100-105		<0.002	Z2 R90-663 300-305		0.002
Z2 R90-663 105-110		<0.002	Z2 R90-663 305-310		<0.002
Z2 R90-663 110-115		<0.002	Z2 R90-663 310-315		<0.002
Z2 R90-663 115-120		<0.002	Z2 R90-663 315-320		0.008
Z2 R90-663 120-125		<0.002	Z2 R90-663 320-325		0.031
Z2 R90-663 125-130		<0.002	Z2 R90-663 325-330		0.002
Z2 R90-663 130-135		<0.002	Z2 R90-663 330-335		<0.002
Z2 R90-663 135-140		<0.002	Z2 R90-663 335-340		<0.002
Z2 R90-663 140-145		<0.002	Z2 R90-663 340-345		0.004
Z2 R90-663 145-150		<0.002	Z2 R90-663 345-350		<0.002
Z2 R90-663 150-155		<0.002	Z2 R90-663 350-355		0.002
Z2 R90-663 155-160		0.005	Z2 R90-663 355-360		0.002
Z2 R90-663 160-165		<0.002	Z2 R90-663 360-365		<0.002
Z2 R90-663 165-170		<0.002	Z2 R90-663 365-370		0.002
Z2 R90-663 170-175		<0.002	Z2 R90-663 370-375		<0.002
Z2 R90-663 175-180		<0.002	Z2 R90-663 375-380		<0.002
Z2 R90-663 180-185		<0.002	Z2 R90-663 380-385		<0.002
Z2 R90-663 185-190		0.007	Z2 R90-663 385-390		<0.002
Z2 R90-663 190-195		0.007	Z2 R90-663 390-395		<0.002
Z2 R90-663 195-200		0.002	Z2 R90-663 395-400		<0.002

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 5-FEB-90

REPORT: R90-30072.4

PROJECT: R90-663

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT
R90-663 10-15		<0.002			
Duplicate		<0.002			
R90-663 60-65		<0.002			
Duplicate		<0.002			
R90-663 120-125		<0.002			
Duplicate		<0.002			
R90-663 170-175		<0.002			
Duplicate		<0.002			
R90-663 230-235		<0.002			
Duplicate		<0.002			
R90-663 280-285		0.003			
Duplicate		0.003			
R90-663 340-345		0.004			
Duplicate		0.004			
R90-663 390-395		<0.002			
Duplicate		<0.002			

CASCADIA MINING CO
FEB 15 1990
RECEIVED

RECEIVED
FEB 1 2 1990
BROHM MINING CO.

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30072.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC dry	80	R90-663	Au	
		0-5		
		395-400		

Total No. Samples _____ Date Shipped 1/26/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

BROHM ☐ Results ☐ Invoice (for payment)

☐ Results ☐ Invoice (copy)

☐ Results ☐ Invoice (copy)

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30073

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC wet	15	K90-663	Au	
		400-405		
		470-475		

Total No. Samples _____ Date Shipped 1/26/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

BROHM ☐ Results ☐ Invoice (for payment)

☐ Results ☐ Invoice (copy)

☐ Results ☐ Invoice (copy)

Samples submitted by V. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

```
"TITLE 05-02-90 09:52:36 R90-30072.4   BARRON                30/01/90"
"CLIENT BROHM MINING CORPORATION                                      "
"PROJECT R90-663          #SAMPLES:   80 REFERENCE: 0-400                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   80 0.002 999.90 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z      OTHER DRILL TYPES   "
"  41 P17=  80           ASSAY PREP          "
"  42 P98=   1           SAMPLE PICKUP/MILE  "
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,1(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au"
"00720001" "Z" "2" "R90-663 0-5          "   -0.002
"00720002" "Z" "2" "R90-663 5-10         "   -0.002
"00720003" "Z" "2" "R90-663 10-15        "   -0.002
"00720005" "Z" "2" "R90-663 15-20        "   -0.002
"00720006" "Z" "2" "R90-663 20-25        "   -0.002
"00720007" "Z" "2" "R90-663 25-30        "   -0.002
"00720008" "Z" "2" "R90-663 30-35        "   -0.002
"00720009" "Z" "2" "R90-663 35-40        "   -0.002
"00720010" "Z" "2" "R90-663 40-45        "   -0.002
"00720011" "Z" "2" "R90-663 45-50        "   -0.002
"00720012" "Z" "2" "R90-663 50-55        "   -0.002
"00720013" "Z" "2" "R90-663 55-60        "   -0.002
"00720014" "Z" "2" "R90-663 60-65        "   -0.002
"00720015" "Z" "2" "R90-663 65-70        "   -0.002
"00720016" "Z" "2" "R90-663 70-75        "   -0.002
"00720017" "Z" "2" "R90-663 75-80        "   -0.002
"00720018" "Z" "2" "R90-663 80-85        "   -0.002
"00720019" "Z" "2" "R90-663 85-90        "   -0.002
"00720020" "Z" "2" "R90-663 90-95        "   -0.002
"00720021" "Z" "2" "R90-663 95-100       "   -0.002
"00720022" "Z" "2" "R90-663 100-105      "   -0.002
"00720025" "Z" "2" "R90-663 105-110      "   -0.002
"00720026" "Z" "2" "R90-663 110-115      "   -0.002
"00720027" "Z" "2" "R90-663 115-120      "   -0.002
"00720028" "Z" "2" "R90-663 120-125      "   -0.002
"00720030" "Z" "2" "R90-663 125-130      "   -0.002
"00720031" "Z" "2" "R90-663 130-135      "   -0.002
"00720032" "Z" "2" "R90-663 135-140      "   -0.002
"00720033" "Z" "2" "R90-663 140-145      "   -0.002
"00720034" "Z" "2" "R90-663 145-150      "   -0.002
"00720035" "Z" "2" "R90-663 150-155      "   -0.002
"00720036" "Z" "2" "R90-663 155-160      "    0.005
"00720037" "Z" "2" "R90-663 160-165      "   -0.002
"00720038" "Z" "2" "R90-663 165-170      "   -0.002
"00720039" "Z" "2" "R90-663 170-175      "   -0.002
"00720040" "Z" "2" "R90-663 175-180      "   -0.002
"00720041" "Z" "2" "R90-663 180-185      "   -0.002
"00720042" "Z" "2" "R90-663 185-190      "    0.007
"00720043" "Z" "2" "R90-663 190-195      "    0.007
"00720044" "Z" "2" "R90-663 195-200      "    0.002
"00720045" "Z" "2" "R90-663 200-205      "   -0.002
"00720046" "Z" "2" "R90-663 205-210      "    0.010
"00720049" "Z" "2" "R90-663 210-215      "    0.011
"00720050" "Z" "2" "R90-663 215-220      "    0.004
"00720051" "Z" "2" "R90-663 220-225      "    0.004
"00720052" "Z" "2" "R90-663 225-230      "    0.005
```

"00720053"	"Z"	"2"	"R90-663	230-235	"	-0.002
"00720055"	"Z"	"2"	"R90-663	235-240	"	0.003
"00720056"	"Z"	"2"	"R90-663	240-245	"	0.037
"00720057"	"Z"	"2"	"R90-663	245-250	"	-0.002
"00720058"	"Z"	"2"	"R90-663	250-255	"	-0.002
"00720059"	"Z"	"2"	"R90-663	255-260	"	0.004
"00720060"	"Z"	"2"	"R90-663	260-265	"	-0.002
"00720061"	"Z"	"2"	"R90-663	265-270	"	0.011
"00720062"	"Z"	"2"	"R90-663	270-275	"	0.014
"00720063"	"Z"	"2"	"R90-663	275-280	"	0.002
"00720064"	"Z"	"2"	"R90-663	280-285	"	0.003
"00720065"	"Z"	"2"	"R90-663	285-290	"	-0.002
"00720066"	"Z"	"2"	"R90-663	290-295	"	-0.002
"00720067"	"Z"	"2"	"R90-663	295-300	"	-0.002
"00720068"	"Z"	"2"	"R90-663	300-305	"	0.002
"00720069"	"Z"	"2"	"R90-663	305-310	"	-0.002
"00720070"	"Z"	"2"	"R90-663	310-315	"	-0.002
"00720073"	"Z"	"2"	"R90-663	315-320	"	0.008
"00720074"	"Z"	"2"	"R90-663	320-325	"	0.031
"00720075"	"Z"	"2"	"R90-663	325-330	"	0.002
"00720076"	"Z"	"2"	"R90-663	330-335	"	-0.002
"00720077"	"Z"	"2"	"R90-663	335-340	"	-0.002
"00720078"	"Z"	"2"	"R90-663	340-345	"	0.004
"00720080"	"Z"	"2"	"R90-663	345-350	"	-0.002
"00720081"	"Z"	"2"	"R90-663	350-355	"	0.002
"00720082"	"Z"	"2"	"R90-663	355-360	"	0.002
"00720083"	"Z"	"2"	"R90-663	360-365	"	-0.002
"00720084"	"Z"	"2"	"R90-663	365-370	"	0.002
"00720085"	"Z"	"2"	"R90-663	370-375	"	-0.002
"00720086"	"Z"	"2"	"R90-663	375-380	"	-0.002
"00720087"	"Z"	"2"	"R90-663	380-385	"	-0.002
"00720088"	"Z"	"2"	"R90-663	385-390	"	-0.002
"00720089"	"Z"	"2"	"R90-663	390-395	"	-0.002
"00720090"	"Z"	"2"	"R90-663	395-400	"	-0.002

"END"

```
"TITLE 07-02-90 09:13:45 R90-30073.4   BARRON                05/02/90"
"CLIENT BROHM MINING CORPORATION                                      "
"PROJECT R90-663          #SAMPLES:   15 REFERENCE: 0-400                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   15 0.002 999.90 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z      OTHER DRILL TYPES   "
"  41 P17=  15           ASSAY PREP          "
"  42 P64= 307           EXCESSIVE WETNESS/LB"
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,1(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au"
"00730001" "Z" "2" "R90-663 400-405     "    0.002
"00730002" "Z" "2" "R90-663 405-410     "    0.002
"00730003" "Z" "2" "R90-663 410-415     "   -0.002
"00730004" "Z" "2" "R90-663 415-420     "    0.011
"00730006" "Z" "2" "R90-663 420-425     "    0.007
"00730007" "Z" "2" "R90-663 425-430     "    0.002
"00730008" "Z" "2" "R90-663 430-435     "   -0.002
"00730009" "Z" "2" "R90-663 435-440     "   -0.002
"00730010" "Z" "2" "R90-663 440-445     "   -0.002
"00730011" "Z" "2" "R90-663 445-450     "   -0.002
"00730012" "Z" "2" "R90-663 450-455     "   -0.002
"00730013" "Z" "2" "R90-663 455-460     "   -0.002
"00730014" "Z" "2" "R90-663 460-465     "   -0.002
"00730015" "Z" "2" "R90-663 465-470     "   -0.002
"00730016" "Z" "2" "R90-663 470-475     "   -0.002
"END"
```

Contractor: Lang | Coordinates: 47448.04 25644.13 | Project: Expansion | Hole No.: RAD-664

Drill Type: D40K | Casing Depth: | State: | Sheet 1 of 4

Hole Size: | Bearing: | Inclination: -90° | Date Started: 1/25/90 | Property: Gilt Edge / Anchor Hill

Collar Elev.: 5676.4 | Final Depth: 565' | Date Completed: 1/26/90 | Hole Surveyed:

Distance (feet)	Alteration	Total Sulfides (vol %)	Rock Code	Ore Code	Down Hole Location: Distance Down Hole (feet)	Down Hole Location: Structure Elevation	Rock Type	Description: Mineralogy, Alteration, Textures, Grain Size, Fragment Size	Mineralization: Distribution (Massive, Disseminated, Veinlet, Replacement)	Mineralization: Type	Assay: Au	Assay: Ag
			85	3	0-5	712	Tq+p	0-435 Quartz trachyte por.	0-535 Oxide			
						0-565		(0-70 sericitic? alteration, phenos, highly altered - rust colored clay)	(0-40 highly oxidized)			
					20-25							
					45-50							
								(60-70 large secondary qtz grains and adularia? - cleavage)				
					70-75			(70-435 phenos altered to varying degrees)				
								(80-95 large secondary qtz grains and adularia? cleavage)				
					95-100							
								(105-135 minor white clay)				
					120-125							
					145-150							
					170-175							

DRILL CUTTING LOG

Logged by: J. Groff

Contractor _____ Coordinates _____ Project _____ Hole No. R90-664

Drill Type _____ Casing Depth _____ State _____ Sheet 2 of 4

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

Distance (feet)	Graphic Logs: Alteration (1 Weak, 2 Moderate, 3 Strong)	Total Sulfides (vol %)	Rock Code	Ore Code	Down Hole Location: Distance Down Hole (feet)	Elevation	Rock Type	Geologic Notes: Description (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	Mineralization: Distribution (Massive, Disseminated, Veinlet, Replacement)	Type	Assay: Au	Ag
			85	3	175-180		Tq+p	Cont. Quartz trachyte				
					195-200							
								(205-215 minor white clay and secondary quartz, adularia ?)				
					220-225							
					245-250			(240-270 minor iron stained and white clay) (250-260 secondary adularia ?)				
					270-275							
								(285-310 iron stained clay)	(290-310 increased oxidation)			
					295-300							
					320-325			(325-330 iron stained clay)				
					345-350							

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 3 of 4

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION (Weak, Moderate, Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement)	TYPE	ASSAY: Au	Ag
			45	3	350-355		Tq+P	Cont. Quartz trachyte				
								(350-355 iron stained clay)	(increased oxidation 355-455)			
									(385-390 extreme oxidation - red)			
					370-375							
								(385-390 iron stained clay)				
					395-400							
					420-425							
			30				Cdh	435 - 450, Deadwood horntels				
					445-450			(435-440 quartz veins)				
								(445-450) greenish clay)				
			40				Cdq	450 - 470 Deadwood quartzite				
			20		470-475			470 - 485 Precambrian chert - micaceous				
			10					485 - 545 Precambrian amphibolite				
					495-500							
					520-525							

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 4 of 4

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE)	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlets, Replacement)	TYPE	ASSAY Au	ASSAY Ag
			10	3	525-530		Pt	Cont Precambrian Amphibolite				
				2				(535-545 Chert frags)	535-565 Mix, 1% pyrite			
					545-550			545-565 Precambrian Qtz. mica schist				
								(560-565 chert frags)				
					570-575			E.O.H 565'				
					595-600							
					620-625							
					645-650							
					670-675							
					695-700							

DRILL CUTTING LOG

Logged by:

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30075.4 (COMPLETE)

REFERENCE INFO: 455-565

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-664

SUBMITTED BY: BARRON
DATE PRINTED: 7-FEB-90

ORDER	ELEMENT		NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au	Gold	22	0.002 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	22	2 -150	22	ASSAY PREP	22
				EXCESSIVE WETNESS/LB	342

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 7-FEB-90

REPORT: R90-30075.4

PROJECT: R90-664

SAMPLE NUMBER	ELEMENT UNITS	Au OPT
Z2 R90-664 455-460		0.075
Z2 R90-664 460-465		0.010
Z2 R90-664 465-470		<0.002
Z2 R90-664 470-475		0.032
Z2 R90-664 475-480		0.024
Z2 R90-664 480-485		0.015
Z2 R90-664 485-490		0.023
Z2 R90-664 490-495		0.013
Z2 R90-664 495-500		0.008
Z2 R90-664 500-505		<0.002
Z2 R90-664 505-510		0.008
Z2 R90-664 510-515		<0.002
Z2 R90-664 515-520		<0.002
Z2 R90-664 520-525		0.004
Z2 R90-664 525-530		<0.002
Z2 R90-664 530-535		<0.002
Z2 R90-664 535-540		0.007
Z2 R90-664 540-545		0.003
Z2 R90-664 545-550		0.008
Z2 R90-664 550-555		<0.002
Z2 R90-664 555-560		<0.002
Z2 R90-664 560-565		<0.002

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 7-FEB-90

REPORT: R90-30075.4

PROJECT: R90-664

SAMPLE NUMBER	ELEMENT UNITS	Au OPT
R90-664 480-485		0.015
Duplicate		0.012
R90-664 530-535		<0.002
Duplicate		<0.002

RECEIVED
FEB 13 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
62 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30074.4 (COMPLETE)

REFERENCE INFO: 0-455

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-664

SUBMITTED BY: BARRON
DATE PRINTED: 5-FEB-90

ORDER	ELEMENT		NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au	Gold	91	0.002 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	91	2 -150	91	ASSAY PREP	91
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
62[illegible] Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 5-FEB-90

REPORT: R90-300074.4

PROJECT: R90-664

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT
Z2 R90-664 0-5		0.016	Z2 R90-664 200-205		<0.002
Z2 R90-664 5-10		0.063	Z2 R90-664 205-210		<0.002
Z2 R90-664 10-15		0.093	Z2 R90-664 210-215		<0.002
Z2 R90-664 15-20		0.061	Z2 R90-664 215-220		<0.002
Z2 R90-664 20-25		0.038	Z2 R90-664 220-225		<0.002
Z2 R90-664 25-30		0.050	Z2 R90-664 225-230		<0.002
Z2 R90-664 30-35		0.071	Z2 R90-664 230-235		0.003
Z2 R90-664 35-40		0.109	Z2 R90-664 235-240		0.002
Z2 R90-664 40-45		0.005	Z2 R90-664 240-245		0.003
Z2 R90-664 45-50		0.002	Z2 R90-664 245-250		<0.002
Z2 R90-664 50-55		0.002	Z2 R90-664 250-255		<0.002
Z2 R90-664 55-60		<0.002	Z2 R90-664 255-260		0.002
Z2 R90-664 60-65		0.002	Z2 R90-664 260-265		<0.002
Z2 R90-664 65-70		0.003	Z2 R90-664 265-270		0.005
Z2 R90-664 70-75		<0.002	Z2 R90-664 270-275		<0.002
Z2 R90-664 75-80		<0.002	Z2 R90-664 275-280		0.007
Z2 R90-664 80-85		0.002	Z2 R90-664 280-285		0.007
Z2 R90-664 85-90		0.002	Z2 R90-664 285-290		0.006
Z2 R90-664 90-95		0.002	Z2 R90-664 290-295		0.028
Z2 R90-664 95-100		<0.002	Z2 R90-664 295-300		0.029
Z2 R90-664 100-105		<0.002	Z2 R90-664 300-305		0.083
Z2 R90-664 105-110		0.033	Z2 R90-664 305-310		0.050
Z2 R90-664 110-115		0.003	Z2 R90-664 310-315		0.057
Z2 R90-664 115-120		<0.002	Z2 R90-664 315-320		0.021
Z2 R90-664 120-125		<0.002	Z2 R90-664 320-325		0.042
Z2 R90-664 125-130		<0.002	Z2 R90-664 325-330		0.039
Z2 R90-664 130-135		0.018	Z2 R90-664 330-335		0.016
Z2 R90-664 135-140		0.002	Z2 R90-664 335-340		0.006
Z2 R90-664 140-145		0.002	Z2 R90-664 340-345		0.006
Z2 R90-664 145-150		<0.002	Z2 R90-664 345-350		0.006
Z2 R90-664 150-155		<0.002	Z2 R90-664 350-355		0.013
Z2 R90-664 155-160		<0.002	Z2 R90-664 355-360		0.165
Z2 R90-664 160-165		<0.002	Z2 R90-664 360-365		0.011
Z2 R90-664 165-170		<0.002	Z2 R90-664 365-370		0.056
Z2 R90-664 170-175		<0.002	Z2 R90-664 370-375		0.026
Z2 R90-664 175-180		<0.002	Z2 R90-664 375-380		0.031
Z2 R90-664 180-185		0.003	Z2 R90-664 380-385		0.040
Z2 R90-664 185-190		<0.002	Z2 R90-664 385-390		0.122
Z2 R90-664 190-195		<0.002	Z2 R90-664 390-395		0.030
Z2 R90-664 195-200		<0.002	Z2 R90-664 395-400		0.017

Bondar-Clegg, Inc.
62[illegible] Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

Geochemical Lab Report

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

DATE PRINTED: 5-FEB-90

REPORT: R90-30074.4

PROJECT: R90-664

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT
Z2 R90-664 400-405		0.012			
Z2 R90-664 405-410		0.014			
Z2 R90-664 410-415		0.011			
Z2 R90-664 415-420		0.014			
Z2 R90-664 420-425		0.012			
Z2 R90-664 425-430		0.014			
Z2 R90-664 430-435		0.026			
Z2 R90-664 435-440		0.022			
Z2 R90-664 440-445		0.116			
Z2 R90-664 445-450		0.024			
Z2 R90-664 450-455		0.018			

Bondar-Clegg, Inc.
62 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

RECEIVED FEB 15 1990 BOHM MINING CO.

REPORT: R90-30074.4

DATE PRINTED: 5-FEB-90
PROJECT: R90-664

SAMPLE NUMBER	ELEMENT UNITS	Au OPT
R90-664 20-25		0.038
Duplicate		0.039
R90-664 70-75		<0.002
Duplicate		<0.002
R90-664 130-135		0.018
Duplicate		0.019
R90-664 180-185		0.003
Duplicate		0.002
R90-664 240-245		0.003
Duplicate		0.005
R90-664 290-295		0.028
Duplicate		0.034
R90-664 350-355		0.013
Duplicate		0.011
R90-664 400-405		0.012
Duplicate		0.011

RECEIVED
FEB 13 1990
BROHM MINING CO.

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30074.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC dry	91	R90-664	Au	
		0-5		
		450-455		

Total No. Samples _____ Date Shipped 1/26/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

BROHM ☐ Results ☐ Invoice (for payment)

☐ Results ☐ Invoice (copy)

☐ Results ☐ Invoice (copy)

Samples submitted by J. BARRON

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30075.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC wet	22	R90-664	Au	
		455-460		
		560-565		

Total No. Samples _____ Date Shipped 1/26/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

Brolin ☐ Results ☐ Invoice (for payment)

☐ Results ☐ Invoice (copy)

☐ Results ☐ Invoice (copy)

Samples submitted by J. Basson

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

```
"TITLE 05-02-90 08:48:24 R90-30074.4   BARRON                30/01/90"
"CLIENT BROHM MINING CORPORATION                                      "
"PROJECT R90-664          #SAMPLES:   91 REFERENCE: 0-455                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   91 0.002 999.90 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z       OTHER DRILL TYPES   "
"  41 P17=  91            ASSAY PREP          "
"  42 P98=   1            SAMPLE PICKUP/MILE  "
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,1(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au"
"00740001" "Z" "2" "R90-664 0-5          "    0.016
"00740002" "Z" "2" "R90-664 5-10         "    0.063
"00740003" "Z" "2" "R90-664 10-15        "    0.093
"00740004" "Z" "2" "R90-664 15-20        "    0.061
"00740005" "Z" "2" "R90-664 20-25        "    0.038
"00740007" "Z" "2" "R90-664 25-30        "    0.050
"00740008" "Z" "2" "R90-664 30-35        "    0.071
"00740009" "Z" "2" "R90-664 35-40        "    0.109
"00740010" "Z" "2" "R90-664 40-45        "    0.005
"00740011" "Z" "2" "R90-664 45-50        "    0.002
"00740012" "Z" "2" "R90-664 50-55        "    0.002
"00740013" "Z" "2" "R90-664 55-60        "   -0.002
"00740014" "Z" "2" "R90-664 60-65        "    0.002
"00740015" "Z" "2" "R90-664 65-70        "    0.003
"00740016" "Z" "2" "R90-664 70-75        "   -0.002
"00740017" "Z" "2" "R90-664 75-80        "   -0.002
"00740018" "Z" "2" "R90-664 80-85        "    0.002
"00740019" "Z" "2" "R90-664 85-90        "    0.002
"00740020" "Z" "2" "R90-664 90-95        "    0.002
"00740021" "Z" "2" "R90-664 95-100       "   -0.002
"00740022" "Z" "2" "R90-664 100-105      "   -0.002
"00740025" "Z" "2" "R90-664 105-110      "    0.033
"00740026" "Z" "2" "R90-664 110-115      "    0.003
"00740027" "Z" "2" "R90-664 115-120      "   -0.002
"00740028" "Z" "2" "R90-664 120-125      "   -0.002
"00740029" "Z" "2" "R90-664 125-130      "   -0.002
"00740030" "Z" "2" "R90-664 130-135      "    0.018
"00740032" "Z" "2" "R90-664 135-140      "    0.002
"00740033" "Z" "2" "R90-664 140-145      "    0.002
"00740034" "Z" "2" "R90-664 145-150      "   -0.002
"00740035" "Z" "2" "R90-664 150-155      "   -0.002
"00740036" "Z" "2" "R90-664 155-160      "   -0.002
"00740037" "Z" "2" "R90-664 160-165      "   -0.002
"00740038" "Z" "2" "R90-664 165-170      "   -0.002
"00740039" "Z" "2" "R90-664 170-175      "   -0.002
"00740040" "Z" "2" "R90-664 175-180      "   -0.002
"00740041" "Z" "2" "R90-664 180-185      "    0.003
"00740042" "Z" "2" "R90-664 185-190      "   -0.002
"00740043" "Z" "2" "R90-664 190-195      "   -0.002
"00740044" "Z" "2" "R90-664 195-200      "   -0.002
"00740045" "Z" "2" "R90-664 200-205      "   -0.002
"00740046" "Z" "2" "R90-664 205-210      "   -0.002
"00740049" "Z" "2" "R90-664 210-215      "   -0.002
"00740050" "Z" "2" "R90-664 215-220      "   -0.002
"00740051" "Z" "2" "R90-664 220-225      "   -0.002
"00740052" "Z" "2" "R90-664 225-230      "   -0.002
```

5-40
35' @ .069

"00740053"	"Z"	"2"	"R90-664	230-235	"	0.003
"00740054"	"Z"	"2"	"R90-664	235-240	"	0.002
"00740055"	"Z"	"2"	"R90-664	240-245	"	0.003
"00740057"	"Z"	"2"	"R90-664	245-250	"	-0.002
"00740058"	"Z"	"2"	"R90-664	250-255	"	-0.002
"00740059"	"Z"	"2"	"R90-664	255-260	"	0.002
"00740060"	"Z"	"2"	"R90-664	260-265	"	-0.002
"00740061"	"Z"	"2"	"R90-664	265-270	"	0.005
"00740062"	"Z"	"2"	"R90-664	270-275	"	-0.002
"00740063"	"Z"	"2"	"R90-664	275-280	"	0.007
"00740064"	"Z"	"2"	"R90-664	280-285	"	0.007
"00740065"	"Z"	"2"	"R90-664	285-290	"	0.006
"00740066"	"Z"	"2"	"R90-664	290-295	"	0.028
"00740067"	"Z"	"2"	"R90-664	295-300	"	0.029
"00740068"	"Z"	"2"	"R90-664	300-305	"	0.083
"00740069"	"Z"	"2"	"R90-664	305-310	"	0.050
"00740070"	"Z"	"2"	"R90-664	310-315	"	0.057
"00740073"	"Z"	"2"	"R90-664	315-320	"	0.021
"00740074"	"Z"	"2"	"R90-664	320-325	"	0.042
"00740075"	"Z"	"2"	"R90-664	325-330	"	0.039
"00740076"	"Z"	"2"	"R90-664	330-335	"	0.016
"00740077"	"Z"	"2"	"R90-664	335-340	"	0.006
"00740078"	"Z"	"2"	"R90-664	340-345	"	0.006
"00740079"	"Z"	"2"	"R90-664	345-350	"	0.006
"00740080"	"Z"	"2"	"R90-664	350-355	"	0.013
"00740082"	"Z"	"2"	"R90-664	355-360	"	0.165
"00740083"	"Z"	"2"	"R90-664	360-365	"	0.011
"00740084"	"Z"	"2"	"R90-664	365-370	"	0.056
"00740085"	"Z"	"2"	"R90-664	370-375	"	0.026
"00740086"	"Z"	"2"	"R90-664	375-380	"	0.031
"00740087"	"Z"	"2"	"R90-664	380-385	"	0.040
"00740088"	"Z"	"2"	"R90-664	385-390	"	0.122
"00740089"	"Z"	"2"	"R90-664	390-395	"	0.030
"00740090"	"Z"	"2"	"R90-664	395-400	"	0.017
"00740091"	"Z"	"2"	"R90-664	400-405	"	0.012
"00740092"	"Z"	"2"	"R90-664	405-410	"	0.014
"00740093"	"Z"	"2"	"R90-664	410-415	"	0.011
"00740094"	"Z"	"2"	"R90-664	415-420	"	0.014
"00740097"	"Z"	"2"	"R90-664	420-425	"	0.012
"00740098"	"Z"	"2"	"R90-664	425-430	"	0.014
"00740099"	"Z"	"2"	"R90-664	430-435	"	0.026
"00740100"	"Z"	"2"	"R90-664	435-440	"	0.022
"00740101"	"Z"	"2"	"R90-664	440-445	"	0.116
"00740102"	"Z"	"2"	"R90-664	445-450	"	0.024
"00740103"	"Z"	"2"	"R90-664	450-455	"	0.018
"END"						

290 - 330
40' @ .044

355 - 395
40' @ .060

430 - 490
60' @ .032

TD = 565

K0010
K0030
K0040

TT.TMP

K0060.P

ID20G1U
60
80
85

ID2SG30
40
50
70

```
"TITLE 07-02-90 13:40:25 R90-30075.4   BARRON                05/02/90"
"CLIENT BROHM MINING CORPORATION                                      "
"PROJECT R90-664          #SAMPLES:   22 REFERENCE: 455-565                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   22 0.002 999.90 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z      OTHER DRILL TYPES   "
"  41 P17=  22           ASSAY PREP          "
"  42 P64= 342           EXCESSIVE WETNESS/LB"
"****"
"FORMAT (A8,1X,A1,A1,1X,A20,1(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "     Au"
"00750001" "Z" "2" "R90-664 455-460     "    0.075
"00750002" "Z" "2" "R90-664 460-465     "    0.010
"00750003" "Z" "2" "R90-664 465-470     "   -0.002
"00750004" "Z" "2" "R90-664 470-475     "    0.032
"00750005" "Z" "2" "R90-664 475-480     "    0.024
"00750006" "Z" "2" "R90-664 480-485     "    0.015
"00750008" "Z" "2" "R90-664 485-490     "    0.023
"00750009" "Z" "2" "R90-664 490-495     "    0.013
"00750010" "Z" "2" "R90-664 495-500     "    0.008
"00750011" "Z" "2" "R90-664 500-505     "   -0.002
"00750012" "Z" "2" "R90-664 505-510     "    0.008
"00750013" "Z" "2" "R90-664 510-515     "   -0.002
"00750014" "Z" "2" "R90-664 515-520     "   -0.002
"00750015" "Z" "2" "R90-664 520-525     "    0.004
"00750016" "Z" "2" "R90-664 525-530     "   -0.002
"00750017" "Z" "2" "R90-664 530-535     "   -0.002
"00750018" "Z" "2" "R90-664 535-540     "    0.007
"00750019" "Z" "2" "R90-664 540-545     "    0.003
"00750020" "Z" "2" "R90-664 545-550     "    0.008
"00750021" "Z" "2" "R90-664 550-555     "   -0.002
"00750022" "Z" "2" "R90-664 555-560     "   -0.002
"00750025" "Z" "2" "R90-664 560-565     "   -0.002
"END"
```