Contractor: Ling | Coordinates: 47268.43 25481.80 | Project: Expansion | Hole No.: R90-678 (Site A-75)

Drill Type: M40K | Casing Depth: | State: | Sheet 1 of 5

Hole Size: | Bearing: | Inclination: -90° | Date Started: 2/10/90 | Property: Gilt Edge / Anchor Hill

Collar Elev.: 5658.4 | Final Depth: 745' | Date Completed: 2/11/90 | Hole Surveyed: Yes

Distance (feet)	Graphic Logs: Alteration (Weak, Moderate, Strong)	Total Sulfides (vol %)	Rock Code	Ore Code	Down Hole Location: Distance Down Hole (feet)	Structure Elevation	Rock Type	Geologic Notes: Description (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	Mineralization: Distribution (Massive, Disseminated, Veinlets, Replacement) / Type	Assay: Au	Ag
			885	3	0-5	712	Tatp	0-375 Quartz trachyte, generally oxidized to pink or reddish hue and altered. Groundmass is bleached and sometimes pitted; difficult to distinguish phenocrysts. Chip size is generally variable throughout. Oxidation decreases below 600 ft.	0-745 Oxide zones at intense oxidation - brick red.		
						0-360					
					20-25						
					45-50				(40-45 intense oxidation)		
									(55-60 intense oxidation)		
					70-75						
					95-100				(90-100 intense oxidation)		
									(115-125 intense oxidation)		
					120-125						
					145-150				(140-195 intense oxidation)		
					170-175						

DRILL CUTTING LOG

Logged by: Graff

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 2 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

Distance (feet)	Graphic Logs: Alteration (Weak, Moderate, Strong)	Total Sulfides (vol %)	Rock Code	Ore Code	Down Hole Location: Distance Down Hole (feet)	Elevation	Rock Type	Geologic Notes: Description (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	Mineralization: Distribution (Massive, Disseminated, Veinlets, Replacement)	Type	Assay: Au	Assay: Ag
			85	3	175-180		Tatp	Cont Quartz trachyte				
					195-200				(200-335 intense oxidation)			
					220-225							
					245-250							
					270-275							
								(280-285 vugs after phenocrysts)	(290-300 extreme oxidation – entire interval is brick red)			
					295-300							
								(310-315 vugs after phenocrysts				
					320-325							
					345-350							

DRILL CUTTING LOG

Logged by:

530

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 3 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

GRAPHIC LOGS					DOWN HOLE LOCATION		GEOLOGIC NOTES				
DISTANCE (feet)	ALTERATION: 1 Weak, 2 Moderate, 3 Strong	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION Massive, Disseminated, Veinlet, Replacement / TYPE	ASSAY Au	ASSAY Ag
			85	3	350-355		Tq tp				
								(360-395 highly altered vuggy)			
					370-375						
			70				Tbxa	375-395 Breccia, quartz trachyte encloses hornfels and quartzite	(380-410 intense oxidation)		
			85		395-400		Tq tp	395-530 Quartz trachyte (395-405 loose chips of hornfels)			
					420-425						
					445-450			(450-455 vugs after phenocrysts) (450-480 random chips of quartzite-hornfels and hornblende trachyte)			
					470-475						
								(485-490 vugs after phenocrysts) (490-495 numerous chips of quartzite and precambrian Amphibolite)			
					495-500						
					520-525						

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 4 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

Distance (feet)	Graphic Logs: Alteration (Weak / Moderate / Strong)	Total Sulfides (vol %)	Rock Code	Ore Code	Down Hole Location: Distance Down Hole (feet)	Elevation	Rock Type	Geologic Notes: Description (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	Mineralization: Distribution (Massive, Disseminated, Veinlet, Replacement)	Type	Assay: Au	Ag
				3	525-530							
			70				Tbxa	530-540 Breccia; Quartz trachyte encloses Pt Amphibilite and chert				
			85				Ta+p	540-565 Quartz trachyte				
					545-550							
			70				Tbxa	565-570 Breccia, as above				
			85		570-575		Ta+p	570-620 Quartz trachyte				
					595-600							
								(610-620 loose chips of Pt Amphib.)				
			70		620-625		Tbxa	620-670 Breccia, as above				
								(630-675 Chips up to half an inch across)				
					645-650							
			85		670-675		Ta+p	670-715 Quartz trachyte				
					695-700							

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 5 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION (1 Weak, 2 Moderate, 3 Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement)	TYPE	ASSAY Au	ASSAY Ag
			85	3	700-705							
			10				PE	715-745 Precambrian Amphibolite				
					720-725							
					745-750			745' E.O.H				
					770-775							
					795-800							
					820-825							
					845-850							
					870-875							

DRILL CUTTING LOG

Logged by:

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30127.4 (COMPLETE)

REFERENCE INFO: 0-165

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-678

SUBMITTED BY: BARRON
DATE PRINTED: 22-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	33	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	7	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	3	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
7 OTHER DRILL TYPES	33	2 -150	33	ASSAY PREP	33
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 22-FEB-90

REPORT: R90-30127.4

PROJECT: R90-678

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-678 0-5		0.012		
Z2 R90-678 5-10		0.024		
Z2 R90-678 10-15		0.025		
Z2 R90-678 15-20		0.090	0.090	0.087
Z2 R90-678 20-25		0.043		
Z2 R90-678 25-30		0.031		
Z2 R90-678 30-35		0.057		
Z2 R90-678 35-40		0.062	0.074	
Z2 R90-678 40-45		0.060	0.065	0.065
Z2 R90-678 45-50		0.016		
Z2 R90-678 50-55		0.004		
Z2 R90-678 55-60		0.020		
Z2 R90-678 60-65		0.015		
Z2 R90-678 65-70		0.036	0.024	0.022
Z2 R90-678 70-75		0.009		
Z2 R90-678 75-80		0.002		
Z2 R90-678 80-85		0.003		
Z2 R90-678 85-90		0.002	0.002	
Z2 R90-678 90-95		<0.002		
Z2 R90-678 95-100		<0.002		
Z2 R90-678 100-105		0.002	0.006	
Z2 R90-678 105-110		0.012		
Z2 R90-678 110-115		0.012		
Z2 R90-678 115-120		0.027		
Z2 R90-678 120-125		0.009		
Z2 R90-678 125-130		0.008		
Z2 R90-678 130-135		0.013		
Z2 R90-678 135-140		0.008		
Z2 R90-678 140-145		0.006		
Z2 R90-678 145-150		0.008	0.009	
Z2 R90-678 150-155		0.008		
Z2 R90-678 155-160		0.010		
Z2 R90-678 160-165		0.008		

RECEIVED
FEB 27 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30130.4 (COMPLETE)

REFERENCE INFO: 405-745

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-678

SUBMITTED BY: BARRON
DATE PRINTED: 27-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	68	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	15	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	6	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	68	2 -150	68	ASSAY PREP	68
				EXCESSIVE WETNESS/LB	1462
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 27-FEB-90

REPORT: R90-30130.4

PROJECT: R90-678

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-678 405-410		0.120	0.135		Z2 R90-678 605-610		0.008		
Z2 R90-678 410-415		0.053			Z2 R90-678 610-615		0.006		
Z2 R90-678 415-420		0.047			Z2 R90-678 615-620		0.008		
Z2 R90-678 420-425		0.115	0.120	0.133	Z2 R90-678 620-625		0.008		
Z2 R90-678 425-430		0.082	0.060		Z2 R90-678 625-630		0.006	0.006	
Z2 R90-678 430-435		0.029			Z2 R90-678 630-635		0.008		
Z2 R90-678 435-440		0.103	0.105	0.178	Z2 R90-678 635-640		0.008		
Z2 R90-678 440-445		0.028			Z2 R90-678 640-645		0.010		
Z2 R90-678 445-450		0.038			Z2 R90-678 645-650		0.028		
Z2 R90-678 450-455		0.017			Z2 R90-678 650-655		0.024		
Z2 R90-678 455-460		0.021	0.018		Z2 R90-678 655-660		0.016		
Z2 R90-678 460-465		0.013			Z2 R90-678 660-665		0.006	0.006	0.005
Z2 R90-678 465-470		0.022			Z2 R90-678 665-670		0.010		
Z2 R90-678 470-475		0.013			Z2 R90-678 670-675		0.009		
Z2 R90-678 475-480		0.014			Z2 R90-678 675-680		0.003	0.003	
Z2 R90-678 480-485		0.041			Z2 R90-678 680-685		0.002		
Z2 R90-678 485-490		0.002			Z2 R90-678 685-690		0.003		
Z2 R90-678 490-495		0.024			Z2 R90-678 690-695		0.003		
Z2 R90-678 495-500		0.022			Z2 R90-678 695-700		0.003		
Z2 R90-678 500-505		0.042	0.046		Z2 R90-678 700-705		0.004		
Z2 R90-678 505-510		0.056			Z2 R90-678 705-710		0.003		
Z2 R90-678 510-515		0.010			Z2 R90-678 710-715		0.004		
Z2 R90-678 515-520		0.011	0.011		Z2 R90-678 715-720		<0.002		
Z2 R90-678 520-525		0.009			Z2 R90-678 720-725		0.009		
Z2 R90-678 525-530		0.075	0.080	0.066	Z2 R90-678 725-730		<0.002		
Z2 R90-678 530-535		0.032			Z2 R90-678 730-735		<0.002		
Z2 R90-678 535-540		0.018			Z2 R90-678 735-740		0.002	0.002	
Z2 R90-678 540-545		0.053	0.022	0.044	Z2 R90-678 740-745		0.009		
Z2 R90-678 545-550		0.022							
Z2 R90-678 550-555		0.025							
Z2 R90-678 555-560		0.018							
Z2 R90-678 560-565		0.024							
Z2 R90-678 565-570		0.037	0.026	0.026					
Z2 R90-678 570-575		0.030							
Z2 R90-678 575-580		0.011							
Z2 R90-678 580-585		0.010							
Z2 R90-678 585-590		0.011							
Z2 R90-678 590-595		0.011	0.009						
Z2 R90-678 595-600		0.010							
Z2 R90-678 600-605		0.032							

RECEIVED
MAR 5 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30128.4 (COMPLETE)

REFERENCE INFO: 165-405

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-678

SUBMITTED BY: BARRON
DATE PRINTED: 27-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	48	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	11	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	9	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	48	2 -150	48	ASSAY PREP	48
				EXCESSIVE WETNESS/LB	1201
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 27-FEB-90

REPORT: R90-30128.4

PROJECT: R90-678

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-678 165-170		0.014		
Z2 R90-678 170-175		0.015		
Z2 R90-678 175-180		0.027	0.028	0.026
Z2 R90-678 180-185		0.016		
Z2 R90-678 185-190		0.012		
Z2 R90-678 190-195		0.015		
Z2 R90-678 195-200		0.006		
Z2 R90-678 200-205		0.006		
Z2 R90-678 205-210		0.015	0.013	0.013
Z2 R90-678 210-215		0.012		
Z2 R90-678 215-220		0.017	0.019	0.016
Z2 R90-678 220-225		0.012		
Z2 R90-678 225-230		0.013		
Z2 R90-678 230-235		0.009		
Z2 R90-678 235-240		0.011		
Z2 R90-678 240-245		0.013		
Z2 R90-678 245-250		0.009		
Z2 R90-678 250-255		0.018		
Z2 R90-678 255-260		0.010	0.009	0.004
Z2 R90-678 260-265		0.012		
Z2 R90-678 265-270		0.008		
Z2 R90-678 270-275		0.021		
Z2 R90-678 275-280		0.011	0.010	
Z2 R90-678 280-285		0.026		
Z2 R90-678 285-290		0.030		
Z2 R90-678 290-295		0.024		
Z2 R90-678 295-300		0.012		
Z2 R90-678 300-305		0.024		
Z2 R90-678 305-310		0.026		
Z2 R90-678 310-315		0.031		
Z2 R90-678 315-320		0.041	0.046	
Z2 R90-678 320-325		0.079	0.108	0.072
Z2 R90-678 325-330		0.123		
Z2 R90-678 330-335		0.372	0.164	0.259
Z2 R90-678 335-340		0.246		
Z2 R90-678 340-345		0.203		
Z2 R90-678 345-350		0.183		
Z2 R90-678 350-355		0.315	0.273	0.363
Z2 R90-678 355-360		0.118		
Z2 R90-678 360-365		0.038		
Z2 R90-678 365-370		0.078	0.089	0.077
Z2 R90-678 370-375		0.038		
Z2 R90-678 375-380		0.020		
Z2 R90-678 380-385		0.006		
Z2 R90-678 385-390		0.075		
Z2 R90-678 390-395		0.122	0.135	0.125
Z2 R90-678 395-400		0.034		
Z2 R90-678 400-405		0.063		

RECEIVED
MAR 5 1990
BROHM MINING CO.

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-3012 7.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC dry	33	R90-678	Au	
		8-5		
		160-165		

Total No. Samples _____ Date Shipped 2/11/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Results and Invoices To Be Sent To

B Holm ☐ Results ☐ Invoice (for payment)

_____ ☐ Results ☐ Invoice (copy)

_____ ☐ Results ☐ Invoice (copy)

Printed in Canada

White - Send with Samples Yellow - Client Copy

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30128.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC wet	48	R90-678	Au	
		165-170		
		400-405		

Total No. Samples _____ Date Shipped 2/11/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

Brohn

☐ Results
☐ Invoice (for payment)

☐ Results
☐ Invoice (copy)

☐ Results
☐ Invoice (copy)

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30130-4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC wet	68	R90-678	Au	
		405-410		
		740-745		

Total No. Samples _____ Date Shipped 2/12/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Results and Invoices To Be Sent To

Brohm ☐ Results ☐ Invoice (for payment)

☐ Results ☐ Invoice (copy)

☐ Results ☐ Invoice (copy)

White - Send with Samples Yellow - Client Copy

Printed in Canada

"TITLE 22-02-90 15:10:02 R90-30127.4 BARRON 14/02/90"
"CLIENT BROHM MINING CORPORATION "
"PROJECT R90-678 #SAMPLES: 33 REFERENCE: 0-165 "
"SPECIAL VALUES"
" IS Insufficient Sample"
" -9 No Value Recorded"
" Values above the upper limit are shown as +uplimt"
" Values below the lower limit are shown as -lolmt (ie not detected)"
"DETERMINATIONS"
" ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
" 01 Au FA OPT 33 0.002 999.90 Results Reported "
" 02 AU DUP FA OPT 7 0.002 9999.0 Results Reported "
" 03 AU Dup FA OPT 3 0.001 9999.0 Results Reported "
"SAMPLE PREPS"
" 40 SAMPLE TYPE=Z OTHER DRILL TYPES "
" 41 P17= 33 ASSAY PREP "
" 42 P98= 1 SAMPLE PICKUP/MILE "
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"

2/22

"BEGIN "	"Type"	"Frac"	"Sample ID"	"		Au"	"AU DUP"	"AU Dup"
"01270001"	"Z"	"2"	"R90-678 0-5	"		0.012	-9	-9
"01270002"	"Z"	"2"	"R90-678 5-10	"		0.024	-9	-9
"01270003"	"Z"	"2"	"R90-678 10-15	"		0.025	-9	-9
"01270004"	"Z"	"2"	"R90-678 15-20	"	89	0.090	0.090	0.087
"01270005"	"Z"	"2"	"R90-678 20-25	"		0.043	-9	-9
"01270006"	"Z"	"2"	"R90-678 25-30	"		0.031	-9	-9
"01270007"	"Z"	"2"	"R90-678 30-35	"		0.057	-9	-9
"01270008"	"Z"	"2"	"R90-678 35-40	"	68	0.062	0.074	-9
"01270010"	"Z"	"2"	"R90-678 40-45	"	63	0.060	0.065	0.065
"01270011"	"Z"	"2"	"R90-678 45-50	"		0.016	-9	-9
"01270012"	"Z"	"2"	"R90-678 50-55	"		0.004	-9	-9
"01270013"	"Z"	"2"	"R90-678 55-60	"		0.020	-9	-9
"01270014"	"Z"	"2"	"R90-678 60-65	"		0.015	-9	-9
"01270015"	"Z"	"2"	"R90-678 65-70	"	27	0.036	0.024	0.022
"01270016"	"Z"	"2"	"R90-678 70-75	"		0.009	-9	-9
"01270017"	"Z"	"2"	"R90-678 75-80	"		0.002	-9	-9
"01270018"	"Z"	"2"	"R90-678 80-85	"		0.003	-9	-9
"01270019"	"Z"	"2"	"R90-678 85-90	"		0.002	0.002	-9
"01270020"	"Z"	"2"	"R90-678 90-95	"		-0.002	-9	-9
"01270021"	"Z"	"2"	"R90-678 95-100	"		-0.002	-9	-9
"01270022"	"Z"	"2"	"R90-678 100-105	"		0.002	0.006	-9
"01270025"	"Z"	"2"	"R90-678 105-110	"		0.012	-9	-9
"01270026"	"Z"	"2"	"R90-678 110-115	"		0.012	-9	-9
"01270027"	"Z"	"2"	"R90-678 115-120	"		0.027	-9	-9
"01270028"	"Z"	"2"	"R90-678 120-125	"		0.009	-9	-9
"01270029"	"Z"	"2"	"R90-678 125-130	"		0.008	-9	-9
"01270030"	"Z"	"2"	"R90-678 130-135	"		0.013	-9	-9
"01270031"	"Z"	"2"	"R90-678 135-140	"		0.008	-9	-9
"01270032"	"Z"	"2"	"R90-678 140-145	"		0.006	-9	-9
"01270033"	"Z"	"2"	"R90-678 145-150	"		0.008	0.009	-9
"01270035"	"Z"	"2"	"R90-678 150-155	"		0.008	-9	-9
"01270036"	"Z"	"2"	"R90-678 155-160	"		0.010	-9	-9
"01270037"	"Z"	"2"	"R90-678 160-165	"		0.008	-9	-9

"END"

5-70
65' @ .037

```
"TITLE 26-02-90 17:10:13 R90-30128.4   BARRON                    19/02/90"
"CLIENT BROHM MINING CORPORATION                                 "
"PROJECT R90-678          #SAMPLES:   48 REFERENCE: 165-405                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   48 0.002 999.90 Results Reported     "
"  02 AU DUP FA        OPT   11 0.002 9999.0 Results Reported     "
"  03 AU Dup FA        OPT    9 0.001 9999.0 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z      OTHER DRILL TYPES   "
"  41 P17=  48           ASSAY PREP          "
"  42 P64=1201           EXCESSIVE WETNESS/LB"
"  43 P98=   1           SAMPLE PICKUP/MILE  "
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au" "AU DUP" "AU Dup"
"01280001" "Z" "2" "R90-678 165-170     "    0.014      -9       -9
"01280002" "Z" "2" "R90-678 170-175     "    0.015      -9       -9
"01280003" "Z" "2" "R90-678 175-180     "    0.027   0.028    0.026  x̄=.027
"01280004" "Z" "2" "R90-678 180-185     "    0.016      -9       -9
"01280005" "Z" "2" "R90-678 185-190     "    0.012      -9       -9
"01280006" "Z" "2" "R90-678 190-195     "    0.015      -9       -9
"01280007" "Z" "2" "R90-678 195-200     "    0.006      -9       -9
"01280008" "Z" "2" "R90-678 200-205     "    0.006      -9       -9
"01280009" "Z" "2" "R90-678 205-210     "    0.015   0.013    0.013  x̄=.014
"01280011" "Z" "2" "R90-678 210-215     "    0.012      -9       -9
"01280012" "Z" "2" "R90-678 215-220     "    0.017   0.019    0.016
"01280013" "Z" "2" "R90-678 220-225     "    0.012      -9       -9
"01280014" "Z" "2" "R90-678 225-230     "    0.013      -9       -9
"01280015" "Z" "2" "R90-678 230-235     "    0.009      -9       -9
"01280016" "Z" "2" "R90-678 235-240     "    0.011      -9       -9
"01280017" "Z" "2" "R90-678 240-245     "    0.013      -9       -9
"01280018" "Z" "2" "R90-678 245-250     "    0.009      -9       -9
"01280019" "Z" "2" "R90-678 250-255     "    0.018      -9       -9
"01280020" "Z" "2" "R90-678 255-260     "    0.010   0.009    0.004
"01280021" "Z" "2" "R90-678 260-265     "    0.012      -9       -9
"01280022" "Z" "2" "R90-678 265-270     "    0.008      -9       -9
"01280025" "Z" "2" "R90-678 270-275     "    0.021      -9       -9
"01280026" "Z" "2" "R90-678 275-280     "    0.011   0.010 x̄=.010 -9
"01280027" "Z" "2" "R90-678 280-285     "    0.026      -9       -9
"01280028" "Z" "2" "R90-678 285-290     "    0.030      -9       -9
"01280029" "Z" "2" "R90-678 290-295     "    0.024      -9       -9
"01280030" "Z" "2" "R90-678 295-300     "    0.012      -9       -9
"01280031" "Z" "2" "R90-678 300-305     "    0.024      -9       -9
"01280032" "Z" "2" "R90-678 305-310     "    0.026      -9       -9
"01280033" "Z" "2" "R90-678 310-315     "    0.031      -9       -9
"01280034" "Z" "2" "R90-678 315-320   x̄=.044 0.041   0.046       -9
"01280036" "Z" "2" "R90-678 320-325   x̄=.086 0.079   0.108    0.072
"01280037" "Z" "2" "R90-678 325-330     "    0.123      -9       -9
"01280038" "Z" "2" "R90-678 330-335   x̄=.265 0.372   0.164    0.259
"01280039" "Z" "2" "R90-678 335-340     "    0.246      -9       -9
"01280040" "Z" "2" "R90-678 340-345     "    0.203      -9       -9
"01280041" "Z" "2" "R90-678 345-350     "    0.183      -9       -9
"01280042" "Z" "2" "R90-678 350-355   x̄=.317 0.315   0.273    0.363
"01280043" "Z" "2" "R90-678 355-360     "    0.118      -9       -9
"01280044" "Z" "2" "R90-678 360-365     "    0.038      -9       -9
"01280045" "Z" "2" "R90-678 365-370   x̄=.081 0.078   0.089    0.077
```

"01280046"	"Z"	"2"	"R90-678	370-375	"	0.038	-9	-9
"01280049"	"Z"	"2"	"R90-678	375-380	"	0.020	-9	-9
"01280050"	"Z"	"2"	"R90-678	380-385	"	0.006	-9	-9
"01280051"	"Z"	"2"	"R90-678	385-390	"	0.075	-9	-9
"01280052"	"Z"	"2"	"R90-678	390-395	$\bar{x} \pm .127$	0.122	0.135	0.125
"01280053"	"Z"	"2"	"R90-678	395-400	"	0.034	-9	-9
"01280054"	"Z"	"2"	"R90-678	400-405	"	0.063	-9	-9

"END"

```
"TITLE 26-02-90 17:04:12 R90-30130.4   BARRON                    19/02/90"
"CLIENT BROHM MINING CORPORATION                                 "
"PROJECT R90-678          #SAMPLES:   68 REFERENCE: 405-745                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   68 0.002 999.90 Results Reported     "
"  02 AU DUP FA        OPT   15 0.002 9999.0 Results Reported     "
"  03 AU Dup FA        OPT    6 0.001 9999.0 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z       OTHER DRILL TYPES   "
"  41 P17=  68            ASSAY PREP          "
"  42 P64=1462            EXCESSIVE WETNESS/LB"
"  43 P98=   1            SAMPLE PICKUP/MILE  "
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "     Au" "AU DUP" "AU Dup"
"01300001" "Z" "2" "R90-678 405-410    x̄=.128 0.120    0.135       -9
"01300003" "Z" "2" "R90-678 410-415      "    0.053       -9        -9
"01300004" "Z" "2" "R90-678 415-420      "    0.047       -9        -9
"01300005" "Z" "2" "R90-678 420-425    x̄=.123 0.115    0.120     0.133
"01300006" "Z" "2" "R90-678 425-430    x̄=.071 0.082    0.060       -9
"01300007" "Z" "2" "R90-678 430-435      "    0.029       -9        -9
"01300008" "Z" "2" "R90-678 435-440    x̄=.129 0.103    0.105     0.178
"01300009" "Z" "2" "R90-678 440-445      "    0.028       -9        -9
"01300010" "Z" "2" "R90-678 445-450      "    0.038       -9        -9
"01300011" "Z" "2" "R90-678 450-455      "    0.017       -9        -9
"01300012" "Z" "2" "R90-678 455-460    x̄=.020 0.021    0.018       -9
"01300013" "Z" "2" "R90-678 460-465      "    0.013       -9        -9
"01300014" "Z" "2" "R90-678 465-470      "    0.022       -9        -9
"01300015" "Z" "2" "R90-678 470-475      "    0.013       -9        -9
"01300016" "Z" "2" "R90-678 475-480      "    0.014       -9        -9
"01300017" "Z" "2" "R90-678 480-485      "    0.041       -9        -9
"01300018" "Z" "2" "R90-678 485-490      "    0.002       -9        -9
"01300019" "Z" "2" "R90-678 490-495      "    0.024       -9        -9
"01300020" "Z" "2" "R90-678 495-500      "    0.022       -9        -9
"01300021" "Z" "2" "R90-678 500-505    x̄=.044 0.042    0.046       -9
"01300022" "Z" "2" "R90-678 505-510      "    0.056       -9        -9
"01300025" "Z" "2" "R90-678 510-515      "    0.010       -9        -9
"01300026" "Z" "2" "R90-678 515-520      "    0.011    0.011        -9
"01300028" "Z" "2" "R90-678 520-525      "    0.009       -9        -9
"01300029" "Z" "2" "R90-678 525-530    x̄=.074 0.075    0.080     0.066
"01300030" "Z" "2" "R90-678 530-535      "    0.032       -9        -9
"01300031" "Z" "2" "R90-678 535-540      "    0.018       -9        -9
"01300032" "Z" "2" "R90-678 540-545    x̄=.040 0.053    0.022     0.044
"01300033" "Z" "2" "R90-678 545-550      "    0.022       -9        -9
"01300034" "Z" "2" "R90-678 550-555      "    0.025       -9        -9
"01300035" "Z" "2" "R90-678 555-560      "    0.018       -9        -9
"01300036" "Z" "2" "R90-678 560-565      "    0.024       -9        -9
"01300037" "Z" "2" "R90-678 565-570    x̄=.030 0.037    0.026     0.026
"01300038" "Z" "2" "R90-678 570-575      "    0.030       -9        -9
"01300039" "Z" "2" "R90-678 575-580      "    0.011       -9        -9
"01300040" "Z" "2" "R90-678 580-585      "    0.010       -9        -9
"01300041" "Z" "2" "R90-678 585-590      "    0.011       -9        -9
"01300042" "Z" "2" "R90-678 590-595      "    0.011    0.009        -9
"01300043" "Z" "2" "R90-678 595-600      "    0.010       -9        -9
"01300044" "Z" "2" "R90-678 600-605      "    0.032       -9        -9
"01300045" "Z" "2" "R90-678 605-610      "    0.008       -9        -9
```

525 - 575
50' @

"01300046"	"Z"	"2"	"R90-678	610-615	"	0.006	-9	-9
"01300049"	"Z"	"2"	"R90-678	615-620	"	0.008	-9	-9
"01300050"	"Z"	"2"	"R90-678	620-625	"	0.008	-9	-9
"01300051"	"Z"	"2"	"R90-678	625-630	"	0.006	0.006	-9
"01300053"	"Z"	"2"	"R90-678	630-635	"	0.008	-9	-9
"01300054"	"Z"	"2"	"R90-678	635-640	"	0.008	-9	-9
"01300055"	"Z"	"2"	"R90-678	640-645	"	0.010	-9	-9
"01300056"	"Z"	"2"	"R90-678	645-650	"	0.028	-9	-9
"01300057"	"Z"	"2"	"R90-678	650-655	"	0.024	-9	-9
"01300058"	"Z"	"2"	"R90-678	655-660	"	0.016	-9	-9
"01300059"	"Z"	"2"	"R90-678	660-665	"	0.006	0.006	0.005
"01300060"	"Z"	"2"	"R90-678	665-670	"	0.010	-9	-9
"01300061"	"Z"	"2"	"R90-678	670-675	"	0.009	-9	-9
"01300062"	"Z"	"2"	"R90-678	675-680	"	0.003	0.003	-9
"01300063"	"Z"	"2"	"R90-678	680-685	"	0.002	-9	-9
"01300064"	"Z"	"2"	"R90-678	685-690	"	0.003	-9	-9
"01300065"	"Z"	"2"	"R90-678	690-695	"	0.003	-9	-9
"01300066"	"Z"	"2"	"R90-678	695-700	"	0.003	-9	-9
"01300067"	"Z"	"2"	"R90-678	700-705	"	0.004	-9	-9
"01300068"	"Z"	"2"	"R90-678	705-710	"	0.003	-9	-9
"01300069"	"Z"	"2"	"R90-678	710-715	"	0.004	-9	-9
"01300070"	"Z"	"2"	"R90-678	715-720	"	-0.002	-9	-9
"01300073"	"Z"	"2"	"R90-678	720-725	"	0.009	-9	-9
"01300074"	"Z"	"2"	"R90-678	725-730	"	-0.002	-9	-9
"01300075"	"Z"	"2"	"R90-678	730-735	"	-0.002	-9	-9
"01300076"	"Z"	"2"	"R90-678	735-740	"	0.002	0.002	-9
"01300078"	"Z"	"2"	"R90-678	740-745	"	0.009	-9	-9

645-655 10@.026

"END"

Contractor: Lang | Coordinates: 47447.79 25464.75 | Project: Expansion | Hole No.: R90-679 (Site A-76)

Drill Type: D40 K | Casing Depth: | State: | Sheet 1 of 5

Hole Size: | Bearing: | Inclination: -90° | Date Started: 2/11/90 | Property: Gilt Edge / Anchor Hill

Collar Elev.: 5715.0 | Final Depth: 845' | Date Completed: 2/12/90 | Hole Surveyed: yes

GRAPHIC LOGS: DISTANCE (feet)	ALTERATION (Weak / Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	STRUCTURE ELEVATION	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE)	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlets, Replacement)	TYPE	ASSAY: Au	Ag
			85	3	0-5	712	Tqtp	0-755 Quartz trachyte,	0-755 Oxide			
						0-845		variable degreps of oxidation-				
								some highly oxidized zones.	(0-20 highly oxidized)			
								generally altered, some				
					20-25			bleaching and clay alter phenos				
								Chip size is generally small but				
								zones with large variations occur.				
								Oxidation and alteration decrease	(35-45 highly oxidized)			
								below 225 Ft. (Note: Quartz				
					45-50			trachyte is more of a brown to green				
								instead of gray as usual for Anchor				
								except in 10 Ft interval at bottom				
								of hole).				
					70-75							
					95-100							
									(110-195 highly oxidized)			
					120-125							
					145-150							
					170-175							

DRILL CUTTING LOG

Logged by: [illegible]

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 2 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION (Weak, Moderate, Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	GEOLOGIC NOTES: DESCRIPTION (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement)	TYPE	ASSAY: Au	Ag
			85	3	175-180		Tatn	Cont Quartz trachyte				
					195-200							
									(210 - 225 highly oxidized)			
					220-225							
					245-250							
					270-275							
					295-300							
					320-325							
								(340 - 350 large variation in chip size)				
					345-350							

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 3 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

GRAPHIC LOGS				DOWN HOLE LOCATION		GEOLOGIC NOTES				
DISTANCE (feet)	ALTERATION: Weak, Moderate, Strong	TOTAL % SULFIDES (vol %)	ROCK CODE	ORE CODE	DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlets, Replacement) / TYPE	ASSAY: Au / Ag
			45	3	350-355		Tatn	Cont. Quartz trachyte		
					370-375					
					395-400					
					420-425					
								(435-445 large variation in chip size)		
					445-450					
					470-475					
					495-500					
					520-525					

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 4 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION (1 Weak, 2 Moderate, 3 Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	GEOLOGIC NOTES: ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement) TYPE	ASSAY: Au	Ag
			85	3	525-530		Tqtp	Cont Quartz trachyte			
					545-550						
					570-575				(570-575 increased oxidation)		
					595-600						
					620-625				(625-640 increased oxidation)		
					645-650				(645-650 increased oxidation)		
					670-675						
					695-700						

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 5 of 5

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed ?

GRAPHIC LOGS																GEOLOGIC NOTES					
DISTANCE (feet)	ALTERATION (1 Weak, 2 Moderate, 3 Strong)									TOTAL SULFIDES % (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	DOWN HOLE LOCATION: ELEVATION	ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement)	MINERALIZATION: TYPE	ASSAY: Au	ASSAY: Ag
											85	3	700-705		Tqtp	Cont Quartz trachyte				
																(700 - increased alteration -				
																groundmass is pitted / corroded				
													720-725				(725 - 745 increased oxidation)			
																(730 - 755 quartz veining)				
													745-750							
											10	2			PE	755 - 765 Precambrian Amphibolite	755 - 785 Mixed 1-2% pyrite-			
																	disseminated and veinlet			
											85				Tqtp	765 - 780 Quartz trachyte,				
													770-775			gray instead of brown - green as				
																in top of hole (very little				
											10				PE	alteration and oxidation)	785 - 825 Sulfide 2-3%			
												1				780 - 845 Precambrian Amphibolite,	disseminated / pyrite			
																some random chips of chert				
													795-800							
													820-825				825 - 845 Mixed, 1-2% pyrite			
												2					(Chert is preferential oxidized			
																	and mineralized over Amphibolite			
																	disseminated and veinlet pyrite)			
																845' E.O.H				
													845-850							
													870-875							

DRILL CUTTING LOG

Logged by:

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30133.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC dry	88	R90-679	Au	
		0-5		
		435-440		

Total No. Samples _____ Date Shipped 2/12/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

Brohm ☐ Results ☐ Invoice (for payment)

☐ Results ☐ Invoice (copy)

☐ Results ☐ Invoice (copy)

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30134.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☐ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC wet	60	R90-679	Au	
(frozen)		440-445		
		735-740		

Total No. Samples _____ Date Shipped 2/13/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Results and Invoices To Be Sent To

Brohm

☐ Results
☐ Invoice (for payment)

☐ Results
☐ Invoice (copy)

☐ Results
☐ Invoice (copy)

White - Send with Samples Yellow - Client Copy

Printed in Canada

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30135.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC frozen	21	R90-679	Au	
		740-745		
		840-845		

Total No. Samples _____ Date Shipped 2/13/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

Brolin ☐ Results ☐ Invoice (for payment)

☐ Results ☐ Invoice (copy)

☐ Results ☐ Invoice (copy)

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30133.4 (COMPLETE)

REFERENCE INFO: 0-440

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-679

SUBMITTED BY: BARRON
DATE PRINTED: 26-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	88	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	18	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	6	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	88	2 -150	88	ASSAY PREP	88
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 26-FEB-90

REPORT: R90-30133.4

PROJECT: R90-679

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-679 0-5		0.127	0.109	0.084	Z2 R90-679 200-205		0.016	0.022	
Z2 R90-679 5-10		0.078			Z2 R90-679 205-210		0.018		
Z2 R90-679 10-15		0.062			Z2 R90-679 210-215		0.144		
Z2 R90-679 15-20		0.015	0.016		Z2 R90-679 215-220		0.184	0.143	0.147
Z2 R90-679 20-25		0.064			Z2 R90-679 220-225		0.042		
Z2 R90-679 25-30		0.042			Z2 R90-679 225-230		0.007		
Z2 R90-679 30-35		0.101			Z2 R90-679 230-235		0.005		
Z2 R90-679 35-40		0.149	0.130	0.130	Z2 R90-679 235-240		0.006	0.006	
Z2 R90-679 40-45		0.119			Z2 R90-679 240-245		0.006		
Z2 R90-679 45-50		0.004			Z2 R90-679 245-250		0.029		
Z2 R90-679 50-55		0.005			Z2 R90-679 250-255		0.004		
Z2 R90-679 55-60		<0.002			Z2 R90-679 255-260		0.004		
Z2 R90-679 60-65		0.002			Z2 R90-679 260-265		0.010		
Z2 R90-679 65-70		<0.002	<0.002		Z2 R90-679 265-270		0.042	0.045	0.038
Z2 R90-679 70-75		<0.002			Z2 R90-679 270-275		0.017		
Z2 R90-679 75-80		<0.002			Z2 R90-679 275-280		0.015		
Z2 R90-679 80-85		<0.002			Z2 R90-679 280-285		0.093	0.107	0.077
Z2 R90-679 85-90		0.002			Z2 R90-679 285-290		0.025	0.020	
Z2 R90-679 90-95		0.003			Z2 R90-679 290-295		0.010		
Z2 R90-679 95-100		0.004			Z2 R90-679 295-300		0.036		
Z2 R90-679 100-105		<0.002			Z2 R90-679 300-305		0.025		
Z2 R90-679 105-110		<0.002			Z2 R90-679 305-310		0.010		
Z2 R90-679 110-115		0.030			Z2 R90-679 310-315		0.005		
Z2 R90-679 115-120		0.023	0.022		Z2 R90-679 315-320		0.010		
Z2 R90-679 120-125		0.051	0.045	0.045	Z2 R90-679 320-325		0.003		
Z2 R90-679 125-130		0.002	0.002		Z2 R90-679 325-330		0.011		
Z2 R90-679 130-135		0.005			Z2 R90-679 330-335		0.002		
Z2 R90-679 135-140		0.002			Z2 R90-679 335-340		0.003		
Z2 R90-679 140-145		0.007			Z2 R90-679 340-345		0.011		
Z2 R90-679 145-150		0.003			Z2 R90-679 345-350		0.005	0.005	
Z2 R90-679 150-155		0.002			Z2 R90-679 350-355		0.005		
Z2 R90-679 155-160		0.009			Z2 R90-679 355-360		0.004		
Z2 R90-679 160-165		0.003			Z2 R90-679 360-365		0.002		
Z2 R90-679 165-170		0.005			Z2 R90-679 365-370		0.005		
Z2 R90-679 170-175		0.007			Z2 R90-679 370-375		0.002		
Z2 R90-679 175-180		0.017	0.026		Z2 R90-679 375-380		<0.002		
Z2 R90-679 180-185		0.005			Z2 R90-679 380-385		0.004		
Z2 R90-679 185-190		0.022			Z2 R90-679 385-390		<0.002		
Z2 R90-679 190-195		0.008			Z2 R90-679 390-395		<0.002		
Z2 R90-679 195-200		0.009			Z2 R90-679 395-400		0.002	0.003	

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

RECEIVED
WAB 5 1990

DATE PRINTED: 26-FEB-90

REPORT: R90-30133.4

PROJECT: R90-679

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-679 400-405		0.004							
Z2 R90-679 405-410		0.003							
Z2 R90-679 410-415		<0.002							
Z2 R90-679 415-420		0.004	0.002						
Z2 R90-679 420-425		0.004							
Z2 R90-679 425-430		<0.002							
Z2 R90-679 430-435		0.007							
Z2 R90-679 435-440		0.015	0.019						

RECEIVED
MAR 2 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30135.4 (COMPLETE)

REFERENCE INFO: 740-845

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-679

SUBMITTED BY: BARRON
DATE PRINTED: 28-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	21	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	2	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	0	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	21	2 -150	21	ASSAY PREP	21
				EXCESSIVE WEINESS/LB	523

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 28-FEB-90

REPORT: R90-30135.4

PROJECT: R90-679

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-679 740-745		0.015		
Z2 R90-679 745-750		0.014		
Z2 R90-679 750-755		0.007		
Z2 R90-679 755-760		0.008		
Z2 R90-679 760-765		0.004		
Z2 R90-679 765-770		0.005	0.005	
Z2 R90-679 770-775		0.002		
Z2 R90-679 775-780		0.004		
Z2 R90-679 780-785		0.013		
Z2 R90-679 785-790		0.006		
Z2 R90-679 790-795		0.014		
Z2 R90-679 795-800		0.005		
Z2 R90-679 800-805		0.002		
Z2 R90-679 805-810		0.003		
Z2 R90-679 810-815		0.002		
Z2 R90-679 815-820		0.003	0.003	
Z2 R90-679 820-825		0.005		
Z2 R90-679 825-830		0.008		
Z2 R90-679 830-835		0.002		
Z2 R90-679 835-840		<0.002		
Z2 R90-679 840-845		<0.002		

RECEIVED
MAR . 5 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30134.4 (COMPLETE)

REFERENCE INFO: 440-740

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-679

SUBMITTED BY: BARRON
DATE PRINTED: 27-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	60	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	15	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	11	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	60	2 -150	60	ASSAY PREP	60
				EXCESSIVE WETNESS/LB	1425
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 27-FEB-90

REPORT: R90-30134.4

PROJECT: R90-679

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-679 440-445		0.005			Z2 R90-679 640-645		0.009		
Z2 R90-679 445-450		0.005			Z2 R90-679 645-650		0.042		
Z2 R90-679 450-455		0.005			Z2 R90-679 650-655		0.035		
Z2 R90-679 455-460		0.004			Z2 R90-679 655-660		0.445	0.377	0.376
Z2 R90-679 460-465		0.006	0.005		Z2 R90-679 660-665		0.061		
Z2 R90-679 465-470		0.004			Z2 R90-679 665-670		0.132	0.120	0.074
Z2 R90-679 470-475		0.004			Z2 R90-679 670-675		0.032		
Z2 R90-679 475-480		0.005			Z2 R90-679 675-680		0.017		
Z2 R90-679 480-485		0.008			Z2 R90-679 680-685		0.013	0.013	
Z2 R90-679 485-490		0.009			Z2 R90-679 685-690		0.036		
Z2 R90-679 490-495		0.252	0.284	0.233	Z2 R90-679 690-695		0.056		
Z2 R90-679 495-500		0.055			Z2 R90-679 695-700		0.031		
Z2 R90-679 500-505		0.010			Z2 R90-679 700-705		0.035		
Z2 R90-679 505-510		0.124	0.148	0.146	Z2 R90-679 705-710		0.062	0.059	0.059
Z2 R90-679 510-515		0.032	0.028	0.040	Z2 R90-679 710-715		0.044		
Z2 R90-679 515-520		0.017			Z2 R90-679 715-720		0.036		
Z2 R90-679 520-525		0.030			Z2 R90-679 720-725		0.042		
Z2 R90-679 525-530		0.016	0.010	0.013	Z2 R90-679 725-730		0.051		
Z2 R90-679 530-535		0.004			Z2 R90-679 730-735		0.040	0.034	
Z2 R90-679 535-540		0.015			Z2 R90-679 735-740		0.018		
Z2 R90-679 540-545		0.009							
Z2 R90-679 545-550		0.003							
Z2 R90-679 550-555		0.002							
Z2 R90-679 555-560		0.007							
Z2 R90-679 560-565		0.007							
Z2 R90-679 565-570		0.042	0.030	0.062					
Z2 R90-679 570-575		0.027	0.018	0.016					
Z2 R90-679 575-580		0.025							
Z2 R90-679 580-585		0.010							
Z2 R90-679 585-590		0.019							
Z2 R90-679 590-595		0.019							
Z2 R90-679 595-600		0.010							
Z2 R90-679 600-605		0.079	0.070	0.076					
Z2 R90-679 605-610		0.042							
Z2 R90-679 610-615		0.016							
Z2 R90-679 615-620		0.010							
Z2 R90-679 620-625		0.018	0.022						
Z2 R90-679 625-630		0.097	0.093	0.094					
Z2 R90-679 630-635		0.043							
Z2 R90-679 635-640		0.031							

RECEIVED
MAR 5 1990
BROHM MINING CO.

"TITLE 26-02-90 16:07:22 R90-30133.4 BARRON 15/02/90"
"CLIENT BROHM MINING CORPORATION "
"PROJECT R90-679 #SAMPLES: 88 REFERENCE: 0-440 "
"SPECIAL VALUES"
" IS Insufficient Sample"
" -9 No Value Recorded"
" Values above the upper limit are shown as +uplimt"
" Values below the lower limit are shown as -lolmt (ie not detected)"
"DETERMINATIONS"

"		ELNAME	METHO	ECO	UNI	#SAM	LOLMT	UPLIMT	COMMENTS"
"	01	Au	FA		OPT	88	0.002	999.90	Results Reported "
"	02	AU DUP	FA		OPT	18	0.002	9999.0	Results Reported "
"	03	AU Dup	FA		OPT	6	0.001	9999.0	Results Reported "

"SAMPLE PREPS"

"	40	SAMPLE TYPE=Z	OTHER DRILL TYPES	"
"	41	P17= 88	ASSAY PREP	"
"	42	P98= 1	SAMPLE PICKUP/MILE	"

"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"

"BEGIN "	"Type"	"Frac"	"Sample ID"	"	Au"	"AU DUP"	"AU Dup"	
"01330001"	"Z"	"2"	"R90-679 0-5	$\bar{x}$ ± .107	0.127	0.109	0.084	0-45
"01330002"	"Z"	"2"	"R90-679 5-10	"	0.078	-9	-9	
"01330003"	"Z"	"2"	"R90-679 10-15	"	0.062	-9	-9	
"01330004"	"Z"	"2"	"R90-679 15-20	$\bar{x}$ ± .016	0.015	0.016	-9	45' @ .076
"01330006"	"Z"	"2"	"R90-679 20-25	"	0.064	-9	-9	
"01330007"	"Z"	"2"	"R90-679 25-30	"	0.042	-9	-9	
"01330008"	"Z"	"2"	"R90-679 30-35	"	0.101	-9	-9	
"01330009"	"Z"	"2"	"R90-679 35-40	$\bar{x}$ ± .136	0.149	0.130	0.130	
"01330010"	"Z"	"2"	"R90-679 40-45	"	0.119	-9	-9	
"01330011"	"Z"	"2"	"R90-679 45-50	"	0.004	-9	-9	
"01330012"	"Z"	"2"	"R90-679 50-55	"	0.005	-9	-9	
"01330013"	"Z"	"2"	"R90-679 55-60	"	-0.002	-9	-9	
"01330014"	"Z"	"2"	"R90-679 60-65	"	0.002	-9	-9	
"01330015"	"Z"	"2"	"R90-679 65-70	"	-0.002	-0.002	-9	
"01330016"	"Z"	"2"	"R90-679 70-75	"	-0.002	-9	-9	
"01330017"	"Z"	"2"	"R90-679 75-80	"	-0.002	-9	-9	
"01330018"	"Z"	"2"	"R90-679 80-85	"	-0.002	-9	-9	
"01330019"	"Z"	"2"	"R90-679 85-90	"	0.002	-9	-9	
"01330020"	"Z"	"2"	"R90-679 90-95	"	0.003	-9	-9	
"01330021"	"Z"	"2"	"R90-679 95-100	"	0.004	-9	-9	
"01330022"	"Z"	"2"	"R90-679 100-105	"	-0.002	-9	-9	
"01330025"	"Z"	"2"	"R90-679 105-110	"	-0.002	-9	-9	
"01330026"	"Z"	"2"	"R90-679 110-115	"	0.030	-9	-9	110-125
"01330027"	"Z"	"2"	"R90-679 115-120	$\bar{x}$ ".022	0.023	0.022	-9	15' @ .033
"01330028"	"Z"	"2"	"R90-679 120-125	$\bar{x}$ ± .047	0.051	0.045	0.045	
"01330029"	"Z"	"2"	"R90-679 125-130	"	0.002	0.002	-9	
"01330031"	"Z"	"2"	"R90-679 130-135	"	0.005	-9	-9	
"01330032"	"Z"	"2"	"R90-679 135-140	"	0.002	-9	-9	
"01330033"	"Z"	"2"	"R90-679 140-145	"	0.007	-9	-9	
"01330034"	"Z"	"2"	"R90-679 145-150	"	0.003	-9	-9	
"01330035"	"Z"	"2"	"R90-679 150-155	"	0.002	-9	-9	
"01330036"	"Z"	"2"	"R90-679 155-160	"	0.009	-9	-9	
"01330037"	"Z"	"2"	"R90-679 160-165	"	0.003	-9	-9	
"01330038"	"Z"	"2"	"R90-679 165-170	"	0.005	-9	-9	
"01330039"	"Z"	"2"	"R90-679 170-175	"	0.007	-9	-9	
"01330040"	"Z"	"2"	"R90-679 175-180	$\bar{x}$ ± .0021	0.017	0.026	-9	
"01330041"	"Z"	"2"	"R90-679 180-185	"	0.005	-9	-9	
"01330042"	"Z"	"2"	"R90-679 185-190	"	0.022	-9	-9	
"01330043"	"Z"	"2"	"R90-679 190-195	"	0.008	-9	-9	
"01330044"	"Z"	"2"	"R90-679 195-200	"	0.009	-9	-9	
"01330045"	"Z"	"2"	"R90-679 200-205	"	0.016	0.022	-9	
"01330046"	"Z"	"2"	"R90-679 205-210	"	0.018	-9	-9	

"01330049"	"Z"	"2"	"R90-679	210-215		0.144	-9	-9	
"01330050"	"Z"	"2"	"R90-679	215-220	$\bar{x}$=.158	0.184	0.143	0.147	210-225
"01330051"	"Z"	"2"	"R90-679	220-225	"	0.042	-9	-9	15'@ .115
"01330052"	"Z"	"2"	"R90-679	225-230	"	0.007	-9	-9	
"01330053"	"Z"	"2"	"R90-679	230-235	"	0.005	-9	-9	
"01330054"	"Z"	"2"	"R90-679	235-240	"	0.006	0.006	-9	
"01330056"	"Z"	"2"	"R90-679	240-245	"	0.006	-9	-9	
"01330057"	"Z"	"2"	"R90-679	245-250	"	0.029	-9	-9	
"01330058"	"Z"	"2"	"R90-679	250-255	"	0.004	-9	-9	
"01330059"	"Z"	"2"	"R90-679	255-260	"	0.004	-9	-9	
"01330060"	"Z"	"2"	"R90-679	260-265	"	0.010	-9	-9	
"01330061"	"Z"	"2"	"R90-679	265-270	$\bar{x}$=.042	0.042	0.045	0.038	265-305
"01330062"	"Z"	"2"	"R90-679	270-275	"	0.017	-9	-9	
"01330063"	"Z"	"2"	"R90-679	275-280	"	0.015	-9	-9	40'@ .032
"01330064"	"Z"	"2"	"R90-679	280-285	$\bar{x}$=.092	0.093	0.107	0.077	
"01330065"	"Z"	"2"	"R90-679	285-290	$\bar{x}$=.022	0.025	0.020	-9	
"01330066"	"Z"	"2"	"R90-679	290-295	"	0.010	-9	-9	
"01330067"	"Z"	"2"	"R90-679	295-300	"	0.036	-9	-9	
"01330068"	"Z"	"2"	"R90-679	300-305	"	0.025	-9	-9	
"01330069"	"Z"	"2"	"R90-679	305-310	"	0.010	-9	-9	
"01330070"	"Z"	"2"	"R90-679	310-315	"	0.005	-9	-9	
"01330073"	"Z"	"2"	"R90-679	315-320	"	0.010	-9	-9	
"01330074"	"Z"	"2"	"R90-679	320-325	"	0.003	-9	-9	
"01330075"	"Z"	"2"	"R90-679	325-330	"	0.011	-9	-9	
"01330076"	"Z"	"2"	"R90-679	330-335	"	0.002	-9	-9	
"01330077"	"Z"	"2"	"R90-679	335-340	"	0.003	-9	-9	
"01330078"	"Z"	"2"	"R90-679	340-345	"	0.011	-9	-9	
"01330079"	"Z"	"2"	"R90-679	345-350	"	0.005	0.005	-9	
"01330081"	"Z"	"2"	"R90-679	350-355	"	0.005	-9	-9	
"01330082"	"Z"	"2"	"R90-679	355-360	"	0.004	-9	-9	
"01330083"	"Z"	"2"	"R90-679	360-365	"	0.002	-9	-9	
"01330084"	"Z"	"2"	"R90-679	365-370	"	0.005	-9	-9	
"01330085"	"Z"	"2"	"R90-679	370-375	"	0.002	-9	-9	
"01330086"	"Z"	"2"	"R90-679	375-380	"	-0.002	-9	-9	
"01330087"	"Z"	"2"	"R90-679	380-385	"	0.004	-9	-9	
"01330088"	"Z"	"2"	"R90-679	385-390	"	-0.002	-9	-9	
"01330089"	"Z"	"2"	"R90-679	390-395	"	-0.002	-9	-9	
"01330090"	"Z"	"2"	"R90-679	395-400	"	0.002	0.003	-9	
"01330091"	"Z"	"2"	"R90-679	400-405	"	0.004	-9	-9	
"01330092"	"Z"	"2"	"R90-679	405-410	"	0.003	-9	-9	
"01330093"	"Z"	"2"	"R90-679	410-415	"	-0.002	-9	-9	
"01330094"	"Z"	"2"	"R90-679	415-420	"	0.004	0.002	-9	
"01330097"	"Z"	"2"	"R90-679	420-425	"	0.004	-9	-9	
"01330098"	"Z"	"2"	"R90-679	425-430	"	-0.002	-9	-9	
"01330099"	"Z"	"2"	"R90-679	430-435	"	0.007	-9	-9	
"01330100"	"Z"	"2"	"R90-679	435-440	"	0.015	0.019	-9	

"END"

```
"TITLE 26-02-90 17:00:23 R90-30134.4   BARRON                    19/02/90"
"CLIENT BROHM MINING CORPORATION                                 "
"PROJECT R90-679          #SAMPLES:   60 REFERENCE: 440-740                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   60 0.002 999.90 Results Reported     "
"  02 AU DUP FA        OPT   15 0.002 9999.0 Results Reported     "
"  03 AU Dup FA        OPT   11 0.001 9999.0 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z       OTHER DRILL TYPES   "
"  41 P17=  60            ASSAY PREP          "
"  42 P64=1425            EXCESSIVE WETNESS/LB"
"  43 P98=   1            SAMPLE PICKUP/MILE  "
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au" "AU DUP" "AU Dup"
"01340001" "Z" "2" "R90-679 440-445     "    0.005      -9       -9
"01340002" "Z" "2" "R90-679 445-450     "    0.005      -9       -9
"01340003" "Z" "2" "R90-679 450-455     "    0.005      -9       -9
"01340004" "Z" "2" "R90-679 455-460     "    0.004      -9       -9
"01340005" "Z" "2" "R90-679 460-465     "    0.006   0.005       -9
"01340007" "Z" "2" "R90-679 465-470     "    0.004      -9       -9
"01340008" "Z" "2" "R90-679 470-475     "    0.004      -9       -9
"01340009" "Z" "2" "R90-679 475-480     "    0.005      -9       -9
"01340010" "Z" "2" "R90-679 480-485     "    0.008      -9       -9
"01340011" "Z" "2" "R90-679 485-490     "    0.009      -9       -9
"01340012" "Z" "2" "R90-679 490-495     X̄=.2560.252   0.284    0.233
"01340013" "Z" "2" "R90-679 495-500     "    0.055      -9       -9
"01340014" "Z" "2" "R90-679 500-505     "    0.010      -9       -9
"01340015" "Z" "2" "R90-679 505-510     X̄=.139 0.124   0.148    0.146
"01340016" "Z" "2" "R90-679 510-515     X̄=.033 0.032   0.028    0.040
"01340017" "Z" "2" "R90-679 515-520     "    0.017      -9       -9
"01340018" "Z" "2" "R90-679 520-525     "    0.030      -9       -9
"01340019" "Z" "2" "R90-679 525-530     "    0.016   0.010    0.013
"01340020" "Z" "2" "R90-679 530-535     "    0.004      -9       -9
"01340021" "Z" "2" "R90-679 535-540     "    0.015      -9       -9
"01340022" "Z" "2" "R90-679 540-545     "    0.009      -9       -9
"01340025" "Z" "2" "R90-679 545-550     "    0.003      -9       -9
"01340026" "Z" "2" "R90-679 550-555     "    0.002      -9       -9
"01340027" "Z" "2" "R90-679 555-560     "    0.007      -9       -9
"01340028" "Z" "2" "R90-679 560-565     "    0.007      -9       -9
"01340029" "Z" "2" "R90-679 565-570     X̄=.045 0.042   0.030    0.062
"01340030" "Z" "2" "R90-679 570-575     X̄=.020 0.027   0.018    0.016
"01340032" "Z" "2" "R90-679 575-580     "    0.025      -9       -9
"01340033" "Z" "2" "R90-679 580-585     "    0.010      -9       -9
"01340034" "Z" "2" "R90-679 585-590     "    0.019      -9       -9
"01340035" "Z" "2" "R90-679 590-595     "    0.019      -9       -9
"01340036" "Z" "2" "R90-679 595-600     "    0.010      -9       -9
"01340037" "Z" "2" "R90-679 600-605     X̄=.075 0.079   0.070    0.076
"01340038" "Z" "2" "R90-679 605-610     "    0.042      -9       -9
"01340039" "Z" "2" "R90-679 610-615     "    0.016      -9       -9
"01340040" "Z" "2" "R90-679 615-620     "    0.010      -9       -9
"01340041" "Z" "2" "R90-679 620-625     "    0.018   0.022       -9
"01340042" "Z" "2" "R90-679 625-630     X̄=.095 0.097   0.093    0.094
"01340043" "Z" "2" "R90-679 630-635     "    0.043      -9       -9
"01340044" "Z" "2" "R90-679 635-640     "    0.031      -9       -9
"01340045" "Z" "2" "R90-679 640-645     "    0.009      -9       -9
```

490 - 525
35' @ .077

565-580
15' @ .030

600-610
10' @ .058

625-735
110' @ .060

"01340046"	"Z"	"2"	"R90-679	645-650	"	0.042	-9	-9
"01340049"	"Z"	"2"	"R90-679	650-655	"	0.035	-9	-9
"01340050"	"Z"	"2"	"R90-679	655-660	$\bar{x}$=.399	0.445	0.377	0.376
"01340051"	"Z"	"2"	"R90-679	660-665	"	0.061	-9	-9
"01340052"	"Z"	"2"	"R90-679	665-670	$\bar{x}$=.109	0.132	0.120	0.074
"01340053"	"Z"	"2"	"R90-679	670-675	"	0.032	-9	-9
"01340054"	"Z"	"2"	"R90-679	675-680	"	0.017	-9	-9
"01340055"	"Z"	"2"	"R90-679	680-685	$\bar{x}$=.013	0.013	0.013	-9
"01340057"	"Z"	"2"	"R90-679	685-690	"	0.036	-9	-9
"01340058"	"Z"	"2"	"R90-679	690-695	"	0.056	-9	-9
"01340059"	"Z"	"2"	"R90-679	695-700	"	0.031	-9	-9
"01340060"	"Z"	"2"	"R90-679	700-705	"	0.035	-9	-9
"01340061"	"Z"	"2"	"R90-679	705-710	$\bar{x}$=.060	0.062	0.059	0.059
"01340062"	"Z"	"2"	"R90-679	710-715	"	0.044	-9	-9
"01340063"	"Z"	"2"	"R90-679	715-720	"	0.036	-9	-9
"01340064"	"Z"	"2"	"R90-679	720-725	"	0.042	-9	-9
"01340065"	"Z"	"2"	"R90-679	725-730	"	0.051	-9	-9
"01340066"	"Z"	"2"	"R90-679	730-735	$\bar{x}$=.037	0.040	0.034	-9
"01340067"	"Z"	"2"	"R90-679	735-740	"	0.018	-9	-9

"END"

```
"TITLE 27-02-90 16:32:15 R90-30135.4   BARRON                20/02/90"
"CLIENT BROHM MINING CORPORATION                            "
"PROJECT R90-679         #SAMPLES:   21 REFERENCE: 740-845                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   21 0.002 999.90 Results Reported     "
"  02 AU DUP FA        OPT    2 0.002 9999.0 Results Reported     "
"  03 AU Dup FA        OPT   21 0.001 9999.0 Test not yet complete"
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z      OTHER DRILL TYPES   "
"  41 P17=  21           ASSAY PREP          "
"  42 P64= 523           EXCESSIVE WETNESS/LB"
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au" "AU DUP" "AU Dup"
"01350001" "Z" "2" "R90-679 740-745     "    0.015       -9       -9
"01350002" "Z" "2" "R90-679 745-750     "    0.014       -9       -9
"01350003" "Z" "2" "R90-679 750-755     "    0.007       -9       -9
"01350004" "Z" "2" "R90-679 755-760     "    0.008       -9       -9
"01350005" "Z" "2" "R90-679 760-765     "    0.004       -9       -9
"01350006" "Z" "2" "R90-679 765-770     "    0.005    0.005       -9
"01350008" "Z" "2" "R90-679 770-775     "    0.002       -9       -9
"01350009" "Z" "2" "R90-679 775-780     "    0.004       -9       -9
"01350010" "Z" "2" "R90-679 780-785     "    0.013       -9       -9
"01350011" "Z" "2" "R90-679 785-790     "    0.006       -9       -9
"01350012" "Z" "2" "R90-679 790-795     "    0.014       -9       -9
"01350013" "Z" "2" "R90-679 795-800     "    0.005       -9       -9
"01350014" "Z" "2" "R90-679 800-805     "    0.002       -9       -9
"01350015" "Z" "2" "R90-679 805-810     "    0.003       -9       -9
"01350016" "Z" "2" "R90-679 810-815     "    0.002       -9       -9
"01350017" "Z" "2" "R90-679 815-820     "    0.003    0.003       -9
"01350018" "Z" "2" "R90-679 820-825     "    0.005       -9       -9
"01350019" "Z" "2" "R90-679 825-830     "    0.008       -9       -9
"01350020" "Z" "2" "R90-679 830-835     "    0.002       -9       -9
"01350021" "Z" "2" "R90-679 835-840     "   -0.002       -9       -9
"01350022" "Z" "2" "R90-679 840-845     "   -0.002       -9       -9
"END"
```

Contractor: Lang | Coordinates: 47550.95 25578.36 | Project: Expansion | Hole No.: RAO-680 (Site A-1)

Drill Type: D40K | Casing Depth: | State: | Sheet 1 of 4

Hole Size: | Bearing: | Inclination: -90° | Date Started: 2/12/90 | Property: Gilt Edge / Anchor Hill

Collar Elev.: 5706.5 | Final Depth: 585' | Date Completed: 2/13/90 | Hole Surveyed:

GRAPHIC LOGS: Distance (feet)	Alteration (Weak / Moderate / Strong)	Total Sulfides (vol %)	Rock Code	Ore Code	Down Hole Location: Distance Down Hole (feet)	Azimuth / Elevation	Rock Type	Geologic Notes: Description (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	Mineralization: Distribution (Massive, Disseminated, Veinlet, Replacement) / Type	Assay: Au	Assay: Ag
			85	3	0-5	712	Tqtp	0-460 Quartz trachyte	0-585 oxide		
						0-585		generally light oxidation - pinkish (rust,	(0-10 highly oxidized)		
								zones of intense oxidation.			
								Generally weak alteration of phenocrysts			
					20-25			and groundmass, zones of increased	(20-80 increased oxidation		
								alteration - pitted or corroded appearance	some chips highly oxidized)		
					45-50						
					70-75						
									(80-100 highly oxidized)		
					95-100						
					120-125						
					145-150						
									(155-165 highly oxidized)		
									(165-180 increased oxidation -		
									some chips highly oxidized)		
					170-175						

DRILL CUTTING LOG

Logged by: J. Goff

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 2 of 4

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

GRAPHIC LOGS				DOWN HOLE LOCATION		GEOLOGIC NOTES				
DISTANCE (feet)	ALTERATION	TOTAL SULPHIDES (vol %)	ROCK CODE	ORE CODE	DISTANCE DOWN HOLE (feet)	ELEVATION	ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlet, Replacement) / TYPE	ASSAY Au / Ag
			85	3	175-180		Tqtp	Cont. Quartz trachyte		
					195-200				(195-230 increased oxidation some chips highly oxidized)	
					220-225					
					245-250					
					270-275			(275-310 altered, pitted or corroded)	(265-315 increased oxidation some chips highly oxidized)	
					295-300					
					320-325				(315-345 extreme oxidation)	
					345-350					

DRILL CUTTING LOG

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 3 of 4

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DRILL CUTTING LOG

Distance (feet)	Graphic Logs: Alteration (Weak, Moderate, Strong)	Total Sulfides (vol %)	Rock Code	Ore Code	Down Hole Location: Distance Down Hole (feet)	Elevation	Rock Type	Geologic Notes: Description (Mineralogy, Alteration, Textures, Grain Size, Fragment Size)	Mineralization: Distribution (Massive, Disseminated, Veinlet, Replacement)	Type	Assay: Au	Assay: Ag
			85	3	350-355		Tqtp	Cont Quartz trachyte				
								(360 - 375 decreased alteration, some phenocrysts altered to clay)				
					370-375				(370 - 400 increased oxidation)			
					395-400							
									(405 - 410 extreme oxidation)			
					420-425							
									(425 - 460 increased oxidation)			
					445-450							
			30				Cdh	460 - 465 Deadwood hornfels				
			40				Cdq	465 - 500 Deadwood Quartzite				
					470-475							
					495-500							
			10				PE	500 - 585 Precambrian Amphibolite				
					520-525							

Logged by:

Contractor _____ Coordinates _____ Project _____ Hole No. _____

Drill Type _____ Casing Depth _____ State _____ Sheet 4 of 4

Hole Size _____ Bearing _____ Inclination _____ Date Started _____ Property _____

Collar Elev. _____ Final Depth _____ Date Completed _____ Hole Surveyed _____

DISTANCE (feet)	GRAPHIC LOGS: ALTERATION (Weak, Moderate, Strong)	TOTAL SULFIDES (vol %)	ROCK CODE	ORE CODE	DOWN HOLE LOCATION: DISTANCE DOWN HOLE (feet)	ELEVATION	GEOLOGIC NOTES: ROCK TYPE	DESCRIPTION: MINERALOGY, ALTERATION, TEXTURES, GRAIN SIZE, FRAGMENT SIZE	MINERALIZATION: DISTRIBUTION (Massive, Disseminated, Veinlets, Replacement)	TYPE	ASSAY: Au	Ag
			10	3	525-530		PE	Cont Precambrian Amphibolite				
					545-550							
					570-575							
								585 E.O.H				
					595-600							
					620-625							
					645-650							
					670-675							
					695-700							

DRILL CUTTING LOG

Logged by:

"TITLE 26-02-90 17:06:59 R90-30136.4 BARRON 19/02/90"
"CLIENT BROHM MINING CORPORATION "
"PROJECT R90-680 #SAMPLES: 61 REFERENCE: 0-305 "
"SPECIAL VALUES"
" IS Insufficient Sample"
" -9 No Value Recorded"
" Values above the upper limit are shown as +uplimt"
" Values below the lower limit are shown as -lolmt (ie not detected)"
"DETERMINATIONS"

	ELNAME	METHO	ECO	UNI	#SAM	LOLMT	UPLIMT	COMMENTS
01	Au	FA		OPT	61	0.002	999.90	Results Reported
02	AU DUP	FA		OPT	10	0.002	9999.0	Results Reported
03	AU Dup	FA		OPT	2	0.001	9999.0	Results Reported

"SAMPLE PREPS"
" 40 SAMPLE TYPE=Z OTHER DRILL TYPES "
" 41 P17= 61 ASSAY PREP "
" 42 P98= 1 SAMPLE PICKUP/MILE "
"****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"

"BEGIN "	"Type"	"Frac"	"Sample ID"	"	Au"	"AU DUP"	"AU Dup"	
"01360001"	"Z"	"2"	"R90-680 0-5	"	0.022	-9	-9	0-15 15' @ .021
"01360002"	"Z"	"2"	"R90-680 5-10	"	0.018	-9	-9	
"01360003"	"Z"	"2"	"R90-680 10-15	"	0.023	-9	-9	
"01360004"	"Z"	"2"	"R90-680 15-20	"	0.010	-9	-9	
"01360005"	"Z"	"2"	"R90-680 20-25	"	0.011	-9	-9	
"01360006"	"Z"	"2"	"R90-680 25-30	"	0.013	0.013	-9	
"01360007"	"Z"	"2"	"R90-680 30-35	"	0.010	0.011	-9	
"01360009"	"Z"	"2"	"R90-680 35-40	"	0.011	-9	-9	
"01360010"	"Z"	"2"	"R90-680 40-45	"	0.012	-9	-9	
"01360011"	"Z"	"2"	"R90-680 45-50	"	0.009	-9	-9	
"01360012"	"Z"	"2"	"R90-680 50-55	"	0.011	-9	-9	
"01360013"	"Z"	"2"	"R90-680 55-60	"	0.025	-9	-9	
"01360014"	"Z"	"2"	"R90-680 60-65	"	0.010	-9	-9	
"01360015"	"Z"	"2"	"R90-680 65-70	"	0.010	-9	-9	
"01360016"	"Z"	"2"	"R90-680 70-75	"	0.011	-9	-9	
"01360017"	"Z"	"2"	"R90-680 75-80	"	0.020	-9	-9	75-90 15' @ .025
"01360018"	"Z"	"2"	"R90-680 80-85	"	0.028	0.028	-9	
"01360019"	"Z"	"2"	"R90-680 85-90	"	0.028	-9	-9	
"01360020"	"Z"	"2"	"R90-680 90-95	"	0.009	-9	-9	
"01360021"	"Z"	"2"	"R90-680 95-100	"	0.013	-9	-9	
"01360022"	"Z"	"2"	"R90-680 100-105	"	0.018	-9	-9	
"01360025"	"Z"	"2"	"R90-680 105-110	"	0.026	-9	-9	105-175 70' @ .049
"01360026"	"Z"	"2"	"R90-680 110-115	"	0.021	0.018	$\bar{x}$=.020 -9	
"01360027"	"Z"	"2"	"R90-680 115-120	"	0.030	-9	-9	
"01360028"	"Z"	"2"	"R90-680 120-125	"	0.049	-9	-9	
"01360029"	"Z"	"2"	"R90-680 125-130	"	0.078	-9	-9	
"01360030"	"Z"	"2"	"R90-680 130-135	$\bar{x}$=.139	0.146	0.164	0.108	
"01360031"	"Z"	"2"	"R90-680 135-140	"	0.048	-9	-9	
"01360032"	"Z"	"2"	"R90-680 140-145	$\bar{x}$=.044	0.046	0.042	-9	
"01360034"	"Z"	"2"	"R90-680 145-150	"	0.038	-9	-9	
"01360035"	"Z"	"2"	"R90-680 150-155	"	0.033	-9	-9	
"01360036"	"Z"	"2"	"R90-680 155-160	"	0.033	-9	-9	
"01360037"	"Z"	"2"	"R90-680 160-165	$\bar{x}$=.069	0.104	0.043	0.059	
"01360038"	"Z"	"2"	"R90-680 165-170	"	0.031	-9	-9	
"01360039"	"Z"	"2"	"R90-680 170-175	"	0.042	-9	-9	
"01360040"	"Z"	"2"	"R90-680 175-180	"	0.015	-9	-9	
"01360041"	"Z"	"2"	"R90-680 180-185	"	0.016	-9	-9	
"01360042"	"Z"	"2"	"R90-680 185-190	"	0.018	-9	-9	
"01360043"	"Z"	"2"	"R90-680 190-195	$\bar{x}$=.014	0.015	0.013	-9	
"01360044"	"Z"	"2"	"R90-680 195-200	"	0.016	-9	-9	
"01360045"	"Z"	"2"	"R90-680 200-205	"	0.025	-9	-9	
"01360046"	"Z"	"2"	"R90-680 205-210	"	0.010	-9	-9	

"01360049"	"Z"	"2"	"R90-680	210-215	"	0.015	-9	-9	
"01360050"	"Z"	"2"	"R90-680	215-220	"	0.028	-9	-9	200-230
"01360051"	"Z"	"2"	"R90-680	220-225	"	0.032	-9	-9	30' @ .022
"01360052"	"Z"	"2"	"R90-680	225-230	"	0.021	-9	-9	
"01360053"	"Z"	"2"	"R90-680	230-235	"	0.015	-9	-9	
"01360054"	"Z"	"2"	"R90-680	235-240	"	0.010	-9	-9	
"01360055"	"Z"	"2"	"R90-680	240-245	"	0.014	-9	-9	
"01360056"	"Z"	"2"	"R90-680	245-250	"	0.009	-9	-9	
"01360057"	"Z"	"2"	"R90-680	250-255	"	0.016	0.016	-9	
"01360059"	"Z"	"2"	"R90-680	255-260	"	0.018	-9	-9	
"01360060"	"Z"	"2"	"R90-680	260-265	"	0.022	-9	-9	260-270
"01360061"	"Z"	"2"	"R90-680	265-270	"	0.023	-9	-9	10' @ .022
"01360062"	"Z"	"2"	"R90-680	270-275	"	0.014	-9	-9	
"01360063"	"Z"	"2"	"R90-680	275-280	"	0.013	-9	-9	
"01360064"	"Z"	"2"	"R90-680	280-285	"	0.010	-9	-9	
"01360065"	"Z"	"2"	"R90-680	285-290	"	0.016	-9	-9	
"01360066"	"Z"	"2"	"R90-680	290-295	"	0.016	-9	-9	
"01360067"	"Z"	"2"	"R90-680	295-300	"	0.028	-9	-9	
"01360068"	"Z"	"2"	"R90-680	300-305	$\bar{x}$=.029	0.028	0.030	-9	295-360
"END"									65' @ .030

```
"TITLE 27-02-90 09:47:53 R90-30138.4   BARRON                20/02/90"
"CLIENT BROHM MINING CORPORATION                                    "
"PROJECT R90-680          #SAMPLES:   32 REFERENCE: 305-465                                  "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   32 0.002 999.90 Results Reported      "
"  02 AU DUP FA        OPT    6 0.002 9999.0 Results Reported      "
"  03 AU Dup FA        OPT    1 0.001 9999.0 Results Reported      "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z      OTHER DRILL TYPES    "
"  41 P17=  32           ASSAY PREP           "
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au" "AU DUP" "AU Dup"
"01380001" "Z" "2" "R90-680 305-310      X̄=.027 0.026    0.028       -9
"01380002" "Z" "2" "R90-680 310-315      "    0.015       -9       -9
"01380003" "Z" "2" "R90-680 315-320      "    0.021       -9       -9
"01380004" "Z" "2" "R90-680 320-325      "    0.030       -9       -9
"01380005" "Z" "2" "R90-680 325-330      "    0.019       -9       -9
"01380006" "Z" "2" "R90-680 330-335      "    0.026       -9       -9
"01380007" "Z" "2" "R90-680 335-340      "    0.032       -9       -9
"01380008" "Z" "2" "R90-680 340-345      X̄'=.088 0.096    0.086    0.081
"01380009" "Z" "2" "R90-680 345-350      X̄'=.032 0.034    0.030       -9
"01380011" "Z" "2" "R90-680 350-355      "    0.024       -9       -9
"01380012" "Z" "2" "R90-680 355-360      "    0.022       -9       -9
"01380013" "Z" "2" "R90-680 360-365      "    0.018       -9       -9
"01380014" "Z" "2" "R90-680 365-370      "    0.006       -9       -9
"01380015" "Z" "2" "R90-680 370-375      "    0.015       -9       -9
"01380016" "Z" "2" "R90-680 375-380      "    0.018       -9       -9
"01380017" "Z" "2" "R90-680 380-385      X̄'=.026 0.025    0.026       -9
"01380018" "Z" "2" "R90-680 385-390      "    0.023       -9       -9
"01380019" "Z" "2" "R90-680 390-395      "    0.015       -9       -9
"01380020" "Z" "2" "R90-680 395-400      "    0.012    0.012       -9
"01380021" "Z" "2" "R90-680 400-405      "    0.020       -9       -9
"01380022" "Z" "2" "R90-680 405-410      "    0.011       -9       -9
"01380025" "Z" "2" "R90-680 410-415      "    0.020       -9       -9
"01380026" "Z" "2" "R90-680 415-420      "    0.004       -9       -9
"01380027" "Z" "2" "R90-680 420-425      "    0.006       -9       -9
"01380028" "Z" "2" "R90-680 425-430      "    0.037       -9       -9
"01380029" "Z" "2" "R90-680 430-435      "    0.025       -9       -9
"01380030" "Z" "2" "R90-680 435-440      "    0.024       -9       -9
"01380031" "Z" "2" "R90-680 440-445      "    0.026       -9       -9
"01380032" "Z" "2" "R90-680 445-450      "    0.023       -9       -9
"01380033" "Z" "2" "R90-680 450-455      "    0.024       -9       -9
"01380034" "Z" "2" "R90-680 455-460      X̄'=.058 0.064    0.053       -9
"01380036" "Z" "2" "R90-680 460-465      "    0.010       -9       -9
"END"
```

380-485
105' @ .023

```
"TITLE 27-02-90 11:20:40 R90-30137.4   BARRON                    19/02/90"
"CLIENT BROHM MINING CORPORATION                                 "
"PROJECT R90-680          #SAMPLES:   24 REFERENCE: 465-585                          "
"SPECIAL VALUES"
"  IS Insufficient Sample"
"  -9 No Value Recorded"
" Values above the upper limit are shown as  +uplimt"
" Values below the lower limit are shown as  -lolmt   (ie not detected)"
"DETERMINATIONS"
"     ELNAME METHO ECO UNI #SAM LOLMT UPLIMT COMMENTS"
"  01 Au     FA        OPT   24 0.002 999.90 Results Reported     "
"  02 AU DUP FA        OPT    2 0.002 9999.0 Results Reported     "
"  03 AU Dup FA        OPT    2 0.001 9999.0 Results Reported     "
"SAMPLE PREPS"
"  40 SAMPLE TYPE=Z       OTHER DRILL TYPES   "
"  41 P17=  24            ASSAY PREP          "
"  42 P64= 376            EXCESSIVE WETNESS/LB"
"*****"
"FORMAT (A8,1X,A1,A1,1X,A20,3(1X,A7,A1))"
"BEGIN " "Type" "Frac" "Sample ID"          "    Au" "AU DUP" "AU Dup"
"01370001" "Z" "2" "R90-680 465-470     "    0.043       -9       -9
"01370002" "Z" "2" "R90-680 470-475     "    0.035       -9       -9
"01370003" "Z" "2" "R90-680 475-480     "    0.023       -9       -9
"01370004" "Z" "2" "R90-680 480-485     "    0.021       -9       -9
"01370005" "Z" "2" "R90-680 485-490     "    0.014       -9       -9
"01370006" "Z" "2" "R90-680 490-495     "    0.010       -9       -9
"01370007" "Z" "2" "R90-680 495-500     "    0.011       -9       -9
"01370008" "Z" "2" "R90-680 500-505     "    0.004    0.004    0.004
"01370010" "Z" "2" "R90-680 505-510     "    0.006       -9       -9
"01370011" "Z" "2" "R90-680 510-515     "    0.005       -9       -9
"01370012" "Z" "2" "R90-680 515-520     "    0.005       -9       -9
"01370013" "Z" "2" "R90-680 520-525     "    0.004       -9       -9
"01370014" "Z" "2" "R90-680 525-530     "    0.003       -9       -9
"01370015" "Z" "2" "R90-680 530-535     "   -0.002       -9       -9
"01370016" "Z" "2" "R90-680 535-540     "   -0.002       -9       -9
"01370017" "Z" "2" "R90-680 540-545     "   -0.002       -9       -9
"01370018" "Z" "2" "R90-680 545-550     "    0.004       -9       -9
"01370019" "Z" "2" "R90-680 550-555     "   -0.002    0.002    0.002
"01370020" "Z" "2" "R90-680 555-560     "   -0.002       -9       -9
"01370021" "Z" "2" "R90-680 560-565     "    0.003       -9       -9
"01370022" "Z" "2" "R90-680 565-570     "    0.002       -9       -9
"01370025" "Z" "2" "R90-680 570-575     "    0.004       -9       -9
"01370026" "Z" "2" "R90-680 575-580     "    0.005       -9       -9
"01370027" "Z" "2" "R90-680 580-585     "    0.007       -9       -9
"END"
```

BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30136.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC dry	61	R90-680	Au	
		0-5		
		300-305		

Total No. Samples _____ Date Shipped 2/13/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Results and Invoices To Be Sent To

Bohm

☐ Results
☐ Invoice (for payment)

☐ Results
☐ Invoice (copy)

☐ Results
☐ Invoice (copy)

White - Send with Samples Yellow - Client Copy

Printed in Canada

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30138.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
PC DRY	32	R90-68 D	AU	
		305-310		
		460-465		

Total No. Samples _____ Date Shipped 2/14/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Results and Invoices To Be Sent To

BROHM

☐ Results
☐ Invoice (for payment)

☐ Results
☐ Invoice (copy)

☐ Results
☐ Invoice (copy)

Samples submitted by J BARRON

Shipment number _____

Client project number _____

Purchase order number _____

Printed in Canada

White - Send with Samples Yellow - Client Copy

BC
BONDAR-CLEGG

SUBMITTAL FORM

LAB. REPORT NO. L90-30137.4

130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5
or
P.O. Box 8059
Blaine, WA. 98230

Phone (604) 985-0681
or (702) 331-1813
Fax (604) 985-1071
Telex 04-352667

1A-625 Spice Island Dr.
Sparks, Nevada 89431
(702) 359-9330
Fax (702) 359-9386

12980 West Cedar Dr.
Lakewood, Colorado 80228
(303) 989-1404
Fax (303) 986-9441

243 Catlin St.
Missoula, Montana 59801
(406) 721-4452

37 Sherman St.
Deadwood, S.D. 57732
(605) 578-1903

c/o Lerch Brothers
4th Ave. W. at Grant St.
Hibbing, Minn. 55746
(218) 262-5003

136 Industrial Road
Whitehorse, Yukon Territory
Y1A 2V1
(403) 667-6523

6631 Wes Way
Anchorage, Ak. 99518
(907) 561-0909

Please analyze by **Assay (% ore grade)** ☒ **Geochemical (ppm, trace level)** ☐

Comments _____

Type of Samples	No. of Samples	Sample Numbers (Series)	Elements to be Analyzed	Remarks
DC Wet	24	R90-680	Au	
		~~580-585~~		
		465-470		
		580-585		

Total No. Samples _____ Date Shipped 2/14/90 Prepaid ☐ Collect ☐

No. Parcels in Shipment _____ Date Rec'd at Bondar-Clegg _____

PLEASE CHECK ✓ BELOW

REJECTS
(COARSE OVERSIZE)

Free storage for 60 days and then discarded unless marked below.

Return immediately ☐

Return collect after 60 days ☐

Store to January at a cost of $10/box (approx. 1 cu. ft.) ☐

(You will then be contacted)

PULPS

Free storage until year end and then discarded unless marked below.

Return collect immediately ☐

Return collect at year end ☐

Samples submitted by J. Barron

Shipment number _____

Client project number _____

Purchase order number _____

Results and Invoices To Be Sent To

BROHM ☐ Results ☐ Invoice (for payment)

_____ ☐ Results ☐ Invoice (copy)

_____ ☐ Results ☐ Invoice (copy)

Printed in Canada

White - Send with Samples Yellow - Client Copy

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30136.4 (COMPLETE)

REFERENCE INFO: 0-305

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-680

SUBMITTED BY: BARRON
DATE PRINTED: 27-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	61	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	10	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	2	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	61	2 -150	61	ASSAY PREP	61
				SAMPLE PICKUP/MILE	1

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 27-FEB-90

REPORT: R90-30136.4

PROJECT: R90-680

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT	SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-680 0-5		0.022			Z2 R90-680 200-205		0.025		
Z2 R90-680 5-10		0.018			Z2 R90-680 205-210		0.010		
Z2 R90-680 10-15		0.023			Z2 R90-680 210-215		0.015		
Z2 R90-680 15-20		0.010			Z2 R90-680 215-220		0.028		
Z2 R90-680 20-25		0.011			Z2 R90-680 220-225		0.032		
Z2 R90-680 25-30		0.013	0.013		Z2 R90-680 225-230		0.021		
Z2 R90-680 30-35		0.010	0.011		Z2 R90-680 230-235		0.015		
Z2 R90-680 35-40		0.011			Z2 R90-680 235-240		0.010		
Z2 R90-680 40-45		0.012			Z2 R90-680 240-245		0.014		
Z2 R90-680 45-50		0.009			Z2 R90-680 245-250		0.009		
Z2 R90-680 50-55		0.011			Z2 R90-680 250-255		0.016	0.016	
Z2 R90-680 55-60		0.025			Z2 R90-680 255-260		0.018		
Z2 R90-680 60-65		0.010			Z2 R90-680 260-265		0.022		
Z2 R90-680 65-70		0.010			Z2 R90-680 265-270		0.023		
Z2 R90-680 70-75		0.011			Z2 R90-680 270-275		0.014		
Z2 R90-680 75-80		0.020			Z2 R90-680 275-280		0.013		
Z2 R90-680 80-85		0.028	0.028		Z2 R90-680 280-285		0.010		
Z2 R90-680 85-90		0.028			Z2 R90-680 285-290		0.016		
Z2 R90-680 90-95		0.009			Z2 R90-680 290-295		0.016		
Z2 R90-680 95-100		0.013			Z2 R90-680 295-300		0.028		
Z2 R90-680 100-105		0.018			Z2 R90-680 300-305		0.028	0.030	
Z2 R90-680 105-110		0.026							
Z2 R90-680 110-115		0.021	0.018						
Z2 R90-680 115-120		0.030							
Z2 R90-680 120-125		0.049							
Z2 R90-680 125-130		0.078							
Z2 R90-680 130-135		0.146	0.164	0.108					
Z2 R90-680 135-140		0.048							
Z2 R90-680 140-145		0.046	0.042						
Z2 R90-680 145-150		0.038							
Z2 R90-680 150-155		0.033							
Z2 R90-680 155-160		0.033							
Z2 R90-680 160-165		0.104	0.043	0.059					
Z2 R90-680 165-170		0.031							
Z2 R90-680 170-175		0.042							
Z2 R90-680 175-180		0.015							
Z2 R90-680 180-185		0.016							
Z2 R90-680 185-190		0.018							
Z2 R90-680 190-195		0.015	0.013						
Z2 R90-680 195-200		0.016							

RECEIVED
MAR 5 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30138.4 (COMPLETE)

REFERENCE INFO: 305-465

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-680

SUBMITTED BY: BARRON
DATE PRINTED: 27-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	32	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	6	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	1	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	32	2 -150	32	ASSAY PREP	32

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 27-FEB-90

REPORT: R90-30138.4

PROJECT: R90-680

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-680 305-310		0.026	0.028	
Z2 R90-680 310-315		0.015		
Z2 R90-680 315-320		0.021		
Z2 R90-680 320-325		0.030		
Z2 R90-680 325-330		0.019		
Z2 R90-680 330-335		0.026		
Z2 R90-680 335-340		0.032		
Z2 R90-680 340-345		0.096	0.086	0.081
Z2 R90-680 345-350		0.034	0.030	
Z2 R90-680 350-355		0.024		
Z2 R90-680 355-360		0.022		
Z2 R90-680 360-365		0.018		
Z2 R90-680 365-370		0.006		
Z2 R90-680 370-375		0.015		
Z2 R90-680 375-380		0.018		
Z2 R90-680 380-385		0.025	0.026	
Z2 R90-680 385-390		0.023		
Z2 R90-680 390-395		0.015		
Z2 R90-680 395-400		0.012	0.012	
Z2 R90-680 400-405		0.020		
Z2 R90-680 405-410		0.011		
Z2 R90-680 410-415		0.020		
Z2 R90-680 415-420		0.004		
Z2 R90-680 420-425		0.006		
Z2 R90-680 425-430		0.037		
Z2 R90-680 430-435		0.025		
Z2 R90-680 435-440		0.024		
Z2 R90-680 440-445		0.026		
Z2 R90-680 445-450		0.023		
Z2 R90-680 450-455		0.024		
Z2 R90-680 455-460		0.064	0.053	
Z2 R90-680 460-465		0.010		

RECEIVED
MAR 5 1990
BROHM MINING CO.

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R90-30137.4 (COMPLETE)

REFERENCE INFO: 465-585

CLIENT: BROHM MINING CORPORATION
PROJECT: R90-680

SUBMITTED BY: BARRON
DATE PRINTED: 27-FEB-90

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au Gold	24	0.002 OPT		Fire Assay
2	AU DUP GOLD DUPLICATE -150	2	0.002 OPT		Fire Assay
3	AU Dup Gold Duplicate	2	0.001 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	24	2 -150	24	ASSAY PREP	24
				EXCESSIVE WETNESS/LB	376

REPORT COPIES TO: MR. JIM BARRON
MR. JIM BARRON

INVOICE TO: MR. JIM BARRON

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 27-FEB-90

REPORT: R90-30137.4

PROJECT: R90-680

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	AU DUP OPT	AU Dup OPT
Z2 R90-680 465-470		0.043		
Z2 R90-680 470-475		0.035		
Z2 R90-680 475-480		0.023		
Z2 R90-680 480-485		0.021		
Z2 R90-680 485-490		0.014		
Z2 R90-680 490-495		0.010		
Z2 R90-680 495-500		0.011		
Z2 R90-680 500-505		0.004	0.004	0.004
Z2 R90-680 505-510		0.006		
Z2 R90-680 510-515		0.005		
Z2 R90-680 515-520		0.005		
Z2 R90-680 520-525		0.004		
Z2 R90-680 525-530		0.003		
Z2 R90-680 530-535		<0.002		
Z2 R90-680 535-540		<0.002		
Z2 R90-680 540-545		<0.002		
Z2 R90-680 545-550		0.004		
Z2 R90-680 550-555		<0.002	0.002	0.002
Z2 R90-680 555-560		<0.002		
Z2 R90-680 560-565		0.003		
Z2 R90-680 565-570		0.002		
Z2 R90-680 570-575		0.004		
Z2 R90-680 575-580		0.005		
Z2 R90-680 580-585		0.007		

RECEIVED
MAR 5 1990
MINING CO.